

Original Research Article

GROWTH OF CdS AND CdTe THIN FILMS AND ANALYSIS OF THEIR ELECTRICAL PROPERTIES FOR FABRICATION OF CdS/CdTe SOLAR CELL.

ABSTRACT

Thin films of cadmium sulphide (CdS) and cadmium telluride (CdTe) have gained a great deal of interest due to its potential applications in solar cells. deposition of CdS and CdTe thin films were performed on Soda Lime glass/FTO substrate at 400°C and 300°C respectively using spray pyrolysis technique. The properties such as Hall effect were measured on the deposited CdS and CdTe films. These results shows the resistivity and mobility of CdS and CdTe polycrystalline films deposited at 400°C were $1.588 \times 10^4 \Omega\text{cm}$ and $5.619 \times 10^2 \text{cm}^2/\text{Vs}$, respectively, while those of CdTe thin film deposited at 300°C were $1.016 \times 10^4 \Omega\text{cm}$ and $1.998 \times 10^2 \text{cm}^2/\text{Vs}$. The electrical conductivity of the films was found to be within the range of $10^{-4} - 10^{-6} (\Omega\text{cm})^{-1}$, with CdS n – type and CdTe p – type of conduction mechanism respectively, which are suitable as window and absorber layers for efficient solar cells.

KEYWORD: Cadmium Sulphide, Cadmium Telluride FTO, P-type and N-type

1. INTRODUCTION

Thin films of cadmium sulphide (CdS) and cadmium telluride (CdTe) have gained a popular of attention because of their potential uses in solar cells (Fang et al., 2013). These are all direct band-gap semiconductors, which means they can ingest solar power at a far smaller thickness than silicon wafers used in crystalline silicon (Si) solar cells (Morales-Acevedo, 2006). CdS is an n-type semiconductor with a large direct band gap (2.42 eV) that is commonly employed as the window layer in hetero-junction thin film solar cells coated over p-type CdTe (Rahman et al., 2019; Tiwari, Verma, Jain, & Bajpai, 2014) or copper indium selenide (CuInSe₂) (Sajedur et al., 2019). The value of 1.45 eV band gap of CdTe suited the Air Mass (AM) of 1.5 solar spectrum. Although only a few millimetres of absorber film were needed for solar cell functioning, the high absorption coefficient was attributable to this phenomenon (Ahmad et al., 2022). CdS and CdTe thin-films are widely acknowledged as two of the most promising prospects for second-generation solar cells due to their wide range of inexpensive production methods and great efficiency (Kulkarni, Rondiya, Pawbake, Waykar, & Jadhavar, 2017). Mobility, resistivity, carrier concentration, and the types of semiconductors are all key issues in the electrical properties of semiconductor measurements (Seboui et al., 2013). Two important criteria that affect whether CdS and CdTe thin films

may be used as window and absorber materials in CdS/CdTe heterojunction solar cells are electrical resistivity and carrier concentration (Garba, 2011).

There are many techniques identified to be successful in deposition *CdS* and *CdTe* thin-films. The most significant ones are Close Space Sublimation CSS (Sobayel et al., 2020), Chemical Bath Deposition CBD (Ikhmayies & Ahmad-bitar, 2010). Some techniques used to deposit material include electro-deposition, vacuum evaporation, sputtering, Vapor Transport Deposition (VTD), Metal Organic Chemical Vapor Deposition (MOCVD), Molecular Beam Epitaxy (MBE), screen printing, and Spray Pyrolysis Deposition. However, it has been discovered that layers produced using the Spray Pyrolysis method are among of the most effective second-generation solar cells to date (Ashour, 2003). Additionally, this method appeals to researchers since it is simple to use, has a rapid deposition rate, and can easily produce large quantities of commercial modules (Dharmadasa et al., 2014). Also with the use of this methodology, specialized materials can be quickly and efficiently deposited across enormous regions. It has been used for many years in the photovoltaic and solar cell industries for this reason, according to Ojeda-barrero, Oliva-avilés, Oliva, Maldonado, and Acosta (2018).

This research examines the electrical properties of *CdS* and *CdTe* thin film samples deposited using the Spray Pyrolysis process (at room temperature utilizing a Hall Effect Measurement instrument). The Hall effect measurement is a common, dependable, and more straightforward technique for determining the basic electrical characteristics of semiconductors (Miyake, Murase, Hirato, & Awakura, 2004).

2. THEORETICAL BACKGROUND

Hall Effect is one of the most important techniques in determination of parameters that characterizes a semiconductor from electrical point of view (Kulkarni et al., 2017). The Hall effect is a phenomenon that occurs when a semiconductor carrying current I is placed in a transverse magnetic field of flux density B . This phenomenon is known as the Hall effect and is used for the following purposes: (i) to identify the charge carrier of a semiconductor, which may be N-type or P-type; (ii) to find carrier concentration; (iii) to measure the conductivity of the materials; and (iv) to identify carrier mobility.

Hall coefficient is given as;

$$R_H = \frac{1}{nq} \quad (1)$$

Charge carrier mobility;

$$\mu = \left| \frac{V_d}{E} \right| \text{ and its unit is } m^{-2}V^{-1}s^{-1} \quad (2)$$

The Hall mobility,

$$\mu = \left| \frac{R_H}{\rho} \right| \text{ or } \mu = |R_H|\sigma \quad (3)$$


The Resistivity is given as;

$$\rho = \frac{1}{N_e\mu} \quad (4)$$

Where ρ is resistivity, μ mobility, N_e bulk concentration (Mohammed, 2018).

3. MATERIALS AND METHOD

The practical steps for depositing (*CdS* and *CdTe*) thin films are covered in this study. Spray Pyrolysis was used to deposit *CdS* and *CdTe* layers on soda lime glass substrates. For *CdS* thin films, an aqueous solution of Cadmium acetate dihydrate $Cd(CH_3COOH)_2 \cdot 2H_2O$ and Thiourea $(NH_2)_2CS$ were employed as Cd and S sources, respectively. The pumping and exhausting gas scrubbing systems, the reaction chamber where the substrate was heated, the precursor solution and carrier gas (air) assembly connected to the spray nozzle, and a temperature controller with a Copper-Constantan thermocouple to control the substrate temperature make up the deposition setup. The solution was sprayed onto a glass substrate that had already been cleaned. The temperature of the substrate was kept constant at 400°C. The normalized distance between the spray nozzle and the substrate was adjusted to 20 cm. The pressure of the carrier gas (air) was kept constant at 1 bar. The solution flow rate was kept constant at 0.5 ml/m throughout the experiment. The grown *CdS* films colour changes with the time from greenish yellow to bright yellow. The possible chemical reaction that takes place on the heated substrate to produce *CdS* is shown



3.1 FOR CADMIUM TELLURIDE DEPOSITION.

Deposition procedure was covered in five stages.

Stage I; 0.056g TeO_2 Was added to 100ml NH_3 at room temperature, the solution was stir using magnetic stirrer until solution turn colourless.

Stage II; 10.66g $Cd(CH_3COOH)_2 \cdot 2H_2O$ + 18.6g EDTA Disodium salt was dissolved in deionized water, and the mixture was stirred continuously until it took on a milky appearance. Deionized water was added to the mixture while hydrazine was added, stirring constantly to maintain the PH level. Deionized water was continuously added until the desired concentration, and stirring was done until the solution was completely dissolved and crystal clear.

Step III; the resulting solution was put into two necks round bottom flask on the lab tech mantle heater set at 200°C. A total of six hours were spent heating the solution, after which it was let to cool at room temperature. The resulting mixture was centrifuged four times, resulting in the separation of the components.

Step IV; the solution was divided into two equal parts in test tubes by weighing on analytical digital balance. The two test tubes were then placed on a centrifuge model 800 machine to centrifuge for three 3minutes at 4000rpm. this process was repeated five times. The centrifuging is for proper separation. The pair of $CdTe$ solutions were mixed together and rinsed with saturated Cadmium Chloride $CdCl_2$ in N-methyl-2 Pyridine NMP.

Stage V; before the deposition of $CdTe$ solution on the SLG substrate, the spray chamber was purged with nitrogen gas for 15 min. In addition, nitrogen gas was used as a carrier gas for spraying the final precursor solution on substrates. The films were deposited on thoroughly cleaned substrates at 300°C using the following processing parameters: (i) spray gun nozzle to substrate distance= 20cm, (ii) spray solution concentration= 0.1M, (iii) carrier N_2 gas flow rate=10l/min, (iv) deposition time= 20minutes, and (v) solution flow rate= 5ml/min. After completing the $CdTe$ thin film coating process which lasted 20minutes by spray pyrolysis method, The films were cooled naturally to the room temperature. The chemical reaction that takes place in the chamber;



4. RESULTS AND DISCUSSION

The three primary electrical properties of the formed Cd and CdTe thin films, namely carrier concentration, mobility, and resistivity, were determined at room temperature using Hall and resistivity measurements. For this, the Abuja Science and Technical Laboratory Complex's ECOPIA Hall effect measurement system (HMS-3000), which is combined with a resistivity measurement tool, was employed. For the Hall measurements, the system employs the four-probe van der Pauw method. Throughout the trials, a constant magnetic field was created using two permanent magnets and then applied orthogonally to the top surface of the films. The thin film samples were electrically coupled to a constant DC current source and a DC (direct current) was generated through one of the two diagonal pairs of gold electrodes. The voltage created in the hall was detected by the remaining electrode pair. The applied magnetic field's strength stayed constant at 0.51 T. The system employed a positive (+) or negative (-) symbol to denote the type (p or n) of the CdS and CdTe films in front of the numerical value of the carrier concentration.

4.1 ELECTRICAL PROPERTIES

The mobility, resistivity, and carrier concentration of a semiconductor are revealed by the Hall Effect measurement. Mobility is a metric for the epitaxial layer's impurity level, consistency, and homogeneity. The current density to electrical field ratio is known as resistivity (Munna et al., 2020). Table 1 includes the electrical resistivity, bulk concentration, and mobility data for the deposited films.

Table 1. The values of electrical resistivity, bulk concentration, mobility obtained from Hall Effect measurements

| SAMPLE | RESISTIVITY (Ωcm) | MOBILITY cm^2/Vs | BULK CONCENTRATION cm^{-3} | AVERAGE HALL COEFFICIENT cm^3/C |
|----------------------|--------------------------------------|-------------------------------------|-------------------------------------------|-------------------------------------------------------|
| <i>CdS at 1hr</i> | 1.588×10^4 | 6.619×10^2 | 6.996×10^{11} | 8.923×10^6 |
| <i>CdS at 30mins</i> | 2.234×10^4 | 7.262×10^2 | 3.629×10^{11} | -1.769×10^7 |

According to Table 1, the resistivity marginally decreases with regard to deposition time, going from 2.234×10^4 to 1.588×10^4 cm. It is well known that the rise in particle packing density with the increase in grain size is what causes the resistivity to drop (Mousavi, Jilavi, Mu, & Oliveira, 2014).

Faraj, Eisa, & Pakhuruddin, (2019) also reported that the nearer resistivity value for CdS film by Spray Pyrolysis technique. The CdS films deposited have the conductivity value

about 4.106×10^{-5} and $6.297 \times 10^{-5} ((\Omega cm)^{-1})$ which are in good agreement with the previous report of (Ahmad et al., 2022). The prepared *CdS* thin film has *n* – type conductivity(Kerimova, Bagiyev, Aliyeva, & Bayramov, 2017).

The bulk concentration is found to be increased from 3.629×10^{11} to 6.996×10^{11} for the increasing of deposition time from 30minutes to 1hour.it was in agreement with work of (Miyake et al., 2004). The film's thickness and crystallinity have a significant impact on how well the bulk concentration and mobility are improved. All *CdS* films displayed semiconducting activity, with resistivities ranging from 10^{-3} to 10^{-5} cm (Ashour, 2003).

The film's resistivity was seen to decrease with longer deposition times.

For *CdTe* thin film deposited on soda lime glass substrate at 1hour deposition time. The values of electrical resistivity , bulk concentration, mobility for the deposited films are listed in Table 2.

Table 2. The values of electrical resistivity, bulk concentration, mobility obtained from Hall Effect measurements.

| SAMPLE | RESISTIVITY (Ωcm) | MOBILITY cm^2/Vs | BULK CONCENTRATION cm^{-3} | AVERAGE HALL COEFFICIENT cm^3/C |
|-------------|--------------------------------|-----------------------|---------------------------------|-----------------------------------------|
| <i>CdTe</i> | 1.016×10^4 | 1.996×10^2 | 3.074×10^{12} | 2.030×10^6 |

From table 2 the resistivity value of *CdTe* thin film was $1.016 \times 10^4 \Omega cm$. This is in agreement with previous works of (Rahman et al., 2019). Miyake, Murase, Hirato, & Awakura,(2004) reported similar values of resistivity of the order 10^4 to 10^8 . Hall effect measurement revealed that the *CdTe* thin film had *p* – type conductivity as the average hall voltage value was found to be positive(Nithyayini & Ramasesha, 2015). The bulk concentration of the *CdTe* thin film value was observed to be $3.074 \times 10^{12} cm^{-3}$. This is in agreement with previous work of (Ahmad et al., 2022).

5. CONCLUSION

CdS and *CdTe* thin films were fabricated by a spray pyrolysis technique. For *CdS* thin films, an aqueous solution of Cadmium acetate dihydrate $\text{Cd}(\text{CH}_3\text{COOH})_2 \cdot 2\text{H}_2\text{O}$ and Thiourea $(\text{NH}_2)_2\text{CS}$, while mixture of $\text{Cd}(\text{CH}_3\text{COOH})_2 \cdot 2\text{H}_2\text{O}$ and Tellurium oxide TeO_2 were used for the production of *CdTe* thin film. From Hall-effect measurements, it is observed that the electrical resistivity of *CdS* thin films decreased from 2.234×10^4 to $1.588 \times 10^4 \Omega\text{cm}$ with respect to deposition time while the conductivity increases. The negative sign and positive sign of the Average Hall coefficient confirmed the *n*-type nature of the semiconducting *CdS* films and p-type nature of *CdTe* thin film.

References;

- Ahmad, F., Maqbool, E., Qurban, N., Fatima, Z., Ahmad, T., Zahid, I., & Ali, A. (2022). *ASEAN Journal of Science and Engineering Electrical Characterization of II-VI Thin Films for Solar Cells Application*. 2(2), 199–208.
- Ashour, A. (2003). *Physical Properties of Spray Pyrolysed CdS Thin*. 27, 551–558.
- Atay, F., Bilgin, V., Akyuz, I., & Kose, S. (2003). *The effect of In doping on some physical properties of CdS films*. 6, 197–203. [https://doi.org/10.1016/S1369-8001\(03\)00085-4](https://doi.org/10.1016/S1369-8001(03)00085-4)
- Dharmadasa, I. M., Bingham, P. A., Echendu, O. K., Salim, H. I., Druffel, T., Dharmadasa, R., ... Abbas, A. (2014). *Fabrication of CdS/CdTe-Based Thin Film Solar Cells Using an Electrochemical Technique*. 380–415. <https://doi.org/10.3390/coatings4030380>
- Fang, L., Chen, J., Xu, L., Su, W. N., Yu, Y., Xu, J., & Ma, Z. Y. (2013). Electron beam evaporation deposition of cadmium sulphide and cadmium telluride thin films: Solar cell applications. *Chinese Physics B*, 22(9). <https://doi.org/10.1088/1674-1056/22/9/098802>
- Faraj, M. G., Eisa, M. H., & Pakhuruddin, M. Z. (2019). *Physical Properties of Spray Pyrolysed Cadmium Sulfide Thin Films Deposited on Different Polymer Substrates*. 14, 10633–10641. <https://doi.org/10.20964/2019.11.11>
- Garba, D. (2011). *Research and development of CdTe based thin film PV solar cells*.
- Hasnat, A., & Podder, J. (2012). *Effect of Annealing Temperature on Structural, Optical and Electrical Properties of Pure CdS Thin Films Deposited by Spray Pyrolysis Technique*.

2012(December), 226–231.

- Ikhmayies, S. J., & Ahmad-bitar, R. N. (2010). Applied Surface Science The influence of the substrate temperature on the photovoltaic properties of spray-deposited CdS : In thin films. *Applied Surface Science*, 256(11), 3540–3544.
<https://doi.org/10.1016/j.apsusc.2009.12.104>
- Jamil, S., & Ahmad-bitar, R. N. (2013). Original article A study of the optical bandgap energy and Urbach tail of spray-deposited CdS : In thin films. *Integrative Medicine Research*, 2(3), 221–227. <https://doi.org/10.1016/j.jmrt.2013.02.012>
- Kerimova, A., Bagiyev, E., Aliyeva, E., & Bayramov, A. (2017). Nanostructured CdS thin films deposited by spray pyrolysis method. *Physica Status Solidi (C) Current Topics in Solid State Physics*, 14(6), 9–11. <https://doi.org/10.1002/pssc.201600144>
- Kulkarni, R., Rondiya, S., Pawbake, A., Waykar, R., & Jadhavar, A. (2017). Structural and optical properties of CdTe thin films deposited using RF magnetron sputtering. *Energy Procedia*, 110(December 2016), 188–195. <https://doi.org/10.1016/j.egypro.2017.03.126>
- Miyake, M., Murase, K., Hirato, T., & Awakura, Y. (2004). *Hall effect measurements on CdTe layers electrodeposited from acidic aqueous electrolyte*. 562, 247–253.
<https://doi.org/10.1016/j.jelechem.2003.09.008>
- Mohammed, B. (2018). *MORPHOLOGICAL AND ELECTRICAL PROPERTIES OF SP DEPOSITED CADMIUM*. (October 2013).
- Mousavi, S. H., Jilavi, M. H., Mu, T. S., & Oliveira, P. W. De. (2014). *Formation and properties of cadmium sulfide buffer layer for CIGS solar cells grown using hot plate bath deposition*. 2786–2794. <https://doi.org/10.1007/s10854-014-1943-x>
- Munna, F. T., Chelvanathan, P., Sobayel, K., Nurhafiza, K., Sarkar, D. K., Nour, M., ... Akhtaruzzaman, M. (2020). Effect of zinc doping on the optoelectronic properties of cadmium sulphide (CdS) thin films deposited by chemical bath deposition by utilising an alternative sulphur precursor. *Optik*, 218(July).
<https://doi.org/10.1016/j.ijleo.2020.165197>
- Nithyayini, K. N., & Ramasesha, S. K. (2015). Fabrication of Semi-Transparent Photovoltaic Cell by a Cost-Effective Technique. *Metallurgical and Materials Transactions E*, 2(3),

157–163. <https://doi.org/10.1007/s40553-015-0053-x>

- Ojeda-barrero, G., Oliva-avilés, A. I., Oliva, A. I., Maldonado, R. D., & Acosta, M. (2018). Materials Science in Semiconductor Processing Effect of the substrate temperature on the physical properties of sprayed-CdS films by using an automatized perfume atomizer. *Materials Science in Semiconductor Processing*, 79(January), 7–13. <https://doi.org/10.1016/j.mssp.2018.01.018>
- Rahman, K. S., Harif, M. N., Rosly, H. N., Kamaruzzaman, M. I. Bin, Akhtaruzzaman, M., Alghoul, M., ... Amin, N. (2019). Influence of deposition time in CdTe thin film properties grown by Close-Spaced Sublimation (CSS) for photovoltaic application. *Results in Physics*, 14(May), 102371. <https://doi.org/10.1016/j.rinp.2019.102371>
- Sajedur, K., Najib, M., Nisham, H., Ibrahim, M., Kamaruzzaman, B., & Alghoul, M. (2019). *Results in Physics Influence of deposition time in CdTe thin film properties grown by Close- Spaced Sublimation (CSS) for photovoltaic application. 14(May).*
- Seboui, Z., Cuminal, Y., Kamoun-turki, N., Seboui, Z., Cuminal, Y., & Kamoun-turki, N. (2013). *Physical properties of Cu₂ZnSnS₄ thin films deposited by spray pyrolysis technique Physical properties of Cu₂ZnSnS₄ thin films deposited by spray pyrolysis technique. 023113.* <https://doi.org/10.1063/1.4795399>
- Sobayel, K., Ra, B., Amin, N., Alharbi, H. F., Luqman, M., Ayob, A., ... Bais, B. (2020). *OPEN WS 2 : A New Window Layer Material for Solar Cell Application. 1–11.* <https://doi.org/10.1038/s41598-020-57596-5>
- Tiwari, A. K., Verma, V. K., Jain, T. A., & Bajpai, P. K. (2014). *Conclusive Growth of CdTe Nanorods by Solvothermal Decomposition Using Single Source Precursors.* (September). <https://doi.org/10.1680/nme.14.00015>