

Review Article

REMINERALIZATION OF TOOTH: A LITERATURE REVIEW

ABSTRACT

Non-cavitated carious lesions are managed non-invasively through remineralization in an attempt to prevent disease progression, and to improve strength, esthetics, and function of teeth in the modern dentistry. The emphasis presently is being given to new technologies which suggest the changes in the understanding of dental caries, and most of them gave significant positive outcome regarding remineralisation when used clinically. The aim of this review article is to put a light on various available remineralizing agents along with some recently introduced agents.

Keywords: Caries, Remineralisation, fluorides, non-fluoridated remineralizing agents

INTRODUCTION

Dental caries is one of the most common oral diseases that affects 60-90% of schoolchildren¹. Dental caries is a multifactorial disease that starts with microbiological shifts within the complex biofilm and is affected by salivary flow and composition, exposure to fluoride, consumption of dietary sugars, and by preventive behaviours (cleaning teeth)². In the face of failure to remove plaque from retentive tooth areas, a diet high in refined carbohydrates, and frequent carbohydrate ingestion, the dynamic equilibrium between demineralization and remineralization will be tipped towards demineralization with the development of clinically detectable white spot lesions³. However, if the pH is higher than 4.5 and F is present, the biofilm fluid is supersaturated with respect to fluorapatite (FA) and there is reprecipitation of minerals in the enamel. As a consequence, the net demineralization is reduced⁴.

“The remineralization process is a natural repair mechanism to restore the minerals again, in ionic forms, to the hydroxyapatite (HAP) crystal

lattice. The process of tooth remineralisation has been studied over many decades of research and has led to the development of technologies that can promote enamel remineralisation or reduce enamel demineralisation thus giving potential oral health benefits”⁵. “Numerous types of remineralizing agents and remineralizing techniques have been researched and many of them are being used clinically, with significantly predictable positive results”⁶.

METHODOLOGY

Articles from “Pubmed” were searched with the keywords Remineralization-demineralization, Casein derivatives, Fluoridated remineralisation agents, Non-fluoridated remineralizing agents. 80 articles discussing remineralizing agents were read and 33 most relevant articles were included in this paper.

DISCUSSION

“F is present in dental biofilm in enamel remineralisation. once After the exposure to sugars has ceased, acids in the biofilm are converted to salts which increases the pH. Once the pH reaches 5.5 or higher, the biofilm fluid is supersaturated with respect to HA and FA. The lost Ca and P by enamel can be recovered more efficiently if the biofilm still contains F”⁴.

IDEAL REQUIREMENTS OF A REMINERALIZING AGENT:⁴

- Calcium and phosphate delivered into the subsurface
- No excess of calcium should be delivered
- No calculus formation
- Able to work at acidic pH during a carious attack to stop demineralization
- Effective in xerostomic patients also, as it increases carious process due to reduced saliva.
- Increases the remineralizing properties of saliva
- Should be able to show some benefits over fluoride.

INDICATIONS:⁴

- An adjunct to preventive therapy in high-risk patients for reducing caries.
- Reduce dental erosion in patients with gastric reflux or other disorders.
- Reduces decalcification in orthodontic patients.
- To repair enamel involving white spot lesions.
- Used for fluorosis, for teeth whitening and to desensitize sensitive teeth.


CLASSIFICATION OF REMINERALISING AGENT⁶

Remineralizing agents have been classified as:

- Fluorides
- Non-fluoride remineralizing agents
 - ✓ Alpha tricalcium phosphate (TCP) and beta TCP (β -TCP)
 - ✓ Amorphous calcium phosphate
 - ✓ CPP-ACP
 - ✓ Sodium calcium phosphosilicate (bioactive glass)
 - ✓ Xylitol
 - ✓ Dicalcium phosphate dehydrate (DCPD)
 - ✓ Nanoparticles for remineralization
 - Calcium fluoride nanoparticles
 - Calcium phosphate-based nanomaterials.
 - NanoHAP particles
 - ACP nanoparticles
 - Nanobioactive glass materials
 - ✓ Polydopamine
 - ✓ PA
 - ✓ Oligopeptides
 - ✓ Theobromine
 - ✓ Arginine
 - ✓ Self-assembling peptides
 - ✓ Electric field-induced remineralization

FLUORIDATED REMINERALIZING AGENTS

Fluoride enhances the mineral content of early carious lesions and increases the speed of remineralisation process, hence, enhances the enamel remineralisation⁷. When enamel is exposed to ionic fluoride, it may result in the formation of either fluorhydroxyapatite or calcium fluoride⁸.



After fluoride therapy, calcium fluoride act as a fluoride reservoir which is not readily soluble. There are several types and forms of fluoride agents used in dentistry⁷.

- 1) Topically applied fluoride therapy: self-applied and professionally applied methods.
 - Self-applied fluoride involves fluoride toothpastes and mouthrinses.
 - “Professionally applied products include fluoride gels, silver diamine fluoride, fluoride varnish, and fluoride-containing restorations and sealants, such as glass ionomer cement”⁹. It is used to arrest dentine caries, to remineralise early enamel caries or white spot lesions⁷.
- 2) Systemic fluorides include milk fluoridation, water fluoridation, fluoride tablets/drops/lozenges and salt fluoridation.

SODIUM FLUORIDE:

The hydroxyapatite crystals in enamel reacts with sodium fluoride solution applied on to the tooth surfaces to form calcium fluoride which forms main end product of the reaction which further forms fluoridated hydroxyapatite. The hydroxyapatite thus formed increases the resistant of tooth surface against the caries attack by increasing the concentration of fluoride on enamel surface. **Gao et al.** showed that the effectiveness of 5% sodium fluoride varnish to remineralize incipient caries lesions¹⁰.

STANNOUS FLUORIDE:

Muhler et al. [1950] introduced 8% and 10% solution of stannous fluoride as a topical anticaries agent during the decade of 1950-1960 and beyond with the pH of 2.1. It was based on the fact that greater reduction in rate of acid dissolution was seen when powdered enamel

was treated with SnF₂. “Some clinical trials showed a greater caries reduction was seen in some clinical trials with one or two annual applications of 8% SnF₂ than from three or four applications of sodium fluoride. However, this conclusion was not seen with other trials”¹¹.

ACIDULATED PHOSPHATE FLUORIDE:

“APF solutions and gels have shown most impressive evidence in support of its use, as a cariostatic reagent, over other agents”¹¹. After the application of APF, dehydration and shrinkage in the volume of hydroxyapatite crystals is seen forming an intermediate product called dicalcium phosphate dihydrate (DCPD) on hydrolysis. This shrinkage results in more fluoride penetration into the crystals more deeply through the openings leading to formation of fluorapatite¹⁰. **Fernandez et al., 2017** has shown “in situ, that the enamel demineralization was inhibited by the combination of single application of a gel containing APF (12,300 ppm F) plus the daily use of a dentifrice (1,100 ppm F) which is as effective as a highly fluoridated dentifrice containing NaF (5,000 ppm F)”¹².

SILVER DIAMINE FLUORIDE:

“Silver diamine fluoride (SDF) is used for caries prevention or control of dental caries as it is an anti-caries agent. SDF is applied until the child is old enough to cooperate during dental treatment”¹³. “The concentration of the most commonly used SDF was 38%, which contains 44,800 ppm fluoride”¹⁴. High concentrations of 38% SDF (44,800 ppm F; 253,870 ppm Ag) and 30% SDF (35,400 ppm F; 200,400 ppm Ag) was used by **Chibinski et al.** and concluded that high concentration of 38% provided greater efficacy in the prevention of dental caries in deciduous teeth than low concentrations¹³. To mask the staining of the cavitated lesions treated with SDF, self-curing glass ionomer cement is used. This technique has been referred to as silver modified atraumatic restorative treatment (SMART)¹⁵.

FLUORIDE CONTAINING SEALANTS AND RESTORATIONS:

According to **Kusgoz et al. 2010**, the incorporation of fluoride in resin-based FS inhibit demineralization of the adjacent tooth structure by releasing fluoride and recharge abilities which is lowered compared

to glass ionomer sealants. It has been seen that fissure sealants forms physical barrier which inhibits the formation of occlusal dental caries as well as the progression of existing carious lesions (**Azarpazhooh and Main,2008**)¹⁶.

NON-FLUORIDATED REMINERALISING AGENTS

TRICALCIUM PHOSPHATE: Tricalcium phosphate (TCP) enhances the levels of calcium in plaque and saliva¹⁷. Remineralization properties are seen in Tri-calcium phosphates with the advantage of the calcium phosphate system, that does not effect the activity of fluoride in dentifrices and is stable in aqueous environment¹⁸. This material is available in two forms of α and β (β particles are less soluble than α particles) with calcium: phosphate ratio of 1:5¹⁹. 5000 ppm sodium fluoride dentifrice and a 5% sodium fluoride varnish are the products available with TCP⁴. **Rao R et al (2017)** evaluated the remineralization potential of fluoride using control group with no surface treatment, ClinPro Tooth Crème, ReminPro paste, Duraphat fluoride varnish. The best remineralization potential was seen by ClinPro tooth Creme followed by Duraphat and ReminPro⁸.

AMORPHOUS CALCIUM PHOSPHATE: The Amorphous Calcium Phosphate (ACP) technology has been developed and commercialized which is an unstabilized calcium and phosphate system where a phosphate salt (e.g., potassium phosphate) and a calcium salt (e.g., calcium sulphate) are delivered. They can be delivered separately (e.g., from a dual-chamber device) intra-orally or delivered in a product with a low water activity (Tung and Eichmiller, 2004)²⁰. In 1999, ACP was first introduced as Enamelon by incorporating into toothpaste and later Church and Dwight reintroduced as Enamel Care toothpaste in 2004¹⁷. "ACP and FACP are considered promising biomimetic materials to hinder demineralization of dental hard tissues in preventive dentistry" according to **Iafisco M. et al (2018)**. "The acid-etched dentin showed good ability to partially occlude the tubules and the demineralized enamel was restored into its native structure"²¹.

CASEIN PHOSPHOPEPTIDES – AMORPHOUS CALCIUM

PHOSPHATE: Casein stabilizes the calcium and phosphate ions by releasing small sequences of peptides (CPPs) through partial enzymic digestion. This leads to the development of a remineralization technology based on casein phosphopeptide-stabilized amorphous calcium fluoride phosphate complexes (CPP -ACFP) and casein phosphopeptide stabilized amorphous calcium phosphate complexes (CPP-ACP)⁴. In 1998, Prof. Reynolds introduced a remineralizing agent at the school of Dental Sciences at the University of Melbourne in Australia named as CPP-ACP (Tooth Mousse, GC India). There is a synergism in remineralising potential when CPP-ACP is combined with fluoride. CPPs enhances efficacy of fluoride as a remineralizing agent by keeping fluoride ions in solution by forming fluoroapatite⁸. **Bailey et al., 2009** concluded that CPP-ACP cream treatment regressed more post-orthodontic white-spot lesions over a 12-week period²⁰.

BIOACTIVE GLASS: Bioglass (BG) consist of calcium, sodium, phosphate, and silicate and belongs to class of bioactive material⁶. Bioactive materials have potential applications in tooth remineralisation and induce calcium phosphate formation. Hench & Anderson bioactive glass in 1969. Bioactive glass formulation consists of 6 wt% P₂O₅, 45 wt% SiO₂ and 4.5 wt% Na₂O and CaO⁸. A fluoride-containing bioactive glass (BioMinF; <http://www.biomin.co.uk>) was introduced recently in toothpastes as a caries remineralising and preventive additive¹⁵. Dr. Len and Dr. Hack introduced Novamin which is manufactured by Novamin technology and is a trade name for bioactive glass⁸. **TahaAA et al (2017)** extensively studied the Bioglass45S5 regarding the remineralization of white spot lesions. Remineralization potential was compared between CPP-ACP treatment, topical fluoride, bioactive glasses, and concluded that enamel remineralization is enhanced by bioactive glasses and is more effective⁸.

XYLITOL: Xylitol has been shown to have cariostatic effects as well as noncariogenic. It is a tooth friendly non-fermentable sugar alcohol⁶. The xylitol chewing gum enhances the protective properties of saliva by

increasing salivary flow rate. This increases the concentration of phosphate and bicarbonate in stimulated saliva. As a result, phosphate and bicarbonate increases in plaque pH which in turn prevents demineralization of tooth structure by increasing the salivary buffering capacity. Moreover, calcium, hydroxyl and phosphate ions in higher concentration in such saliva also enhances remineralization⁵. **Milburn et al. (2015)** have shown the greatest initial fluoride release in the first four hours in fluoride varnish, containing xylitol-coated calcium and phosphate, exceeding 10 times than that of other varnishes such as, Vanish, Duraphat® and Enamel Pro®⁶.

DICALCIUM PHOSPHATE DEHYDRATE : DCPD readily turns into fluorapatite in the presence of fluoride as it is a precursor for apatite⁶. **Walsh LJ, 2009** concluded that inclusion of dicalcium phosphate dehydrate (DCPD) in a dentifrice increases the levels of free calcium ions in plaque fluid when compared to conventional silica dentifrices, which remain elevated for up to 12 hours after brushing¹⁷.

NANOPARTICLES FOR REMINERALISATION: Recently, nanotechnology has attracted a great deal of attention²². Increased cumulative fluoride release on addition of nanoCaF₂ was seen when compared to the traditional glass ionomer cements (**Xu HHK et al.**). When compared with traditional glass ionomer cements, the CaF₂ nanoparticle (nano-CaF₂) has a 20-fold higher surface area⁶. β -TCP nanoparticles with improved cariostatic and remineralizing properties can be prepared on the enamel surface¹⁹. Nano-HA increases the degree of remineralization in acidic conditions by aiding more ions diffusion in the center of the demineralized zone²³. Addition of ACP nanoparticles in composite resins, adhesives and ionomer cements tends to be the source of calcium and phosphate ions⁶. According to **Sheng et al. (2016)**, nanoBG particles promote mineral formation on dentin surfaces and make dentin more acid resistant²⁴.

POLYDOPAMINE: Dopamine, regardless of type, size, and shape of hybridized counterpart materials, has been extensively used for

biomaterial surface modification. **Zhou YZ (2012)** have found that demineralized dentin remineralization was promoted by polydopamine. It was seen that densely packed hydroxyapatite crystals occludes all dentin tubules²⁵.

PA: Polyphenols have anti-inflammatory and antioxidant. Polyphenols are plant-derived substances. Proanthocyanidin (PA) is a polyphenol which is a benzene-pyran-phenolic acid molecular nucleus containing bioflavanoid. Proanthocyanidin, is free radical scavenger and a natural antioxidant. Collagen forms a proline–PA complex as it has high affinity for PA-based components (GSE is a powerful source of PA) and is a proline-rich proteins. There are four different mechanism by which the collagen cross-links increases in GSE : hydrophobic interactions, hydrogen bonding, ionic and covalent. It is expected that GSE is involved in the remineralisation of enamel defects by exogenous collagen crosslinks. **Nagi SM et al (2019)** evaluated that the positive effects of GSE hydrogels on the remineralization process of bleached enamel²⁶.

THEOBROMINE: Two types of substances are present in theobromine which provides cariostatic property: one which exhibits anti-bacterial activity and the other anti-glucosyltransferase²⁷. According to **Amaechi et al.**, theobromine and fluoride toothpaste has given a significantly higher mineral gain with relative to artificial saliva showing the remineralising potential of theobromine⁶.

ARGININE: Arginine bicarbonate is an amino acid with particles of calcium carbonate, which adheres to the mineral surface. After the calcium carbonate dissolves, the release of carbonate may cause a slight rise in local pH whereas the released calcium is available to remineralize the mineral⁶. Recently, arginine incorporated into dentifrice formulations suppresses mineral loss via a buffering effect [**Cummins, 2013a**]. A superior effect of arginine-containing FD (AFD) has been observed in terms of the reversal of white spot lesions in many clinical studies over regular FD [**Srisilapanan et al., 2013; Yin et al., 2013; Li**

et al., 2015a]. However, it is still under debate regarding its clinical significance [Ástvaldsdóttir and Östlund, 2017]²⁸.

SELF-ASSEMBLING PEPTIDES: A biomimetic technology was introduced about a decade ago to promote faster remineralization as minerals from saliva or supplied by other therapies need nucleation sites for precipitation and remineralization, (Kirkham et al. 2007)²⁹. Under defined environmental conditions, rationally designed β -sheet-forming peptides P114 form three-dimensional scaffolds by self-assembling themselves. They nucleate hydroxyl apatite de novo. Self-assembling peptides mimicks the action of enamel matrix proteins during tooth development and have been used in mineralized tissue regeneration⁴. Nowadays, P11-4 is available as a commercial products named as Curolox Technology (credentis ag, Windisch, Switzerland)³⁰. **Alkilzy et al. (2017)** suggested that on promoting remineralization of early carious lesions , P11-4 in combination with F varnish (22,600-ppm F) is superior than F varnish alone. Others RCTs are currently registered (NCT02101255, NCT02020681, NCT02119507, NCT02913885, NCT02341872)²⁹.

ELECTRIC FIELD-INDUCED REMINERALIZATION: Wu et al. (2015) have introduced this technique to shorten the mineralization time with the help of electrophoresis achieved in the absence of both calcium phosphates and their analogs. It also remineralize the completely demineralized dentin collagen matrix and³¹.

CONCLUSION

The preventive approach of identification, conservation, and non-restorative treatment of incipient caries saves both dental manpower and expense and suffering for the patient. With a clearer understanding of the implementation of these remineralizing agents and new technologies accessible to dentists, one can create a more favorable relationship in which remineralization occurs more often than demineralization. And further requires more detailed clinical knowledge and trials along with a

“watching brief” methodology necessary for this rapidly progressing area of dental science.

REFERENCES

1. Kundu H, Patthi B, Singla A, Jankiram C, Jain S, Singh K. Dental Caries Scenario Among 5, 12 and 15-Year-old Children in India- A Retrospective Analysis. *J Clin Diagn Res.* 2015 Jul;9(7):ZE01-5. doi: 10.7860/JCDR/2015/12439.6150. Epub 2015 Jul 1. PMID: 26393229; PMCID: PMC4573062.
2. Selwitz RH, Ismail AI, Pitts NB. Dental caries. *Lancet.* 2007 Jan 6;369(9555):51-9. doi: 10.1016/S0140-6736(07)60031-2. PMID: 17208642.
3. Hicks J, Garcia-Godoy F, Flaitz C. Biological factors in dental caries enamel structure and the caries process in the dynamic process of demineralization and remineralization (part 2). *J Clin Pediatr Dent.* 2004 Winter;28(2):119-24. doi: 10.17796/jcpd.28.2.617404w302446411. Erratum in: *J Clin Pediatr Dent.* 2004 Spring;38(3):214. PMID: 14969369.
4. Preethi, Naveena. (2014). Remineralizing Agent -Then and Now -An Update. *Dentistry.* 04. 10.4172/2161-1122. 1000256.
5. Li X, Wang J, Joiner A, Chang J. The remineralisation of enamel: a review of the literature. *J Dent.* 2014 Jun;42 Suppl 1:S12-20. doi: 10.1016/S0300-5712(14)50003-6. PMID: 24993850.
6. Arifa MK, Ephraim R, Rajamani T. Recent Advances in Dental Hard Tissue Remineralization: A Review of Literature. *Int J Clin Pediatr Dent.* 2019 Mar-Apr;12(2):139-144. doi: 10.5005/jp-journals-10005-1603. PMID: 31571787; PMCID: PMC6749882.
7. Gao SS, Zhang S, Mei ML, Lo EC, Chu CH. Caries remineralisation and arresting effect in children by professionally applied fluoride treatment - a systematic review. *BMC Oral Health.* 2016 Feb 1;16:12. doi: 10.1186/s12903-016-0171-6. PMID: 26831727; PMCID: PMC4736084.
8. Jindal L, Anukriti NB. Tooth Remineralization: Averting the Dental Decay. *J Res Adv Dent* 2020;10:4:37-45.
9. Nantanee R, Santiwong B, Trairatvorakul C, Hamba H, Tagami J. Silver diamine fluoride and glass ionomer differentially remineralize early caries

- lesions, in situ. Clin Oral Investig. 2016 Jul;20(6):1151-7. doi: 10.1007/s00784-015-1603-4. Epub 2015 Sep 23. PMID: 26395352.
10. Peter S. (2017). Essentials Of Public Health Dentistry (Community Dentistry). 6th Edition.
 11. Nikiforuk, G. (1985). Understanding Dental Caries i Etiology and Mechanisms Basic and Clinical Aspects.
 12. Erdwey D, Meyer-Lueckel H, Esteves-Oliveira M, Apel C, Wierichs RJ. Demineralization Inhibitory Effects of Highly Concentrated Fluoride Dentifrice and Fluoride Gels/Solutions on Sound Dentin and Artificial Dentin Caries Lesions in vitro. Caries Res. 2021;55(1):41-54. doi: 10.1159/000509931. Epub 2020 Dec 7. PMID: 33285548.
 13. Punhagui MF, Jussiani EI, Andrello AC, Favaro JC, Guiraldo RD, Lopes MB, Berger SB. Effect of application time and concentration of silver diamine fluoride on the enamel remineralization. J Clin Exp Dent. 2021 Jul 1;13(7):e653-e658. doi: 10.4317/jced.58318. PMID: 34306528; PMCID: PMC8291156.
 14. Yu OY, Mei ML, Zhao IS, Li QL, Lo EC, Chu CH. Remineralisation of enamel with silver diamine fluoride and sodium fluoride. Dent Mater. 2018 Dec;34(12):e344-e352. doi: 10.1016/j.dental.2018.10.007. Epub 2018 Oct 25. PMID: 30482611.
 15. Amaechi BT. Remineralisation - the buzzword for early MI caries management. Br Dent J. 2017 Aug 11;223(3):173-182. doi: 10.1038/sj.bdj.2017.663. PMID: 28798421.
 16. Dionysopoulos D, Sfeikos T, Tolidis K. Fluoride release and recharging ability of new dental sealants. Eur Arch Paediatr Dent. 2016 Feb;17(1):45-51. doi: 10.1007/s40368-015-0200-1. Epub 2015 Aug 12. PMID: 26264161.
 17. Goswami M, Saha S, Chaitra TR. Latest developments in non-fluoridated remineralizing technologies. J Indian Soc Pedod Prev Dent. 2012 Jan-Mar;30(1):2-6. doi: 10.4103/0970-4388.95561. PMID: 22565510.
 18. Bajaj M, Poornima P, Praveen S, Nagaveni NB, Roopa KB, Neena IE, Bharath KP. Comparison of CPP-ACP, Tri-Calcium Phosphate and Hydroxyapatite on Remineralization of Artificial Caries Like Lesions on Primary Enamel -An in vitro Study. J Clin Pediatr Dent. 2016;40(5):404-9. doi: 10.17796/1053-4628-40.5.404. PMID: 27617382.

19. Tavassoli-Hojjati S, Atai M, Haghgoo R, Rahimian-Imam S, Kameli S, Ahmaian-Babaki F, Hamzeh F, Ahmadyar M. Comparison of various concentrations of tricalcium phosphate nanoparticles on mechanical properties and remineralization of fissure sealants. *J Dent (Tehran)*. 2014 Jul;11(4):379-88. Epub 2014 Jul 31. PMID: 25584048; PMCID: PMC4283738.
20. Cochrane NJ, Cai F, Huq NL, Burrow MF, Reynolds EC. New approaches to enhanced remineralization of tooth enamel. *J Dent Res*. 2010 Nov;89(11):1187-97. doi: 10.1177/0022034510376046. Epub 2010 Aug 25. PMID: 20739698.
21. Iafisco M, Degli Esposti L, Ramírez-Rodríguez GB, Carella F, Gómez-Morales J, Ionescu AC, Brambilla E, Tampieri A, Delgado-López JM. Fluoride-doped amorphous calcium phosphate nanoparticles as a promising biomimetic material for dental remineralization. *Sci Rep*. 2018 Nov 19;8(1):17016. doi: 10.1038/s41598-018-35258-x. PMID: 30451901; PMCID: PMC6242929.
22. Manchery N, John J, Nagappan N, Subbiah GK, Premnath P. Remineralization potential of dentifrice containing nanohydroxyapatite on artificial carious lesions of enamel: A comparative *in vitro* study. *Dent Res J (Isfahan)*. 2019 Sep 5;16(5):310-317. PMID: 31543937; PMCID: PMC6749857.
23. Juntavee A, Juntavee N, Hirunmoon P. Remineralization Potential of Nanohydroxyapatite Toothpaste Compared with Tricalcium Phosphate and Fluoride Toothpaste on Artificial Carious Lesions. *Int J Dent*. 2021 Mar 20;2021:5588832. doi: 10.1155/2021/5588832. PMID: 33824661; PMCID: PMC8007336.
24. Sheng XY, Gong WY, Hu Q, Chen XF, Dong YM. Mineral formation on dentin induced by nano-bioactive glass. *Chinese Chemical Letters*. 2016 Sep 1;27(9):1509-14.
25. Zhou YZ, Cao Y, Liu W, Chu CH, Li QL. Polydopamine-induced tooth remineralization. *ACS Appl Mater Interfaces*. 2012 Dec;4(12):6901-10. doi: 10.1021/am302041b. Epub 2012 Dec 4. PMID: 23176019.
26. Nagi SM, Hassan SN, Abd El-Alim SH, Elmissiry MM. Remineralization potential of grape seed extract hydrogels on bleached enamel compared to fluoride gel: An *in vitro* study. *J Clin Exp Dent*. 2019 May 1;11(5):e401-e407. doi: 10.4317/jced.55556. PMID: 31275511; PMCID: PMC6599700.

27. Premnath P, John J, Manchery N, Subbiah GK, Nagappan N, Subramani P. Effectiveness of Theobromine on Enamel Remineralization: A Comparative In-vitro Study. *Cureus*. 2019 Sep 17;11(9):e5686. doi: 10.7759/cureus.5686. PMID: 31720155; PMCID: PMC6823004.
28. Sanchez AY, de Oliveira CL, Negrini TC, Hashizume LN, Hara AT, Maltz M, Arthur RA. In situ Effect of Arginine-Containing Dentifrice on Plaque Composition and on Enamel Demineralization under Distinct Cariogenic Conditions. *Caries Res*. 2018;52(6):588-597. doi: 10.1159/000488212. Epub 2018 May 4. PMID: 29730666.
29. González-Cabezas C, Fernández CE. Recent Advances in Remineralization Therapies for Caries Lesions. *Adv Dent Res*. 2018 Feb;29(1):55-59. doi: 10.1177/0022034517740124. PMID: 29355426.
30. Jablonski-Momeni A, Nothelfer R, Morawietz M, Kiesow A, Korbmacher-Steiner H. Impact of self-assembling peptides in remineralisation of artificial early enamel lesions adjacent to orthodontic brackets. *Sci Rep*. 2020 Sep 15;10(1):15132. doi: 10.1038/s41598-020-72185-2. PMID: 32934335; PMCID: PMC7493957.
31. Wu XT, Mei ML, Li QL, Cao CY, Chen JL, Xia R, Zhang ZH, Chu CH. A Direct Electric Field-Aided Biomimetic Mineralization System for Inducing the Remineralization of Dentin Collagen Matrix. *Materials (Basel)*. 2015 Nov 20;8(11):7889-7899. doi: 10.3390/ma8115433. PMID: 28793685; PMCID: PMC5458896.