

Original Research Article
Quality Characterization of Instant Pounded Yam Flour and Its Composites Using Principal Component Analysis

ABSTRACT

Aims: This study examined the functional and pasting characteristics of composite Instant Pounded Yam Flour (IPYF) made from varying substitution levels (15%, 30% and 45%) of Dehulled White Sorghum Flour (DWSF), White Rice Flour (WREF) and High Quality Cassava Flour (HQCF).

Study Design: The study was a factorial design.

Place and Duration of Study: The study was carried out at Food Technology Department, Federal Institute of Industrial Research, Oshodi, Lagos State and Department of Food, Nutrition and Home Science, University of Port Harcourt (Processing and analysis of raw materials) between September, 2022 and May, 2023.

Methodology: Raw materials were processed into flours and combined with at varying levels. The functional and pasting properties of the flours (individual and composite samples) were subsequently determined and then subjected to Principal Component Analysis.

Results: Significant differences ($P=0.05$) were found between the functional and pasting characteristics of the various flour samples, with IPYF having the highest mean value of 0.85 ± 0.02 , 243.00 ± 3.00 , 79.50 ± 1.00 , 7.00 ± 0.56 and 83.10 ± 0.75 for pack bulk density, water absorption capacity, water binding capacity, peak time and pasting temperature respectively among others while HQCF has the highest mean value for oil absorption capacity (104.95 ± 2.77) and peak viscosity (350.75 ± 1.04), DWSF has the highest mean value setback viscosity (140.33 ± 0.92) and white rice flour has the highest mean value for trough viscosity (227.75 ± 1.84) and final viscosity (334.67 ± 1.62). Significant variations ($P=0.05$) were also seen across the composite flours, with the peak viscosity of the HQCF-IPYF increasing with the level of replacement.

Conclusion: 15% HQCF substitution would be recommended for the production of composite IPYF that has the same functional and pasting characteristics of 100% Instant Pounded Yam Flour.

Keywords: Functional Properties, Pasting Properties, Instant Pounded Yam Flour, Composite Flour, Principal Component Analysis.

1.0 INTRODUCTION

In most Sub-Saharan African nations, yam (*Dioscorea esculenta*), is one of the key staple food crops that has been highlighted as one of the strategies to fight hunger, reduce post-harvest losses, and give rural farmers more leverage [1]. Apart from this, yam occupies an exalted position when it comes to African traditional rites and celebrations that only allow for the preparation of pounded yam [2]. However, researchers have developed the concept of Instant Pounded Yam Flour (IPYF) in response to the desire for a convenient food and the removal laboriousness involved in making pounded yam [3,4,5].

IPYF is a value-added yam product that is gaining popularity since it can be quickly transformed into pounded yam by gradually dissolving with continuous of the flour in a measured quantity of boiling water over a fire until a solid mass with the correct texture is obtain [5,6]

Over the years, investors have begun the creation of composite IPYF as a means of decreasing the cost of production and maximizing profit returns on investment [7]. Composite flour is an innovative flour that has attracted much attention in research as well as food product development [8,9,10,11,12].

Some of the components that are now being added to IPYF are flour made from staple cereal and tuber crops. These crops include cereals (sorghum, rice, maize) as well as roots and tubers (cassava and potatoes). Since functional and pasting qualities are among the important quality indices that define the degree of acceptability of starch-based foods products by consumers; therefore the level of substitution would has a considerable impact on the overall quality of the product [13]. Researchers have investigated the functional and pasting qualities of composite flour from various biological sources [11, 14, 15, 16].

The use of principal component analysis (PCA) to find patterns in data and express that data in a fashion that highlights its similarities and differences is growing; and the main goal of PCA is to keep as much variance in the data set as feasible while reducing the dimensionality of a data set made up of numerous connected variables [17].

In this work, Dehulled White Sorghum Flour, High Quality Cassava Flour and Rice flour were investigated for their possible use at varied levels of substitution in the manufacturing of IPYF composite. Based on their functional and pasting characteristics, the composite flour generated was compared and contrasted using principal component analysis (PCA).

2.0 MATERIALS AND METHODS

2.1 Materials: The yam tubers (*Dioscorea esculenta*), rice (*Oryza sativa*) (white variety) and sorghum (*Sorghum bicolor*) (white variety) were purchased from Ile-Epo commodity market in Lagos State while High Quality Cassava Flour (HQCF) was supplied by Wahan Food Nigeria Ltd.

2.2 Methods

2.2.1 Production of Flours

The rice (white) was first cleaned and sorted to remove all extraneous matter before milling into flour and packaging to obtain the white rice flour. The sorghum (white) was also cleaned, sorted, dehulled and milled to obtain dehulled white sorghum flour. These flours and HQCF were used as substitute for the production of composite Instant Pounded Yam Flour (IPYF).

The method of FIIRO[6] was used in the production of Instant Pounded Yam Flour (IPYF). The processes are: weighing and sorting of raw yam tubers, washing and peeling, size-reduction (3-5mm in thickness), pre-treatment ($\text{Na}_2\text{S}_2\text{O}_5$ Solution (200ppm) for 15 min contact time), steam parboiling, drying (cabinet (60°C for 5hr)), milling, cooling and packaging.

2.2.2 Production of composite IPYF

High Quality Cassava Flour (HQCF), Dehulled White Sorghum Flour (DWSF) and White Rice Flour (WREF) were used for the production of composite IPYF at three different levels (15, 30 and 45%) of substitutions.

2.3 Analyses

2.3.1 Functional Properties

A. Loose and Pack Bulk Densities:

These were determined using the method of AOAC [18]. About 10 g of the flours was weighed into a 50 ml graduated measuring cylinder. The cylinder were not tapped (loose bulk densities) and gently tapped (pack bulk densities) against the palm of the hand until a constant volume was obtained.

$$\text{Loose bulk density} = \frac{\text{Weight of sample} \times 100}{\text{Volume of sample without tapping}}$$

$$\text{Pack bulk density} = \frac{\text{Weight of sample} \times 100}{\text{Volume of sample after tapping}}$$

B. Water Absorption Capacity (WAC) and Oil Absorption Capacity (OAC)

The water absorption capacity (WAC) and oil absorption capacity (OAC) (replacing water with olive oil) of the samples was determined using the method described by Beuchat [19]. About one gram (1 g) each of a sample was mixed with 10 ml of distilled water (or olive oil) and blended for 30 s. It was allowed to stand for 30 min and centrifuged at 3,500 rpm for 30 min at room temperature. The supernatant was decanted and weight of water absorbed by the flour was calculated and expressed as WAC (or OAC).

C. Water Binding Capacity

Water binding capacity of the samples was determined using the Medcalf and Gillies [20] method. About 15 ml of distilled water was added into 1.25 g of the flour and was centrifuged for 10 min at 3000 rpm. The weight of the centrifuge tube and content was determined after decanting the water and allowed to drain for another 10 min. The bound water was determined by the change in weight. It was calculated by the following formula.

$$\text{Water binding capacity (WBC)} = \frac{\text{Bound water (g)} \times 100}{\text{Weight of sample}}$$

D. Dispersibility

This was determined by the method describe by Kulkarni *et al.* [21]. Samples were weighed (10 g each) into 100 ml measuring cylinder and distilled water added to reach a volume of 100 ml. The set up was stirred vigorously and allowed to settle for 3 h. The volume of settled particles was recorded and subtracted from 100. The difference was then reported as percentage dispersibility.

2.3.2 Pasting Properties

The pasting properties of the samples were determined as described by Adebawale *et al.*, [22] using a Rapid Visco Analyzer (RVA) (Model RVA - 4C, Newport Scientific, Warriewood, Australia) interfaced with a personal computer equipped with the Thermocline Software also supplied by Newport Scientific.

Approximately 3 g of each sample was weighed into a canister and made into slurry by adding 25 ml of distil water. This canister (covered with a stirrer) was inserted into the RVA. The heating and cooling cycles of the RVA was programmed such that the slurry was held at 50 °C for 1 min, heated to 95 °C within 3 min and then held at 95 °C for 2 min. It was subsequently cooled to 50 °C within 3 min and then held at 50 °C for 2 min, while maintaining a rotation speed of 160 rpm. The viscosity was expressed as rapid viscosity units (RVU).

The following parameters were determined automatically by the RVA - peak viscosity (the maximum viscosity during pasting), breakdown viscosity (the difference between the peak viscosity and the minimum viscosity during pasting), setback viscosity (the difference between the maximum viscosity during cooling and the minimum viscosity during pasting), final viscosity (the viscosity at the end of the RVA run), pasting temperature ($^{\circ}\text{C}$) (the temperature at which there is a sharp increase in viscosity of flour suspension after the commencement of heating) and peak time (min) (time taken for the paste to reach the peak viscosity).

2.4 Statistical Analysis

The data obtained were subjected to Analysis of Variance (ANOVA) and Pearson correlation using SPSS (Version 17.0) software package. The significance of sample means was tested at $p < 0.05$ probability level using Duncan's Multiple Range Test (DMRT).

Principal component analysis (PCA) (to examine the variation in the functional and pasting properties of the flour samples) was done with the Statistical Tool for Agricultural Research (STAR) Software (Version 2.0.1). Solution was accepted when eigen values were greater than one (1) [23]. Factor loadings equal to or greater than 0.3 were considered to be defining part of a principal component). Biplot and scree plot displays of PCA was used to visualize the variation pattern.

3.0 Results and Discussion

3.1 Functional Properties of Flour Samples

Table 1 presents the functional properties of the flour samples. Density compares the weight and volume of any substance. It has an impact on materials handling and packaging design and how wet processing could be used in the food business [24,25]. The results of the densities for High Quality Cassava Flour (HQCF), rice flour (WREF), dehulled white sorghum flour (DWSF) and Instant Pounded Yam Flour (IPYF) ranged from 0.30– 0.71(g/cm^3) and 0.48 – 0.85(g/cm^3) respectively for loose bulk density (LBD) and pack bulk density (PBD) of the flour samples. The result revealed that the samples differ significantly ($P=0.05$) from one another with IPYF having the highest value for these two properties while HQCF had the least values. Shittu *et al.*, [26] reported that the bulk density value for HQCF from 43 cassava varieties resistant to mosaic disease ranges from 0.39 – 0.55(g/cm^3). This indicated that HQCF might need the least amount of packaging material due to its densities [27].

The capacity of flour to absorb significant amounts of water, preventing exudation while swelling for better meal consistency, is known as water absorption capacity. All flours and starches used in food preparations must possess the capacity to absorb water [28]. The water absorption capacity values of HQCF, DWSF, WREF and IPYF were significantly different ($p < 0.05$) with values ranging from 120.79% to 229.41%.

The mean values for IPYF and DWSF were respectively the greatest and lowest which however did not differ significantly ($P=0.05$) from WREF. This implies that IPYF have more hydrophilic constituent than HQCF, DWSF and WREF; and hence would have better reconstitution ability [29].

Generally, the ability of any food materials to absorb water is more often than not attributed to its proteins content [30]. However, this cannot be said of these flour samples because they are mainly starch-based and are very poor in protein; therefore the observed differences in water absorbed may have been due to the nature of the starch in the flour samples [31]. Carbohydrate has also been linked to influence water absorption capacity of foods [32]. This view was also supported by Adegunwa *et al.* [33] who reported that observed differences in water absorption capacity of the carbohydrate based flours may be due to factors like their amylose/amylopectin ratio as well as their molecular structure.

Table 1: Functional Properties of High Quality Cassava Flour (HQCF), Dehulled White Sorghum Flour (DWSF), White Rice Flour (WREF) and Instant Pounded Yam Flour (IPYF) and their Composites

Sample		LDB (g/cm ³)	PBD (g/cm ³)	WAC (%)	OAC (%)	WBC (g/g)	Disp (%)	
100 % Flour	HQCF	0.30 ^d ± 0.02	0.48 ^c ± 0.02	128.01 ^b ± 3.01	104.95 ^a ± 2.77	137.00 ^b ± 3.12	76.50 ^b ± 0.5	
	DWSF	0.36 ^c ± 0.02	0.58 ^b ± 0.01	120.79 ^c ± 3.81	76.47 ^c ± 3.74	131.68 ^b ± 2.17	69.00 ^c ± 0.20	
	WREF	0.46 ^b ± 0.02	0.59 ^b ± 0.01	127.72 ^{cb} ± 4.78	72.28 ^d ± 2.14	133.33 ^{bc} ± 3.26	75.50 ^b ± 0.50	
	IPYF	0.71 ^a ± 0.03	0.85 ^a ± 0.02	229.41 ^a ± 4.73	90.29 ^b ± 3.75	243.00 ^a ± 3.00	79.50 ^a ± 1.00	
Composite Flours	HQCF	15%	0.58 ^c ± 0.02	0.63 ^c ± 0.01	222.75 ^a ± 4.12	76.24 ^b ± 2.06	228.43 ^a ± 2.56	73.00 ^a ± 1.00
		30%	0.48 ^e ± 0.01	0.56 ^d ± 0.01	213.96 ^b ± 2.98	75.49 ^{bc} ± 1.92	213.86 ^{cd} ± 3.03	72.00 ^{ab} ± 1.00
		45%	0.47 ^e ± 0.02	0.55 ^d ± 0.01	201.98 ^c ± 4.10	89.22 ^a ± 2.10	200.99 ^f ± 4.61	71.00 ^{bc} ± 0.50
	DWSF	15%	0.62 ^b ± 0.02	0.76 ^b ± 0.01	213.53 ^b ± 3.25	69.31 ^e ± 1.92	220.79 ^b ± 3.94	71.50 ^{bc} ± 1.00
		30%	0.54 ^d ± 0.02	0.76 ^b ± 0.02	196.04 ^c ± 4.01	72.82 ^{cd} ± 2.02	219.00 ^{bc} ± 4.03	70.50 ^{de} ± 0.50
		45%	0.47 ^e ± 0.01	0.64 ^d ± 0.01	182.97 ^d ± 3.95	68.63 ^e ± 1.81	190.00 ⁱ ± 3.00	70.00 ^c ± 1.00
	WREF	15%	0.70 ^a ± 0.01	0.79 ^a ± 0.02	218.43 ^b ± 2.51	64.08 ^f ± 1.12	222.77 ^{ab} ± 4.15	72.50 ^{ab} ± 1.00
		30%	0.61 ^b ± 0.01	0.79 ^a ± 0.01	200.99 ^c ± 3.00	71.29 ^{de} ± 1.07	208.82 ^{de} ± 4.07	71.00 ^{bcd} ± 1.00
		45%	0.63 ^b ± 0.02	0.75 ^b ± 0.03	188.00 ^d ± 3.01	68.63 ^e ± 1.42	202.97 ^{ef} ± 4.10	71.00 ^{cde} ± 0.50

Note: Values are means of triplicate determinations; ± - SD value;

Mean values with different superscript within column are significantly different (P<0.05).

LBD = Loose bulk density, PBD = Pack bulk density, WAC = Water absorption capacity, OAC = Oil absorption capacity, WBC = Water binding capacity, DISP = Dispersibility

Fat serves as a flavor keeper and enhances the mouth feel of foods; therefore the flour's ability to physically bind fat through capillary attraction is known as its oil absorption capacity [34]. The mean oil absorption capacity of the flour samples differs significantly ($P=0.05$) with WREF having the least value (72.28%) while HQCF has the highest value (104.95%). The ability of flour to absorb oil well makes it possible to improve flavor and mouth feel [24].

The capacity of starch or starch blends to reconstitute in water is measured by dispersibility. There was a significant ($P=0.05$) difference in the dispersibility of the flours with IPYF having the maximum dispersibility. This might be as a result of IPYF absorbing more water than the other samples [35]; suggesting that it might reconstitute easily and create a fine paste free of lumps more effectively than the other flour [36].

The range of values for the composite samples are 0.47 - 0.70 (g/cm^3) for LBD and 0.55 - 0.79 (g/cm^3) for PBD, respectively. The results of the composite flours showed that the sample with the highest mean packed bulk density value had a 15% substitution of white rice flour, while the composite with the lowest mean packed bulk density value had a 45% substitution of HQCF, though it did not differ significantly ($P=0.05$) from the composite with 30% HQCF and 45% sorghum flour substitution.

With the exception of composites made with white rice flour, which do not significantly differ ($P=0.05$) at 30 and 45% levels of substitution, there was generally a decrease in the mean packed bulk density value of the composite flour as the level of substitution of the cereal and tuber flours to IPYF increased. This trend would enhance ease of dispersion as well a decrease in paste thickness which are two crucial factors in convalescent kid feeding, making higher bulk density desirable [37].

Similar to the composite IPYF, their mean water absorption capacity indicated a significant variation ($P=0.05$), with values ranging from 188.00% to 222.75%. As the rate of substitution increases, the values fall regardless of the type of flour used. The loose connection of amylose and amylopectin in native starch granules and the reduced associative interactions within the granule structure may be responsible for this effect [38]. The discrepancies in the mean water absorption capacity values of the composite samples may also reflect differences in the degree of engagement to establish covalent and hydrogen bonds between starch chains and the degree of availability of water binding sites among the starches [39].

With the composite flours, the ability of HQCF-IPYF composite to absorb oil rises as the degree of substitution is increased, but that of DWSF-IPYF and WREF-IPYF composites fall as the level of substitution increases. The obtained values differed significantly ($P=0.05$) across the composite IPYF samples with the value decreasing as the quantity of substitution increases. This might negatively affect the qualities of meals and the food capacity to reconstitute, texture and mouthfeel [35]. The correlation result (Table 3) of this investigation showed that bulk density (LBD and PBD) had favorable positive correlations with water binding capacity ($r = 0.611$, $P<0.01$) and ($r = 0.766$, $P<0.01$) respectively for LBD and PBD, trough viscosity ($r = 0.401$, ($P=0.05$)) for LBD, peak time ($r = 0.584$, $P<0.01$) and ($r = 0.521$, $P<0.01$) respectively for LBD and PBD and pasting temperature ($r = 0.401$, $P<0.05$) and ($r = 0.632$, $P<0.01$) while it has negative correlation with breakdown viscosity ($r = - 0.550$, $P<0.01$). Awoyaleet *al.* [40] found a significant positive association between bulk density and water absorption index. Water absorption capacity has a positive correlation ($r = 0.599$, $P<0.01$) with oil absorption capacity, water binding capacity ($r = 0.372$, $P<0.05$), peak viscosity ($r = 0.403$, $P=0.05$) and negative correlation with dispersibility ($r = - 0.397$, $P=0.05$) and pasting temp ($r = - 0.401$, $P=0.05$). Dispersibility has a negative correlation ($r = - 0.555$, $P<0.01$) with peak time.

3.2 Pasting Properties of Flour Samples

The pasting qualities of starch-based meals are typically evaluated to determine whether their use as a functional ingredient in foods and other industrial goods is appropriate [41,42]. Pasting temperature, peak viscosity, viscosity at 95°C (trough), viscosity at constant 95°C (breakdown), viscosity at 50°C (final viscosity), and viscosity at constant 50°C (setback) are the characteristics that are significant and typically measured during the pasting cycle [43].

The pasting characteristics of High Quality Cassava Flour (HQCF), Dehulled White Sorghum Flour (DWSF), White Rice Flour WREF and Instant Pounded Yam Flour (IPYF) samples are as presented in Table 2. The peak viscosity is the highest viscosity that the paste can reach while being heated (50°C and 95°C) as a result of the starch granules expanding and the subsequent leaching of the soluble ingredients into the solution. It illustrates the starch granules' capacity to expand without restriction before breaking down physically [44].

The mean peak viscosity of the flour samples varied significantly ($P=0.05$) for the flour samples. Both HQCF and IPYF had mean peak viscosities that were higher than those of either rice flour or sorghum flour. This result supported earlier claims made by Van Hung *et al.*, [43] and Biliaderis [44] that cereal starches have lower peak viscosities than tuber and root starches; and that higher peak viscosities are associated with pastes with desirable texture [46]. According to Eriksson *et al.*, [47], the difference in the peak viscosity of the flour samples can be attributable to the starch granules' varying degrees of swelling.

He reported that the associative bonding of the amylose fraction is responsible for the structure and pasting behavior of starch granule.

With rice flour having the greatest mean value and sorghum having the lowest; the mean results of the trough viscosity (minimum viscosity value that assesses the ability of the paste to withstand breakdown during cooling of the samples) revealed a significant difference ($p<0.05$). This shows that compared to the other samples, rice flour was better able to endure shear at high temperatures [48,49].

When starch is cooked to 95°C, its breakdown viscosity usually decreases; this is a sign of starch gel stability or dissolution during cooking [42]. The differences in the breakdown viscosity of the flour samples were significant ($P=0.05$). When the flour samples (HQCF, DWSF, WREF, and IPYF) were broken down, it was found that HQCF had the highest value and IPYF had the lowest value. The ability of the sample to tolerate heating and shear stress during cooking was shown to be inversely correlated with the degree of viscosity breakdown, according to authors' reports [22,42,50]. This suggests that IPYF would be more able to tolerate heating and shear stress during cooking than the other flour samples as the breakdown viscosity is typically regarded as a measure of paste stability [51].

The change in viscosity after cooking starch at 50°C is the final viscosity. The ability of a starch-based sample to form a gel or viscous paste after cooking and chilling, as well as the resistance of the viscous paste to shear stress during stirring, is one of the most frequently used parameters to define the quality of a starch-based sample [22]. The final viscosity of the flour samples differs significantly ($P=0.05$). HQCF was the only sample with a higher hot paste viscosity than IPYF and the other samples.

The outcome confirms that after cooking and cooling, yam pastes generally produce firm gels rather than viscous gels. This is caused by the strong connection and high re-crystallization potential of the starch-water systems, which cause steadily increasing viscosities as yam starches cool [52]. Additionally, he noted that the degree of starch-water binding, which may be influenced by processes that impact how the starch particles interact with water, determines how quickly the formation of stiffness happens in yam starches.

When a heated substance is cooled, its viscosity recovers, and this is known as setback viscosity.

The mean setback viscosity value showed a significant difference ($P=0.05$) for the flour samples with IPYF having the highest value. This result is in agreement with the findings of some authors [53,54,55] who reported that yam starch has a high setback as a result of retrogradation in comparison with other root and tuber crops.

The pasting temperature is an indicator of the lowest temperature needed to cook a specific flour or starch sample. It is also the temperature at which the first discernible rise in viscosity, a marker of the first alteration brought on by the starch swelling is detected [56,57]. The pasting temperatures of the flour samples varied significantly ($P=0.05$). Of the flour samples, IPYF sample had the highest mean pasting temperature, while rice flour had the lowest.

Table 2: Pasting Properties of High Quality Cassava Flour (HQCF), Dehulled White Sorghum Flour (DWSF), White Rice Flour (WREF) and Instant Pounded Yam Flour (IPYF) and their Composites

Sample		Peak Viscosity (RVU)	Trough Viscosity (RVU)	Breakdown Viscosity (RVU)	Final Viscosity (RVU)	Setback Viscosity (RVU)	Peak Time (Mins)	Pasting Temp. (°C)	
100 % Flours	HQCF	350.75 ^a ± 1.04	159.08 ^b ± 0.94	191.67 ^a ± 0.84	225.25 ^c ± 0.42	66.17 ^c ± 0.48	4.13 ^c ± 0.22	74.45 ^b ± 0.12	
	DWSF	173.42 ^d ± 0.96	116.33 ^c ± 0.52	57.08 ^c ± 0.51	256.67 ^b ± 0.75	140.33 ^a ± 0.92	5.07 ^b ± 0.35	79.90 ^{ab} ± 1.26	
	WREF	241.00 ^c ± 0.78	227.75 ^a ± 1.84	13.25 ^b ± 0.63	334.67 ^a ± 1.62	107.75 ^b ± 0.94	5.60 ^b ± 0.31	79.85 ^{ab} ± 0.68	
	IPYF	310.17 ^b ± 0.96	225.25 ^a ± 1.52	84.75 ^d ± 0.92	333.58 ^a ± 1.86	108.33 ^b ± 0.64	7.00 ^a ± 0.56	83.10 ^a ± 0.75	
Composite Flours	HQCF	15%	254.83 ^a ± 1.03	234.3 ^b ± 1.08	20.50 ^d ± 1.43	282.58 ^d ± 1.68	48.25 ^f ± 1.02	7.00 ^a ± 0.12	76.65 ^d ± 0.06
		30%	244.65 ^b ± 1.54	225.00 ^c ± 2.54	24.80 ^b ± 1.21	317.83 ^b ± 2.53	92.83 ^d ± 1.25	6.53 ^b ± 0.20	73.45 ^e ± 0.05
		45%	245.08 ^b ± 1.48	215.3 ^d ± 2.16	29.75 ^a ± 0.95	305.67 ^c ± 1.64	90.33 ^d ± 1.36	5.33 ^d ± 0.15	73.40 ^e ± 0.03
	DWSF	15%	161.25 ^e ± 1.03	242.75 ^a ± 2.04	14.50 ^e ± 0.92	334.75 ^a ± 3.74	92.00 ^d ± 1.16	6.33 ^b ± 0.18	81.45 ^b ± 0.16
		30%	157.42 ^f ± 1.12	144.42 ^f ± 1.52	15.58 ^e ± 0.84	246.45 ^f ± 1.57	102.03 ^c ± 1.06	6.16 ^b ± 0.25	81.45 ^b ± 0.12
		45%	113.50 ^g ± 1.06	138.90 ^g ± 1.28	22.58 ^{bc} ± 1.34	259.16 ^e ± 1.62	120.24 ^a ± 2.08	5.60 ^c ± 0.08	79.90 ^c ± 0.12
	WREF	15%	243.67 ^b ± 1.39	183.25 ^e ± 1.73	5.50 ^g ± 1.65	259.08 ^e ± 1.05	75.83 ^e ± 1.07	7.00 ^a ± 0.14	82.35 ^a ± 0.21
		30%	224.75 ^c ± 1.06	213.50 ^d ± 1.98	11.25 ^f ± 1.30	304.00 ^c ± 1.82	90.50 ^d ± 1.25	5.73 ^c ± 0.12	79.97 ^c ± 0.08
		45%	188.75 ^d ± 1.10	221.08 ^c ± 2.18	22.58 ^{bc} ± 1.28	328.17 ^a ± 3.92	107.08 ^b ± 1.21	5.60 ^c ± 0.09	79.90 ^c ± 0.14

Note: Values are means of triplicate determinations; ± - SD value; RVU - Rapid Visco Unit.

Mean values with different superscript within column are significantly different (P<0.05).

It is the temperature at which gelatinized starch reaches its maximum viscosity when being heated in water, and it represents the starch's ability to bind water [45].

The pasting characteristics of composites Instant Pounded Yam Flour (IPYF) from varying levels (15%, 30% and 45%) of High Quality Cassava Flour (HQCF), Dehulled White Sorghum Flour (DWSF) and White Rice Flour (WREF) inclusion (Table 2) revealed that the mean value of the peak viscosity of the composite IPYF varies significantly ($P=0.05$), with the composites from HQCF increasing with increasing levels of replacement while those from sorghum and rice flour decreasing with increasing levels of substitution. The good texture of pounded yam generally benefits from high peak viscosity, which is mostly dependent on high viscosity and fairly high gel strength [45]. An indicator that the flours can be utilized for the production of samples that require low gel strength and elasticity is the relative effect of peak viscosity decreasing with an increase in sorghum and rice flour substitution [22].

In the composite IPYF samples, the mean trough viscosity values increases as the proportion of WREF to IPYF increases, whereas for HQCF and DWSF, the mean trough viscosity values decreases as the rate of replacement increases. With the mean value increases with increasing levels of replacement, the breakdown viscosity of the composite samples also varies significantly ($P=0.05$), which is unfavorable since it results in uneven viscosity and the cohesive nature of the starch paste [51].

The mean setback viscosity values for the composite flours likewise varied significantly ($P=0.05$) from one another. The mean setback viscosity value of the flour samples reduces with an increase in HQCF substitution; this suggests that the flour may be relatively more stable when cooked [42, 58]. However, the mean setback viscosity increase as the quantity of white rice flour substitution increases, this suggests that the level of retrogradation during cooling increases proportionately as well [59]. Higher setback viscosity values have typically been linked to cohesive paste and high-quality pounded yam or fufu [45,60].

In general, as the level of substitution is increased, the peak time of the composite flours decreases. This suggests that the heating/cooking time required for gelatinization was generally decreased during the preparation of composite IPYF. Therefore, when all other parameters are similar, flours with shorter peak times may be preferable in terms of heat consumption during cooking.

For all the composite flours, there were slight decreases in the pasting temperature with increase in the level of substitution. For technical and economic reasons, flours with low pasting temperature may be preferred when all other properties are equal.

Peak viscosity has a strong positive correlation with trough viscosity ($r = 0.975, P<0.01$), final viscosity ($r = 0.924, P<0.01$) and setback viscosity ($r = 0.597, P<0.01$). Also, trough viscosity has a strong positive correlation with final and set back viscosities ($r = 0.912, P<0.01$) and ($r = 0.597, P<0.01$) respectively. Breakdown viscosity has strong negative correlation ($r = - 0.724, P<0.01$) with peak time; while final viscosity has a positive correlation with setback viscosity ($r = 0.662, P<0.01$) (Table 3).

3.3: Principal Component Analysis of the Flour Samples

Generally, principal component analysis (PCA) gives details on similarities or otherwise between samples; as well as the inter-relationships between the measured variables. Figure 1 gives the PCA plots of the flour (IPYF and the composites) samples

The distance between the flour samples location (shown by their numbers on the score plot) is directly related to how different or similar they are from each another. Positive correlation exists between properties whose curves are close to one another on the plot, and negative correlation exists between properties whose curves run in the opposite directions.

According to the variables investigated, the flour samples (10) is divided into four groups by the first two axes, with each group having similar characteristics based on the measured properties. The first group (positive coefficient PC 1 and PC 2) contains two flour samples (1 and 10); the second group with positive coefficient for PC1 and negative values for PC2 also had two samples (4 and 7). The third group with negative values for both PC1 and PC2 had four samples (5, 6, 8 and 9) while the last group with two samples (2 and 3), had negative coefficient for PC1 and positive coefficient for PC2.

Table 3: Pearson correlation between the functional and pasting properties of the flour samples

Parameters	LBD	PBD	WAC	OAC	WBC	Disp	PkVis	TrVis	BdVis	FIVis	SbVis	PkTe	PgTp
Loose Bulk Density (LBD)	1												
Pack Bulk Density (PBD)	.796**	1											
Water Absorption Capacity (WAC)	-.049	-.099	1										
Oil Absorption Capacity (OAC)	-.093	-.019	.599**	1									
Water Binding Capacity (WBC)	.611**	.766**	.372*	.340	1								
Dispersibility (Disp)	-.208	-.196	-.397*	-.514**	-.592**	1							
Peak Viscosity (PkVis)	.283	.146	.403*	.383*	.241	-.243	1						
Trough Viscosity (TrVis)	.401*	.218	.317	.326	.284	-.275	.975**	1					
Breakdown Viscosity (BdVis)	-.550**	-.356	.440*	.383*	-.249	.073	.043	-.151	1				
Final Viscosity (FIVis)	.361	.233	.256	.373*	.226	-.189	.924**	.912**	.034	1			
Setback Viscosity (SbVis)	.234	.336	-.028	.449*	.164	-.198	.597**	.554**	.295	.662**	1		
Peak Time (PkTe)	.584**	.521**	-.169	-.087	.581**	-.555**	.039	.177	-.724**	.013	-.009	1	
Pasting Temp (PgTm)	.401*	.632**	-.401*	-.604**	.290	.186	-.369	-.348	-.235	-.259	-.194	.228	1

** . Correlation is significant at the 0.01 level (2-tailed).

* . Correlation is significant at the 0.05 level (2-tailed).

UNDER REVIEW

A total of 93.49% of the variability was explained by the first, second, third and fourth PCs (Table 4) which were described by 47.07%, 20.91%, 15.72% and 09.79% respectively of the variation.

While all remaining composites are on the negative side of the first principal component (PC1), the 15% composite samples (1, 4 and 7) and the 100% IPYF flour samples were all positioned on the positive side of the Biplot (Fig. 1). Additionally, the second principal component (PC2) had all of the HQCF composites and 100% of IPYF on the positive side and the rest on the negative.

Based on its ability to absorb water and the dispersibility of the flour, Sample 10 (100% IPYF) was clearly distinguished from the other flour samples. On the basis of their relative setback viscosity and pasting temperature, samples 7 (IPYF with 15% WREF) and 9 (IPYF with 45% WREF) stood out from the other samples; while sample 6 (45% DWSF composite) had a big negative score in PC1, sample 10 (100% IPYF) displayed a large positive score. Sample 3 (45% HQCF composite) had a big positive score in the second principal component, whereas Sample 7 (15% WREF composite) had a large negative score (PC2).

UNDER PEER REVIEW




Fig 1. Loading plot with first and second components of the principal component analysis of the variables of the functional and pasting attributes of the flour samples

Where: (1) - IPYF with 15% HQCF; (2) - IPYF with 30% HQCF; (3) - IPYF with 45% HQCF;
 (4) - IPYF with 15% DWSF; (5) - IPYF with 30% DWSF; (6) - IPYF with 45% DWSF;
 (7) - IPYF with 15% WREF; (8) - IPYF with 30% WREF; (9) - IPYF with 45% WREF;
 (10) - 100% IPYF




Fig 2. Scree plot with first and second components of the principal component analysis of the variables of the functional and pasting attributes of the flour samples

Table 4: Eigenvalues, total variance, cumulative variance and correlation coefficients between measured variables and the first four principal components that described the variation measured characteristics on flour samples

Factor	Principal components			
	1	2	3	4
Loose Bulk Density (LBD)	0.294	-0.336	*	0.272
Packed Bulk Density (PBD)	0.294	-0.338	-0.122	0.174
Water Absorption Capacity (WAC)	0.358	*	0.265	-0.119
Oil Absorption Capacity (OAC)	0.183	0.419	-0.240	-0.294
Water Binding Capacity (WBC)	0.374	-0.116	*	-0.134
Dispersibility (DISP)	0.373	*	-0.203	-0.177
Peak Viscosity (Peak Vis)	0.332	0.222	*	-0.102
Trough Viscosity (Trough Vis)	0.238	0.295	0.153	0.530
Breakdown Viscosity (Breakdown Vis)	0.257	0.185	-0.446	-0.233
Final Viscosity (Final Vis)	0.180	0.296	-0.208	0.589
Setback Viscosity (Setback Vis)	-0.137	*	-0.269	*
Peak Time	0.229	-0.212	0.252	-0.218
Pasting temperature	0.113	-0.522	-0.269	*
Eigen values of correlation matrix	6.119	2.718	2.044	1.273
Explained proportion of total variance %	47.07	20.91	15.72	09.79
Cumulative proportion of total variance %	47.07	67.98	83.70	93.49

N.B - Bold values indicate correlation coefficients with value equal to or greater than 0.3 in absolute value;
 *-Loading value <0.1.

4.0 CONCLUSION

The functional and pasting properties of Instant Pounded Yam Flour (IPYF) and the composites from High Quality Cassava Flour (HQCF), white rice flour (WREF), dehulled white sorghum flour (DWSF) were significantly ($p < 0.05$) affected by their level of substitutions (15%, 30% and 45%). Based on the PCA, 15% level of substitution with HQCF would give an acceptable composite IPYF close to 100% IPYF.

REFERENCES

1. Stathers T, Holcroft D, Kitinoja L, Mvumi BM, English A, Omotilewa O, Torero M. A scoping review of interventions for crop postharvest loss reduction in sub-Saharan Africa and South Asia. *Nature Sustainability*, 2020; 3(10), 821-835.
2. Ajibosin IO, Daodu MA, Omotade SA, Komolafe AO. Capacity building for Instant Pounded Yam Flour production. *Nigerian Journal of Information Studies*, 2005; 4(4): 1-5.
3. Olaoye JO, Oyewole SN. Optimization of some "Poundo" Yam Production Parameters. *Agricultural Engineering International: CIGR Journal*, 2012; 14(2), 58-67.
4. Akinoso R, Olatoye KK. Energy utilization and conservation in instant-pounded yam flour production. *International Food Research Journal*, 2013; 20 (2): 575-579.
5. Asiru WB, Kosoko SB, Owolabi SO, Adegbite A, Elemo GN. Preliminary investigation of the effect of granulation on the quality characteristics of instant pounded yam flour. *Conference of International Society of Tropical Roots and Tuber Crop (ISTRC)*. 2013.
6. FIIRO, Federal Institute of Industrial Research, Oshodi, Nigeria. Instant pounded yam flour production technology. Available at: fiiro-ng.org/Instant-pounded-yam.htm. 2005.
7. Malomo O, Ogunmoyela OAB, Adekoyeni OO, Jimoh O, Oluwajoba SO, Sobanwa MO. Rheological and functional properties of Soy-Poundo yam flour. *International Journal of Food Science and Nutrition Engineering*, 2012; 2 (6):101-107.
8. Suresh C, Samsher S, Durvesh K. Evaluation of functional properties of composite flours and sensorial attributes of composite flour biscuits. *Journal of Food Science and Technology*, 2015; 52(6), 3681–3688.
9. Gbenga-Fabusawa FJ, Oladele EP, Obboh G, Adefegha SA, Oshodi AA. Nutritional Properties, Sensory Qualities and Glycaemic Response of Biscuits Produced From Pigeon Pea-Wheat Composite Flour. *Journal of Food Biochemistry*, 2018; 42(4), e12505. <https://doi.org/10.1111/jfbc.12505>
10. Hasmadi M, Jahurul MHA, Mohamad Khairi Z, Yu AL. The Influence of Seaweed Composite Flour on the Quality of Muffin. *Journal of Aquatic Food Product Technology*, 2018; 27(5), 635–642. <https://doi.org/10.1080/10498850.2018.1468841>
11. Falade KO, Okafor CA. Physical, Functional, and Pasting Properties of Flours from Corms of Two Cocoyam (*Colocasia esculenta* and *Xanthosoma sagittifolium*) Cultivars. *Journal of Food Science and Technology*, 2015; 52, 3440-3448.
12. Emmanuel KO, Michael AI, Olajide PS, Bakare HA. Quality Attributes and Storage Stability of Bread from Wheat-Tigernut Composite Flour. *Journal of Culinary Science and Technology*, 2019; 17(1), 1-14.
13. Waldron KW, Parker ML, Smith AC. Plant Cell Walls and Food Quality. *Comprehensive Reviews in Food Science and Food Safety*, 2003; 2(4), 128-146.
14. Awoyale W, Sanni LO, Shittu TA, Adegunwa MO. Effect of varieties on the functional and pasting properties of biofortified cassava root starches. *Journal of Food Measurement and Characterization*, 2015; 9, 225-232.
15. Iwe MO, Onyeukwu U, Agiriga AN. Proximate, functional and pasting properties of FARO 44 rice, African yam bean and brown cowpea seeds composite flour. *Cogent Food and Agriculture*, 2016; 2(1), 1142409.
16. Ocheme OB, Adedeji OE, Chinma CE, Yakubu CM, Ajibo, UH. Proximate composition, functional, and pasting properties of wheat and groundnut protein concentrate flour blends. *Food Science and Nutrition*, 2018; 6(5), 1173-1178.
17. Jolliffe IT. *Principal component analysis for special types of data*. Springer New York. 2002; 338-372.
18. AOAC, *Official methods of analysis of the association of official analytical chemists*, 15th edn. AOAC, Arlington. 1990.
19. Beuchat LR. Functional and electrophoretic characteristic of succinylated peanut flour. *Agric. Food Chem.* 1977; 25, 258–261.

20. Medcalf DJ, Gilles KA. Wheat starches I. Comparison of physicochemical properties. *Cereal Chemistry*, 1965; 42: 558-568.
21. Kulkarni KO, Kulkarni DN, Ingle UM. Sorghum malt based weaning food formulation preparation, functional properties and nutritive value. *Food and Nutrition Bulletin*.1991; 13 (14): 322-327.
22. Adebowale AA, Sanni LO, Awonorin SO. Effects of texture modifiers on the physicochemical and sensory properties of dried fufu. *International Journal of Food Science and Technology*.2005; 11(5): 373-382.
23. Lotti C, Marcotrigiano AR, De Giovanni C, Resta P, Ricciardi A, Zonno V, Fanizza G, Ricciardi L. Univariate and multivariate analysis performed on bioagronomical traits of *Cucumis melo* L. germplasm. *Euphytica*.2008; 55:511–22.
24. Adebowale AA, Sanni SA, Oladapo FO. Chemical, functional and sensory properties of instant yam breadfruit flour. *Nigerian Food J*. 2008; 26(1):2-12.
25. Odadeji JO, Oyeleke WA. Comparative studies on functional properties of whole and dehulled cowpea seed flour (*Vigna unguiculata*). *Pakistan Journal of Nutrition*, 2011; 10(9): 899-902.
26. Shittu TA, Sanni LO, Awonorin SO, Maziya-Dixon B, Dixon A. Use of multivariate techniques in studying the flour making properties of some CMD resistant cassava clones. *Food Chemistry*.2007; 101:1606–1615.
27. Ikujenlola AV. Chemical and functional properties of complementary food from malted and unmalted Acha (*Digitaria exilis*), Soybean (*Glycine max*) and Defatted sesame seeds (*Sesamunindicum*). *J. Eng. Appl. Sci*. 2008; 39(6), 471–475.
28. Odadeji JO, Oyeleke WA. Comparative studies on functional properties of whole and dehulled cowpea seed flour (*Vigna unguiculata*). *Pakistan Journal of Nutrition*, 2011, 10(9): 899-902.
29. Asaam ES, Adubofuor J, Amoah I, Apeku OJD. Functional and pasting properties of yellow maize–soya bean–pumpkin composite flours and acceptability study on their breakfast cereals. *Cogent Food & Agriculture*, 2018; 4(1), 1501932.
30. Osundahunsi OF, Fagbemi TN, Kesselman E, Shimoni E. Comparison of the physico-chemical properties and pasting characteristics of flour and starch from red and white sweet potato cultivars. *Journal of Agriculture and Food Chemistry*. 2003; 51: 2232-2236.
31. Cummings JH, Stephen AM. Carbohydrate terminology and classification. *European journal of clinical nutrition*, 2007;61(1), S5-S18.
32. Echendu CA, Onimawo IA, Somtochi A. Production and Evaluation of doughnuts and Biscuits from Maize – Pigeon pea flour Blends. *Nigerian Food Journal*. 2004; (22): 147 – 153.
33. Adegunwa MO, Alamu EO, Omitogun LA. Effect of processing on the nutritional content of yam and cocoyam tubers. *Journal of Applied Bioscience*.2011; (46): 3086-3092.
34. Appiah F, Asibuo JY, Kumah P. Physicochemical and functional properties of bean flours of three cowpea (*Vigna unguiculata* L. Walp) varieties in Ghana. *African Journal of Food Science*, 2011; 5(2): 100-104.
35. Moorthy SN. Physicochemical and functional properties of tropical tuber starches. *Starch/Stärke*.2002; (54): 559-592.
36. Amonsou E, Sakyi-Dawson E, Saalia F. Effects of cowpea flour fractionation on sensory qualities and acceptability of *kpejigaou* (a griddled cowpea paste food). *Journal of Food Quality*. 2010; (33): 61-78.
37. Twinomuhwezi H, Awuchi CG, Rachael M. Comparative study of the proximate composition and functional properties of composite flours of amaranth, rice, millet, and soybean. *American Journal of Food Science and Nutrition*. 2020;6(1); 6-19.
38. Wang S, Copeland L. Molecular disassembly of starch granules during gelatinization and its effect on starch digestibility: A Review. *Food and function*. 2013;4(11); 1564-1580.
39. Bolaji OT, Oyewo AO, Adepoju PA. Soaking and drying effect on the functional properties of Ogi produce from some selected maize varieties. *American Journal of Food Science and Technology*. 2014; 2(5); 150-157.
40. Awoyale W, Sanni LO, Shittu TA, Adegunwa MO. Effect of varieties on the functional and pasting properties of bio-fortified cassava root starches. *Journal of Food Measurement and Characterization*.2015; 9(2): 225-232. DOI 10.1007/s11694-015-9227-6
41. Singh N, Singh J, Kaur L, Sodhi NS, Gill SB. Morphological, thermal and rheological properties of Starches from different botanical sources. *Food Chemistry*, 2003; (81): 219-231.

42. Sanni LO, Kosoko, SB, Adebawale AA, Adeoye RJ. The influence of palm oil and chemical modification on the pasting and sensory properties of fufu flour. *International Journal of Food Properties*.2004;7(2): 229 - 237.
43. Van Hung P, Yamamori M, Morita N. Formation of enzyme-resistant starch in bread as affected by high amylose wheat flour substitutions. *Cereal Chemistry*.2005; 82: 690 - 694.
44. Biliaderis CG. Structural transitions and related physical properties of starch. In: BeMiller J, Whistler R, editors. *Starch: Chemistry and Technology*, 3rd edition. New York: Academic Press.2009; 293–372.
45. Otegbayo B, Aina J, Asiedu R, Bokanga M. Pasting characteristics of fresh yams (*Dioscorea spp*) as indicators of textural quality in a major food product.-‘pounded yam’. *Food Chemistry*.2006; (99): 663-669.
46. OtegbayoB, Oguniyan D, Akinwumi, O. Physicochemical and functional characterization of yam starch for potential industrial applications. *Starch-Stärke*, 2014; (66) (3-4), 235-250.
47. Eriksson E, Koch K, Tortoe C, Akonor PT, Baidoo E. Physicochemical, functional and pasting characteristics of three varieties of cassava in wheat composite flours. *British Journal of Applied Science and Technology*.2014; 4(11): 1609-1621.
48. Farhat IA, Oguntona T, Neale JR. Characterization of starches from West African yams. *Journal of Science Food and Agriculture*.1999; (79): 2105-2112.
49. Sharma C, Singh B, Hussain SZ, Sharma S. Investigation of process and product parameters for physicochemical properties of rice and Mung bean (*Vigna radiata*) flour based extruded snacks. *Journal of Food Science and Technology*. 2017; (54), 1711-1720.
50. Eliasson AC. *Starch in Food: Structure, Function and Applications* (Woodhead/CRC Press, New York, 2004).
51. Arisa NN, Adelakan AO, Alamu AE, Ogunfowora EJ. The effect of pre-treatment of plantain (*Musa paradisiaca*) flour on the pasting and sensory characteristics of Biscuit. *International Journal of Food and Nutrition Science*.2013; 2(1) 10-23.
52. Ayernor GS. The Yam (*Dioscorea*) Starches. In: *Advances in Yam Research*. 1stedn. Godson Osuji. Anambra State University of Technology Publishers. Nigeria. 1985; 79-88.
53. Peroni FHG, Rocha TS, Franco CML. Some structural and physicochemical characteristics of tuber and root starches. *International Journal of Food Science and Technology*.2006;12 (6): 505-513.
54. Huang CC, Lai P, Chen IH, Liu YF, Wang CC. Effects of mucilage on the thermal and pasting properties of yam, taro, and sweet potato starches. *LWT-Food Science and Technology*. 2010;43(6), 849-855.
55. Wireko-Manu FD, Ellis WO, Oduro I, Asiedu R, Maziya-Dixon B. Physicochemical and pasting characteristics of water yam (*D. alata*) in comparison with pona (*D. rotundata*) from Ghana. *European Journal of Food Research & Review*.2011; 1(3): 149-158.
56. AfoakwaEO, Sefa-Dedeh S. Viscoelastic properties and changes in pasting characteristics of trifoliate yam (*Dioscorea dumetorum*) starch after harvesting. *Food Chemistry*.2002; (77): 203-208.
57. Adegunwa MO, Ganiyu AA, Bakare HA, Adebawale AA. Quality evaluation of composite millet-wheat Chin-chin. *Agriculture and Biology Journal of North America*. 2014;5(1); 33-39.
58. Odurol, Ellis WO, Aryeetey SK, Ahenkora K, Otoo JA. Pasting characteristics of starch from new varieties of sweet potato. *Tropical Science*.2000; 40: 25 - 28.
59. Delcour JA, Vansteelandt J, Hythier MC, Abecassis J. Fractionation and reconstitution experiments provide insight into the role of starch gelatinization and pasting properties in pasta quality. *Journal of Agricultural and Food Chemistry*, 2000; 48(9); 3774-3778.
60. Obioma OG, Doshima IB, Kwagh-hal IJ, Ann KN, Amak DAM. Proximate Composition and Pasting Properties of Modified Starches of White Yam, Trifoliate Yam and Sweet Potato. *World*, 2022; 6(3); 58-68.