

Morphological and Structural Characterization of Algae-based Nanoformulation

Abstract

In the present study, confirmation of *Spirulina platensis*-mediated TiO₂NPs formation was indicated by a noticeable shift in hue from white to light yellow. TEM analysis revealed the presence of irregularly distributed nanoparticles with sizes between 50 and 60 nm, while TEM analysis further disclosed a hexagonal structure. EDAX analysis identified elemental composition, with titanium peaks appearing at 4.5 to 5 keV, carbon peaks at 0.5 keV, oxygen peaks at 0.4 to 1.0 keV, silica peaks at 1.7 to 2.0 keV, zinc peaks at 8.0 keV, copper peaks at 7 keV, potassium peaks at 4 keV, phosphorus peaks at 3 keV, and iron peaks at 6 keV. These comprehensive findings confirm the successful synthesis of well-defined *Spirulina platensis*-mediated TiO₂ nanoparticles and provide valuable insights into their structural and elemental characteristics.

Keywords: *Spirulina*, TiO₂ NPs and TEM with EDAX analysis

Introduction

Efforts to boost silk production, such as hybridization, artificial diets, and phyto-juvenoid use, lack significant results, urging novel approaches (Ni *et al.*, 2015). Nanotechnology's integration into sericulture opens new pathways for enhancing silk output, serving fields like drug delivery and electronic imaging (Sankar *et al.*, 2014). Emerging methods, like green-synthesized nanoparticles from sources like *Spirulina platensis*, offer eco-friendly alternatives, enriching silk gland parameters (Thangapandiya and Dharanipriya, 2019,12,13,14). Metal oxide semiconductors, notably TiO₂ nanoparticles, possess antibacterial properties and promote cocoon quality, suggesting their potential as feed additives (Li *et al.*, 2015). In summary, nanotechnology's adoption, especially via eco-friendly synthesis, and the use of metal oxide nanoparticles like TiO₂, show promise for advancing silk production sustainably in sericulture.

Materials and Methods

Collection of algae materials

Spirulina platensis dried powder was acquired from the India's R.K. Algae Centre is located in Mandapam, Tamil Nadu. The Botanical Survey of India in Coimbatore, Tamil Nadu, carried out the process of verifying the identity of algal species. (Plate 1).



Plate 1. Confirmation of algal species (BSI, Coimbatore)

Preparation of aqueous extraction of *Spirulina platensis*

About 10g of finely chopped *Spirulina platensis* powder was heated for 45 minutes at 90°C in 100 milliliters of deionized water aqueous extract. Debris was then removed by passing a filter through the first Whatman filter paper. For the following experiments, the clear green solution that subsequently cooled to a temperature of 4–8°C (Some et al., 2019).

Synthesis of titanium dioxide nanoparticles

Applying a water-based extract of *Spirulina platensis* as a capping agent and bio-reductant, 0.01 mM titanium dioxide was used to create *Spirulina*-mediated TiO₂NPs in an environmentally friendly synthesis. Twenty milliliters of watery extract were combined with eighty milliliters of 0.01 M solution TiO₂, which was stirred continuously in a hotplate magnetic stirrer for six hours at room temperature. a color shift that indicates TiO₂NP production. To characterize the green synthesised *Spirulina*-mediated TiO₂NPs, TEM with EDAX were employed.

Transmission Electron Microscopy with Energy Dispersive X-Ray Spectroscopy

Characterizing the individual particles of the material was done using transmission electron microscopy, which has a resolution Tenfold greater than that of scanning electron microscopy. An small quantity of green synthesised TiO₂NPs was sonicated for 10 minutes and then dispersed in dry ethanol for TEM analysis. In the prepared sample, On a grid covered in copper, a single drop of *Spirulina*-mediated TiO₂NPs was carefully positioned. TEM pictures were taken with a Jeol JEM-2100 electron microscope (Japan). With EDAX, the generated TiO₂NPs' elemental analysis was also completed.

Results and Discussions

Synthesis of TiO₂NPs using aqueous *Spirulina platensis* extract





After heating 10 g of finely chopped *Spirulina platensis* powder was heated to 90°C for 45 minutes in 100 milliliters of deionized water. The mixture was then filtered through Whatman filter paper No. 41 to remove impurities and yielded the aqueous extract of *Spirulina platensis*. The resulting transparent solution was kept at 4 to 8°C. The *Spirulina platensis* mediated TiO₂NPs were prepared using Both titanium dioxide and *Spirulina platensis* aqueous extract are used as capping and bio-reductants. After adding 20 milliliters of *Spirulina* aqueous extract to 80 milliliters of 0.01 mM TiO₂ solution, the mixture was stirred continuously at ambient temperature 200 rpm. The formation of green synthesised *Spirulina platensis* mediated TiO₂NPs was confirmed by the change of colour (pale yellow) within an hour. In the present investigation, the formation of *Spirulina platensis* mediated TiO₂NPs was verified by the shift in hue from white to pale yellow. This result corroborates Using the results of Gunasundari *et al.* (2014) who stated that the formation of *Spirulina platensis* mediated with various metal nanoparticles (Silver, Chromium, Zinc, Lead and Iron) were confirmed by the change of colours such as The hue of AgNps transformed from yellow to brown in the solution; the color of CrNPs changed changing from orange to green; the color of PbNPs changed blue instead of white; the color of ZnNPs became white instead of green; and the color of FeNPs changed from yellow to green.

Characterization of nanoparticles

The structural and particle size characterization of *Spirulina platensis* mediated TiO₂NPs were investigated by TEM with EDAX analysis. In the present experiment, *S. platensis* mediated TiO₂NPs were characterized through TEM with EDAX analysis. The results are present here.

Transmission Electron Microscopy (TEM) with Energy Dispersive X-Ray Spectroscopy (EDAX)

TEM images were used to assess the size, shape, and crystallinity of *Spirulina platensis*-mediated TiO₂NPs. The nanoparticles had a moderate degree of size variation and an uneven, hexagonal shape. The dimensions fell between 50 to 60 nm (Plate 2a)






Plate 2a. TEM images of *Spirulina platensis* mediated TiO₂NPs

The analysis using energy dispersive X-ray spectroscopy (EDAX) showed the elemental composition, which was present in the *Spirulina platensis* mediated TiO₂NPs (Plate 2b). The titanium peaks appeared at 4.5 to 5 keV, carbon peaks at 0.5 keV, oxygen peaks at 0.4 to 1.0 keV, silica peaks at 1.7 to 2.0 keV, zinc peaks at 8.0 keV, copper peaks at 7 keV, potassium peaks at 4 keV, phosphorus peaks at 3 keV, iron peaks at 6 keV and various metal oxides were found and the existence of magnesium, carbon, and oxygen, zinc, phosphorus and potassium and chlorine indicated the existence of biomolecules deposited on the exterior of titanium nanoparticles. The particles were in the energy dispersive analysis, which demonstrated fact metallic and crystalline TiO₂NPs. The TEM analysis was applied for estimating the volume and morphological appearance of artificial NPs. In the present study, the obtained results of TEM with EDAX analysis the, nanoparticles' sizes varied from 50 to 60 nm and the EDAX analysis showed the elemental composition such as carbon, oxygen, magnesium, zinc, phosphorus and potassium and chlorine indicates biomolecules that have been adsorbed onto the surface of titanium nanoparticles. The particles were in the energy dispersive analysis, which demonstrated fact metallic and crystalline TiO₂NPs. Spherical shape and interconnected NPs were identified from *A. indica* leaf extract mediated TiO₂NPs (Sankar *et al.*, 2014). Hariharan *et al.* (2017) used TEM images to reveal the size, shape, and crystallinity of green synthesised TiO₂NPs. The nanoparticles varied in shape from irregular to hexagonal, and their sizes varied somewhat ranging from 13 to 34 nm. Based on the above

information the synthesised *Spirulina platensis* mediated TiO₂NPs could be used for various biological purposes.




Plate 2b. TEM with EDAX element of *Spirulina platensis* mediated TiO₂NPs

Conclusions

The TEM analysis demonstrated the production of TiO₂ nanoparticles (TiO₂NPs), which revealed a hexagonal structure in *Spirulina platensis*-mediated TiO₂NPs. These findings underscore the effectiveness of *Spirulina platensis* as a bioresource for synthesizing well-defined and structured TiO₂ nanoparticles, holding promise for diverse applications in nanotechnology and highlighting the potential of environmentally friendly biogenic synthesis methods.

Disclaimer (Artificial intelligence)

Option 1:

Author(s) hereby declare that NO generative AI technologies such as Large Language Models (ChatGPT, COPILOT, etc) and text-to-image generators have been used during writing or editing of manuscripts.

Option 2:

Author(s) hereby declare that generative AI technologies such as Large Language Models, etc have been used during writing or editing of manuscripts. This explanation will include the name, version, model, and source of the generative AI technology and as well as all input prompts provided to the generative AI technology

Details of the AI usage are given below:

- 1.
- 2.
- 3.

References

1. Dharanipriya, R., & Thangapandiya. (2019). Comparative study of nutritional and economical parameters of silkworm (*Bombyx mori*) treated with silver nanoparticles and *Spirulina*. *The Journal of Basic and Applied Zoology*, **80**(1), 1-12.
2. Gunasundari, E., Senthil Kumar, P., Christopher, F. C., Arumugam, T., & Saravanan, A. (2017). Green synthesis of metal nanoparticles loaded ultrasonic-assisted *Spirulina platensis* using algal extract and their antimicrobial activity. *IET Nanobiotechnology*, **11**(6), 754-758.
3. Hariharan, D., Srinivasan, K., & Nehru, L. (2017). Synthesis and characterization of TiO₂ nanoparticles using *Cynodon dactylon* leaf extract for antibacterial and anticancer (A549 Cell Lines) Activity. *Journal of Nanomedicine Research*, **5**(6), 1-5.
4. Kumar, P., Govindaraju, M., Senthamilselvi, S., & Premkumar, K. (2013). Photocatalytic degradation of methyl orange dye using silver (Ag) nanoparticles synthesized from *Ulvalactuca*. *Colloids and Surfaces B: Biointerfaces*, **103**, 658-661.
5. Li, M., Li, F., Lu, Z., Fang, Y., Qu, J., Mao, T., ... Li, B. (2015). Effects of TiO₂ nanoparticles on intestinal microbial composition of silkworm, *Bombyx mori*. *Science of the Total Environment*, **704**, 1352-73.
6. Miankushki, H. N., Sedghi, A., & Baghshahi, S. (2018). Facile and scalable fabrication of graphene/polypyrrole/MnO_x/Cu(OH)₂ composite for high-performance supercapacitors. *Journal of Solid State Electrochemistry*, **22**(11), 3317-3329.
7. Ni, M., Li, F., Tian, J., Hu, J., Zhang, H., Xu, K., Li, B. (2015). Effects of titanium dioxide nanoparticles on the synthesis of fibroin in silkworm (*Bombyx mori*). *Biological Trace Element Research*, **166**(2), 225-235.
8. Sahoo, S., Parveen, S., & Panda, J. (2007). The present and future of nanotechnology in human healthcare. *Nanomedicine: Nanotechnology, biology and medicine*, **3**(1), 20-31.

9. Sankar,R.,Rizwana,K.,Shivashangari,K.S.,&Ravikumar,V.(2014).Ultra-rapidphotocatalytic activity of Azadirachtaindica engineered colloidal titanium dioxidenanoparticles.*Applied Nanoscience*,**5**(6), 731-736.
10. Santhoshkumar,T.,Rahuman,A.A.,Jayaseelan,C.,Rajakumar,G.,Marimuthu,S.,Kirthi, A.V., . . . Kim, S.-K. (2014). Green synthesis of titanium dioxide nanoparticles usingPsidium guajava extract and its antibacterial and antioxidant properties. *Asian Pacificjournalof tropical medicine*,**7**(12), 968-976.
11. Some,S.,Bulut,O.,Biswas,K.,Kumar,A.,Roy,A.,Sen,I.K.,...Neog,K.(2019).Effectoffeed supplementation with biosynthesized silver nanoparticles using leaf extract ofMorusindicaL.V1onBombyxmoriL.(Lepidoptera:Bombycidae).*Scientificreports*,**9**(1),1-13.
12. Yedurkar, S., Maurya, C., &Mahanwar, P. (2016). Biosynthesis of zinc oxide nanoparticlesusingixoracoccinealeafextract—agreeenapproach.*OpenJournalofSynthesisTheoryandApplications*,**5**(1), 1-14.
13. DukarePradip G., Pavithra, M. R., Thrilekha D., Ashrith. S, P. Harshita Mala, and Bagde A. S. 2024. “Application of Nanotechnology in Sericulture: A Review”. *Journal of Advances in Biology & Biotechnology* 27 (6):616-24. <https://doi.org/10.9734/jabb/2024/v27i6921>.
14. Chen L, Meng X, Gu J, Fan W, Abdlli N, Peprah FA, Wang N, Zhu F, Lü P, Ma S, Chen K. Silver nanoparticle toxicity in silkworms: Omics technologies for a mechanistic understanding. *Ecotoxicology and Environmental Safety*. 2019 May 15;172:388-95.