

COMPARISON OF SHEAR STRENGTH AFTER BONDING OF ORTHODONTIC BRACKETS WITH IMMEDIATE AND LATE LIGHT CURING

ABSTRACT

Objective: This study aimed to compare the shear bond strength of brackets bonded to tooth enamel with immediate and late light curing of different orthodontic resins. **Material and methods:** 108 bovine teeth were used, divided into three groups of 36, according to the type of resin used for bonding (G1 Transbond XT, G2 Orthocem, G3 Natural Ortho) and each group was subdivided into three subgroups of 12, with immediate light curing (T0), delay of 5 minutes (T5), and delay of 10 minutes (T10). The mandibular incisor brackets were bonded to the teeth and, after 24 hours, subjected to the shear test in a universal testing machine with a 500N load cell and a constant speed of 1mm/min. Intergroup comparisons were performed using the ANOVA and Tukey tests. **Results:** There was a significant difference between the types of resin and time for light curing. The Transbond XT resin showed significantly higher shear strength at times T5 and T10. Regarding the comparison between the light-curing times, there was a significant difference for the Transbond XT resin and all resins together, with the adhesion strength at T10 being significantly higher than at T0. **Conclusion:** The delay in photopolymerization tends to increase the adhesion strength of orthodontic resins, as there was a significant difference between immediate and 10-minute delayed photopolymerization when all resins were compared together.

KEYWORDS: Shear Strength; Light-Curing of Dental Adhesives; Orthodontic Brackets.

INTRODUCTION

In the early days of orthodontics, accessories were affixed to the teeth using metal bands. Each tooth was fitted with a band, and a tube or bracket was attached to it. This hindered cleaning, compromised aesthetics, and made the clinical implementation of orthodontics more complex and time-consuming.^{1,2}

The advent of acid etching of dental enamel in the 1970s opened up the possibility of increased adhesion of resin materials to the tooth structure, which revolutionized orthodontics. This enabled direct bonding of orthodontic accessories to the dental crown, reducing working time for the procedure, facilitating cleaning and caries detection, and resulting in more pleasing aesthetics.³ However, the failure to adhere brackets to dental structures is a frustrating and inherent aspect of orthodontic practice, often resulting in additional work, treatment delays, and increased costs.⁴ One advantage of using light-curing materials is the flexibility it offers orthodontic professionals to position brackets on enamel surfaces since polymerization only begins when the operator exposes the material to visible light from a light-curing device.⁵ In the clinic, some professionals cure the adhesive system immediately after placing the brackets. In contrast, others prefer to position all the brackets of a semi-arch or complete arch. However, it is unknown whether delayed light curing could affect the bond strength of these orthodontic accessories

Taubock *et al.*⁶ investigated the influence of time delay and duration of photoactivation on the microhardness of a dual-cure resin composite. Results showed that delay in light exposure did not influence microhardness, regardless of depth. Additionally, photoactivation of the tested resin composite did not provide clinically relevant benefits compared to self-curing regarding the degree of hardening.

Thomas *et al.*⁷ examined the effect of light-curing initiation time on orthodontic bond strength in a resin-modified glass ionomer cement. They found that a delay in light curing may reduce curing efficiency and alter the structure of the material, but shear strength was not affected. However, to date, no studies have examined

the effect of time delay for light curing of orthodontic resins on the shear strength of orthodontic accessories bonded to tooth enamel.

Therefore, the present study aims to compare the shear strength of brackets bonded to dental enamel with immediate and delayed light curing of various orthodontic resins.

MATERIAL AND METHODS

The sample calculation determined the minimum number of specimens in each group. It was considered $\alpha=5\%$ (type I error), $\beta=20\%$ (type II error), and a standard deviation of 1.2⁸ to detect a minimum difference of 1.45 MPa for the shear strength. The results showed the need for a minimum number of 36 specimens in each group (12 specimens in each subgroup).

Laboratory research was carried out using 108 bovine incisor teeth, divided into three groups of 36 teeth, one for each type of resin used. The groups of each of the resins were subdivided into three subgroups, with immediate light curing (T0), with a delay of 5 minutes (T5), and with a delay of 10 minutes (T10). Thus, 12 teeth were used for each time of each resin, divided according to a draw for randomization of the sample.

Group 1 was bonded with Transbond XT Resin (3M Unitek, Maplewood, USA) and subdivided into three subgroups: Subgroup 1A for time T0, Subgroup 1B for time T5, and Subgroup 1C for time T10.

Group 2 used Orthocem Resin (FGM, Joinville, Brazil) and was subdivided into Subgroup 2A for Time T0, Subgroup 2B for Time T5, and Subgroup 2C for Time T10.

Group 3 was bonded with Ortho Natural Resin (DFL, Rio de Janeiro, Brazil), subdivided into Subgroup 3A for time T0, Subgroup 3B for time T5, and Subgroup 3C for time T10.

Bovine teeth were stored in a saline solution under refrigeration. The specimens were analyzed with a magnifying glass, and those with cracks, grooves, cracks, or fractures were discarded. The teeth had their crowns wrapped in self-curing

acrylic resin to expose an enamel window, allowing the orthodontic bracket to be glued onto it, using a glass plate to create a tangent plane to the enamel surface.

These teeth subsequently had their root portion inserted into an acrylic base in a PVC ring using a glass device, which allowed the bracket to be positioned perpendicularly to the PVC base.

All teeth wrapped in acrylic resin were polished with silicon carbide sandpaper with decreasing grain (#600 and #1200) in a metallographic polisher (Aropol-2V, São Paulo, Brazil). After polishing, the specimens were treated with felts (TOP, RAM, SUPRA – Arotec, Cotia-SP) associated with diamond pastes (1, ½, and 1/4 μ).

The samples were washed in an ultrasonic vat between each polishing step for cleaning. They were submitted to prophylaxis with a Robinson brush and pumice stone paste and water for 10 seconds, with each Robinson brush being used in only four specimens; the surface was washed with a jet of air and distilled water for 10 seconds and dried with a tissue.

After prophylaxis, the brackets were bonded, respecting the manufacturer's specifications for each orthodontic resin. Roth Max metal brackets were used for lower incisors (Morelli, São José do Rio Preto, São Paulo – Brazil – ref. 10.10.410), whose base area is 9.94 mm².

To bond the brackets, the enamel surface was etched with Condac 37, 37% phosphoric acid (FGM, Joinville, Brazil) for 15 seconds, then washed in water for 10 seconds and dried with an air jet for 10 seconds. A micro brush was used to apply the specific adhesive made from Transbond XT resin, as recommended by the manufacturer. According to the manufacturer's instructions, Orthocem and Natural Ortho resins do not use adhesives.

After positioning the brackets with the resin, the excess was removed with an exploratory probe, and the times for light-curing were observed according to the subgroups.

For light-curing, the DBA iLed CE light-curing device (Guangxi, China) was used for 12 seconds, divided into 3 seconds for each side of the bracket: mesial, distal,

upper, and lower, at a distance of 3mm between the light beam and the bracket, according to the manufacturer's instructions.

Twenty-four hours after bonding the brackets, the specimens were taken to the laboratory and subjected to shear in an EMIC® DL 500 Universal Assay Machine (Emic Equipamentos e Sistemas de Assay Ltda., São José dos Pinhais, Brazil) at a constant speed of 1mm/min. A 500N load cell was connected to the computer so the Newtons' shear forces could be registered by the TESC Emic software (InterMetric, Mogi das Cruzes, Brazil). Forces in Newtons were converted to MPa by the formula $MPa = N/mm^2$.

After bracket debonding, the enamel surface and brackets were examined with a stereoscopic magnifying glass to verify the Adhesive Remnant Index (ARI).⁹ The remaining adhesive was evaluated with scores ranging from 0 to 3. A score of zero (0) indicates that there is no resin adhered to the enamel surface of the tooth; (1) indicates that less than half of the resin has adhered to the tooth's enamel surface; (2) indicates that more than half of the resin has adhered to the tooth enamel surface; (3) indicates that all the resin has adhered to the tooth enamel.

Statistical analysis

Data normality was verified with the Shapiro-Wilk test, demonstrating normal distribution, and parametric tests are recommended.

The two-ANOVA was used to analyze the time to light curing and resin type.

To compare the groups of different resins at each time for light curing and between the different times for light curing of each type of resin, the one way-ANOVA and Tukey test when necessary was used.

To verify intergroup differences in the ARI, the chi-square test was used.

Tests were performed with Statistica for Windows software version 10.0 (StatSoft, Tulsa, Okla, USA), and data were considered significant for $p < 0.05$.

RESULTS

There was a difference regarding the variables: type of resin, time for light curing, and the interaction between them (Table 1).

In the comparison between the resins at times 5 and 10 minutes, there was a significant difference between them (Table 2). At T5, Transbond XT resin had the highest bond strength, followed by Natural Ortho resin and Orthocem resin, which had the lowest bond strength, with a significant difference between them all (Table 2). At T10, Transbond XT resin had significantly higher bond strength than Orthocem resin (Table 2).

Regarding the comparison between times, there was a statistically significant difference between the Transbond XT resin and all of them together (Table 3), with the bond strength at T10 being significantly higher than at T0 (Table 3).

The Remaining Adhesive Index evaluation showed no statistically significant difference between the groups (Table 4).

DISCUSSION

In the present study, bovine teeth were used. Several studies support using bovine teeth as an alternative to human teeth for adhesion tests.¹⁰⁻¹² In the study by Nakamichi, Iwaku, and Fusayama¹³, no significant differences were found in adhesion to human and bovine dental enamel in all materials tested, enabling the use of bovine enamel in different adhesion tests. Bovine teeth have structural similarities to human teeth and are easy to acquire and manipulate.¹⁴

After bonding the brackets, the specimens were stored until the moment of shearing, which was 24 hours, based on the study by Bishara *et al.*¹⁵, who found that the highest bond strengths were obtained after 24 hours of storage. The Orthocem and Natural Ortho resins were selected because they are widely used in the local market and have an affordable value when compared to the Transbond XT resin, which, in addition to being one of the most used by orthodontists, is considered the gold standard in terms of adhesion.¹⁶⁻¹⁹

The orthodontic bracket must have an adhesive strength sufficient to withstand masticatory forces and activate the mechanics used.²⁰ The force transmitted to the bracket during mastication ranges from 40 to 120N; thus, a bracket should

have an adhesion strength to tooth enamel greater than 120N.²¹ Reynolds²² previously described that the minimum ideal bond strength between the enamel and the bracket should be 5.9 to 7.8 MPa. Several studies have verified that the clinically verified orthodontic forces generated during treatment can vary between 5 and 20 MPa.²³⁻²⁶ Therefore, the shear strength values for all resins and evaluated times were suitable for use in orthodontic bonding. The mean values found in this research ranged from 9.83 MPa (Orthocem at T0) to 19.36 MPa (Transbond XT at T10) (Table 2).¹⁶ The bond strength does not need to exceed the mean value to be considered sufficient, as these brackets will be removed and should not cause damage to tooth enamel.²⁷

The Transbond XT resin showed better results than the others, confirming its gold-standard status in the orthodontic literature.²⁸ The Natural Ortho resin presented superior results to the Orthocem resin. Still, they all demonstrated adequate adhesion to withstand orthodontic forces and satisfy clinical requirements for bracket bonding, with sufficient adhesion to resist them.²⁹

Regarding the comparison between the different times of light-curing, it is observed that all resins alone showed increasing shear strength as the delay in light-curing increased; however, only with a significant difference between the times immediately after bracket placement and 10 minutes after (Table 3).

Although we are unaware of studies evaluating the effect of delayed light curing on the bond strength of orthodontic resins, a few studies with resinous glass ionomers indicated this tendency towards increased adhesiveness^{30,31}. In contrast, others stated that there was no change, and another still showed decreased adhesiveness.⁷ We can speculate that this delay in the start of light curing reduces the conversion degree of photo-activated components, and effecting changes in the structure of the material, without compromising orthodontic shear bond strength (SBS).⁷ These alterations results in an increase in SBS.

Regarding the results of the Adhesive Remnant Index (ARI), there was no statistically significant difference between the groups, and the vast majority of

specimens from all groups presented the absence of adhesive material on the enamel after shear, evaluated as a score of 0 (Table 4).

The fact that the ARI values were higher can be considered positive, as it indicates that the rupture occurred at the bracket/resin interface, and this gives the orthodontist more confidence by preventing enamel fractures, which helps to maintain its integrity.³²

Objectively, in our study, lower scores were obtained, mostly scores 0 (zero) in all groups, showing that the breakage of adhesion occurred at the enamel/resin interface but without damage to the enamel surface; these results were confirmed by another study, including for the Transbond XT resin.²⁹

Unlike our clinical speculation that adhesiveness would decrease, increasing bracket loosening during orthodontic treatment, the results of the present study showed the opposite, increasing bond strength with a more significant delay in light curing. Guimarães *et al.*³³ state that reducing irradiance at the beginning of the photoactivation process can extend the pre-gel phase of the resin composite, in which the material can flow and undergo molecular rearrangement, compensating for the shrinkage forces. Therefore, it is speculated that the increase in adhesion strength with the most significant delay in light curing may occur by exposing the resin to ambient light, starting a natural and continuous light activation, which is then completed by the light-curing device.

Some studies demonstrate that different light-curing techniques involving immediate and late polymerization of composite resins can change the hardness and strength of the composite due to the prolongation of the pre-gel phase. Silva *et al.*³⁴, evaluated the micro tensile strength and microhardness of different composite resins using the conventional polymerization technique, the “soft-start” technique in which an initial polymerization with low intensity and a final polymerization with high intensity, and the “pulse delay” technique, performing an initial polymerization with low intensity and a final with high intensity after 3 minutes. The method that generated greater resistance to micro tensile and microhardness was the “pulse delay”, apparently due to the prolongation of the pre-gel phase, which allows greater flow of the composite resin before its

complete polymerization, reducing the shrinkage stress and consequently increases the strength of the composite.

Our study has some limitations, mainly related to its laboratory nature, which may not reproduce oral biology exactly. Another limitation is that we didn't test all possible types of conditioning techniques or brackets, such as precoated brackets.^{35,36}

Although the results show an increase in the bond strength of the brackets on tooth enamel when using late light curing, clinical studies are needed since laboratory studies do not reproduce the same conditions as in the oral cavity.

CONCLUSION

The delay in light-curing tends to increase the bond strength of orthodontic resins since there was a significant difference between immediate curing and a 10-minute delay when comparing all resins.

Disclaimer (Artificial intelligence)

Option 1:

Author(s) hereby declare that NO generative AI technologies such as Large Language Models (ChatGPT, COPILOT, etc.) and text-to-image generators have been used during the writing or editing of this manuscript.

Option 2:

Author(s) hereby declare that generative AI technologies such as Large Language Models, etc. have been used during the writing or editing of manuscripts. This explanation will include the name, version, model, and source of the generative AI technology and as well as all input prompts provided to the generative AI technology

Details of the AI usage are given below:

- 1.
- 2.
- 3.

Consent

As per international standards or university standards, patient(s) written consent has been collected and preserved by the author(s).

REFERENCES

1. Gange P. The evolution of bonding in orthodontics. *Am J Orthod Dentofacial Orthop* 2015;147:S56-63.
2. Ireland AJ, Soro V, Sprague SV, Harradine NW, Day C, Al-Anezi S et al. The effects of different orthodontic appliances upon microbial communities. *Orthod Craniofac Res* 2014;17:115-123.
3. Araújo RVd, Coelho AS, Fialho T, Peloso RM, Oliveira RCGd, Cotrin P et al. Evaluation of the Effect of Enamel Deproteinization Combined with a Self-etching Primer on the Adhesion of Orthodontic Brackets: An Study. *Open Dent J* 2022;16.
4. Dudás C, Czumbel LM, Kiss S, Gede N, Hegyi P, Mártha K et al. Clinical bracket failure rates between different bonding techniques: a systematic review and meta-analysis. *Eur J Orthod* 2022.
5. Ribeiro JLdO, Bezerra RB, Campos EdJ, Freitas AAd. Avaliação da resistência adesiva e do padrão de descolagem de diferentes sistemas de colagem de braquetes associados à clorexidina. *Dental Press J Orthod* 2008;13:117-126.
6. Tauböck TT, Buchalla W, Hildebrand U, Roos M, Krejci I, Attin T. Influence of the interaction of light- and self-polymerization on subsurface hardening of a dual-cured core build-up resin composite. *Acta Odontol Scand* 2011;69:41-47.
7. Thomas JT, Roberts HW, Diaz L, Bradley TG, Berzins DW. Effect of light-cure initiation time on polymerization efficiency and orthodontic bond strength with a resin-modified glass-ionomer. *Orthod Craniofac Res* 2012;15:124-134.
8. Komori A, Ishikawa H. The effect of delayed light exposure on bond strength: light-cured resin-reinforced glass ionomer cement vs light-cured resin. *Am J Orthod Dentofacial Orthop* 1999;116:139-145.

9. Artun J, Bergland S. Clinical trials with crystal growth conditioning as an alternative to acid-etch enamel pretreatment. *Am J Orthod* 1984;85:333-340.
10. Brauchli L, Steineck M, Ball J. Shear bond strength of a novel silorane adhesive to orthodontic brackets and unprepared bovine enamel. *J Adhes Dent* 2013;15:7-10.
11. Perciano SG, Carneiro DPA, Santos PRD, Correr AB, Vedovello SAS, Valdrighi HC. Do dental bleaching sessions prior to orthodontic treatment change the bond strength of esthetic brackets? *Dental Press J Orthod* 2021;26:e2119124.
12. Scribante A, Gallo S, Pascadopoli M, Catalano F, Gandini P, Sfondrini MF. Effect of different enamel pretreating agents on bonding efficacy and survival rates of orthodontic brackets: In vitro study and split-mouth randomized clinical trial. *Am J Orthod Dentofacial Orthop* 2022;162:297-306.
13. Nakamichi I, Iwaku M, Fusayama T. Bovine teeth as possible substitutes in the adhesion test. *J Dent Res* 1983;62:1076-1081.
14. Soares FZ, Follak A, da Rosa LS, Montagner AF, Lenzi TL, Rocha RO. Bovine tooth is a substitute for human tooth on bond strength studies: A systematic review and meta-analysis of in vitro studies. *Dent Mater* 2016;32:1385-1393.
15. Bishara SE, VonWald L, Olsen ME, Laffoon JF. Effect of time on the shear bond strength of glass ionomer and composite orthodontic adhesives. *Am J Orthod Dentofacial Orthop* 1999;116:616-620.
16. Isber H, Ambrosio AR, Carvalho PE, Valle-Corotti KM, Siqueira DF. Comparative in vitro study of the shear bond strength of brackets bonded with restorative and orthodontic resins. *Braz Oral Res* 2011;25:49-55.
17. Mahmoud GA, Grawish ME, Shamaa MS, Abdelnaby YL. Characteristics of adhesive bonding with enamel deproteinization. *Dental Press J Orthod* 2019;24:29.e21-29.e28.

18. Pithon MM, Santos RLd, Oliveira MVd, Sant'Anna EF, Ruellas ACdO. Avaliação da resistência ao cisalhamento do compósito Orthobond em diferentes condições. *Rev Gauch Odonto* 2008;56:405-410.
19. Rocha L, Marinho M, Toledo MFS, Serapião M, NevesS ACC, Rode SM. Avaliação in vitro da resistência ao cisalhamento de três materiais adesivos na colagem de braquetes ortodônticos. *RPG Rev Pós-Grad* 2010;17:63-68.
20. Fleischmann LA, Sobral MC, Santos Júnior GC, Habib F. Estudo comparativo de seis tipos de braquetes ortodônticos quanto à força de adesão. *Dental Press J Orthod* 2008;13:107-116.
21. Eliades T, Brantley WA. The inappropriateness of conventional orthodontic bond strength assessment protocols. *Eur J Orthod* 2000;22:13-23.
22. Reynolds IR. A review of direct orthodontic bonding. *Br J Orthod* 1975;2:171-178.
23. Altmann AS, Degrazia FW, Celeste RK, Leitune VC, Samuel SM, Collares FM. Orthodontic bracket bonding without previous adhesive priming: A meta-regression analysis. *Angle Orthod* 2016;86:391-398.
24. Bilal R, Arjumand B. Shear Bond Strength and Bonding Properties of Orthodontic and nano Adhesives: A Comparative In-Vitro Study. *Contemp Clin Dent* 2019;10:600-604.
25. Buyuk SK, Cantekin K, Demirbuga S, Ali Ozturk M. Are the low-shrinking composites suitable for orthodontic bracket bonding? *Eur J Dent* 2013;7:284-288.
26. Summers A, Kao E, Gilmore J, Gunel E, Ngan P. Comparison of bond strength between a conventional resin adhesive and a resin-modified glass ionomer adhesive: an in vitro and in vivo study. *Am J Orthod Dentofacial Orthop* 2004;126:200-206; quiz 254-205.
27. Guram G, Shaik JA. Comparison of Light-Emitting Diode-Curing Unit and Halogen-Based Light-Curing Unit for the Polymerization of Orthodontic Resins: An In vitro Study. *J Int Soc Prev Community Dent* 2018;8:409-415.

28. Hellak A, Rusdea P, Schauseil M, Stein S, Korbmacher-Steiner HM. Enamel shear bond strength of two orthodontic self-etching bonding systems compared to Transbond™ XT. *J Orofac Orthop* 2016;77:391-399.
29. Neves MG, Brandão GA, de Almeida HA, Brandão AM, de Azevedo DR. In vitro analysis of shear bond strength and adhesive remnant index comparing light curing and self-curing composites. *Dental Press J Orthod* 2013;18:124-129.
30. Khoroushi M, Hosseini-Shirazi M, Soleimani H. Effect of acid pre-conditioning and/or delayed light irradiation on enamel bond strength of three resin-modified glass ionomers. *Dent Res J (Isfahan)* 2013;10:328-336.
31. Khoroushi M, Karvandi TM, Sadeghi R. Effect of prewarming and/or delayed light activation on resin-modified glass ionomer bond strength to tooth structures. *Oper Dent* 2012;37:54-62.
32. Pithon MM, Santos RL, Oliveira MV, Ruellas ACO. Estudo comparativo in vitro da resistência ao cisalhamento da colagem e do índice de remanescente adesivo entre os compósitos Concise e Fill Magic. *Dental Press J Orthod* 2006;11:76-80.
33. Guimarães GF, Marcelino E, Cesarino I, Vicente FB, Grandini CR, Simões RP. Minimization of polymerization shrinkage effects on composite resins by the control of irradiance during the photoactivation process. *J Appl Oral Sci* 2018;26:e20170528.
34. Silva ALF, Pereira GD, Dias CT, Paulillo LAS. Effect of the composite photoactivation mode on microtensile bond strength and Knoop microhardness. *Dent Mater* 2006;22:203-210.
35. Golshah A, Bagheri N, Moslem Imani M, Safari-Faramani R. Effects of different types of laser etching versus phosphoric acid etching on shear bond strength of metal brackets to human enamel: A systematic review and meta-analysis of in vitro studies. *Int Orthod* 2020;18:673-683.

36. Miller M, Mon HH, Xu X, Chapple A, Dupree P, Ballard RW et al. Shear bond strength of adhesive precoated brackets: A comparative in vitro study. *Int Orthod* 2023;21:100752.

Table 1. Two-way ANOVA test results. Interaction between different resins and light curing times.

	DF	SS	MS	F	p
Intercept	1	19778.02	19778.02	1654.68	0.000*
RESIN	2	602.55	301.28	25.20	0.000*
TIME	2	150.05	75.02	6.27	0.002*
RESIN*TIME	4	175.26	43.82	3.66	0.007*
Error	99	1183.32	11.95		
Total	107	2111.18			

* Statistically significant for $p < 0.05$.

Table 2. Analysis of shear strength between different orthodontic resins (N=12).

Shear bond strength (Mpa)	TRANSBOND Mean (s.d.)	ORTHOCEM Mean (s.d.)	NATURAL Mean (s.d.)	p
T0	12.80 (3.96)	9.83 (2.27)	12.96 (4.28)	0.071
T5	16.22 (3.17) A	10.27 (1.59) B	13.38 (3.00) C	0.000*
T10	19.36 (4.33) A	11.13 (3.77) B	15.80 (3.70) AB	0.000*

One-way ANOVA and Tukey test

* Statistically significant for $p < 0.05$.

Different letters on the same row indicate the presence of a statistically significant difference.

Table 3. Analysis of variance of shear force (Mpa) between light curing times (N=12).

Shear bond strength (Mpa)	T0 Mean (s.d.)	T5 Mean (s.d.)	T10 Mean (s.d.)	P
TRANSBOND	12.80 (3.96) A	16.22 (3.17) AB	19.36 (4.33) B	0.000*
ORTHOCEM	9.83 (2.27)	10.27 (1.59)	11.13 (3.77)	0.493
NATURAL	12.96 (4.28)	13.38 (3.00)	15.80 (3.70)	0.142
ALL	11.86 (3.80) A	13.29 (3.58) AB	15.43 (5.13) B	0.002*

One-way ANOVA and Tukey test

* Statistically significant for $p < 0.05$.

Different letters on the same row indicate the presence of a statistically significant difference.

Table 4. Comparison of adhesive remnant index (ARI) between groups (N=12) (chi-square test).

ARI Group	0	1	2	3
TRANSBOND XT T0	11	1	0	0
TRANSBOND XT T5	9	1	0	2
TRANSBOND XT T10	10	2	0	0
ORTHOCEM T0	9	3	0	0
ORTHOCEM T5	10	2	0	0
ORTHOCEM T10	11	1	0	0
NATURAL ORTHO T0	12	0	0	0
NATURAL ORTHO T5	12	0	0	0
NATURAL ORTHO T10	11	1	0	0
X²=23.15	DF=16		P=0.109	