

## Sonochemical Analysis of Methylene Blue with Additives and ZnO Nanoparticles in Aqueous Medium (specific aqueous medium)

### Abstract


The use of ultrasound was found to be a very suitable and effective method for the degradation of hazardous dyestuffs. Various of additives by ultrasonic irradiation was investigated in order to clarify the degradation mechanism toward to evacuate hazardous dyestuffs in aqueous medium. Please state what method (established method). The degradation of dye molecules in aqueous media in the presence of various additives by ultrasonic irradiation was investigated in order to clarify the degradation mechanism. In this investigation, Methylene Blue (MB) have been used as a representative of azo dye and inorganic salts like NaCl and Na<sub>2</sub>SO<sub>4</sub> is used as additives where 10mg is taken from both of them in per litre of CCl<sub>4</sub> and 20mg for H<sub>2</sub>O<sub>2</sub> solutions respectively. The volume of all solutions was 100ml containing 25mg/L of MB.ZnO nanoparticle is also used for the investigation of degradation. The sonication of dye molecules were conducted for 0, 5, 15, 25 minutes. From the experiments it is clear that the acidic condition is favorable for dye degradation. Evaluating the results we have also found that all additives aided the degradation comparatively higher or lower the extent depending on their used amount in solution. The degradation mechanism was discussed in details adopting UV-vis spectra. So, it is a clear indication that azo dyes from waste water can be efficiently removed by using sonochemical irradiation method under acidic condition.

**Keywords:** Azo dye, Methylene Blue, Sonochemical Analysis, Additives, Decomposition.

**1. Introduction:** Organic dyes are utilized in many different industries, including optical data discs, food, cosmetics, pharmaceuticals, solar cells, and traditional textile manufacturing. For

instance, MB [Methylene blue \(MB\)](#) is a significant synthetic dye that is utilized in water testing, sulfide analysis, medicine, and biology [1]. It also serves as a peroxide generator and a redox indicator [\(citation\)](#). However, they [MB](#) generally disrupt ecosystems and are poisonous, mutagenic, and carcinogenic to aquatic and human life [2-4]. It is necessary to create the technology for eliminating organic dyes from water. To get rid of these chemicals, numerous techniques including chemical, physical, and biological ones have been devised [4-6]. [Give at least two techniques, state advantages and the drawbacks.](#)

The potential for completely mineralizing organic pollutants to CO<sub>2</sub> and H<sub>2</sub>O has made advanced oxidation processes (AOPs) a hot topic of attention. In AOPs for wastewater treatment, ultrasonography has recently been employed [7-9].[\(restructure this sentence\)](#) The pyrolysis reactions that occur at and inside hot regions during collapsing bubbles and the radical reactions by OH and H radicals [10] that are generated by the pyrolysis of water are the two fundamental principles of sonochemical reactions.



Numerous studies have investigated the sonochemical degradation of phenolic compounds and dyes [4, 11–17]. The creation of efficient additives to speed up the decomposition of organic molecules has been the focus of intensive research. Recent studies [17–19] have looked into how adding CCl<sub>4</sub> or C<sub>6</sub>F<sub>14</sub> affects sonochemical degradation. Although CCl<sub>4</sub> is one of the [\(hazardous\)](#) [dangerous](#) chemicals and is therefore highly regulated in usage, it is a valuable additive to speed up the sonochemical breakdown of the target organic molecules. According to Sponza et al. [18], the presence of 19 mg L<sup>-1</sup> C<sub>6</sub>F<sub>14</sub> increased the elimination rates of phenol in the wastewater from the olive mill. Zeng et al. [19] reported that the sonochemical degradation of phenol increased from 0.014 to 0.031 min<sup>-1</sup> or from 0.014 to 0.032 min<sup>-1</sup>, respectively, in the presence of 150 M

CCl<sub>4</sub> or 1.5 M C<sub>6</sub>F<sub>14</sub>. According to studies [18,19], the action of CCl<sub>4</sub> or C<sub>6</sub>F<sub>14</sub> as a H atom scavenger is what causes these beneficial effects. Additionally, it has been noted that the use of certain chemicals can influence how quickly colours degrade [20-22]. On the other hand, metal oxide semiconductors have received much research into their potential as photocatalysts to purify water and air of organic contaminants [23-26]. The active sites of electron-hole pairs are produced when the metal oxides are activated by the right amount of photon energy, and this increases the catalytic activity on the metal oxide surfaces. [27]. Due to its excellent stability and relatively straightforward preparation process, TiO<sub>2</sub> is regarded as the oldest, most prevalent, and optimal material among these metal oxides [28-31]. Zinc oxide (ZnO), a metal oxide with an exciton binding energy of 60 meV and a rather broad band gap of 3.37 eV, has been extensively studied as a photocatalyst for the degradation of various organic pollutants. Moreover, ZnO nanostructures are preferred over TiO<sub>2</sub> as photocatalyst alternatives for photodegradation due to their more favorable solar spectrum absorption, affordability, and nontoxicity [32]. In numerous studies, ZnO nanostructures demonstrated significant photocatalytic activity for the removal of organic pollutants, such as organic dyes [33]. Restructure this sentence. Thus, in this study, there are several additives such as CCl<sub>4</sub>, H<sub>2</sub>O<sub>2</sub>, NaCl, Na<sub>2</sub>SO<sub>4</sub>, and ZnO nanoparticles affected the sonochemical degradation of MB in this study. In addition, there are ~~Additionally, we have researched several~~ several parameters such as aqueous temperatures, additive concentrations (CCl<sub>4</sub>, H<sub>2</sub>O<sub>2</sub>, NaCl, Na<sub>2</sub>SO<sub>4</sub>, and ZnO nanoparticle) in order to obtain the optimal ~~towards the efficiency for the degradation rate of MB in water by sonochemistry in optimize the~~ ~~sonochemical breakdown rate of MB in water.~~

## 2. Experimental

**2.1 Materials and equipments:** Methylene Blue ( $C_{16}H_{18}ClN_3S$ ), Merck Life Science Private Limited, Godraj One, 8<sup>th</sup> Floor, pirojshanagar, Eastern Express highway, Vadhroli East, Mumbai-400079, Sodium Chloride (NaCl), RANBAXY Fine chemicals Limited A-3, Okhla industrial area, phase-1, New Delhi-110020 (ISO 9001: 2000 certified company), Sodium sulphate ( $Na_2SO_4$ ), Merck Specialities Private Limited, Shiv Sagor Estate `A` DrAnnic Besant Road, Worli, Mumbai-400018, Hydrogen peroxide ( $H_2O_2$ ), Merck KGaA, 64271 Darmstadt, Germany, Carbon tetrachloride ( $CCl_4$ ), Merck, D-6100 Darmstadt, FR. Germany.



**Fig. 1:** Sonicator bath used in sonochemical degradation. ([formatting merge figure 1 and 2](#))

## 2. 2 Preparation of Solutions

25.0 mg/l solutions of MB were prepared. In 100 ml of distilled water, solutions of the inorganic salts NaCl and  $Na_2SO_4$  were produced using 36.0 and 13.9 grams of each salt, respectively, according to their greatest saturation points. One liter of distilled water has been mixed with 1.02 mg and 2.04 milligrams of  $H_2O_2$ , respectively, to create 10 mg/l and 20 mg/l  $H_2O_2$  solutions. Using a tiny syringe, the 200, 400, and 600  $\mu$ M/L  $CCl_4$  is adjusted. Dyestuffs in water can absorb and reflect light, decreasing the transparency of the water naturally. Normally, dye effluent

includes between 10 and 50 mg/L, though 1.0 mg/L dye solutions are visible and might be considered as contaminants and objectionable [34, 35].



Fig. 2: Prepared methylene blue solution

### 3. Results and Discussion

#### 3.1 Effect of Sonochemical Degradation of MB under various pH

Based on the first-order kinetics model function, exponential curves are represented in the figure as solid curves.

$$x = ae^{-kt} \dots \dots \dots (1) \text{ (CHECK PROPER) LABEL (NUMBERING EQUATION)}$$

Where, the constant 'a' is primary concentration of MB, 25mg/l, k is a fitting parameter need to be optimized and t is the degradation time. The degradation rates of MB without additives using sonochemical irradiation processes in different conditions are shown and discussed below. NaOH and H<sub>2</sub>SO<sub>4</sub> Solutions have been used to maintain the pH of the solution.





Fig. 3: [Effect of Sonochemical degradation of pure MB at different time for various pH.](#)

Figure-3 shows the degradation rate of MB in acidic condition of pH: 3 is higher than that of the neutral, i.e. pH: 7 and basic condition, viz. pH: 8. With additives where the acidic condition is maintained in the sonochemical degradation, there is a high possibility of an increased of degradation rate of MB. [There is no adequate justification from your findings , please justify and put a support citation.](#)

### 3.2. [Effect CCl<sub>4</sub> on sonolytic degradation of MB](#)

[We examined The the](#) effect of CCl<sub>4</sub> at 200, 400, and 600 µM/L concentrations on the sonochemical degradation of MB [were studied.](#) The result is represented in Fig. 4.




**Fig. 4: Effect of CCl<sub>4</sub> on the degradation of MB**



In presence of CCl<sub>4</sub>, 100 µM CCl<sub>4</sub> enhanced the sonolytic degradation the rate of MB degradation rose initially and increased highly when 400 µM CCl<sub>4</sub> was present. Thus, it enhanced the performance of largely degradation as compared to pure MB

~~In the presence of 600 µM/L CCl<sub>4</sub>, the rate is also greatly increased; However,~~ at 200 µM/L, the rate of degradation first sharply declines before increasing with increasing sonication time, with the exception at 25 minutes. Our findings indicate that active Cl radicals or related species are produced during the sonolysis of CCl<sub>4</sub>, and that these radicals or species would be useful for the breakdown of MB, despite some researchers' reports that CCl<sub>4</sub> could operate as a H atom scavenger [19]. According to earlier research [17, 36–39], the following responses ought to occur:



(LABEL PROPERLY)






The radicals that develop containing chlorine ( $\text{Cl}$ ,  $\text{CCl}_3$ ,  $\text{CCl}_2$ ),  $\text{Cl}_2$ , etc., may accelerate the degradation of MB in an aqueous solution. According to Merouani et al. [13], the presence of  $200 \text{ mg L}^{-1}$  of  $\text{CCl}_4$  enhanced the sonochemical degradation rate of rhodamine B at 300 kHz by 21 times. According to Okitsu et al. [31], the addition of 100 ppm  $\text{CCl}_4$  enhanced the sonochemical breakdown rate of MO at 200 kHz by 41 times. The efficiency of  $\text{CCl}_4$  for MB degradation we have found in this study agrees with these results. From the above viewpoints, though  $\text{CCl}_4$  has high toxicity [40] it can be used as an additive.

### 3.3 Effect of $\text{H}_2\text{O}_2$ on the rate of degradation of MB

Sonolytic degradation of MO was also carried out in presence of  $\text{H}_2\text{O}_2$  and  $\text{CCl}_4$  (citation) .Figure 5 shows that the rate of decomposition was increased by the addition of  $\text{H}_2\text{O}_2$ .

From the Fig. 5, it is evident that for 10 mg/L  $\text{H}_2\text{O}_2$  solution, the decomposition rate increases in presence of  $\text{H}_2\text{O}_2$ . It is clear from the data that the amount 20 and 200  $\mu\text{L}$  increased the rate of deterioration in comparison to pure MB but in presence of 100  $\mu\text{L}$  the degradation rate decreased. Fig. 5 demonstrates the graphical representation of the degradation of MB in presence of 20 mg/L  $\text{H}_2\text{O}_2$  solution (figure 5). Here, it is noticeable from Fig 5 that The lowest amount 20  $\mu\text{L}$  and 200  $\mu\text{L}$  of 20 mg/L  $\text{H}_2\text{O}_2$  solution added to the MB solution shows the highest degradation rate as compared with the amount 100  $\mu\text{L}$  of that  $\text{H}_2\text{O}_2$  solution.  $\text{H}_2\text{O}_2$  reaction mechanism for dye discoloration has been explained from the formation of free radicals as active species. (support citation)



(7)

~~Previous work~~Research has indicated that the US/UV/H<sub>2</sub>O<sub>2</sub> approach ~~was~~ the most effective in degrading malachite green ~~due to the~~~~because it uses~~ ultrasound to facilitate H<sub>2</sub>O<sub>2</sub> scission in addition to photolysis [41].~~(restructure this sentence)~~~~Another recent study demonstrated that~~ the impact of adding hydrogen peroxide was examined by varying its concentration to 0.05, 0.10, and 0.15 M ~~(citation)~~. The treatment with 0.10 M H<sub>2</sub>O<sub>2</sub> and 45 W was successful and energetically feasible, resulting in a 62.9% absorbance removal for the water assessed [42]. The amount of dissolved gas dropped and the amount of water vapor in the bubbles increased as the temperature of the aqueous solution rise [43], which led to a lower rate of OH radical production. As a result, when solution temperatures raise the rates of MB degradation decreased. The sonolysis of 4-chlorophenol in aqueous solution at 20 and 500 kHz as a function of solution temperature was reported by Jiang et al. [43]. They found that, in the 10–40 °C range, the rates of H<sub>2</sub>O<sub>2</sub> production and 4-chlorophenol degradation increased with the rising of solution temperatures at 500 kHz but reduced with rising solution temperatures at 20 kHz. The sonolysis of bisphenol A in aqueous solution as a function of solution temperatures at 489 kHz was reported by Uddin et al. [44]. The outcome shown that as the temperature of the aqueous solution increased, the rates of degradation increased within the range of 10–40 °C. When compared to earlier studies, it is evident that a variety of applications for hydrogen peroxide (H<sub>2</sub>O<sub>2</sub>) have been developed in the field of water treatment due to its relative safety and ease of use.




Fig. 5a: Effect of 10 mg of H<sub>2</sub>O<sub>2</sub>(10mg) on the degradation of MB




Fig. 5b: Effect of 20 mg of H<sub>2</sub>O<sub>2</sub>(20mg) on the degradation of MB

### 3. 4Effect of Inrganic Salt (NaCl and Na<sub>2</sub>SO<sub>4</sub>) on the degradation of MB:

The sonolytic degradation of MB was investigated in the presence of NaCl and Na<sub>2</sub>SO<sub>4</sub>.NaCl and Na<sub>2</sub>SO<sub>4</sub> were added in amounts of 10ml each to the MB solution in order to find the effects of the addition of inorganic salts on dye degradation. Figure 6 and Figure 7 shows the experimental result. It is seen in the figure, the addition of Na<sub>2</sub>SO<sub>4</sub> improved the degradation of MB, but the addition of NaCl caused it to decrease. Previous studies have shown that various synthetic dye solutions with a number of mixtures of Na<sub>2</sub>SO<sub>4</sub> and NaCl, Na<sub>2</sub>SO<sub>4</sub> influenced the decolourization efficiency more modestly than NaCl(citation). Higher concentration of Na<sub>2</sub>SO<sub>4</sub> did not hinder the decolorization process and even improved the effectiveness of reactive intense red K-2BP in dye solutions with the similar salt or Na<sup>+</sup> concentration [45]. Additionally, the deterioration rate accelerated due to the elevated salt concentration. Following comparison, it can be said that Na<sub>2</sub>SO<sub>4</sub> is superior to NaCl in terms of MB degradation. WHY?

Sonochemical degradation in absence and presence of Na<sub>2</sub>SO<sub>4</sub> or NaCl for 4-chlorophenol, phenol, catechol, and resorcinol under Ar was published by Uddin et al. in 2016 (Uddin et al., 2016)[46]. The rate of phenolic compound breakdown followed a pseudo-first order rate constant [47].






Fig. 6: Effect of NaCl on the degradation of MB

Formatted: Font: (Default) Times New Roman, 12 pt, Not Bold, (Asian) Japanese (Japan), (Other) English (Australia)



**Fig. 7: Effect of Na<sub>2</sub>SO<sub>4</sub> on the degradation of MB**

**3.5 Effect of ZnO nanoparticle on MB degradation:** Figure 8 shows the degradation rate of Methylene blue with ZnO nanoparticle. The degradation of Methylene blue was significantly increased with the increasing of sonication time. Maedeh Asgharian et al. observed the maximum degradation of MB in presence of rGO/ZnO/Cu compound at 25 mg photocatalyst dosage [48]. Please add more the justification of the findings. Presence of ZnO nanoparticle is also showed second highest degradation of MB in this study.



**Fig. 8: Effect of ZnO on the degradation of MB**

#### 4. Conclusions

The sonochemical degradation rate of MB was studied with several parameters, such as pH, addition of [several additives](#) (CCl<sub>4</sub>, H<sub>2</sub>O<sub>2</sub>, NaCl, Na<sub>2</sub>SO<sub>4</sub> and ZnO nanoparticle). [From the research work, the](#) degradation of MB increased under acidic pH condition. 400 µM/L doses of CCl<sub>4</sub> is more efficient to degrade the MB compared to 200 and 600 µM/L doses. It is thought that the degradation of CCl<sub>4</sub> created chlorine species and radicals, which accelerated the destruction of MB. The decomposition rate is also higher in presence of H<sub>2</sub>O<sub>2</sub> compared to the pure MB and 200 µM/L doses of 20mg/L H<sub>2</sub>O<sub>2</sub> shows the highest degradation rate than the other used doses of H<sub>2</sub>O<sub>2</sub> in this study. ~~On the other hand inorganic salt like NaCl and Na<sub>2</sub>SO<sub>4</sub> facilitate the deterioration of MB.~~ [\(put in the discussion\)](#) The degradation power of Na<sub>2</sub>SO<sub>4</sub> is higher than the NaCl. Use of ZnO nanoparticle improved the degradation rate significantly. The results showed that the MB degradation rate increases as the order of H<sub>2</sub>O<sub>2</sub> > ZnO > CCl<sub>4</sub> > Na<sub>2</sub>SO<sub>4</sub> > NaCl. Therefore, all these additives and catalysts are suitable for ultrasonic degradation of methylene blue in aqueous medium. [\(outcome /impact your research toward research question or gap\)](#)

#### References:

- [1] Y.B. Kim, J.H. Ahn, Microwave-assisted decolorization and decomposition of methylene blue with persulfate, *Int. Biodeterior. Biodegrad.* 95 (2014) 208–211 (part A).
- [2] L.C. Moraisi, O.M. Freitas, E.P. Goncalves, L.T. Vasconcelos, C.G. Gonzalez Beca, Reactive dyes removal from wastewaters by adsorption on eucalyptus bark: variables that define the process, *Wat. Res.* 33 (1999) 979–988.
- [3] K. Santhy, P. Selvapathy, Removal of reactive dyes from wastewater by adsorption on coir pith activated carbon, *Bioresour. Technol.* 97 (2006) 1329–1336.
- [4] M.H. Entezari, C. Petrier, P. Devidal, Sonochemical degradation of phenol in water: a comparison of classical equipment with a new cylindrical reactor, *Ultrason. Sonochem.* 10 (2003) 103–108.
- [5] M.Y. Zhu, G.W. Diao, Synthesis of porous Fe<sub>3</sub>O<sub>4</sub> nanospheres and its application for the catalytic degradation of xylol orange, *J. Phys. Chem. C* 115 (2011) 18923–18934.
- [6] L. Zhou, C. Gao, W.J. Xu, Magnetic dendritic materials for highly efficient adsorption of dyes and drugs, *ACS Appl. Mater. Inter.* 2 (2010) 1483–1491.

- [7] Y.G. Adewuyi, Sonochemistry: environmental science and engineering applications, *Ind. Eng. Chem. Res.* 40 (2001) 4681–4715.
- [8] P. Chowdhury, T. Viraraghavan, Sonochemical degradation of chlorinated organic compounds, phenolic compounds and organic dyes—a review, *Sci. Total Environ.* 407 (2009) 2474–2492.
- [9] I. Hua, M.R. Hoffmann, Optimization of ultrasonic irradiation as an advanced oxidation technology, *Environ. Sci. Tech.* 31 (1997) 2237–2243.
- [10] V. Misik, N. Miyoshi, P. Riesz, EPR spin-trapping study of the sonolysis of H<sub>2</sub>O/D<sub>2</sub>O mixtures: probing the temperatures of cavitation regions, *J. Phys. Chem.* 99 (1995) 3605–3611.
- [11] K. Okitsu, K. Iwasaki, Y. Yobiko, H. Bandow, R. Nishimura, Y. Maeda, Sonochemical degradation of azo dyes in aqueous solutions: a new heterogeneous kinetics model taking into account the local concentration of OH radicals and azo dyes, *Ultrason. Sonochem.* 12 (2005) 255–262.
- [12] M. Inoue, F. Okada, A. Sakurai, M. Sakakibara, A new development of dyestuffs degradation system using ultrasound, *Ultrason. Sonochem.* 13 (2006) 313–320.
- [13] S. Merouani, O. Hamdaoui, F. Saoudi, M. Chiha, Sonochemical degradation of Rhodamine B in aqueous phase: effects of additives, *Chem. Eng. J.* 158 (2010) 550–557.
- [14] D. Kobayashi, C. Honma, A. Suzuki, T. Takahashi, H. Matsumoto, C. Kuroda, K. Otake, A. Shono, Comparison of ultrasonic degradation rates constants of methylene blue at 22.8 kHz, 127 kHz, and 490 kHz, *Ultrason. Sonochem.* 19 (2012) 745–749.
- [15] D. Kobayashi, C. Honma, H. Matsumoto, T. Takahashi, C. Kuroda, K. Otake, A. Shono, Kinetics analysis for development of a rate constant estimation model for ultrasonic degradation reaction of methylene blue, *Ultrason. Sonochem.* 21 (2014) 1489–1495.
- [16] P. Kruus, R.C. Burk, M.H. Entezari, R. Otson, Sonication of aqueous solutions of chlorobenzene, *Ultrason. Sonochem.* 4 (1997) 229–233.
- [17] C. Petrier, A. Francony, Ultrasonic waste-water treatment: incidence of ultrasonic frequency on the rate of phenol and carbon tetrachloride degradation, *Ultrason. Sonochem.* 4 (1997) 295–300.
- [18] D.T. Sponza, R. Oztekin, Dephenolization, dearomatization and detoxification of olive mill wastewater with sonication combined with additives and radical scavengers, *Ultrason. Sonochem.* 21 (3) (2014) 1244–1257.

- [19] W. Zheng, M. Maurin, M.A. Tarr, Enhancement of sonochemical degradation of phenol using hydrogen atom scavengers, *Ultrason. Sonochem.* 12 (4) (2005) 313–317.
- [20] Shirajum Monira, Md. Ashifuzzaman, Md. Monjurul Islam, Md. Jahangir Hossain, Kenji Okitsu, Md. Hafizur Rahman, Md. Shaharul Islam & Md. Helal Uddin: Effects of Additives on Sonolytic Degradation of Azo Dye Molecules Found in Industrial Wastewater, *Jurnal Kejuruteraan*, **34(1)** (2022) 41-50.
- [21] Md. Monjurul Islam, B. M. Saifur Rahman, Most. Shahida Khatun, Md. Jahangir Hossain, Md. Tanjirul Huda, Md. Shaharul Islam, G. M. Arifuzzaman Khan, Md. Helal Uddin: Sonochemical degradation of phenol and Para-Chlorophenol in an Ultrasonic bath in the presence of inorganic salts and H<sub>2</sub>O<sub>2</sub>, *International Journal for Excogitation Education and Research*, **1(1)** (2017) 22-33.
- [22] Jahangir Hossain, Shirajum Monira, M. Shahinuzzaman, Md. Samiul Bari Avick, Md. Shaharul Islam, Mst. Marjia Khatun, S. M. Abdur Razzaque and Md. Helal Uddin; Effect of Additives on Decomposition of Methyl Orange and Congo Red Dyes Found in Industrial Wastewater, *Asian Journal of Physical and Chemical Sciences*, 11(3)(2023) 52-63.
- [23] Nagpal, M.; Kakkar, R. Use of metal oxides for the adsorptive removal of toxic organic pollutants. *Sep. Purif. Technol.* **2019**, 211, 522–539. [CrossRef]
- [24] Wawrzekiewicz, M.; Wiśniewska, M.; Wołowicz, A.; Gun'ko, V.M.; Zarko, V.I. Mixed silica-alumina oxide as sorbent for dyes and metal ions removal from aqueous solutions and wastewaters. *Microporous Mesoporous Mater.* **2017**, 250, 128–147. [CrossRef]
- [25] Danish, M.S.S.; Bhattacharya, A.; Stepanova, D.; Mikhaylov, A.; Grilli, M.L.; Khosravy, M.; Senjyu, T. A Systematic Review of Metal Oxide Applications for Energy and Environmental Sustainability. *Metals* **2020**, 10, 1604. [CrossRef]
- [26] Huang, Y.; Su, W.; Wang, R.; Zhao, T. Removal of typical industrial gaseous pollutants: From carbon, zeolite, and metal-organic frameworks to molecularly imprinted adsorbents. *Aerosol Air Qual. Res.* **2019**, 19, 2130–2150. [CrossRef]
- [27] Lee, K.M.; Lai, C.W.; Ngai, K.S.; Juan, J.C. Recent developments of zinc oxide based photocatalyst in water treatment technology: A review. *Water Res.* **2016**, 88, 428–448. [CrossRef]
- [28] Hashimoto, K.; Irie, H.; Fujishima, A. TiO<sub>2</sub> photocatalysis: A historical overview and

- future prospects. *Jpn. J. Appl. Phys.* **2005**, *44*, 8269–8285. [CrossRef]
- [29] Dastan, D.; Panahi, S.L.; Chaure, N.B. Characterization of titania thin films grown by dip-coating technique. *J. Mater. Sci. Mater. Electron.* **2016**, *27*, 12291–12296. [CrossRef]
- [30] Dastan, D.; Panahi, S.L.; Yengantiwar, A.P.; Banpurkar, A.G. Morphological and electrical studies of titania powder and films grown by aqueous solution method. *Adv. Sci. Lett.* **2016**, *22*, 950–953. [CrossRef]
- [31] Dastan, D. Effect of preparation methods on the properties of titania nanoparticles: Solvothermal versus sol-gel. *Appl. Phys. A* **2017**, *1–13*, 123–699. [CrossRef]
- [32] Azmina, M.S.; Nor, R.M.; Rifaie, H.A.; Razak, N.S.A.; Sani, S.F.A.; Osman, Z. Enhanced photocatalytic activity of ZnO nanoparticles grown on porous silica microparticles. *Appl. Nanosci.* **2017**, *7*, 885–892. [CrossRef]
- [33] Hariharan, C. Photocatalytic degradation of organic contaminants in water by ZnO nanoparticles: Revisited. *Appl. Catal. A Gen.* **2006**, *304*, 55–61. [CrossRef]
- [34] M. Hamida, A. Dehane, S. Merouani, O. Hamdaoui, M. Ashokkumar, The role of reactive chlorine species and hydroxyl radical in the ultrafast removal of Safranin O from wastewater by CCl<sub>4</sub>/ultrasound sono-process, *Chemical Engineering and Processing-Process Intensification*. 178(2022) 109014.
- [35] R. Cheng, S. Ou, M. Li, Y. Li, B. Xiang, Ethylenediamine modified starch as biosorbent for acid dyes, *Journal of hazardous materials*. 172(2009) 1665-70.
- [36] K.S. Suslick, M.M. Mdleleni, J.T. Ries, Chemistry induced by hydrodynamic cavitation, *J. Am. Chem. Soc.* 119 (1997) 9303–9304.
- [37] A. Francony, C. Petrier, Sonochemical degradation of carbon tetrachloride in aqueous solution at two frequencies: 20 kHz and 500 kHz, *Ultrason. Sonochem.* 3 (1996) S77–S82.
- [38] I. Hua, M.K. Hoffmann, Kinetics and mechanism of the sonolytic degradation of CCl<sub>4</sub>: intermediates and byproducts, *Environ. Sci. Technol.* 30 (1996) 864–871.
- [39] K. Okitsu, K. Kawasaki, B. Nanzai, N. Takenaka, H. Bandow, Effect of carbon tetrachloride on sonochemical decomposition of methyl orange in water, *Chemosphere* 71 (2008) 36–42.
- [40] R.O. Recknagel, E.A. Glende, J.A. Dolak, R.L. Waller, Mechanisms of carbon tetrachloride toxicity, *Pharmacol. Ther.* 43 (1989) 139–154.
- [41] I.M. Banat, P. Nigam, D. Singh, R. Marchant, Microbial decolorization of textile-dyecontaining effluents: a review, *Bioresource technology*. 58(1996) 217-27.

- [42] L. Miah, Impact of textile dyeing effluent on environment; a study based on Bangladesh.
- [43] Y. Jiang, C. Petrier, T.D. Waite, Sonolysis of 4-chlorophenol in aqueous solution: effects of substrate concentration, aqueous temperature and ultrasonic frequency, *Ultrason. Sonochem.* 13 (2006) 415–422.
- [44] M.H. Uddin, S.I. Hatanaka, S. Hayashi, Effects of aqueous temperature on sonolysis of bisphenol A: rate constants increasing with temperature under oxygen, *J. Chem. Eng. Jpn* 42 (2009) 303–308.
- [45] H. Zollinger. Synthesis, properties of organic dyes and pigments, *Color Chemistry*. VCH Publishers, New York, USA; 1987.
- [46] Uddin, M. H., Nanzai, B. & Okitsu, K. (2016). Effects of  $\text{Na}_2\text{SO}_4$  or  $\text{NaCl}$  on sonochemical degradation of phenolic compounds in an aqueous solution under Ar: Positive and negative effects induced by the presence of salts. *Ultrasonics sonochemistry*, 28 (2016) 144-149.
- [47] A. Bafana, S.S. Devi, T. Chakrabarti, Azo dyes: past, present and the future, *Environmental Reviews*. 19(2011) 350-71.
- [48] Maedeh Asgharian, Mohsen Mehdipourghazi, Behnam Khoshandam, Narjes Keramati, Photocatalytic degradation of methylene blue with synthesized rGO/ZnO/Cu, *Chemical physics letter*, 719(2019)1-7.