

## **Synthesis of Silver Nanomaterials Capping by Bio-mediated Extracts and Antimicrobial Activity: A Critical Review**

### **ABSTRACT**

Natural silver nanoparticles are currently being used innovatively, different bio-mediated fruit peel extracts were used to produce silver nanoparticles (AgNPs) and to explore the synthesis of environmentally friendly. To produce biodegradable AgNPs, natural synthesis employed various bio-mediated fruit peel extracts that function as reducing agents as well as capping agents. It was discovered that several fruit peel extracts decreased the capping agent and silver ions ( $\text{Ag}^+$  to  $\text{Ag}^0$ ). Due to reduction, the reaction changes the hydrogel's distinctive hue to a reddish brown. UV-visible spectra of the AgNPs showed a distinctive surface plasmon resonance (SPR) peak around 460.0 nm. Using X-ray diffraction, the crystalline nature was discovered with Bragg's diffraction. FT-IR confirmed silver ions function as a capping and reducing agent. The transmission electron microscope confirmed that the average size of the nanoparticles was below 100.0 nm. These nanoparticles' ability to combat both bacteria, algae and fungi was also investigated. This manuscript highlights the different bio-mediated and peel extracts that are efficient in producing AgNPs and their function for antimicrobial activity.

**Keywords:** Bio-mediated, nanoparticles (NPs), peel extracts, reducing agent, silver nanoparticles (AgNPs).

### **1. Introduction**

The function of nanotechnology in science and technology is to create novel, unique and unified materials at the nanoscale [1]. One billionth of a metre like  $10^{-9}$  is denoted by the term nano. In 1974, Tokyo Science University professor Norio Taniguchi first used the term "nanotechnology" to refer to the precise synthesis of materials at the nanoscale level [2]. Nanoparticles have distinct chemical, optical and mechanical capabilities, their application is becoming more popular in the twenty-first century [3]. Although the formation of AgNPs by chemical and physical means has been thoroughly investigated, one crucial area of nanotechnology is the development of dependable natural technology to produce nanoparticles [4]. Enzymes and bacteria are proposed as potential natural substitutes [5]. Because noble metal nanoparticles like silver have special optical, electrical, mechanical, magnetic, size-dependent and chemical properties. There has been an increase in the focus of current studies on these nanoparticles and the bulk materials differ greatly from one another [6]. Metal nanoparticles have important uses in electronics, optoelectronics, magnetic, biological and information storage systems because of these size-dependent characteristics [3, 6]. Metal nanoparticles can be synthesized using a variety of methods, including chemical, electrochemical, photochemical and radiation. Toxic compounds produced by the chemical technique may have negative effects on human health and medical applications [6]. Therefore, the biosynthesis of nanoparticles is required. Reduction serves as the primary driving force underlying the widely recognized bottom-up technique known as metal nanoparticle biogenesis [6]. When compared to chemical approaches, this method produces safer more affordable and ecologically friendly nanoparticles [7]. It is more convenient to use agricultural waste such as bio-mediated peel extracts to produce nanoparticles than it is to use other benign biological processes. Fruit peels are particularly readily available, effective, reasonably priced, natural, eco-friendly and abundant in bioactive components [7]. Since these bioactive substances have potential applications as antibacterial and antioxidants. Most researchers are working to find a productive method of removing these substances from fruit

peels[7]. There are numerous methods for creating silver nanoparticles. For example, facile method [8], thermal decomposition of silver compounds[9], electrochemical [10], Sonochemical [11], microwave-assisted process [12] and recently via green chemistry route[13]. To create ecologically safe methods for synthesizing AgNPs without the use of hazardous compounds is expanding[8, 13]. The use of microorganisms or plant extracts in biosynthetic processes has made them a straightforward and practical substitute for physical and chemical synthetic processes. Compared to other biological processes, the extract that serves as a reducing and capping agent for the production of nanoparticles has greater advantages [8, 14].


The plant's nanoparticles are favoured because they are affordable, environmentally beneficial, a one-step procedure for biosynthesis and safe for humans [10-13]. Various substances including extracts[11], fruit [12], bark [13], fruit peels [14], root [15] and callus [16] have been investigated thus far for the production of silver nanoparticles in different sizes, shapes and forms. Plant extracts are used to synthesize natural nanoparticles. All across the world, people eat bananas, papaya, dragon fruits etc. and after the pulp is eaten the peels are usually thrown away [18]. Among the uses for banana peels that have been covered in the literature are used for their therapeutic qualities [19], production of ethanol [20], foundation for the production of fungal biomass [21], synthesis of laccase [22] and biosorbent to remove heavy metals [23]. Furthermore, banana peels which are naturally abundant in polymers like cellulose, hemicellulose, lignin and pectin might be applied to the production of AgNPs[23]. Catalytic activity and other associated qualities such as antibacterial activity of AgNPs are correlated with specific surface area. Because surface energy rises with increasing specific surface area, nanoparticles may potentially become more biologically useful [23, 67]. In medicinal and pharmaceutical uses, noble metal nanoparticles come into direct contact with the human body,

like toothpaste, shampoos, soaps, detergents, shoes and cosmetics[24]. Given the increasing microbial resistance to metal ions, antibiotics and the emergence of resistant strains, researchers are becoming increasingly interested in metallic nanoparticles which exhibit promising antibacterial properties due to their large surface area to volume ratio[7, 24]. With the use of an extract made from leftover banana peels, phytochemicals [24, 69] etc. seek to create silver nanoparticles in an environmentally friendly manner. The AgNPs were characterized using a variety of techniques SEM, TEM, XRD and FTIR[50-55]. AgNPs an inorganic antibacterial agent that are harmless and nontoxic and they can eradicate approximately 650.0 different types of microbes that cause diseases [25-26]. From this point of view, we overview the studies that are easy to find even being envisioned as antibacterial agents of the future any potential aspect.

## **2.0. Materials and Methods**

### **2.1. Materials**

A different variety of fruit peels were screened from the nearby area. After being retrieved from the nearby place such as pomegranate, banana, papaya and dragon fruits in Fig. 1. The peels were taken off and allowed to air dry and investigated crucially. The different parts of these peels were investigated and the best-fitted data was found to be investigated scientifically.



**Fig. 1.** Source of different bio-mediated peel extracts.

## 2.2. Methods

AgNPs are synthesized by the main three possible routes physical methods, chemical methods and biological methods. The three routes follow the possible approach such as the top-down approach and the bottom-up approach [27]. The atoms are submerged in the bottom-up approach and in another way, the bulks are decomposed into smaller ones in a top-down approach [27] expressed in **Table 1**.

**Table 1.** Synthesis procedure of nanomaterials

Methods	Description	Type	Nature
Physical methods	Laser ablation, high energy ball-milling, electro-spraying, inert gas condensation, physical vapour deposition and laser pyrolysis etc.	Top-down approach	Toxic
Chemical methods	Sol-gel method, microemulsion techniques, hydrothermal analysis, polyol synthesis and chemical vapour synthesis etc.	Bottom-up approach	Toxic
Biological methods	Steam, roots, leaves, latex, buds, flowers, seeds, bacteria, fungi, yeast, microalgae and macroalgae etc.	Bottom-up approach	Nontoxic

The bio-mediated peels were cut into little pieces and peels were then cleaned three times using tap water and distilled water to get rid of any external dirt impurities [28]. On paper towels, the peels were then taken off and allowed to dry. After adding 50.0 ml of double-distilled water to a 100.00 ml beaker with about 25.0 g of peel, the mixture was brought to a boil at 800.0 °C for 10.0 minutes [28]. The peel was then filtered twice using Whatman filter paper to exclude macromolecules. As a self-reducing agent in this, banana and papaya peel extract work. To reduce silver nitrate into AgNPs, around 5.0 ml of filtered bio-peel extract is collected, added to 1.0 mM of pure aqueous silver nitrate solution and agitated for 1.0 hour [28]. The solution changes colour from yellow to brownish yellow to deep brown as a result of the reduction process of Ag<sup>+</sup> to Ag<sup>0</sup> and confirmed the formation of nanoparticles. The creation of a brown colour indicates that the AgNPs synthesis was finished [28].

**Table 2.** Bacterial-mediated synthesis of AgNPs

Bacteria	Silver salt	Shape	Size	Application	References
<i>Lactobacillus acidophilus</i>	AgNO <sub>3</sub>	Spherical	10.0-20.0	Antioxidant and antimicrobial activity	[29]
<i>Bacillus cereus</i>	AgNO <sub>3</sub>	Spherical	20.0-40.0	Antioxidant and Antibacterial activity	[30]
<i>Bacillus sp.</i>	AgNO <sub>3</sub>	Spherical	22.0-41.0	Antifungal activity	[31]
<i>Pseudoduganel la eburnean</i>	AgNO <sub>3</sub>	Spherical	8.0-24.0	Antimicrobial activity	[32]
<i>Bacillus siamensis</i>	AgNO <sub>3</sub>	Spherical	25.0-50.0	Antibacterial activity	[33]
<i>Phenerochaete chryso sporium</i>	AgNO <sub>3</sub>	Spherical	34.0-90.0	Antibacterial activity	[34]
<i>Bacillus brevis</i>	AgNO <sub>3</sub>	Spherical	41.0-68.0	Antibacterial activity	[35]
<i>Streptomyces sp.</i>	AgNO <sub>3</sub>	Spherical	10.0-30.0	Antibacterial activity and antiviral activity	[36]

A comparable procedure is used to produce AgNPs using different amounts of papaya and banana peel extract from carioca [28] as well as different sources of bacteria, fungus and algae mediated also applied for the synthesized of silver nanomaterials illustrated in Table 2 to Table 4.

**Table 3.** Fungal medical synthesis of AgNPs

Fungus	Silver salt	Shape	Size	Application	Reference
Talaromyces purpureogenus	AgNO <sub>3</sub>	Spherical	50.0-70.0	Antifungal	[37]
Trichoderma harzianum	AgNO <sub>3</sub>	Spherical	31.13	Antifungal	[38]
Anamorphus bjerkantera	AgNO <sub>3</sub>	Spherical	70.0-90.0	-	[39]
Penicillium verrucosum	AgNO <sub>3</sub>	Spherical	10.0-12.0	Antifungal	[40]
Aspergillus brunneoviolaceus	AgNO <sub>3</sub>	Spherical	0.72-15.21	Antioxidative acidity	[41]
Penicillium oxalicum	AgNO <sub>3</sub>	Spherical	60.0-80.0	Antifungal	[42]
Setosphaeria rostrata	AgNO <sub>3</sub>	Spherical	2.0-20.0	Antifungal	[43]
Fusarium scirpi	AgNO <sub>3</sub>	Spherical	2.0-20.0	Antifungal	[44]

**Table 4.** Algal-mediated synthesis of AgNPs

Algae	Silver salt	Shape	Size (nm)	Application	Reference
Chaetomorpha Ligustica	AgNO <sub>3</sub>	Spherical	2.0-12.0	Anticancer	[45]
Chlorella vulgaris	AgNO <sub>3</sub>	Spherical	55.0	Photocatalytic dye degradation acidity	[46]
Gelidium Corneum	AgNO <sub>3</sub>	Spherical	20.0-50.0	-	[47]
Noctiluca Scintillans	AgNO <sub>3</sub>	Spherical	4.50	Antibacterial	[48]
Botryococcus braunii	AgNO <sub>3</sub>	Cubical and spherical	40.0-90.0	Antimicrobial	[49]

### 3.0. Characterization Technique

Different type of techniques was employed for the characterization of AgNPs such as spectroscopic, X-ray and microscopic listed in Table 5. The spectroscopic techniques interact

with the nanomaterials which produce different signals that can calculate the optical properties, synthesis and stability of NPs by UV-visible; investigate the phytochemical's role in NPs synthesis by FTIR and determine the hydrodynamic diameter and polydispersity index of NPs by DLS [50-52]. Determine the crystalline size, shape, structure, lattice parameters, stress, strain, dislocation density, lattice volume and particle size of NPs, surface morphology, shape, size and electrical and mechanical properties of NPs by X-ray [53].

**Table 5.** Common techniques for the characterization of silver nanoparticles

Techniques	Characterization techniques	Information provided	References
Spectroscopic techniques	UV-visible	Optical properties, synthesis and stability.	[50]
	FTIR	phytochemical's role.	[51]
	DLS	hydrodynamic diameter and polydispersity index.	[52]
X-ray based techniques	XRD, XAS, XRF, XPS	crystalline structure and particle size.	[53]
	AFM	Surface morphology, shape, size, electrical, and mechanical properties.	[53]
Microscopic	SEM	Particle size distribution, morphology and topography.	[54]
	TEM	Morphology, shape, size, elemental composition and electrical conductivity.	[55]


The internal and surface morphology, shape, size, elemental composition, impurities, lattice free energy and electrical conductivity of NPs by scanning electron microscope and transmission electron microscope [55].

## 4.0. Results and Discussion

### 4.1. Visible observation

Fig. 2. shows that the mixture of artificially created AgNPs is made with papaya peel extracts in different concentrations as 5.0 ml, 10.0 ml, 15.0 ml, 20.0 ml and 25.0 ml[56]. Fig. 2. which shows the colour variation of the reaction mixture 1.0 hours after the reaction started, shows how

the concentration of *Carica papaya* bio-mediated peel extracts utilized has an effect [56]. With an increase in peel extract concentration from 5.0 ml to 25.0 ml, the reaction mixture's colour from reddish brown to brown increases and conformation nanoparticles are formed [56].



**Fig. 2.** Silver nanoparticles using (a) 5.0 ml, (b) 10.0 ml, (c) 15.0 ml, (d) 20.0 ml, (e) 25.0 ml of *Carica papaya* peel extract after 1.0 h of incubation.

#### 4.2. UV-visible Spectra Analysis

After the 24.0-hour incubation period, the UV visible absorption spectra of AgNPs at five distinct concentrations 5.0 ml, 10.0 ml, 15.0 ml, 20.0 ml and 25.0 ml of the aqueous papaya peel extract at room temperature peaks are found at 410.0 nm, 420.0 nm, 435.0 nm, 422.0 nm and 418.0 nm respectively [57]. The absorption SPR band is detected for 5.0 ml, 10.0 ml, 15.0 ml, 20.0 ml and 25.0 ml concentrations of papaya peel-mediated silver nanoparticles [57]. At 15.0 ml and 25.0 ml concentrations, the SPR peak with maximum and minimum intensity is detected at 435.0 nm and 418.0 nm [57].

**Table 6.** The optical band gap of papaya peel extracts from *Carica*

Sample	Optical Band Gap (eV)	Reference
05.0 ml	4.9	[56-58]

10.0 ml	4.7	[56-58]
15.0 ml	4.6	[56-58]
20.0 ml	4.7	[56-58]
25.0 ml	4.8	[56-58]
10.0 ml	2.5	[79]
10.0 ml	3.4	[80]


The papaya peel extract concentration rises from 5.0 to 15.0 ml and the optical band gap reduces, confirming that the energy band gap also lowers as particle size increases [58]. The optical band gap is found to rise as the papaya peel extract concentration is increased to 20.0 ml and 25.0 ml, confirming the decrease in the size of the AgNPs for these concentrations which may also be supported by further XRD analysis [58, 79].

#### 4.3. FT-IR Analysis

Bio-mediated carica papaya peel extract's FT-IR transmission spectra absorption bands near  $2924.09\text{ cm}^{-1}$ ,  $2862.36\text{ cm}^{-1}$  and  $1458.18\text{ cm}^{-1}$ ,  $979.84\text{ cm}^{-1}$  can be indicative of C–H alkene stretching or bending vibrations [58]. The bands located approximately at  $3726.47\text{ cm}^{-1}$  and  $918.12\text{ cm}^{-1}$  respectively are ascribed to carboxylic acid vibrations that are either stretching [58]. The bands located approximately at  $1188.15\text{ cm}^{-1}$  and  $1658.78\text{ cm}^{-1}$  can be attributed to amide I and II N–H bending which result from protein peptide bonds and carbonyl stretching, respectively [59]. When compared to pure carica papaya peel extract, the bands around  $3100\text{--}3400\text{ cm}^{-1}$  and  $1600\text{--}1650\text{ cm}^{-1}$  respectively due to carboxylic and amine groups are shifted to higher wavelengths due to the binding of silver ions and the depth of the band decreases [60].

#### 4.4. X-ray Diffraction (XRD) Analysis

The XRD patterns unequivocally demonstrate the crystalline nature of the AgNPs produced by the bio-reduction of silver ions in papaya peel broth. The phase distribution, crystallinity, dislocation density, lattice parameters and purity of the produced silver nanoparticles are assessed by XRD[81]. The two thetas ( $2\theta$ ) values in the diffractogram of the silver nanoparticle range from  $20.0^\circ$  to  $90.0^\circ$ [81]. There are five unique diffractions for the cubic crystal of silver nanoparticles which are (111), (200), (220), (311) and (222) predominant plane when indexed under the standard[61][JCPDS] Card [No. 04-783] in Fig. 3.[81].



**Fig. 3.** X-ray diffractogram of silver nanomaterials


Peel extract may account for the diffraction seen at  $27.0^\circ$  and  $32.0^\circ$ . A capping chemical stabilizing the nanoparticles may have caused these Bragg diffraction[62]. The crystallite sizes of the silver nanoparticles at different concentrations of papaya peel extract are determined [63] by the Debye-Scherrer model denoted equation 1.

$$D = \frac{K\lambda}{\beta \cos \theta} \text{-----(1)}$$

The average crystallite size was determined to be 16.1 nm, 16.3 nm, 17.9 nm, 17.8 nm and 17.7 nm respectively for papaya peel extracts varying concentration [63]. The average crystallite size of the particles is found to grow when the papaya peel extract concentration rises. The average crystallite size of the particles then gradually declines as the concentration rises to a low volume [64]. The UV visible spectrum examination could verify the particle's decreased crystallite size. Further observations reveal that the synthesized silver nanoparticles have a crystallite size that is significantly less than the 28.0 nm reported [64]. This reduction in crystallite size improves the silver nanoparticles' characteristics [68].

#### 4.5. SEM Analysis

SEM analysis is performed to study the surface morphology and shapes of AgNPs illustrated in Fig. 4 [78]. For *Carica papaya* peel is observed that the silver nanoparticles are spherical and the concentration of the extract alters the size and shape of the nanoparticles [65].




**Fig. 4.** SEM images of silver nanoparticles using leaf extract

The particles are uniformly distributed and no aggregations are observed at low concentrations. However, the particles get agglomerated as the concentration of papaya extract and Cajanuscajan leaf extract increases for high concentrations [65, 78]. The agglomeration of particles leads to the destabilization of silver nanoparticles [65, 78].

#### **4.6. TEM analysis**

TEM images of silver nanoparticles synthesized using peel are shown in Fig. 5 [65].



**Fig. 5.** TEM images of silver nanoparticles using peel extract

AgNPs size and form in the solution change with extract concentration. Mostly spherical nanoparticle shape is suggested by these image profiles [65]. There are also a few isolated nanoparticles in some areas, suggesting that sedimentation may have occurred later [66]. The range of 15.0 nm to 20.0 nm is reported to be the average particle size of AgNPs. Parallely proved with the crystallite size determined by XRD analysis as well as TEM the results show good agreement for argument [66].

### **5.0. Antimicrobial Activity of Silver Nanoparticles**

The bio-mediated plant parts such as the leaf, root etc into silver species show outstanding antimicrobial, anticancer, antifungal, cytotoxicity as well as catalytic activity [70-75]. The


properties also depend on its substrate, shape and size impact this antimicrobial activity as well as the surface-to-volume ratio that is responsible for demineralization listed in [Table 7](#).[\[76\]](#).

**Table 7.** Antimicrobial activity of silver nanoparticles

Plants	Plant's part	Shape	Substrates	Applications	References
Allium fistulosum, Tabernaemontana divaricata and Basella alba	Leaf	Rod	AgNO <sub>3</sub>	Antimicrobial	<a href="#">[70]</a>
Tridax procumbens	Leaf	Spherical	AgNO <sub>3</sub>	Antimicrobial, anticancer	<a href="#">[71]</a>
Aloysia citrodora	Leaf	Spherical	AgNO <sub>3</sub>	Antifungal	<a href="#">[72]</a>
Alhagi graecorum	Leaf	Spherical	AgNO <sub>3</sub>	Cytotoxicity and antifungal	<a href="#">[73]</a>
Rubus ellipticus	Root	Spherical	AgNO <sub>3</sub>	Antibacterial	<a href="#">[74]</a>
Rhodiola imbricata with aniasomnifera	Root	Spherical	AgNO <sub>3</sub>	Catalytic activity	<a href="#">[75]</a>

For example, the plant Allium Fistulosum, Tabernaemontana Divaricata and Basella Alba leaf extract produced AgNPs that are rod shape effective for antimicrobial activities[\[70\]](#).

In the agar diffusion test, there was no growth inhibition zone around in disks with 1.0 % and 2.0 % concentrations. However, in [Fig. 6](#), a growth inhibition zone was seen in 5.0 % concentration, with a diameter of 9.5±0.7 mm for *S. mutans*, 8.5±0.7 mm for *S. sanguis* and 8.0 ±1.4 for *L. acidophilus*[\[77\]](#). So, the AgNPs show outstanding microbial properties.



**Fig. 6.** Growth inhibition zone of microbes

### Conclusion

Different doses of bio-mediated peel extract as the reducing agent and capping agent are discussed for the effective green production of silver nanoparticles. These nanoparticles are entirely safe and kind to the environment. The absorption peaks in the UV visible spectra of silver nanoparticles for varying doses are explained. When the peel extract concentration is low then the optical band gap decreases and the absorption peaks redshift, indicating an increase in particle size. Furthermore, it is seen that the absorption peaks blue shift and the optical band gap widens as the concentration of peel extract is high. These observations suggest that the particle size will decrease. By using XRD analysis, these differences in particle size may also be verified. By displaying the relevant bands that are in charge of converting silver ions into silver nanoparticles, the FTIR spectra verify the existence of different functional groups. The average

crystallite diameters of the crystalline silver nanoparticles, as revealed by the XRD diffractogram, are found to be between 16.0 and 18.0 nm which is in good agreement with the results of the TEM investigation. Different microbes were investigated for the antibacterial efficacy of silver nanoparticles. It was discovered that bacteria, algae and fungi have a larger zone of inhibition. This might be because there are more silver nanoparticles in the reaction mixture.

## References

- [1]. Aravind, G., Bhowmik, D., Duraivel, S., & Harish, G. (2013). Traditional and medicinal uses of *Carica papaya*. *Journal of Medicinal Plants Studies*, 1(1), 7–15.
- [2]. Rivera Gómez, C. C., Naranjo, L. G., & Duque, A. M. (2006). De María a un mar de caña. Imaginarios de naturaleza en la transformación del paisaje vallecaucano entre 1950 y 1970. Universidad Autónoma de Occidente.
- [3]. Banerjee, P., Satapathy, M., Mukhopahayay, A., & Das, P. (2014). Leaf extract mediated green synthesis of silver nanoparticles from widely available Indian plants: Synthesis, characterization, antimicrobial property and toxicity analysis. *Bioresources and Bioprocessing*, 1(3), 1–10.
- [4]. Joe, A. W., Yi, L., Natarajan, A., Le Grand, F., So, L., Wang, J., ... & Rossi, F. M. (2010). Muscle injury activates resident fibro/adipogenic progenitors that facilitate myogenesis. *Nature Cell Biology*, 12(2), 153-163.
- [5]. Mohanpuria, P., Rana, N. K., & Yadav, S. K. (2008). Biosynthesis of nanoparticles: technological concepts and future applications. *Journal of nanoparticle research*, 10, 507-517.

- [6]. Hajizadeh, S., Farhadi, K., Forough, M., & Sabzi, R. E. (2011). Silver nanoparticles as a cyanide colourimetric sensor in aqueous media. *Analytical Methods*, 3(11), 2599-2603.
- [7]. Ozgur, S., Buchwald, G., Falk, S., Chakrabarti, S., Prabu, J. R., & Conti, E. (2015). The conformational plasticity of eukaryotic RNA- dependent ATP ases. *The FEBS journal*, 282(5), 850-863.
- [8]. Valli, J. S., & Vaseeharan, B. (2012). Biosynthesis of silver nanoparticles by *Cissus quadrangularis* extracts. *Materials Letters*, 82, 171-173.
- [9]. Saxena, A., Tripathi, R. M., Zafar, F., & Singh, P. (2012). Green synthesis of silver nanoparticles using aqueous solution of *Ficus benghalensis* leaf extract and characterization of their antibacterial activity. *Materials Letters*, 67(1), 91-94.
- [10]. Kumar, V., & Yadav, S. K. (2009). Plant- mediated synthesis of silver and gold nanoparticles and their applications. *Journal of Chemical Technology & Biotechnology: International Research in Process, Environmental & Clean Technology*, 84(2), 151-157.
- [11]. MubarakAli, D., Thajuddin, N., Jeganathan, K., & Gunasekaran, M. (2011). Plant extract mediated synthesis of silver and gold nanoparticles and its antibacterial activity against clinically isolated pathogens. *Colloids and Surfaces B: Biointerfaces*, 85(2), 360-365.
- [12]. Prathna, T. C., Chandrasekaran, N., Raichur, A. M., & Mukherjee, A. (2011). Biomimetic synthesis of silver nanoparticles by *Citrus limon* (lemon) aqueous extract and theoretical prediction of particle size. *Colloids and Surfaces B: Biointerfaces*, 82(1), 152-159.
- [13]. Oak, S. N., Parelkar, S. V., Satishkumar, K. V., Pathak, R., Ramesh, B. H., Sudhir, S., & Keshav, M. (2009). Review of video-assisted thoracoscopy in children. *Journal of Minimal Access Surgery*, 5(3), 57-62.
- [14]. Bankar, A., Joshi, B., Kumar, A. R., & Zinjarde, S. (2010). Banana peel extract mediated novel route for the synthesis of silver nanoparticles. *Colloids and Surfaces A: Physicochemical and Engineering Aspects*, 368(1-3), 58-63.

- [15]. Ahmad, P., Jaleel, C. A., Salem, M. A., Nabi, G., & Sharma, S. (2010). Roles of enzymatic and nonenzymatic antioxidants in plants during abiotic stress. *Critical reviews in biotechnology*, 30(3), 161-175.
- [16]. Nabikhan, A., Kandasamy, K., Raj, A., & Alikunhi, N. M. (2010). Synthesis of antimicrobial silver nanoparticles by callus and leaf extracts from saltmarsh plant, *Sesuvium portulacastrum* L. *Colloids and surfaces B: Biointerfaces*, 79(2), 488-493.
- [17]. Gopinath, B., Hardy, L. L., Baur, L. A., Burlutsky, G., & Mitchell, P. (2012). Physical activity and sedentary behaviours and health-related quality of life in adolescents. *Pediatrics*, 130(1), e167-e174.
- [18]. Bankar, A., Joshi, B., Kumar, A. R., & Zinjarde, S. (2010). Banana peel extract mediated a novel route for the synthesis of silver nanoparticles. *Colloids and Surfaces A: Physicochemical and Engineering Aspects*, 368(1-3), 58-63.
- [19]. Parmar, H. S., & Kar, A. (2008). Medicinal values of fruit peels from *Citrus sinensis*, *Punica granatum*, and *Musa paradisiaca* with respect to alterations in tissue lipid peroxidation and serum concentration of glucose, insulin, and thyroid hormones. *Journal of Medicinal Food*, 11(2), 376-381.
- [20]. Tewari, H. K., Marwaha, S. S., & Rupal, K. (1986). Ethanol from banana peels. *Agricultural wastes*, 16(2), 135-146.
- [21]. Essien, J. P., Akpan, E. J., & Essien, E. P. (2005). Studies on mould growth and biomass production using waste banana peel. *Bioresource Technology*, 96(13), 1451-1456.
- [22]. Osma, J. F., Saravia, V., Toca-Herrera, J. L., & Couto, S. R. (2007). Sunflower seed shells: a novel and effective low-cost adsorbent for the removal of the diazo dye Reactive Black 5 from aqueous solutions. *Journal of Hazardous Materials*, 147(3), 900-905.

- [23]. Annadurai, G., Juang, R. S., & Lee, D. J. (2003). Adsorption of heavy metals from water using banana and orange peels. *Water science and technology*, 47(1), 185-190.
- [24]. Choi, O., Deng, K. K., Kim, N. J., Ross Jr, L., Surampalli, R. Y., & Hu, Z. (2008). The inhibitory effects of silver nanoparticles, silver ions, and silver chloride colloids on microbial growth. *Water research*, 42(12), 3066-3074.
- [25]. Jeong, S. H., Yeo, S. Y., & Yi, S. C. (2005). The effect of filler particle size on the antibacterial properties of compounded polymer/silver fibres. *Journal of Materials Science*, 40, 5407-5411.
- [26]. Mahendra Rai, M. R., Alka Yadav, A. Y., Bridge, P., & Aniket Gade, A. G. (2009). Myconanotechnology: a new and emerging science. *Applied mycology*, 258-267.
- [27]. Zhu, L., Gharib, M., Becker, C., Zeng, Y., Ziefuß, A. R., Chen, L., ... & Chakraborty, I. (2019). Synthesis of fluorescent silver nanoclusters: Introducing bottom-up and top-down approaches to nanochemistry in a single laboratory class. *Journal of Chemical Education*, 97(1), 239-243.
- [28]. Qamer, S., Romli, M. H., Che-Hamzah, F., Misni, N., Joseph, N. M., Al-Haj, N. A., & Amin-Nordin, S. (2021). Systematic review on biosynthesis of silver nanoparticles and antibacterial activities: Application and theoretical perspectives. *Molecules*, 26(16), 5057.
- [29]. Rodríguez-Serrano, C., Guzmán-Moreno, J., Ángeles-Chávez, C., Rodríguez-González, V., Ortega-Sigala, J. J., Ramírez-Santoyo, R. M., & Vidales-Rodríguez, L. E. (2020). Biosynthesis of silver nanoparticles by *Fusarium scirpi* and its potential as antimicrobial agent against uropathogenic *Escherichia coli* biofilms. *Plos one*, 15(3), e0230275.
- [30]. Mujaddidi, N., Nisa, S., Al Ayoubi, S., Bibi, Y., Khan, S., Sabir, M., ... & Qayyum, A. (2021). Pharmacological properties of biogenically synthesized silver nanoparticles using endophyte *Bacillus cereus* extract of *Berberis lyceum* against oxidative stress and pathogenic multidrug-resistant bacteria. *Saudi journal of biological sciences*, 28(11), 6432-6440.

- [31]. Ajaz, S., Ahmed, T., Shahid, M., Noman, M., Shah, A. A., Mehmood, M. A., ... & Li, B. (2021). Bioinspired green synthesis of silver nanoparticles by using a native *Bacillus* sp. strain AW1-2: Characterization and antifungal activity against *Colletotrichum falcatum* Went. *Enzyme and microbial technology*, 144, 109745.
- [32]. Huq, M. A. (2020). Green synthesis of silver nanoparticles using *Pseudoduganellaeburnea* MAHUQ-39 and their antimicrobial mechanisms investigation against drug resistant human pathogens. *International journal of molecular sciences*, 21(4), 1510.
- [33]. Ibrahim, E., Fouad, H., Zhang, M., Zhang, Y., Qiu, W., Yan, C., ... & Chen, J. (2019). Biosynthesis of silver nanoparticles using endophytic bacteria and their role in inhibition of rice pathogenic bacteria and plant growth promotion. *RSC advances*, 9(50), 29293-29299.
- [34]. Saravanan, M., Arokiyaraj, S., Lakshmi, T., & Pugazhendhi, A. (2018). Synthesis of silver nanoparticles from *Phenerochaetechrysosporium* (MTCC-787) and their antibacterial activity against human pathogenic bacteria. *Microbial pathogenesis*, 117, 68-72.
- [35]. Saravanan, M., Barik, S. K., MubarakAli, D., Prakash, P., & Pugazhendhi, A. (2018). Synthesis of silver nanoparticles from *Bacillus brevis* (NCIM 2533) and their antibacterial activity against pathogenic bacteria. *Microbial pathogenesis*, 116, 221-226.
- [36]. Haggag, E. G., Elshamy, A. M., Rabeh, M. A., Gabr, N. M., Salem, M., Youssif, K. A., ... & Abdelmohsen, U. R. (2019). Antiviral potential of green synthesized silver nanoparticles of *Lampranthuscoccineus* and *Malephora lutea*. *International journal of nanomedicine*, 6217-6229.
- [37]. Sharma, A., Sagar, A., Rana, J., & Rani, R. (2022). Green synthesis of silver nanoparticles and its antibacterial activity using fungus *Talaromycespurpureogenus* isolated from *Taxus baccata* Linn. *Micro and Nano Systems Letters*, 10(1), 2.

- [38]. El-Ashmony, R. M., Zaghloul, N. S., Milošević, M., Mohany, M., Al-Rejaie, S. S., Abdallah, Y., & Galal, A. A. (2022). The biogenically efficient synthesis of silver nanoparticles using the fungus *Trichoderma harzianum* and their antifungal efficacy against *Sclerotinia sclerotiorum* and *Sclerotium rolfsii*. *Journal of Fungi*, 8(6), 597.
- [39]. Osorio-Echavarría, J., Osorio-Echavarría, J., Ossa-Orozco, C. P., & Gómez-Vanegas, N. A. (2021). Synthesis of silver nanoparticles using white-rot fungus *Anamorphous Bjerkandera* sp. R1: Influence of silver nitrate concentration and fungus growth time. *Scientific Reports*, 11(1), 3842.
- [40]. Yassin, M. A., Elgorban, A. M., El-Samawaty, A. E. R. M., & Almunqedhi, B. M. (2021). Biosynthesis of silver nanoparticles using *Penicillium verrucosum* and analysis of their antifungal activity. *Saudi Journal of Biological Sciences*, 28(4), 2123-2127.
- [41]. Mistry, H., Thakor, R., Patil, C., Trivedi, J., & Bariya, H. (2021). Biogenically proficient synthesis and characterization of silver nanoparticles employing marine procured fungi *Aspergillus brunneoviolaceus* along with their antibacterial and antioxidative potency. *Biotechnology Letters*, 43, 307-316.
- [42]. Feroze, N., Arshad, B., Younas, M., Afridi, M. I., Saqib, S., & Ayaz, A. (2020). Fungal mediated synthesis of silver nanoparticles and evaluation of antibacterial activity. *Microscopy Research and Technique*, 83(1), 72-80.
- [43]. Akther, T., Khan, M. S., & Hemalatha, S. (2020). Biosynthesis of silver nanoparticles via fungal cell filtrate and their anti-quorum sensing against *Pseudomonas aeruginosa*. *Journal of Environmental Chemical Engineering*, 8(6), 104365.
- [44]. Rodríguez-Serrano, C., Guzmán-Moreno, J., Ángeles-Chávez, C., Rodríguez-González, V., Ortega-Sigala, J. J., Ramírez-Santoyo, R. M., & Vidales-Rodríguez, L. E. (2020). Biosynthesis of

silver nanoparticles by *Fusarium scirpi* and its potential as antimicrobial agent against uropathogenic *Escherichia coli* biofilms. *Plos one*, 15(3), e0230275.

[45]. Al-Zahrani, S. A., Bhat, R. S., Al Rashed, S. A., Mahmood, A., Al Fahad, A., Alamro, G., ... & Al Daihan, S. (2021). Green-synthesized silver nanoparticles with aqueous extract of green algae *Chaetomorpha ligustica* and its anticancer potential. *Green Processing and Synthesis*, 10(1), 711-721.

[46]. Rajkumar, R., Ezhumalai, G., & Gnanadesigan, M. (2021). A green approach for the synthesis of silver nanoparticles by *Chlorella vulgaris* and its application in photocatalytic dye degradation activity. *Environmental Technology & Innovation*, 21, 101282.

[47]. Öztürk, B. Y., Gürsu, B. Y., & Dağ, İ. (2020). Antibiofilm and antimicrobial activities of green synthesized silver nanoparticles using marine red algae *Gelidium corneum*. *Process Biochemistry*, 89, 208-219.

[48]. Elgamouz, A., Idriss, H., Nassab, C., Bihi, A., Bajou, K., Hasan, K., ... & Patole, S. P. (2020). Green synthesis, characterization, antimicrobial, anti-cancer, and optimization of colorimetric sensing of hydrogen peroxide of algae extract capped silver nanoparticles. *Nanomaterials*, 10(9), 1861.

[49]. Arya, A., Mishra, V., & Chundawat, T. S. (2019). Green synthesis of silver nanoparticles from green algae (*Botryococcus braunii*) and its catalytic behavior for the synthesis of benzimidazoles. *Chemical Data Collections*, 20, 100190.

[50]. Punjabi, K., Choudhary, P., Samant, L., Mukherjee, S., Vaidya, S., & Chowdhary, A. (2015). Biosynthesis of nanoparticles: a review. *Int. J. Pharm. Sci. Rev. Res*, 30(1), 219-26.

[51]. Gudikandula, K., & Charya Maringanti, S. (2016). Synthesis of silver nanoparticles by chemical and biological methods and their antimicrobial properties. *Journal of experimental nanoscience*, 11(9), 714-721.

- [52]. True, H., Christiansen, A. H., Knutz, S. E., & Rasmussen, L. B. (2020). On the dynamics of a four-axle railway vehicle with dry friction yaw damping. *International Journal of Heavy Vehicle Systems*, 27(5), 600-621.
- [53]. Uvarov, V., & Popov, I. (2013). Metrological characterization of X-ray diffraction methods at different acquisition geometries for determination of crystallite size in nano-scale materials. *Materials Characterization*, 85, 111-123.
- [54]. Akbari, B., Tavandashti, M. P., & Zandrahimi, M. (2011). Particle size characterization of nanoparticles—a practical approach. *Iranian Journal of Materials Science and Engineering*, 8(2), 48-56.
- [55]. Aygün, A., Özdemir, S., Gülcan, M., Cellat, K., & Şen, F. (2020). Synthesis and characterization of Reishi mushroom-mediated green synthesis of silver nanoparticles for biochemical applications. *Journal of pharmaceutical and biomedical analysis*, 178, 112970.
- [56]. Kumar, V., Singh, A., Mithra, S. A., Krishnamurthy, S. L., Parida, S. K., Jain, S., ... & Mohapatra, T. (2015). Genome-wide association mapping of salinity tolerance in rice (*Oryza sativa*). *DNA research*, 22(2), 133-145.
- [57]. Rivera-Pastrana, D. M., Gardea, A. A., Yahia, E. M., Martínez-Téllez, M. A., & González-Aguilar, G. A. (2014). Effect of UV-C irradiation and low-temperature storage on bioactive compounds, antioxidant enzymes and radical scavenging activity of papaya fruit. *Journal of Food Science and Technology*, 51, 3821-3829.
- [58]. Balavijayalakshmi, J., & Ramalakshmi, V. (2017). Carica papaya peel mediated synthesis of silver nanoparticles and its antibacterial activity against human pathogens. *Journal of applied research and technology*, 15(5), 413-422.

- [59]. Balavijayalakshmi, J., & Ramalakshmi, V. (2017). Carica papaya peel mediated synthesis of silver nanoparticles and its antibacterial activity against human pathogens. *Journal of applied research and technology*, 15(5), 413-422.
- [60]. Sivakumar, T. (2021). A modern review of silver nanoparticles mediated plant extracts and its potential bioapplications. *Int. J. Bot. Stud*, 6(3), 170-175.
- [61]. Saravanakumar, A., Ganesh, M., Jayaprakash, J., & Jang, H. T. (2015). Biosynthesis of silver nanoparticles using Cassia tora leaf extract and its antioxidant and antibacterial activities. *Journal of Industrial and Engineering Chemistry*, 28, 277-281.
- [62]. Ibrahim, H. M. (2015). Green synthesis and characterization of silver nanoparticles using banana peel extract and their antimicrobial activity against representative microorganisms. *Journal of radiation research and applied sciences*, 8(3), 265-275.
- [63]. Rajeshkumar, S., Malarkodi, C., Gnanajobitha, G., Paulkumar, K., Vanaja, M., Kannan, C., & Annadurai, G. (2013). Seaweed-mediated synthesis of gold nanoparticles using Turbinariaconoides and its characterization. *Journal of Nanostructure in Chemistry*, 3, 1-7.
- [64]. Ramesh, P. S., Kokila, T., & Geetha, D. (2015). Plant-mediated green synthesis and antibacterial activity of silver nanoparticles using Emblica officinalis fruit extract. *Spectrochimica Acta Part A: Molecular and Biomolecular Spectroscopy*, 142, 339-343.
- [65]. Balavijayalakshmi, J., & Ramalakshmi, V. (2017). Carica papaya peel mediated synthesis of silver nanoparticles and its antibacterial activity against human pathogens. *Journal of applied research and technology*, 15(5), 413-422.
- [66]. Kale, R., Barwar, S., Kane, P., & More, S. (2018). Green synthesis of silver nanoparticles using papaya seed and its characterization. *Int. J. Res. Appl. Sci. Eng. Technol*, 6, 168-174.

- [67]. Alam, M. A., Munni, S. A., Mostafa, S., Bishwas, R. K., & Jahan, S. A. (2023). An Investigation on Synthesis of Silver Nanoparticles. *Asian Journal of Research in Biochemistry*, 12(3), 1-10.
- [68]. Alam, M. A., Mostafa, S., Bishwas, R. K., Sarkar, D., Tabassum, M., & Jahan, S. A. Low-Temperature Synthesis and Characterization of High Crystalline 3c-Ag Nanoparticle. Available at SSRN 4446717.
- [69]. Islam, M. R., Ahmed, S., Sadia, S. I., Sarkar, A. K., & Alam, M. A. (2023). Comprehensive Review of Phytochemical Content and Applications from *Cestrum nocturnum*: A Comparative Analysis of Physicochemical Aspects. *Asian Journal of Research in Biochemistry*, 13(4), 43-58.
- [70]. Vinodhini, S., Vithiya, B. S. M., & Prasad, T. A. A. (2022). Green synthesis of silver nanoparticles by employing the *Allium fistulosum*, *Tabernaemontana divaricate* and *Basella alba* leaf extracts for antimicrobial applications. *Journal of King Saud University-Science*, 34(4), 101939.
- [71]. Pungle, R., Nile, S. H., Makwana, N., Singh, R., Singh, R. P., & Kharat, A. S. (2022). Green synthesis of silver nanoparticles using the *Tridax Procumbens* plant extract and screening of its antimicrobial and anticancer activities. *Oxidative Medicine and Cellular Longevity*, 2022.
- [72]. Hassanisaadi, M., Bonjar, A. H. S., Rahdar, A., Varma, R. S., Ajalli, N., & Pandey, S. (2022). Eco-friendly biosynthesis of silver nanoparticles using *Aloysia citrodora* leaf extract and evaluations of their bioactivities. *Materials Today Communications*, 33, 104183.
- [73]. Hawar, S. N., Al-Shmgani, H. S., Al-Kubaisi, Z. A., Sulaiman, G. M., Dewir, Y. H., & Rikisahedew, J. J. (2022). Green synthesis of silver nanoparticles from *Alhagi graecorum* leaf extract and evaluation of their cytotoxicity and antifungal activity. *Journal of Nanomaterials*, 2022, 1-8.

- [74]. Khanal, L. N., Sharma, K. R., Paudyal, H., Parajuli, K., Dahal, B., Ganga, G. C., ... & Kalauni, S. K. (2022). Green synthesis of silver nanoparticles from root extracts of *Rubus ellipticus* Sm. and comparison of antioxidant and antibacterial activity. *Journal of Nanomaterials*, 2022, 1-11.
- [75]. Kandiah, M., & Chandrasekaran, K. N. (2021). Green synthesis of silver nanoparticles using *Catharanthus roseus* flower extracts and the determination of their antioxidant, antimicrobial, and photocatalytic activity. *Journal of Nanotechnology*, 2021, 1-18.
- [76]. Teixeira, J. A., Santos Júnior, V. E. D., Melo Júnior, P. C. D., Arnaud, M., Lima, M. G., Flores, M. A. P., ... & Rosenblatt, A. (2018). Effects of a new nano-silver fluoride-containing dentifrice on demineralization of enamel and *Streptococcus mutans* adhesion and acidogenicity. *International journal of dentistry*, 2018.
- [77]. Mirhashemi, A., Bahador, A., Sodagar, A., Pourhajibagher, M., Amiri, A., & Gholamrezayi, E. (2021). Evaluation of antimicrobial properties of nano-silver particles used in orthodontics fixed retainer composites: an experimental in-vitro study. *Journal of Dental Research, Dental Clinics, Dental Prospects*, 15(2), 87.
- [78]. Babu Nagati, V., Koyyati, R., Donda, M. R., Alwala, J., Kundle, K. R., & Padigya, P. R. M. (2012). Green synthesis and characterization of silver nanoparticles from *Cajanus cajan* leaf extract and its antibacterial activity. *International Journal of Nanomaterials and Biostructures*, 2(3), 39-43.
- [79]. Aziz, A., Khalid, M., Akhtar, M. S., Nadeem, M., Gilani, Z. A., Asghar, H. U. H. K., ... & Saleem, M. (2018). structural, morphological and optical investigations of silver nanoparticles synthesized by sol-gel auto-combustion method. *Digest Journal of Nanomaterials & Biostructures (DJNB)*, 13(3).

[80]. Das, A. J., Kumar, R., Goutam, S. P., & Sagar, S. S. (2016). Sunlight irradiation induced synthesis of silver nanoparticles using glycolipid bio-surfactant and exploring the antibacterial activity. *J. Bioeng. Biomed. Sci*, 6(5).

[81]. Ju Park, E., Won Lee, S., Bang, I. C., & Park, H. W. (2011). Optimal synthesis and characterization of Ag nanofluids by electrical explosion of wires in liquids. *Nanoscale research letters*, 6, 1-10.

UNDER PEER REVIEW