

*Short Research Article*  
**Compositional analysis of the lignocellulosic biomass from agricultural waste  
(Rice Husk)**

---

**ABSTRACT**

Rice husk, a byproduct of rice milling, represents a significant agricultural waste biomass with untapped potential for various industrial applications. This study provides a comprehensive compositional analysis of rice husk to explore its utility as a valuable resource. The chemical composition of rice husk such as hemicellulose, cellulose, lignin, ash and extractives were analyzed. The result reported in mean value i.e 9.884 ±0.56 (%) moisture content, 8.077±0.27 (%) extractives, 17.210 ± 0.69 (%) lignin, 21.073 ± 0.62 (%) hemicellulose and 38.640 ± 0.94 (%) cellulose, 15.0 ±0.87 (%) ash. This study concludes that rice husk is an abundant source of cellulose and holds significant potential for cellulose isolation.

*Keywords:* Rice husk, Biomass, cellulose, potential

**Commented [SH1]:** Please, substitute this keyword.

**1. INTRODUCTION**

Agricultural wastes refer to the by-products and residues generated during the cultivation and processing of agricultural materials. Rice husk, a lignocellulosic biomass is a prevalent agricultural by-product in many rice-producing regions worldwide. For every 100 kg of paddy grain processed into rice, approximately 20 kg of rice husk waste is produced [1]. In recent decades, lignocellulosic biomass has come to be seen as a valuable resource rather than waste. Its abundant availability and potential to be converted into valuable products, such as bio energy, chemicals and fertilizers, highlight its significance. This abundant resource can be utilized for energy production through direct combustion, biochar, and biogas generation. In construction, rice husk ash improves the properties of concrete and its insulating capabilities make it valuable for building materials. Agriculturally, rice husk improves soil quality and serves as effective organic fertilizer [2]. Industrial uses include silica extraction for electronics and filtration media. Additionally, it can be incorporated into animal feed, bioplastics, and eco-friendly composites, promoting sustainability and reducing waste [3,4]. In general, agricultural and industrial wastes contain numerous valuable elements that can be extracted and utilized in the production of various materials. Among these elements, cellulose can be derived from such wastes [5].

**Commented [SH2]:** 'Wastes' should be singular number in this case.

**Commented [SH3]:** Please, correct the grammar.

**Commented [SH4]:** Add reference.

The Rice husk is the material, that has high lignocellulose content. Typically, most of the agricultural lignocellulosic biomass is comprised of about 10–25% lignin, 20–30% hemicellulose, and 40–50% cellulose. Cellulose is a primary structural component of plant cell walls, providing mechanical strength. Hemicellulose, composed of repeating polymers of pentoses and hexoses, complements cellulose in the cell wall structure. Lignin, which consists of three

**Commented [SH5]:** Add references.

aromatic alcohols (coniferyl alcohol, sinapyl alcohol, and p-coumaryl alcohol) synthesized through a biosynthetic process, forms a protective barrier around cellulose and hemicellulose, enhancing their stability and integrity [6]. Characterizing raw materials, whether for their composition, structure, or other significant properties, is a fundamental initial step in most experiments and industrial conversion processes. These properties determine the range of products that can be derived from a specific lignocellulosic feedstock in a cost-efficient manner [7]. The composition of lignocellulose generally depends on its source and varies due to the genetic differences among various sources [8]. Various contemporary methods for compositional analysis of lignocellulosic biomass are available. Out of which, NREL methods are commonly used for characterization of lignocellulosic biomass for engineering applications. In present work, the chemical composition analysis of rice husk is done to determine its potential applications.

**Commented [SH6]:** Mention other methods with references.

## 2. MATERIAL AND METHODS

**Commented [SH7]:** It should be plural number.

The Rice husk was collected from Madan milling, Kichha, Uttarakhand. The reagents and Chemicals were purchased from Sigma-Aldrich.

**Commented [SH8]:** Small letter

**Commented [SH9]:** Mention name of purchased chemicals.

### 2.1 INITIAL CHEMICAL COMPOSITION OF RICE HUSK

The chemical composition of lignocellulosic biomass can be divided into five components: cellulose, hemicellulose, lignin, ash, and extractives [9]. Consequently, the chemical composition of rice husk was initially assessed by determining its moisture content

**Commented [SH10]:** Clarify the method that you have done with reference.

#### 2.1.1 DETERMINATION OF INITIAL MOISTURE CONTENT

The moisture content of rice husk was determined using the Official Method of Analysis, 1999 [10]. A 3-gram sample of rice husk was placed in a pre-weighed Petri dish and spread evenly with a spatula. The Petri dish containing the sample was then placed in a hot air oven at 105°C for 3 hours. After this period, the sample was removed and transferred to a desiccator to cool before being weighed. The sample was subsequently returned to the oven, and readings were taken at hourly intervals until a constant weight was achieved. The moisture content (w.b %) was calculated using the following equation:

$$M.C (\%) = \frac{W_1 - W_2}{M} \times 100 \quad \dots\dots (1)$$

Where,

$W_1$  = Weight of sample with petri dish before drying, g

$W_2$  = Weight of sample with petri dish after drying, g

$M$  = initial weight of the sample taken, g

#### 2.1.2 DETERMINATION OF ASH CONTENT

The ash content of rice straw was determined according to the standard laboratory analytical procedure of NREL [11]. A 3-gram sample of rice husk was placed in a dried and pre-weighed crucible. The crucible containing the sample was then heated over a flame until no more smoke was produced. After allowing the sample to cool, the crucible was placed in a muffle furnace at 575°C for 24 hours until a constant weight was achieved. Once cooled in a desiccator, the ash content was determined by the difference in weight, as calculated using Equation (2):

**Commented [SH11]:** It should be small letter.

$$AC (\%) = \frac{W_2 - W_1}{ODW} \times 100 \quad \dots\dots (2)$$

where,

$A$  = Ash content (%) in rice husk

$W_1$  = Weight of empty crucible, g

$W$  = Weight of crucible with sample after process completion, g

ODW = Oven dry weight of the initial sample taken, g

### 2.1.3 DETERMINATION OF EXTRACTIVES

The determination of extractives was performed using ethanol extraction according to the National Renewable Energy Laboratory (NREL) procedure [12] as well as the method described by [13]. A 3-gram sample of rice husk was placed in a thimble and heated in a heating mantle. The extraction process continued for 24 hours. Upon completion, the sample underwent vacuum filtration followed by washing with 100 ml of ethanol. The sample was then air-dried and weighed. The extractives were calculated using the following equation:

$$E (\%) = \frac{W_2 - W_1}{ODW} \quad \dots\dots 3$$

Where,

$E$  = Extractives (%)

$W_1$  = Weight of initial sample, g

$W_2$  = Weight of sample after extraction, g

ODW = Oven dry weight of initial sample taken, g

### 2.1.4 DETERMINATION OF LIGNIN CONTENT

The total lignin content of rice husk was evaluated using a Laboratory Analytical Procedure (LAP) from the National Renewable Energy Laboratory (NREL) [14] as reported by Wang et al. 2018 [15]. Total lignin is the sum of acid-soluble and acid-insoluble lignin. For the determination of acid-soluble lignin, 0.3 grams of rice husk was placed in a 250 ml Erlenmeyer flask, and 3 ml of 72% sulfuric acid was added and mixed well with a Teflon rod. The sample was soaked in a water bath at 30°C for 2 hours. Subsequently, the sulfuric acid concentration was diluted to 4% by adding 84 ml of deionized water, and the mixture was autoclaved for 1 hour at 121°C. After the autoclaving cycle was complete, the sample was removed, cooled to room temperature, and vacuum filtered. The filtrate was then diluted with deionized water to achieve an absorbance range of 0.7-1.0, measured using a UV-VIS spectrophotometer at 205 nm. The acid-soluble lignin was calculated using the following equation.

$$ASL (\%) = \frac{UV_{Abs} \times V_f \times D}{\epsilon \times ODW \times Pathlength} \quad \dots\dots (4)$$

Where,

ASL = Acid insoluble lignin (% w of dry mass)

$UV_{Abs}$  = Absorbance for the sample at appropriate wavelength (205 nm)

$V_f$  = Volume of filtrate (86.6 ml)

$D$  = dilution factor (9)

$\epsilon$  = Absorptivity of biomass at specific wavelength (110 L/g-cm)

ODW = Oven dry weight of sample, g

Path length = Path length of UV-Vis cell in cm (1 cm)

The residue remaining after the hydrolysis process for acid-soluble lignin was washed with hot water until the filtrate became pH neutral. The residue was then placed in a dried and pre-weighed crucible, which was subsequently kept in a muffle furnace at 575°C for 4 hours. After 4 hours, the crucible was removed, placed in a desiccator to cool, and then weighed. The acid-insoluble lignin was then calculated using the following method.

Commented [SH12]: Where does 'A' use in equation?

Commented [SH13]: Where does W is mentioned?

Commented [SH14]: Correct the grammer.

Commented [SH15]: Specify the unit

Commented [SH16]: It should be 'UV-Vis'

Commented [SH17]: Need a space

$$AIL (\%) = \frac{W_{dry} - W_a}{ODW} \times 100 \quad \dots(5)$$

Where,

AIL= Acid insoluble lignin (%)

$W_{dry}$  = Weight of dry material in crucible remained after acid soluble determination, g

$W_a$  = Weight of ash after sample taken out from muffle furnace, g

ODW= Oven dry weight of initial sample taken, g

The total lignin content of rice husk was calculated by adding acid soluble and acid insoluble lignin;

Total lignin (%) = ASL(%) + AIL (%)

.....(6)

### 2.1.5 DETERMINATION OF CELLULOSE AND HEMICELLULOSE

The cellulose and hemicellulose content of rice husk was evaluated using the Technical Association of Pulp and Paper Industry (TAPPI) method as described by De Oliveira et al. [16] and Zheng et al. [17]. A 2-gram sample of rice husk powder was weighed and transferred to a 250 mL conical flask. Then, 25 mL of a nitric acid/ethanol solution (1:4 by volume) was added to the flask. The mixture was refluxed for 1 hour, and this process was repeated several times until the sample turned white. The powder was then repeatedly washed with distilled water and filtered until the pH became neutral. The resulting residue was dried at 105°C. The  $\alpha$ -cellulose content (C, %) was then calculated using the following method.

$$C = \frac{RH}{RH_1(1-W)} \times 100 \quad \dots(7)$$

Where,

RH= Weight of remained residue, g

$RH_1$ = Weight of rice husk sample, g

W= Moisture content of rice husk in %

The hemicellulose of rice husk was calculated by the following equation;

$$HC (\%) = (100 - A - E - TL - C) \times 100] \quad \dots(8)$$

Where,

HC = Hemicellulose (%)

A= Ash content of rice husk (%)

E = Extractives (%)

TL = Total lignin (%)

C = Cellulose (%)

## 3. RESULTS AND DISCUSSION

The chemical composition of the lignocellulosic fibers are the most important variables that determine the overall properties of the fibers [18]. Initial composition of rice husk was determined by the NREL standard methods. The initial composition (initial moisture content, ash, extractives, lignin content, hemicellulose and cellulose) of rice husk were

calculated in triplicate and mean value is reported in Table 1. The obtained results were in accordance with previous studies. The differences in composition is due to climate and geographical conditions, weather conditions and difference in varieties and type of soil etc.

Commented [SH18]: Correct the grammar.

### 3.1 Moisture Content

Moisture content indicates the amount of water present in biomass, expressed as a percentage of the material's weight. It significantly affects not only the harvesting and preparation stages but also the transport, storage, processing, and quality of the final products [19]. The initial moisture content of rice husk was 9.884 %.

### 3.2 Ash

Biomass ash primarily consists of inorganic compounds rich in alkali and alkaline earth metals. It is a significant cause of abrasive wear in biomass processing equipment, particularly in size-reduction machinery where biomass and tools interact at high velocities. The ash content in natural fibers can also affect the properties of composites [20]. The ash content of rice husk was found to be 15 %. These results are in lined with previous studies as mentioned in Table 1.

**Table 1: Initial composition of rice husk and comparison with previous studies.**

S. No.	Constituents	Average (% weight of dry matter)			
		Current study	Previous Studies		
			Johar et al. [21]	Nikzad et al. [22]	Bisht et al. [23]
1.	Moisture Content	9.884 ±0.56	N/A	N/A	N/A
2.	Extractives	8.077±0.27	N/A	11.9	N/A
3.	Total Lignin	17.210 ± 0.69	23	19.22	20
4.	Hemicellulose	21.073 ± 0.62	33	15.24	25
5.	Cellulose	38.640 ± 0.94	35	37.55	35
6.	Ash	15.0 ±0.87	25	16	17

### 3.3 Extractives

The extractives in lignocellulosic biomass primarily include waxes, fats, resins, tannins, sugars, starches, and pigments. Extractives can interfere with component analysis, particularly lignin. Therefore, lignocelluloses with high extractive contents should be extracted first to avoid obtaining unacceptable results. In present study, extractives in rice husk were 8.077 %. Nikzad et al. [22] also reported 11.9 % extractives in rice husk.

### 3.4 Total Lignin

Lignin contributes to hydrophobicity and structural rigidity by binding hemicelluloses to cellulose in the cell wall. Also, lignin negatively impacts the conversion of cellulose. This effect is influenced by several factors, including the total lignin content, lignin composition, and structure, particularly the hydroxyl group content [24]. The total lignin content in

rice husk was 17.21 %. According to literature, lignocellulosic biomass comprises approximately 35%–55% cellulose, 25%–40% hemicellulose, and 15%–25% lignin.

### 3.5 Hemicellulose

Hemicelluloses are considered the second most abundant renewable component of lignocellulosic biomass, after cellulose. The content and structure of hemicellulose, including the length and type of the main chain as well as the distribution and type of side chains, vary depending on the species of lignocellulose. The hemicellulose content in rice husk was 21.973 %. The results obtained in this study are in accordance with previous studies.

**Commented [SH19]:** Add reference.

**Commented [SH20]:** You should discuss valuable explanation of this results with competitiveness in shortly.

### 3.6 Cellulose

Cellulose is one of the leading constituents of lignocellulosic biomass. The results obtained in this study, showed that cellulose content in rice husk is 38 %. The results are in lined with previous studies [21]. The composition of the lignocellulose components varies considerably between different plants. Jung et al. [25] compared the cellulose, hemicellulose, and lignin content in the stems and leaves of Miscanthus, switchgrass, reed, and sorghum and reported that the woodier reed (*Phragmites australis*) contains significantly more lignin than Miscanthus, switchgrass, or sorghum. In general, stalks typically contain higher concentrations of lignin, cellulose, and hemicellulose compared to leaves [26].

## 4. CONCLUSION

Lignocellulosic biomass or agricultural waste can be converted into various value-added products such as bioenergy, biofuels, biochemical and building material. Moreover, these can be used as reinforcement for packaging applications. Understanding the physicochemical properties of biomass is crucial before designing any thermochemical or biochemical processing method, as these properties strongly impact the conversion efficiency of the process. In the present study, the compositional analysis of rice husk was conducted. Rice husk is an excellent source of cellulose. The extraction of cellulose from rice husk will not only provide a sustainable alternative to traditional cellulose sources but will also contribute to waste reduction and environmental conservation.

**Commented [SH21]:** This part is your recommendations based on your findings. So, at first clear your findings result, then add those lines as your recommendations.

**Commented [SH22]:** Please add your achieved value

## REFERENCES

- [1] Yuan s, hou y, liu s, ma y. A comparative study on rice husk, as agricultural waste, in the production of silica nanoparticles via different methods. *Materials*. 2024;17(6):1271.
- [2] Ebaid RA, El-Refaei IS. Utilization of rice husk as an organic fertilizer to improve productivity and water use efficiency in rice fields. *African Crop Science Conference Proceedings 2007*; 8:1923-1928.
- [3] Tayeh BA, Alyousef R, Alabduljabbar H, Alaskar A. Recycling of rice husk waste for a sustainable concrete: a critical review. *Journal of Cleaner Production*. 2021, 312:127734.

- [4] Riseh RS, Vazvani MG, Hassanisaadi M, Thakur VK. Agricultural wastes: A practical and potential source for the isolation and preparation of cellulose and application in agriculture and different industries. *Industrial Crops and Products*. 2024; 208:117904.
- [5] Malik S, Omre PK, Shahi NC, Prakash O, Kumar A. Ultrasound-assisted surface modification of cellulose isolated from rice husk to impart hydrophobicity. *The Pharma Innovation Journal* 2023. 12(1): 2601-2605
- [6] Anwar Z, Gulfranz M, Irshad M. Agro-industrial lignocellulosic biomass a key to unlock the future bio-energy: a brief review. *Journal of radiation research and applied sciences*. 2014; 7(2):163-73
- [7] Krasznai, DJ, Champagne Hartley R, Roy HM, Champagne P, Cunningham MF. Compositional analysis of lignocellulosic biomass: conventional methodologies and future outlook. *Critical reviews in biotechnology*. 2018; 38(2),199-217.
- [8] Chen H. Chemical composition and structure of natural lignocellulose, In: Chen H, editor. *Biotechnology of Lignocellulose: Theory and Practice*, Springer Science, Netherlands 2014, pp. 25–71
- [9] Williams CL, Emerson RM, Tumuluru JS. Biomass Compositional Analysis for Conversion to Renewable Fuels and Chemicals. In: Tumuluru JS, editor. *Biomass Volume Estimation and Valorization for Energy*; Intech Open Limited: London, UK, 2017
- [10] Association of Official Analytical Chemists 1999. *Official methods of analysis*, 16th edn. Association of Official Analytical Chemists, Washington
- [11] Sluiter A, Hames B, Ruiz R, Scarlata C, Sluiter J, Templeton D. Laboratory analytical procedure: Determination of ash in biomass. National Renewable Energy Laboratory. 2005. <https://www.nrel.gov/docs/gen/fy08/42622.pdf>
- [12] Sluiter A, Ruiz R, Scarlata C, Sluiter J, Templeton DJ. Determination of extractives in biomass. *Laboratory analytical procedure (LAP)*. 2005;1617(4):1-6.
- [13] Pasangulapati V, Ramachandriya KD, Kumar A, Wilkins MR, Jones CL, Huhnke RL. Effects of cellulose, hemicellulose and lignin on thermochemical conversion characteristics of the selected biomass. *Bioresource technology*. 2012;114:663-9.
- [14] Sluiter A, Hames B, Ruiz R, Scarlata C, Sluiter J, Templeton D, Crocker DL. Determination of structural carbohydrates and lignin in biomass: Laboratory Analytical Procedure (LAP)(NREL/TP-510-42618). *Natl Renew Energy Lab*. 2012;17.
- [15] Wang Z, Saleem J, Barford JP, McKay G. Preparation and characterization of modified rice husks by biological delignification and acetylation for oil spill cleanup. *Environmental Technology*. 2018; 41(15): 1980-1991.
- [16] de Oliveira JP, Bruni GP, Lima KO, El Halal SL, da Rosa GS, Dias AR, da Rosa Zavareze E. Cellulose fibers extracted from rice and oat husks and their application in hydrogel. *Food chemistry*. 2017; 221:153-60.
- [17] Zheng D, Zhang Y, Yue J. Isolation and Characterization of Nanocellulose with a Novel Shape from Walnut (*Juglans Regia* L.) Shell Agricultural Waste. *Polymers*, 2019; 11 (7): 1130.
- [18] Petroudy SD. Physical and mechanical properties of natural fibers. In : Mizi Fan and Fend Fu, Editors. *Advanced high strength natural fibre composites in construction* . Woodhead Publishing, 2017, pp. 59-83.
- [19] Cai J, He Y, Yu X, Banks SW, Yang Y, Zhang X, et al. Review of physicochemical properties and analytical characterization of lignocellulosic biomass. *Renewable and sustainable energy reviews*. 2017;1(76):309-22.

Commented [SH23]: Remove this link.

- [20] Zhao X, Oyedeji O, Webb E, Wasti S, Bhagia S, Hinton H, Li K, Kim K, Wang Y, Zhu H, Vaidya U. Impact of biomass ash content on biocomposite properties. *Composites Part C: Open Access*. 2022; 9:100319.
- [21] Johar N, Ahmad I, Dufresne A. Extraction, preparation and characterization of cellulose fibres and nanocrystals from rice husk. *Industrial Crops and Products*, 2012; 37(1): 93-99
- [22] Nikzad M, Movagharnjad K, Talebnia F, Aghaiy Z, Mighani M. Modeling of alkali pretreatment of rice husk using response surface methodology and artificial neural network. *Chemical Engineering Communications*, 2015; 202(6): 728-738.
- [23] Bisht, N, Gope PC, Rani N. Rice husk as a fibre in composites: A review. *Journal of the Mechanical Behavior of Materials*, 2020; 29(1): 147-162
- [24] Zoghalmi A, Paës, G. Lignocellulosic biomass: understanding recalcitrance and predicting hydrolysis. *Frontiers in chemistry* 2019; 7:874.
- [25] Jung SJ, Kim S-H, Chung I-M. Comparison of lignin, cellulose, and hemicellulose contents for biofuels utilization among 4 types of lignocellulosic crops. *Biomass and Bioenergy*, 2015; 83:322–327
- [26] Langsdorf A, Volkmar M, Holtmann D, Ulber R. Material utilization of green waste: a review on potential valorization methods. *Bioresources and Bioprocessing*, 2021; 8 (19):1-26