

Intelligent films based on Lobeira fruit starch for fresh chicken meat quality monitoring

Abstract

The use of intelligent films as colorimetric indicator devices in food packaging provides information about changes in the pH, time, temperature and microbiological properties of the product. These devices enable consumers to analyze food with the naked eye, ensuring food safety and quality. Thus, this study explores the use of lobeira (*Solanum lycocarpum* L.) native starch starch and vanillin in the development of colorimetric indicator films for monitoring chicken meat deterioration, aiming at enhancing food packaging safety and longevity. Films were prepared through a casting method using starch, poly(vinyl alcohol) (PVA), and varying concentrations of vanillin. These indicator films were characterized by FTIR spectroscopy and thermal analysis. In this study, degradation monitoring of chicken meat at 12 and 25°C was also performed. Subsequently, color changes in the indicator films were observed over time, indicating meat spoilage. Results revealed that films containing 0.05% and 0.1% vanillin concentrations exhibited more pronounced color changes, indicating higher sensitivity to meat deterioration. Overall, the findings suggest that the developed films, incorporating vanillin as a colorimetric indicator, hold promise for real-time monitoring of food quality and safety within packaging systems, thus contributing to improved consumer protection and product shelf life.

Keywords: *Solanum lycocarpum*, Lobeira fruit, native starch, intelligent films, food quality indicators.

1. Introduction

Innovations in food packaging are rapidly developing in response to consumer demands. The packaging is characterized as an intelligent system in which information related to the quality and safety of the product can be obtained. Such systems involve the incorporation of sensors, dyes or indicator devices, which respond to changes in the initial conditions of the product by electrical, colorimetric or any other signals [1–3]. Concerns about human health in relation to deaths caused by food contamination encourage the use of indicator devices in packaging so that food can be analyzed with the naked eye by the consumer, providing greater security and an even longer life for the product [4–6]. Among the chemical compounds used as indicators in intelligent food packaging, colorimetric indicators are the compounds with the greatest potential for use in this kind of packaging. These compounds change their coloration in the presence of changes in some physical-chemical properties, such as pH [7–9], microbial growth [10–12] or temperature of the product [13–17], providing a visual indication that can be analyzed by the consumer.

Many natural extracts and compounds, as well as synthetic compounds, have been successfully used as potential colorimetric indicators [9,18–22]. Vanillin (VN), which is the main component of natural vanilla, is a natural and widely synthesized compound that has been increasingly used as a colorimetric sensor dye [23,24]. Moreover, VN is an active chemosensor against gram-positive and gram-negative bacteria, such as *Bacillus subtilis*,

Salmonella enteritidis and *Escherichia coli*, and in the presence of these bacteria, VN coloration changes [20]. In addition, this material exhibits antioxidant and antimicrobial properties and therefore has great potential for use not only as a colorimetric indicator but also as a food preservative [25]. The compounds used as chemosensors for food quality indicators need to be applied in a support, mostly polymeric materials, to function properly. Thus, in recent years, biopolymers have been widely applied in the form of films to support the development of intelligent food packaging [1]. Biopolymers have the advantages of being renewable and biodegradable. Examples of biopolymers used to develop intelligent and smart packaging films are proteins [26–28] and carbohydrates [29–32].

Among carbohydrates, starch is one of the most applied in the development of intelligent, smart, and active films for food monitoring and preservation [33–37]. Therefore, native starch has great potential for application as a support to develop novel active and smart films for food packaging [54–57]. As the Brazilian flora is one of the richest floras in the world [38], it is rich in plants that can be a source of native starches with uncommon properties [39–41]. Among these species, *Solanum lycocarpum* St. Hill (Solanaceae), commonly known as “lobeira”, is a common and abundant plant in the Brazilian Cerrado and is rich in starch [42]. This starch is well characterized in the literature because of its high content of amylose, high crystallinity, good mechanical properties, and good film-forming and morphological properties [43–46]. Thus, this starch is a promising material for biotechnological applications, including food packaging.

Hence, in this study, the viability of using lobeira starch and vanillin in the preparation of colorimetric indicator films was investigated to analyze their joint effects as an intelligent food packaging sensor on the deterioration of chicken meat. Blend films made from starch and poly(vinyl alcohol) (PVA) with vanillin as a colorimetric indicator were developed. The use of these materials provides biodegradable colorimetric devices based on biopolymers, in addition to having low cost and no human toxicity, which encourages the application of these sensors in food packaging.

2. Materials and Methods

2.1 Film preparation

Films were obtained by the casting method, which consists of the dehydration of a combined starch/PVA hydrogel solution deposited on polystyrene plates with an internal diameter of 8.5 cm.

For the preparation of the films, PVA hydrogels were prepared by dissolving 1 g of polymer powder (Sigma–Aldrich Art. No. 363146, 99% hydrolysis degree) in 100 mL of distilled water under magnetic stirring at $70\pm 2^\circ\text{C}$ until complete dissolution. Lobeira starch was extracted as previously reported [46]. Then, 2 g of Lobeira starch was dissolved in 100 mL of distilled water under magnetic stirring at 60°C for 30 minutes until a hydrogel solution was formed. Afterwards, the starch and PVA hydrogels were combined at a ratio of 2:1 to obtain the final film-forming hydrogel solution. Fifty milliliters of the film-forming hydrogel solution was poured into 8.5 cm diameter Petri dishes to obtain a control film without vanillin.

Similarly, different concentrations of vanillin (Table 1) were added to the film-forming solution to obtain VN1, VN2, and VN3 films. The standard AL/PVA film was composed of only 50 mL of the matrix without the addition of other active compounds. Subsequently, all the films were dried in an oven at 40°C for 72 h.

Table 1. Different concentrations of AL/PVA were added to 50 mL of the polymeric matrix

Films	VN concentration (%)
-------	----------------------

VN1	0,02%
VN2	0,05%
VN3	0,1%

2.2 Film characterization

2.2.1 Infrared absorption spectroscopy (FTIR)

The FTIR spectra were obtained with a Perkin Elmer Fourier transform spectrophotometer, model Perkin Elmer **Spectrometer** 100, with a resolution of 4 cm^{-1} , in the region between $4000\text{-}600\text{ cm}^{-1}$, using an accessory for the total reflectance technique (ATR) with a germanium crystal (Ge).

2.2.2 Thermal analysis

Thermogravimetric analysis (TG) and differential thermal analysis (DTG) were used to determine the degradation behavior of the films. Each sample had a mass of approximately 10 mg, and TGA/DSC 1 STARe System equipment from Mettler Toledo was used. The heating rate employed was $20^\circ\text{C}/\text{min}$ with a temperature variation of $30\text{-}800^\circ\text{C}$ under an air atmosphere with a flow rate of $60\text{ mL}/\text{min}$.

2.2.3 Food monitoring test

The deterioration of the food was monitored with chicken meat, for which a plate and lid system was prepared. Five grams of chicken breast sample was placed on a polystyrene Petri dish, and under the lid, the film was fixed without contact with the meat. The films used were the VN1, VN2, and VN3 indicators, and the control film was $2\times 2\text{ cm}$ in size.

Similarly, this system was also monitored without the use of meat. The samples were placed in a DBO oven at 25°C and analyzed for five consecutive days for the first test. In the second test, the samples were subjected to 12°C for fifteen days and analyzed after 0, 1, 5, 7, 10, 12, and 15 days of storage. This test was performed in triplicate, and the changes in coloration of the indicator films were recorded by a digital camera.

3. Results and discussion

3.1 Appearance of the films

The control film and the film with VN added are illustrated in **Fig. 1**. Both the surface and the surface without bubbles were homogeneous (Fig. 1 (a) and (b)). Both materials have good malleability and transparency; the surface in contact with the polystyrene plate during drying presented a shiny appearance, and the surface exposed to air during drying had a matte appearance. Regarding the handling characteristics, after drying, all the films could be removed from the support plates without causing cracks or tears and could be easily handled. The different concentrations of vanillin did not affect the visual appearance of the films.




Figure 1. Appearance of the control film (a) and VN film (b)


3.2 Infrared absorption spectroscopy (FTIR)

The spectra in the infrared region represent a fingerprint of a given sample forming absorption peaks that correspond to the frequencies of vibrations between the bonds of the atoms that compose the material. FTIR analyses were performed on the standard AL/PVA, MB4 and VN films.

Vanillin can be identified in a spectrum due to its characteristic molecular structure. **Fig. 2** shows the spectra of the standard film and the VN film containing vanillin. There are some differences between the spectra; a band is observed at 1665 cm^{-1} that corresponds to the C=O stretching vibration of the vanillin aldehyde group [47], which is not observed in the standard film. The stretching vibration peaks at 1591 and 1513 cm^{-1} in the spectrum of the VN3 film can be attributed to the aromatic ring. The peak at 3270 cm^{-1} corresponds to the OH stretching vibration present in both spectra, and another band at 2939 cm^{-1} is attributed to the C-H stretching vibration characteristic of the presence of [14].

The peaks at 1293 and 928 cm^{-1} can be attributed to the bending vibration of the phenolic hydroxyl group (CHO). These peaks, except for the peak at 928 cm^{-1} , can be observed in other vanillin-containing composite films [48]. A very small shift in the absorption peak is observed, possibly due to the chemical interaction between vanillin and the polymer matrix.

Figure 2. Fourier transform infrared spectrum of the Standard AL/PVA film and the VN film of 0.1% concentration of VN in the polymer matrix.



3.3 Thermal analysis


The thermal properties of the materials were investigated using thermogravimetric (TG) methods and differential thermal analysis (DTG) in the temperature range of 30-800°C under an air atmosphere.

Fig. 3 (a) and (b) present the TG and DTG curves for the pure VN materials and the control film. Three thermal decomposition steps are identified in the spectrum of the VN3 film. The first degradation step of the VN film, corresponding to the initial mass loss, occurs below 100°C, with a mass loss rate at a temperature of 109°C in the DTG curve. This step is attributed to the loss of weakly bound water, accompanied by the formation of volatile disintegrated products, such as displaced plasticizers in the mixture and vanillin. Because pure vanillin is a volatile material, it undergoes mass loss in only one step, as shown in **Fig. 3**. At 130°C in the TG curve, pure VN showed a marked loss of mass corresponding to the peak in the DTG curve at 225°C. The rest of the organic portion contained in the pure VN was lost at higher temperatures, leaving no residue on the sample.

The second degradation step in the VN film starts at approximately 250°C, with the maximum mass loss rate corresponding to the peak at 318°C of the DTG curve, which indicates the degradation of starch and PVA by dehydration of the hydroxyl group. Compared to the standard film, which has a maximum mass loss rate at 330°C, the maximum mass loss rate of the VN3 film is less attenuated due to the interaction of vanillin with the polymer matrix. The third mass loss of the VN film occurs at approximately 450°C in the TG curve, with the mass loss rate corresponding to the peak of the DTG curve at a temperature of

514°C. It is assumed that this third stage of film degradation is attributed to the cleavage of the polymeric skeleton or the carbonization of the material [49,50].

Fig. 3: (a) TG curves and (b) DTG curves for the pure VN materials, control AL/PVA film and VN3 film.



3.4 Food monitoring test

The VN1, VN2 and VN3 films were subjected to monitoring of chicken meat as internal indicator devices, which are usually placed inside the packaging and interact with the compounds present in the food. The indicators can be placed in the top space of the package or attached to the lid. For this monitoring test, a plate and lid system were prepared. Five grams of chicken breast sample was placed on a polystyrene Petri dish, and under the lid, a 2x2 cm film was fixed without contact with the meat. Similarly, this system was also monitored without using the meat.

The films used for the test were the control film and the VN1, VN2 and VN3 indicators, and the samples were named 0, 1, 2 and 3, respectively. The samples were placed in a DBO oven at the desired temperature. The test application at room temperature (25°C) was monitored for five consecutive days. **Fig. 4 (I)** shows that there was a color change in the films containing vanillin from day 3 to day 4 of the experiment. Samples 2 and 3, which contained 0.05% and 0.1% VN, respectively, showed more significant color changes on day 4 of the experiment.

It is assumed that the greater the concentration of vanillin in the polymeric matrix of the film is, the more intense the color change due to the degradation of chicken meat. The color changes in the film indicate the probable presence of bacteria such as *Salmonella enteritidis* and *Escherichia coli* and pathogens in chicken meat due to the accumulation of amines and ammonia, which increase the pH of the meat [51,52].

The application test was also performed at 12°C under the same conditions as those used for the previous test, and the samples were monitored during the 15-day period. **Fig. 4 (II)** shows the test images on days 7, 10 and 15. A clear color change is observed in the VN1, VN2 and VN3 films on day 10 of the test. This color change started on day 7 of the experiment and became more intense until the last day of the test (day 15), assuming that, even at low temperature, there was proliferation and exponential growth of bacteria. These spoilage bacteria are called psychrotrophic bacteria (psychro means cold, while trophic means able to grow) because they are able to multiply in cold conditions. Fresh poultry products kept long enough at refrigerator temperatures also spoil because of the growth of psychotropic bacteria [52,53].


The films containing vanillin showed, therefore, a change in coloration against microbiological changes in chicken meat. These indicator films are independent of the pH change, but it is important to note that a fresh chicken is considered to be of very good quality at a pH of 5.8 to 6.0; when the pH is above 6.7, the meat begins to spoil and should not be consumed. In the monitoring test of chicken meat at a temperature of 25°C, the chicken meat had a pH of 7 on the third day of monitoring. In the test at 12°C, the meat pH was 7 after 8 days of monitoring. These results corroborate that there was a deterioration of chicken meat and that it should not be consumed if it has a pH of 7.

UNDER PEER REVIEW

Figure 4. (I) Images from days 1, 3 and 5 of the test with chicken meat at 25°C and (II) Images from days 7, 10 and 15 of the test with chicken meat at 12°C.

(I) Analysis under 25°C temperature

(II) Analysis under 12°C temperature



4. Conclusion

The food monitoring test made it possible to observe and analyze the changes in coloration of the indicator films VN1, VN2 and VN3 in the face of the degradation of chicken meat. The indicators VN2 and VN3, with concentrations of 0.05 and 0.1% vanillin, respectively, proved to be more suitable for monitoring the deterioration of meat. The system in which the indicator was placed in the internal space attached to the lid proved to be effective for monitoring meat, suggesting that films containing vanillin are good colorimetric indicators in the presence of bacteria that cause food degradation.

Data availability

Research data are available on request.

Disclaimer (Artificial intelligence)

Author(s) hereby declare that NO generative AI technologies such as Large Language Models (ChatGPT, COPILOT, etc) and text-to-image generators have been used during writing or editing of manuscripts.

References

1. Amin U, Khan MKI, Maan AA, et al. Biodegradable active, intelligent, and smart packaging materials for food applications. *Food Packag Shelf Life*. 2022;33. doi:10.1016/j.fpsl.2022.100903
2. Janjarasskul T, Suppakul P. Active and intelligent packaging: The indication of quality and safety. *Crit Rev Food Sci Nutr*. 2018;58(5). doi:10.1080/10408398.2016.1225278
3. Lee SY, Lee SJ, Choi DS, Hur SJ. Current topics in active and intelligent food packaging for preservation of fresh foods. *J Sci Food Agric*. 2015;95(14):2799-2810. doi:10.1002/jsfa.7218
4. Dirpan A, Hidayat SH. Quality and Shelf-Life Evaluation of Fresh Beef Stored in Smart Packaging. *Foods*. 2023;12(2). doi:10.3390/foods12020396
5. Mohammadian E, Alizadeh-Sani M, Mahdi Jafari S. Smart monitoring of gas / temperature changes within food packaging based on natural colorants. *Compr Rev Food Sci Food Saf*. 2020;(February):1-47. doi:10.1111/1541-4337.12635
6. Bento L, Silva-Pereira M, Chaves K, Stefani R, Processing MOJF. Development and Evaluation of a Smart Packaging for the Monitoring of Ricotta Cheese Spoilage. *MOJ Food Processing and Technology*. 2015;1(1):3-5. doi:10.15406/mojfpt.2015.01.00004
7. Kuswandi B, Nurfawaidi A. On-package dual sensors label based on pH indicators for real-time monitoring of beef freshness. *Food Control*. 2017;82:91-100. doi:10.1016/j.foodcont.2017.06.028
8. Choi I, Lee JY, Lacroix M, Han J. Intelligent pH indicator film composed of agar/potato starch and anthocyanin extracts from purple sweet potato. *Food Chem*. 2017;218. doi:10.1016/j.foodchem.2016.09.050
9. Kuswandi B, Murdyaningsih EA. Simple on package indicator label for monitoring of grape ripening process using colorimetric pH sensor. *Journal of Food Measurement and Characterization*. 2017;0(0):1-15. doi:10.1007/s11694-017-9603-5
10. Kim MJ, Jung SW, Park HR, Lee SJ. Selection of an optimum pH-indicator for developing lactic acid bacteria-based time-temperature integrators (TTI). *J Food Eng*. 2012;113(3):471-478. doi:10.1016/j.jfoodeng.2012.06.018
11. Demirkol DO, Timur S. Chitosan matrices modified with carbon nanotubes for use in mediated microbial biosensing. *Microchimica Acta*. 2011;173(3-4):537-542. doi:10.1007/s00604-011-0596-1
12. Kim E, Choi DY, Kim HC, Kim K, Lee SJ. Calibrations between the variables of microbial TTI response and ground pork qualities. *Meat Sci*. 2013;95(2):362-367. doi:10.1016/j.meatsci.2013.04.050

13. Shim SD, Jung SW, Lee SJ. Mathematical Evaluation of Prediction Accuracy for Food Quality by Time Temperature Integrator of Intelligent Food Packaging through Virtual Experiments. *Math Probl Eng*. 2013;2013:1-9. doi:10.1155/2013/950317
14. Pereira VA, de Arruda INQ, Stefani R. Active chitosan/PVA films with anthocyanins from Brassica oleraceae (Red Cabbage) as Time-Temperature Indicators for application in intelligent food packaging. *Food Hydrocoll*. 2015;43. doi:10.1016/j.foodhyd.2014.05.014
15. Zhang C, Yin AX, Jiang R, et al. Time--temperature indicator for perishable products based on kinetically programmable Ag overgrowth on Au nanorods. *ACS Nano*. 2013;7(5):4561-4568. doi:10.1021/nn401266u
16. Kreyenschmidt J, Christiansen H, Hübner A, Raab V, Petersen B. A novel photochromic time-temperature indicator to support cold chain management. *Int J Food Sci Technol*. 2010;45(2):208-215. doi:10.1111/j.1365-2621.2009.02123.x
17. Kim K, Kim E, Lee SJ. New enzymatic time-temperature integrator (TTI) that uses laccase. *J Food Eng*. 2012;113(1):118-123. doi:10.1016/j.jfoodeng.2012.05.009
18. Zhang Y, Lim LT. Colorimetric array indicator for NH₃ and CO₂ detection. *Sens Actuators B Chem*. Published online 2018. doi:10.1016/j.snb.2017.09.148
19. Zaragozá P, Ribes S, Fuentes A, et al. Fish Freshness Decay Measurement with a Colorimetric Array. *Procedia Eng*. 2012;47:1362-1365. doi:10.1016/j.proeng.2012.09.409
20. Pires ACDS, Soares NDFF, da Silva LHM, et al. A colorimetric biosensor for the detection of foodborne bacteria. *Sens Actuators B Chem*. 2011;153(1):17-23. doi:10.1016/j.snb.2010.09.069
21. Ziyaina M, Rasco B, Coffey T, Ünlü G, Sablani SS. Colorimetric detection of volatile organic compounds for shelf-life monitoring of milk. *Food Control*. 2019;100(January):220-226. doi:10.1016/j.foodcont.2019.01.018
22. Ma Q, Du L, Wang L. Tara gum/polyvinyl alcohol-based colorimetric NH₃ indicator films incorporating curcumin for intelligent packaging. *Sens Actuators B Chem*. Published online 2017. doi:10.1016/j.snb.2017.01.035
23. Kannan R, Veeraragavan V. Synthesis, characterization of vanillin based colorimetric chemosensor for sensing of fluoride ions. *J Mol Struct*. 2021;1227:129521. doi:10.1016/J.MOLSTRUC.2020.129521
24. Gomes JS, de Sousa RMF, Petrucci JF da S. Paper-based colorimetric sensor array for the rapid and on-site discrimination of green tea samples based on the flavonoid composition. *Anal Methods*. 2022;14(25):2471-2478. doi:10.1039/D2AY00590E
25. Olatunde A, Mohammed A, Ibrahim MA, Tajuddeen N, Shuaibu MN. Vanillin: A food additive with multiple biological activities. *European Journal of Medicinal Chemistry Reports*. 2022;5:100055. doi:https://doi.org/10.1016/j.ejmcr.2022.100055
26. Musso YS, Salgado PR, Mauri AN. Gelatin based films capable of modifying its color against environmental pH changes. *Food Hydrocoll*. Published online 2016. doi:10.1016/j.foodhyd.2016.06.013

27. Musso YS, Salgado PR, Mauri AN. Smart gelatin films prepared using red cabbage (*Brassica oleracea* L.) extracts as solvent. *Food Hydrocoll.* Published online 2019. doi:10.1016/j.foodhyd.2018.11.036
28. de Barros Vinhal GLRR, Silva-Pereira MC, Teixeira JA, Barcia MT, Pertuzatti PB, Stefani R. Gelatine/PVA copolymer film incorporated with quercetin as a prototype to active antioxidant packaging. *J Food Sci Technol.* 2021;58(10):3924-3932. doi:10.1007/s13197-020-04853-0
29. Maciel VB V., Yoshida CMP, Franco TT. Chitosan/pectin polyelectrolyte complex as a pH indicator. *Carbohydr Polym.* Published online 2015. doi:10.1016/j.carbpol.2015.06.047
30. Yoshida CMP, Maciel VB V., Mendonça MED, Franco TT. Chitosan biobased and intelligent films : Monitoring pH variations. *LWT - Food Science and Technology.* 2014;55(1):83-89. doi:10.1016/j.lwt.2013.09.015
31. Moreno O, Cárdenas J, Atarés L, Chiralt A. Influence of starch oxidation on the functionality of starch-gelatin based active films. *Carbohydr Polym.* 2017;178(January):147-158. doi:10.1016/j.carbpol.2017.08.128
32. Zhai X, Shi J, Zou X, et al. Novel colorimetric films based on starch/polyvinyl alcohol incorporated with roselle anthocyanins for fish freshness monitoring. *Food Hydrocoll.* 2017;69:308-317. doi:10.1016/j.foodhyd.2017.02.014
33. Silva-Weiss a., Bifani V, Ihl M, Sobral PJ a., Gómez-Guillén MC. Structural properties of films and rheology of film-forming solutions based on chitosan and chitosan-starch blend enriched with murta leaf extract. *Food Hydrocoll.* 2013;31(2):458-466. doi:10.1016/j.foodhyd.2012.11.028
34. Moazami Goodarzi M, Moradi M, Tajik H, Forough M, Ezati P, Kuswandi B. Development of an easy-to-use colorimetric pH label with starch and carrot anthocyanins for milk shelf life assessment. *Int J Biol Macromol.* 2020;153:240-247. doi:10.1016/j.ijbiomac.2020.03.014
35. Nisa I, Ashwar BA, Shah A, Gani A, Gani A, Masoodi FA. Development of potato starch based active packaging films loaded with antioxidants and its effect on shelf life of beef. *J Food Sci Technol.* 2015;52(November):7245-7253. doi:10.1007/s13197-015-1859-3
36. Silva-Pereira MC, Teixeira JA, Pereira-Júnior VA, Stefani R. Chitosan/corn starch blend films with extract from *Brassica oleracea* (red cabbage) as a visual indicator of fish deterioration. *LWT - Food Science and Technology.* 2015;61(1). doi:10.1016/j.lwt.2014.11.041
37. Souza AC, Goto GEO, Mainardi JA, Coelho ACV, Tadini CC. Cassava starch composite films incorporated with cinnamon essential oil: Antimicrobial activity, microstructure, mechanical and barrier properties. *LWT - Food Science and Technology.* 2013;54(2):346-352. doi:10.1016/j.lwt.2013.06.017
38. Schiassi MCEV, Souza VR de, Lago AMT, Campos LG, Queiroz F. Fruits from the Brazilian Cerrado region: Physico-chemical characterization, bioactive compounds, antioxidant activities, and sensory evaluation. *Food Chem.* 2018;245:305-311. doi:10.1016/j.foodchem.2017.10.104
39. Souza A, Sandrin CZ, Cali6 MFA, Meirelles ST, Pivello VR, Figueiredo-Ribeiro RCL. Seasonal variation of soluble carbohydrates and starch in *Echinolaena inflexa*, a native grass species

- from the Brazilian savanna, and in the invasive grass *Melinis minutiflora*. *Brazilian Journal of Biology*. 2010;70(2):395-404. doi:10.1590/S1519-69842010000200023
40. De Moraes MG, De Carvalho MAM, Franco AC, Pollock CJ, Figueiredo-Ribeiro RDCL. Fire and Drought: Soluble Carbohydrate Storage and Survival Mechanisms in Herbaceous Plants from the Cerrado. *Bioscience*. 2016;66(2):107-117. doi:10.1093/biosci/biv178
 41. Carneiro RV, Figueiredo-Ribeiro RCL, Moraes MG, Carvalho MAM, Almeida VO. Diversity of non-structural carbohydrates in the underground organs of five Iridaceae species from the Cerrado (Brazil). *South African Journal of Botany*. 2014;96:105-111. doi:10.1016/j.sajb.2014.10.003
 42. Clerici MTPS, Kallmann C, Gaspi FOG, Morgano MA, Martinez-Bustos F, Chang YK. Physical, chemical and technological characteristics of *Solanum lycocarpum* A. St. - HILL (Solanaceae) fruit flour and starch. *Food Research International*. 2011;44(7):2143-2150. doi:10.1016/J.FOODRES.2011.01.060
 43. Pascoal AM, Di-Medeiros MCB, Batista KA, Fernandes KF. Physical-chemical Characterization of Lobeira (*Solanum lycocarpum*) Starch. In: *XLII Annual Meeting of SBBq*. Vol 42. ; 2013:1-1.
 44. Di-Medeiros MCB, Pascoal AM, Batista KA, et al. Rheological and biochemical properties of *Solanum lycocarpum* starch. *Carbohydr Polym*. 2014;104(1):66-72. doi:10.1016/J.CARBPOL.2014.01.023
 45. Pascoal AM, Di-Medeiros MCB, Batista KA, Leles MIG, Lião LM, Fernandes KF. Extraction and chemical characterization of starch from *S. lycocarpum* fruits. *Carbohydr Polym*. 2013;98(2):1304-1310. doi:10.1016/J.CARBPOL.2013.08.009
 46. Locatelli APK, Stefani R. Morphological analysis of starches from Lobeira (*Solanum lycocarpum*), Cassava (*Manihot esculenta*) and Corn (*Zea mays*). *Revista Eletrônica Interdisciplinar*. 2023;15(2):174-181. Accessed June 2, 2024. <http://revista.univar.edu.br/rei/article/view/283/348>
 47. Celik S, Ozkok F, Ozel AE, Cakir E, Akyuz S. Synthesis, FT-IR and NMR Characterization, Antibacterial and Antioxidant Activities, and DNA Docking Analysis of a New Vanillin-Derived imine Compound. *J Mol Struct*. 2021;1236:130288. doi:https://doi.org/10.1016/j.molstruc.2021.130288
 48. Isopencu GO, Stoica-Guzun A, Busuioc C, Stroescu M, Deleanu IM. Development of antioxidant and antimicrobial edible coatings incorporating bacterial cellulose, pectin, and blackberry pomace. *Carbohydrate Polymer Technologies and Applications*. 2021;2:100057. doi:https://doi.org/10.1016/j.carpta.2021.100057
 49. Wang Y, Xiang C, Li T, et al. Enhanced Thermal Stability and UV-shielding Properties of Poly(vinyl alcohol) Based on Esculetin. *J Phys Chem B*. Published online 2017:acs.jpcc.6b11453. doi:10.1021/acs.jpcc.6b11453
 50. Abugoch L, Caro N, Medina E, Díaz-dosque M, Luis L, Tapia C. Food Hydrocolloids Novel active packaging based on films of chitosan and chitosan / quinoa protein printed with chitosan-tripolyphosphate-thymol nanoparticles via thermal ink-jet printing. 2016;52:520-532. doi:10.1016/j.foodhyd.2015.07.028

51. Salinas Y, Ros-Lis J V, Vivancos JL, et al. Monitoring of chicken meat freshness by means of a colorimetric sensor array. *Analyst*. 2012;137(16):3635-3643. doi:10.1039/c2an35211g
52. Rukchon C, Nopwinyuwong A, Trevanich S, Jinkarn T, Suppakul P. Development of a food spoilage indicator for monitoring freshness of skinless chicken breast. *Talanta*. Published online 2014. doi:10.1016/j.talanta.2014.07.048
53. Chen Q, Li H, Ouyang Q, Zhao J. Identification of spoilage bacteria using a simple colorimetric sensor array. *Sens Actuators B Chem*. 2014;205:1-8. doi:10.1016/j.snb.2014.08.025
54. Akinwumi AO, Oshodi OA, Olawuyi BS, Atandah RA, Olukade BC, Ogunsola OM, Ajani RA, Oyenekan OI, Olagoke OC. The Effect of Different Natural Antioxidants on Meat Quality of Broiler Chickens. *Ann. Res. Rev. Biol.* [Internet]. 2022 Sep. 15 [cited 2024 Jun. 6];37(9):96-107. Available from: <https://journalarrb.com/index.php/ARRB/article/view/1934>
55. Boateng EF, Nasiru MM, Agyemang M. Meat: Valuable Animal-Derived Nutritional Food. A Review. *AFSJ* [Internet]. 2020 Apr. 9 [cited 2024 Jun. 6];15(1):9-19. Available from: <https://journalafsj.com/index.php/AFSJ/article/view/297>
56. Mir NA, Rafiq A, Kumar F, Singh V, Shukla V. Determinants of broiler chicken meat quality and factors affecting them: a review. *Journal of food science and technology*. 2017 Sep;54:2997-3009.
57. Kokoszyński D, Żochowska-Kujawska J, Kotowicz M, Sobczak M, Piwczyński D, Stęczny K, Majrowska M, Saleh M. Carcass characteristics and selected meat quality traits from commercial broiler chickens of different origin. *Animal Science Journal*. 2022 Jan;93(1):e13709.