

Preparation and characterization of ferrihydrite: application in arsenic removal from aqueous solutions

ABSTRACT

Arsenic pollution is a public health hazard in Burkina Faso due to its impact on human health and water resources. To mitigate this pollution, ferrihydrite material has been synthesized and characterized to be used as adsorbent for arsenic removal in aqueous solutions. This study aims to contribute to the improvement of access to clean drinking water by removing arsenic from water using ferrihydrite. Arsenic removal experiments were carried out using batch mode and aqueous solutions. The characterization of ferrihydrite using Scanning Electron Microscopy (SEM) coupled with Energy Dispersive Spectroscopy (EDX), X-ray Diffraction (XRD), Infrared (IR), and Brunauer Emmett Teller (BET) showed that an amorphous and microporous ferrihydrite was synthesized. The total specific surface area and pH of the charge were 184.518 m²/g and 9.41, respectively. The optimal adsorbent doses were 4g/L for As(V) and 8g/L with As(III). The optimum pH range for the adsorption of As (V) and As (III) was between 2 and 10. The adsorption capacity ranged from 2.0 to 15.07 mg/g for As (V) and from 2.0 to 13.01 mg/g for As (III) with increasing concentration between 2 and 16 mg/L. Equilibrium time for As (V) and As (III) on ferrihydrite was found to be 720 min and 960 min with an adsorption capacities of 623.75 and 618.75 µg/g, respectively. The adsorption of As(V) and As(III) was consistent with the Langmuir monolayer model on ferrihydrite. A very favourable spontaneous chemical reaction was observed. Arsenic removal followed the pseudo-second order kinetic model and occurred on a monolayer.

Keywords: adsorption, arsenic, characterization, ferrihydrite, removal.

1. INTRODUCTION

In different forms, arsenic compounds are known for their high toxicity on living organisms, mainly humans and animals [1, 2]. Due to the human activities, the increase in global mining and mineral processing processes has contributed to the accumulation of arsenic in waste rock and mine drainage water [2,3,4]. The transfer of arsenic with other heavy metals in soil and water resources has been observed in many regions of the world [5,6,7]. Arsenic (III) is less common in water but more toxic than arsenic (V) [2,5]. In addition to its role as a trace element in life, arsenic exposure through daily consumption of arsenic water is responsible for many diseases (cancers, respiratory problems, etc.)

worldwide [8, 9, 10]. In Burkina Faso, arsenic contamination has been noted in several regions due to the consumption of water with concentrations higher than the standard of 10 µg/L according to the World Health Organization (WHO) [10,11]. Boreholes and water sources built in rural areas by the state and partners have been closed for contamination reasons linked to arsenic [10,11]. Arsenic removal from water at a rate of less than 10 µg/L (WHO standard) is becoming a global necessity for the supply of drinking water in developing countries [2,9]. To reduce the harmful effects of arsenic compounds, treatment techniques such as filtration, coagulation-precipitation, reverse osmosis, electro dialysis, adsorption, and coupled techniques have been developed [12,13,14]. Among these techniques, adsorption has been studied in recent years owing to its effectiveness, economy, low cost, and environmental friendliness [14,15]. In the implementation of adsorption technique, the adsorbent material must be effective, selective, and have a high specific surface area to accumulate different forms of arsenic [15,16]. Adsorbents such as activated carbon, clays, laterites, and metal oxy-hydroxides have been tested for the removal of As (III) and As (V) in water [15,16,17]. Literature indicated that adsorbents based on iron oxides and hydroxides are effective for the adsorption of different forms of arsenic because of their amphoteric character [18,19,20].

In this work, ferrihydrite has been used as adsorbent for arsenic removal. Specifically, ferrihydrite has been prepared and characterized using analytical methods. In addition, arsenic removal capacity of percentage and removal mechanism have been investigated under various operating conditions.

2. MATERIALS AND METHODS

2.1 Preparation of ferrihydrite

To prepare the ferrihydrite granular, the method described by Scwertmann *et al.* [21] were used: 100 mL of a 0.25M ferric nitrate monohydrate solution (purity ≥ 98%) (Sigma-Aldrich) has been prepared with distilled water at initial pH of 2.08. The granular ferrihydrite was stored in an enclosure at a temperature between 19 and 21 °C.

2.2 Physico-chemical characterization of ferrihydrite powder

2.2.1 Physical characterization

The moisture content (TH) of the ferrihydrite was determined right after centrifugation of the paste to evaluate the quantity of free water it contained before drying. 50 g (mass m_1) of moisture ferrihydrite was placed in an oven at 110°C for 72h to constant mass denoted m_2 . The moisture content (TH) of the ferrihydrite has been calculated according to the following relationship [19]:

$$TH(\%) = \left(\frac{m_1 - m_2}{m_1} \right) \times 100 \quad (1)$$

The bulk density (d) of the ferrihydrite was determined using a method described elsewhere [16]. Equation 2 was used to determine the bulk density of ferrihydrite:

$$d = \frac{(m_1 - m_0)}{V} \quad (2)$$

The pH at the point of zero charge (pH_{PZC}) has been studied to understand the neutral surface charge of ferrihydrite [22]. The pH_{PZC} value was determined from the curve (initial pH – final pH) as a function of the initial pH intercepting the x-axis of $\text{pH}_i - \text{pH}_f = 0$ [23]. The surface area and the pore dimensions of the ferrihydrite were analyzed using Micromeritic (TriStar II plus version 3.02) controlled with MicroActive software. Before nitrogen (N_2) adsorption at 77.350 K, the ferrihydrite was dried and dispersed in a glass quartzachrome cell at 105 °C for 24 h to remove the adsorbed water and gas. The surface area was determined using the Brunauer, Emmett, and Teller (BET) method and the one of Langmuir [22,24]. The nitrogen adsorption and desorption isotherms obtained by Barrett, Joyner, and Halenda (BJH) method were used to determine the volume and radius of pore.

2.2.2 Chemical characterization

Elemental chemical analysis of the ferrihydrite was carried out using a Microwave Plasma Atomic Emission Spectrometer (MP-AES, Agilent 4200) controlled by Spectra software. The powder was mineralized by the «eau regale method» according to the following protocol: 10 g of the dry powder was weighed into a 100 ml gauge flask. Subsequently, 15 mL of hydrochloric acid (37%, Honeywell) and 5 mL of nitric acid (68%, Flucka) of analytical grade (AR) were added and heated to a temperature of 200 ± 5 °C on a hot plate for one hour. After cooling, the flask was completed up to the gauge mark, homogenized, and used for the determination of chemical elements by MP-AES previously calibrated with standard solution [24]. The Fourier Transform -infrared (FT-IR) spectrum was recorded in the range of 500 to 4000 cm^{-1} with a resolution of 4 cm^{-1} using an OJAFO device (controlled by OPUS software) to evaluate the surface chemical functions. The mineral phase of the ferrihydrite was studied using a Shimadzu diffractometer equipped with a copper tube and graphite monochromator. The diffractogram was collected in an angular range of 2θ from 2° to 90° at a speed of 2° min^{-1} under a voltage of 40 kV and intensity of 30 mA [23]. The morphology and surface composition of the ferrihydrite have been observed using a Microspec-WDX 600/OXFORD brand device coupled to energy dispersive spectroscopy (EDX) [19,25].

2.3 Preparation of arsenic solutions

A stock solution of As (III) (1000 ppm) was prepared by dissolving a sodium arsenite salt (NaAsO_2) in a solution of 20% NaOH (Flucka) [20]. The As (V) solutions were prepared from a stock solution of 1000 ppm ($\text{Na}_2\text{HAsO}_4 \cdot 7\text{H}_2\text{O}$, Merck) by dilution with ultrapure distilled water. Reagents such as NaOH (Flucka) and HNO_3 (Sigma-Aldrich) were of analytical grade (AR) and were used to adjust the pH of the matrix solutions. The pH of As (III) and As (V) solutions was adjusted to be between 7 and 8 with a branded portable pH meter (HANNA, waterproof HI98318).

2.4. Arsenic removal experiments

Batch experiments were conducted to remove As(III) and As(V) from aqueous solutions. 25 mL solution of As (III) or As (V) at a concentration of 5 mg/L was added to 1.0 g of ferrihydrite in test tubes and initial pH was adjusted between 2 and 12. Adsorbent dose was varied over a range of 4 g/L to 14 g/L using initial arsenic concentration of 5 mg/L. The effect of initial arsenic concentration was then evaluated using concentration ranging from 1 to 16 mg/L. Similar experiments were carried out to

assess adsorption kinetics by testing from 01 h to 24 h with a 10g/L dose of adsorbent at an arsenic concentration of 5 mg/L. All experiments were running for 24 h at room temperature in the laboratory $24 \pm 0.15^\circ\text{C}$. Residual arsenic concentration has been analyzed with a Microwave Plasma Atomic Emission Spectrometer (MP-AES Agilent 4200) after filtration. The evaluation of the adsorption efficiency using ferrihydrite was carried out using the percentage of removal denoted As (%) and the adsorption capacity denoted Q_e (mg/g). The arsenic removal was calculated using the following relation:

$$As(\%) = \frac{C_i - C_e}{C_i} \times 100 \quad (4)$$

The adsorption capacity of ferrihydrite was determined by the following formula:

$$Q_e(\text{mg/g}) = \frac{(C_i - C_e) \times V}{m} \quad (5)$$

Where C_i and C_e (mg/L) represent the initial and equilibrium concentrations of As (III) or As (V), respectively, m (g) and V (L) are the mass of the ferrihydrite and the volume of solution, respectively.

3. RESULTS AND DISCUSSION

3.1. Characteristics of ferrihydrite

Figure 1 shows a moist red-brown chocolate cake batter (fig. 1A) and brown-colored ferrihydrite powder (fig. 1B). The mesh size of the ferrihydrite grains used in this work is less than or equal to 75 μm . The appearance and texture of the ferrihydrite powder obtained were similar to those reported by Otgon *et al.*[18] at pH (3-4).



Figure 1: Images of the prepared ferrihydrite

Physicochemical characteristics of the ferrihydrite are listed in Table 1. In this Table, we noticed that ferrihydrite has a large positive surface area relative to its basic pH at zero point (pH_{PZC}). In addition, this material contains a very high moisture content. Ferrihydrite's positively charged surface is therefore capable of adsorbing anions such as arsenic species[23]. The bulk density, which is almost half the density of pure iron ($d = 7.874 \text{ g/cm}^3$), indicates the predominance of iron in the ferrihydrite [19]. The specific surface area of the ferrihydrite powder ($184.518 \text{ m}^2/\text{g}$) is lower than the value reported by Milton *et al.* [26]. The higher Langmuir surface area than the other surfaces recorded in


Table 1 indicates that monolayer adsorption may control the removal of As (V) or As (III) from ferrihydrite [15,19]. The quantitative analysis of ferrihydrite showed the high content of iron (1257 mg/L) confirming its nature of iron oxyhydroxide.

Table 1 : Physicochemical characteristics of ferrihydrite powder

Physical parameter	Quantitative value
Particle size (μm)	≤ 75
Moisture content TH (%)	69.00
Density (d)	4.07
Zero charge pH pHCN	9.41
BET specific surface area (m^2/g)	59.986
Langmuir specific surface area (m^2/g)	73.315
External specific surface area (m^2/g)	51.216
Total specific surface area (SS) (m^2/g)	184.518
Total pore volume (cm^3/g)	0.052
Quantitative analysis of ferrihydrite	
Fe(mg/L)	1257.010
Al(mg/L)	*
Cu(mg/L)	*
Pb(mg/L)	*
Si(mg/L)	*
Ti(mg/L)	0.019
Na(mg/L)	2.310
Zn(mg/L)	0.007

*Not determined

The IR spectrum in Figure 2 shows the characteristic bands of the ferrihydrite. The different vibration bands were assigned according to the literature [19, 26, 27]. The bands around 3400 cm^{-1} correspond to the stretching vibrations of the O-H bonds in the surface hydroxyl groups and water molecules. The




wave numbers around 1630 , 1400 , and 900 cm^{-1} would correspond to adsorbed water molecules, deformation of Fe-O bonds, and deformation of Fe-OH, respectively. Miltonet *al.*[26] showed that the characteristic bands of ferrihydrite are mainly due to the hydroxyl O-H groups, the Fe-O and Fe-OH function of the structure. The relatively weak intensity of the stretching bands of the O-H bonds in the hydroxyl groups can be explained by the metastable nature of ferrihydrite [28].





Figure 2: FT - IR spectrum of ferrihydrite powder

The X-Ray diffraction (XRD) pattern of the ferrihydrite is shown in Figure 3. It highlighted the presence of two broad lines at 2θ values close to 35° and 67° . According to the literature [18,28], this diffraction

pattern can be attributed to "2-line" ferrihydrite rather than "6-line" ferrihydrite, whose diffraction pattern shows 6 lines. Background noise with relatively low peak intensities is observed in the diffraction pattern, indicating that the synthesized ferrihydrite is amorphous format. Otgon *et al.*[18] showed that the intensity of the peaks depended on the morphology and crystallinity of ferrihydrite. The ferrihydrite prepared could therefore be an amorphous 2-line ferrihydrite.




The images in Figure 4 show the surface morphology of ferrihydrite powder particles at different magnification scales. Magnification A (5X) shows a cluster of aggregates formed by small particles. Whereas magnification C (100 X) shows whitish irregular spherical shapes with relatively close pores indicating a larger specific surface area with small pore volumes [21,26]. These irregularly distributed whitish particles indicate the very amorphous character of the ferrihydrite powder revealed by the diffractogram. In their studies on the removal of As (V) by iron-doped activated carbon, Sanou *et al.* [19] showed that the whitish particles were due to the presence of iron and its magnetic nature. Spot chemical analysis of the surface (figure 4D: spectrum EDX) revealed that the ferrihydrite was mainly composed of iron (49.54%) and oxygen (34.18%). The other trace chemical elements are carbon (11.08%), sodium (2.50%), titanium (1.53%) and aluminium (1.05%).



3.2. Influence of operating parameters on arsenic removal


3.2.1. Effect of initial pH

Figure 5 shows the adsorption of As(III) and As(V) over the pH range of 2–12. As(III) and As(V) was 100% removed until $\text{pH}_{\text{ZPC}} = 9.41$. The elimination rate decreased slightly in the pH range 10–12 for As (III) and As (V). The efficiency of the adsorption of different ionic and neutral forms of arsenic, such as H_3AsO_4 , H_2AsO_4^- , HASO_4^{2-} and H_3AsO_3 on the surfaces of ferrihydrite at a pH lower than 9.41 could be explained by a process of attraction due to the positive charge of the ferrihydrite surface. However, beyond $\text{pH}_{\text{PZC}} = 9.41$, the reduction in elimination could be explained by the repulsion of the ionic forms of arsenic (H_2AsO_3^- , AsO_3^{3-} , AsO_4^{3-}) by the negatively charged surface [23,24]. The adsorption of neutral forms (H_3AsO_4 and H_3AsO_3) in the pH range $\leq \text{pH}_{\text{PZC}}$ would be an ionization of the arsenate and arsenite forms on ferrihydrite followed by a ligand exchange mechanism [23]. The average equilibrium pH of the final pH value was 7.29. Thus, the mechanism for eliminating the forms of arsenic on the ferrihydrite surface would be bidentate or monodentate [18,27]. The optimal pH range is 2–10, which corresponds to that of Qi *et al.* [29].



3.2.2. Effect of Adsorbent amount


The influence of the mass of ferrihydrite was evaluated for adsorbent doses ranging from 4 to 40 g/L with an initial concentration of 5 mg/L of As (V) and As (III) at pH 7.45 for 24 h. Figure 6 shows an increase in the arsenic removal from 99.64 to 100% for As (V), and from 87 to 100% for As (III). The optimal adsorbent doses under these conditions were 4 g/L for As (V) and 8 g/L for As (III) on the ferrihydrite. The adsorbent dose for As (III) was double that for As (V) because of the oxidation of As (III) to As (V) before its fixation on the surface of ferrihydrite [25,29]. The increase in the removal rate was due to the increase in the number of active sites on ferrihydrite. The adsorption capacity of ferrihydrite depends on the number of active sites and specific surface area [29].



3.2.3. Effect of initial arsenic concentration

The behavior of the adsorption of As (V) and As (III) onto ferrihydrite was studied over a concentration range of 2–16 mg/L at pH (6.89) with a mass of 1.0 g during 24 h. Figure 7 shows that the removal percentages of As(V) and As(III) on the ferrihydrite surface decreased with the increase of initial arsenic concentration. For As (V), the removal percentage decreased from 100 to 93.95% while by

removing As (III), it decreased from 100 to 85.10%. The adsorption capacity of ferrihydrite increases from 2.0 to 15.07 mg/g for As (V) and from 2.0 to 13.01 mg/g for As (III). This increase in adsorption capacity could be explained by the increase in initial As (V) and As (III) ions fixed on the active sites of the ferrihydrite [20,30]. However, the decrease in arsenic removal percentage could be due to the limited number of arsenic ions adsorbed on the ferrihydrite at low concentrations [30,31]. The optimal concentration of ferrihydrite was 5 mg/L for As (V) and 10 mg/L for As (III).




3.2.4. Effect of contact time

The effect of the contact time was studied from 1h to 24 h (60-1440 min) with a concentration of 5 mg/L and a mass of 10 mg as shown in Figure 8. The removal percentage as a function of the contact time showed an increase according to two steps:

First step indicated an increase of arsenic (V) removal from 78 to 99.80% when the contact time was increased between 60 and 720 min. By removing As(III), it increased from 70 to 99.00% with an increase of contact time between 60 and 960 min. The second step indicated that arsenic removal remained constant after 720 min and 960 min for As(V) and As(III), respectively.

The equilibrium time for optimum removal of As (V) and As (III) on ferrihydrite was 720 min (12h) and 960 min (16h) corresponding to adsorption capacity of 623.75 and 618.75 $\mu\text{g/g}$ respectively for As(V) and As(III). Adsorption of As (V) and As (III) onto ferrihydrite could be chemical reactions of the internal and external complexes on the functional groups of the adsorbent, as shown by the IR spectrum [20,27].



3.2.5. Modelling of isotherms

The adsorption behavior of As (V) and As (III) on ferrihydrite as a function of the initial concentration was modeled using the Langmuir and Freundlich equilibrium isotherms [15,31,32]. Langmuir isotherm model describes the monolayer adsorption with homogenous sites of adsorbent, while multilayer adsorption and heterogenous sites were described by Freundlich isotherm model.

The linearized form of the Langmuir isotherm model is given by the relation:

$$\frac{C_e}{Q_e} = \frac{1}{Q_m} (C_e) + \frac{1}{K_L Q_m} \quad (8)$$

The equation of the Freundlich model is given by the following relation:

$$\ln Q_e = \ln K_f + \frac{1}{n} \ln C_e \quad (9)$$

Figure 9 shows the plots $C_e/Q_e = f(C_e)$ and $\ln C_e = f(C_e)$ as functions of the equilibrium concentration C_e for the Langmuir and Freundlich models. The slopes and intercept of the curves were used to calculate the different constants listed in Table 2.




Figure 9: Representation of Langmuir and Freundlich isotherms for As (V) and As (III)

Table 2: Langmuir and Freundlich constants

Ferrihydrite	Langmuir			Freundlich	
	Q_m (mg/g)	K_L (L/mg)	R^2	K_f (mg/g)	nR^2
As (V)	12.01	1.73	0.98	10.31	30.97
As (III)	11.36	3.28	0.99	10.96	40.98

The values of the Langmuir and Freundlich constants R^2 between 0.98 and 0.99 show a good correlation with the experimental data. The adsorption capacity values for As (V) and As (III) were 12.01 and 11.36 mg/g respectively according to the Langmuir model and 10.31 and 10.96 mg/g respectively according to the Freundlich model (table 2). The removal of As (V) and As (III) better follows the monolayer chemisorption process of homogeneous active sites. The Freundlich affinity constants (n) of As (V) and As (III) are 2.78 and 3.86 respectively, and are all greater than 1, indicating very favourable spontaneous chemical reactions [19,32].

The equilibrium parameter R_L and the Gibbs free energy (ΔG) have been evaluated from the following relations:

$$\Delta G_0 = -RT \cdot \ln K_L(10)$$

$$R_L = \frac{1}{1 + K_L C_0} \quad (11)$$

The calculated R_L values were between 0 and 1, indicating a favorable adsorption process for As (V) and As (III). The positive Gibbs free energies are 2.70 and 1.24 kJ/mole respectively for As(V) and As(III) indicated that the reactions on ferrihydrite are spontaneous process [19].

3.2.6. Kinetic modeling

To study the kinetic of arsenic adsorption onto ferrihydrite, the pseudo-first-order and pseudo-second-order model described by Lagergren and the one given by Ho and Mckay, respectively have been widely studied [19,33].

The integration of the Lagergren's equation (12) and the one of Ho and McKay (13) are given in the following formulas:

$$\ln(Q_e - Q_t) = \ln Q_e - k_1 t \quad (12)$$

$$\frac{t}{Q_t} = \frac{1}{Q_e} t + \frac{1}{K_2 Q_e^2} \quad (13)$$

The representation of these equations is given in Figure 10.




Figure 10: Representation of the kinetic models for the removal of As (V) and As (III) on ferrihydrite

Table 3: Kinetic constants in the removal of As (V) and As (III) on ferrihydrite

Ferrihydrite	Pseudo-first-order				Pseudo-second-order			
	$Q_{e,exp}$	$Q_{e,theo}$	K_1	R^2	$Q_{e,exp}$	$Q_{e,theo}$	K_2	R^2
	mg/g	mg/g	min ⁻¹		mg/g	mg/g	min ⁻¹	
As (V)	1.07	0.31	0.012	0.99	1.00	0.99	3.14	0.98
As (III)	0.99	0.29	0.010	0.98	0.98	1.01	3.78	0.97

The correlation coefficients (R^2) ranging from 0.97 to 0.99 for both models indicate that data are perfectly correlated between the variables. Using the pseudo-second kinetic model, the theoretical

values of the adsorption capacity (Q_e theo) are close to the experimental values (Q_e exp) indicating that arsenic removal followed the pseudo-second-order model. Consequently, chemisorption would control the adsorption process of As (V) and As (III) on the surface of ferrihydrite through an inner-sphere reaction [19,33].

4. CONCLUSION

This study enabled the successful preparation and characterization of ferrihydrite as adsorbent in arsenic removal. Characterization of the powder ferrihydrite indicated an amorphous 2-line ferrihydrite with hydroxide and surface hydroxyl functionalities to give better results. The efficiency of ferrihydrite in arsenic removal, mainly As(V) or As(III) species depended on the initial pH, adsorbent dose, initial concentration, and contact time. The mechanism of the removal of arsenic on ferrihydrite could be described by monolayer adsorption occurred following a spontaneous process. The removal of As (III) or As (V) has been occurred according to the pseudo-second-order kinetic and chemisorption process.

REFERENCES

- [1] Sayan.B., Avishek.T., Shubhalakshmi.S., Tuyelee.D., Abhijit.D., Kaushik.G., Nalok.D., Arsenic contaminated water remediation: A state-of-the-art review in synchrony with sustainable development goals. *Groundwater for Sustainable Development*.2023,23, 2352-801X, DOI: <https://doi.org/10.1016/j.gsd.2023.101000>.
- [2] Hifza.R., Rebecca.S., Paul.K., Human health risk assessment for arsenic: a critical review, *Critical Reviews in Environmental Science and Technology*.2016. DOI: 10.1080/10643389.2016.1245551
- [3] Ackmez.M., Sanjay.K.S., Vinod.K.G., Chin.H.T., Arsenic: An Overview of Applications, Health, and Environmental Concerns and Removal Processes. *Critical Reviews in Environmental Science and Technology*.2011, 41, 435-519. DOI: <http://dx.doi.org/10.1080/10643380902945771>
- [4] Smedley.P. L., Knudsen.J., Maiga.D., Arsenic in groundwater from mineralized Proterozoic basement rocks of Burkina Faso. *Applied Geochemistry*.2007,22, 1074–1092. DOI: <https://doi.org/10.1016/j.apgeochem.2007.01.00>
- [5] Arunima.N., Priya.C., Brij.B., Kapil.G., Seema.S., Mika.S., Removal of emergent pollutants: A review on recent updates and future perspectives on polysaccharide-based composites vis-à-vis traditional adsorbents. *International Journal of Biological Macromolecules*.2024, 258, 0141-8130. DOI: <https://doi.org/10.1016/j.ijbiomac.2023.129092>.
- [6] Thomas.S.Y.C., Chuah.T.G., Robiah.Y., Gregory.F.L. K., Azni.I., Arsenic toxicity, health hazards and removal techniques from water: an overview. *Desalination*.2007, 217, 139-166. DOI: <https://doi.org/10.1016/j.desal.2007.01.015>.
- [7] McArthur.J.M., Sikdar.P.K., Hoque.M.A., Ghosal.U., Waste-water impacts on groundwater: Cl/Br ratios and implications for arsenic pollution of groundwater in the Bengal Basin and Red River Basin,

Vietnam. *Science of the Total Environment*. 2012, 437, 390-402. DOI : <https://doi.org/10.1016/j.scitotenv.2012.07.068>

[8] Smedley.P. L., Kinniburgh.D.G., A review of the source, behaviour and distribution of arsenic in natural waters. *Applied Geochemistry*. 2002, 17, 517-568. DOI: [https://doi.org/10.1016/S0883-2927\(02\)00018-5](https://doi.org/10.1016/S0883-2927(02)00018-5)

[9] Ahoulé.D.G., Lalanne.F., Mendret.J., Brosillon.S., Maïga.A.H., Arsenic in African Waters: A Review. *Water Air Soil Pollution*. 2015, 226, 302. DOI: <https://doi.org/10.1007/s11270-015-2558-4>

[10] Bretzler.A., Lalanne.F., Nikiema.J., Podgorski.J., Pfenninger.N., Berg.M., Schirmer.M., Groundwater arsenic contamination in Burkina Faso, West Africa: Predicting and verifying regions at risk. *Science of the Total Environment*. 2017, 84-585, 958–970. DOI: <https://doi.org/10.1016/j.scitotenv.2017.01.147>

[11] Nic.E., Korte.M.S., Quintus.F.P.D., A review of arsenic (III) in groundwater. *Critical Reviews in Environmental Control*. 1991, 21, 1-39. DOI: <http://dx.doi.org/10.1080/1064338910938840>

[12] Garelick.H., Dybowska.A., Valsami.J.E., Priest.N.D., Remediation technologies for arsenic contaminated drinking waters. *Journal of soils and sediments*. 2005, 5, 182-190. DOI: <https://doi.org/10.1065/jss2005.06.140>

[13] Yang.Y., Ling.Y., Kok.Y.K., Chenghong.W., Chen.J.P., Rare-earth metal-based adsorbents for effective removal of arsenic from water: A critical review. *Critical Reviews in Environmental Science and Technology*. 2018, 48, 1127-1164. DOI: 10.1080/10643389.2018.1514930

[14] Sadiya.A., Shafinaz.S., Norahim.I., Mohammed.J.N., Dai.V.N. Vo., Fazilah.A. Manan., Arsenic removal technologies and future trends: A mini review. *Journal of Cleaner Production*. 2012, 278, 0959-6526. DOI: <https://doi.org/10.1016/j.jclepro.2020.123805>

[15] Gupta.V.K., Saini.V.K., Neera .J., Adsorption of Arsenic (III) from aqueous solutions by iron oxide-coated sand. *Journal of Colloid and Interface Science*. 2005, 288, 55– 60. DOI: <https://doi.org/10.1016/j.jcis.2005.02.054>

[16] Mohan.D.J., Pittman.C.U., Arsenic removal from water/wastewater using adsorbents-A critical review. *Journal of Hazardous Materials*. 2007, 142, 1–53. DOI: <https://doi.org/10.1016/j.jhazmat.2007.01.006>

[17] Patricia.M., Alicia.F., C., Remediation of Arsenic Contaminated Soils by Iron Amendments: A Review. *Critical Reviews in Environmental Science and Technology*. 2010, 40, 93-115. DOI: 10.1080/10643380802202059

[18] Otgon.N., Zhang.G., Zhang.K., Yang.C., Removal and fixation of arsenic by forming a complex precipitate containing scorodite and ferrihydrite. *Hydrometallurgy*. 2019, 186, 58-65. DOI : <https://doi.org/10.1016/j.hydromet.2019.03.012>

- [19] Sanou.Y., *Etude de la performance des charbons actifs, du granulé d'hydroxyde ferrique et de la latérite pour l'élimination de la demande chimique en oxygène, du calcium et de l'arsenic des eaux.* Thèse de doctorat unique, Université Ouaga I Pr Joseph KI-ZERBO.2017, Burkina Faso.
- [20] Pierce.M.L., Moore.C.B., Adsorption of arsenite and arsenate on amorphous iron hydroxide. *Water Resource*.1982, 16, 1247–1253 DOI: [https://doi.org/10.1016/0043-1354\(82\)90143-9](https://doi.org/10.1016/0043-1354(82)90143-9)
- [21] Schwertmann.U., Cornell.R.M., (2007). Iron Oxides in the Laboratory: Preparation and characterization Weinheim. *Wiley-VCH Verlag GmbH*, X p,103-112.DOI: <https://doi.org/10.1002/9783527613229.ch08>
- [22] Lallan.S.Y, Bijay.K.M., Arvind.K., Kakoli.K.P., Arsenic removal using bagasse fly ash-iron coated and sponge iron char. *Journal of Environmental Chemical Engineering*.2014,3, 1467-1473.DOI: <https://doi.org/10.1016/j.jece.2014.06.019>
- [23] Saha. B, Bains R., Greenwood F., Physicochemical characterization of granular ferric hydroxide (GFH) for arsenic(V) sorption from water. *Separation Science and Technology*.2005, 40, 2909 - 2932. DOI: <https://doi.org/10.1080/01496390500333202>
- [24] Yongfeng.J., Liying.X., Zhen.F., George.P., Demo.P., Observation of Surface Precipitation of Arsenate on Ferrihydrite. *Environmental Science Technology*.2006,40,3248-3253.DOI :<https://doi.org/10.1021/es051872+>
- [25] Chen.A., Ying.L., Jianying.S., Yuji.A., Ferrihydrite transformation impacted by coprecipitation of phytic acid. *Environmental Science and Technology*.2020,14,8837–8847.DOI: <https://doi.org/10.1021/acs.est.0c02465>
- [26] Milton.V.G., Mariana.U.A., Katherine.V.E., Mario.V., Rodolfo.Z., Nadia.M.V., Laboratory synthesis of goethite and ferrihydrite of controlled particle sizes. *Boletín de la Sociedad Geológica Mexicana*.2015, 67, 433-446 DOI: 10.18268/BSGM2015v67n3a7
- [27] Yongfeng.J., Liying.X., Xin.W., George.P.D., Infrared spectroscopic and X-ray diffraction characterization of the nature of adsorbed arsenate on ferrihydrite. *Geochimica et Cosmochimica Acta*.2007, 71, 1643-1654. DOI: <https://doi.org/10.1016/j.gca.2006.12.021>.
- [28] Hélène Laversin., *Traceurs et formes chimiques du fer dans les particules émises dans l'atmosphère depuis un site sidérurgique : Etude spectroscopique et caractérisation de composés de référence et de particules collectées dans l'environnement.* Thèse unique de Chimie de l'Université du Littoral - Côte d'Opale.2006, République de France.
- [29] Qi.P., Pichler.T., Closer look at As (III) and As (V) adsorption onto ferrihydrite under competitive conditions : Langmuir. *Journal American Chemical Society*.2014,30,11110–11116.DOI : <https://doi.org/10.1021/la502740w>
- [30] Sanou.Y., Nguyen.T.T.P., Paré.S., Nguyen.V.P., Dynamic Study and Modelling of Arsenic Removal from Groundwater Using Ferromagnetic Carbon as Fixed Bed Adsorbent in Column. *French-Ukrainian Journal of Chemistry*.2023,11, DOI:10.17721/fujcV1111P74-90

[31]Rahman.M., Lamb.D., Rahman.M., Bahar.M., Sanderson.P., Adsorption-Desorption Behavior of Arsenate Using Single and Binary Iron-Modified Biochars: Thermodynamics and Redox Transformation. *ACS Omega*.2022, 7, 101-117. DOI: 10.1021/acsomega.1c04129

[32]Langmuir.I., The adsorption of gases on plane surfaces of glass, mica and platinum. *Journal of American Chemical Society*.1918, 40, 1361–1403, DOI : <http://dx.doi.org/10.1021/ja02242a004>

[33] Abinashi.S., Jeongwon.P., Hyeon.K., Pyung.K.P., Arsenic removal from aqueous solutions by adsorption onto hydrous iron oxide-impregnated alginate beads. *Journal of Industrial and Engineering Chemistry*.2016, 35, 277-28. DOI: <https://doi.org/10.1016/j.jiec.2016.01.005>

UNDER PEER REVIEW