

Opinion Article

A review of rheological properties of steel fiber reinforced concrete

ABSTRACT: The rheological properties of steel fiber reinforced concrete have a significant impact on engineering quality, and experimental characterization of the rheological properties of steel fiber reinforced concrete has significant engineering significance and scientific research value. The article compares and analyzes the construction characteristics and applicable scope of commonly used concrete rheometers, and analyzes the influence of factors such as water cement ratio, mineral admixtures, aggregate properties, steel fiber properties, and additives on the rheological performance test results. This can provide reference for the selection of rheological performance testing methods and parameter control of steel fiber reinforced concrete.

Keywords: steel fiber reinforced concrete; rheological properties; rheometer; rheological model; factors affecting rheological properties

1. INTRODUCTION

Steel fiber reinforced concrete has been extensively studied for its superior mechanical and deformation properties, and has been widely used in construction, water conservancy, road and bridge engineering fields, such as steel fiber reinforced concrete composite beams, steel fiber lightweight aggregate concrete composite beams, steel fiber reinforced concrete lining for weak surrounding rock tunnels, steel fiber reinforced concrete face rockfill dams, etc. Its workability has also been widely concerned in the field of engineering construction [1]. The rheological properties of steel fiber reinforced concrete mixtures are related to their transportation, pumping, pouring, forming, and workability [2], and good workability is a prerequisite for achieving their quality objectives [3]. Therefore, studying the rheological properties of steel fiber reinforced concrete is of great significance. This article summarizes the rheometers and rheological models applicable to concrete, and discusses in detail the influence of different factors on the rheological properties of steel fiber reinforced concrete.

2. RHEOMETER

Rheology is a science about the flow and deformation of matter, and the principles of rheology are applied to cement-based materials, providing an important means for accurately characterizing rheological properties. The rheological properties of concrete are one of the most important indicators of early workability, and excellent rheological properties ensure the performance of concrete mixtures during pouring, forming, and transportation under complex conditions [4]. Rheometer is a device used to test the relationship between torque and rotational speed of materials under shear conditions, and has gradually become the mainstream tool for

characterizing the rheological properties of concrete. The geometric dimensions, testing components, and testing procedures of a rheometer can lead to differences in rheological parameters, which are related to the material composition. Common concrete rheometers include coaxial cylindrical rheometers, blade rheometers, parallel plate rheometers, and so on [5].

At present, most rheometers used for studying the rheology of cement-based materials are coaxial cylindrical. The instrument consists of two coaxial cylinders, one inside and one outside. During measurement, the annular space between the two cylinders is filled with concrete, and one cylinder is kept stationary while the other cylinder rotates. The torque value is measured by changing the rotational speed. Coaxial cylinder rheometers can be divided into two types: one is the Couette type rheometer, which measures the outer cylinder rotation speed and the torque acting on the inner cylinder, and the other is the Searle type rheometer, which measures the inner cylinder rotation speed and torque at the same time [5].

The more common blade rheometer is the ICAR rheometer developed by the International Aggregate Research Center at the University of Texas. This rheometer is more portable and its larger blade size can be used to test the rheological properties of self compacting concrete containing large coarse aggregates. It is mainly composed of an electric motor, a bracket, a rotor, a computer, and a concrete cylinder. The rotor is a cross shaped propeller with ribs on the inner wall of the cylinder, which can prevent relative sliding between the concrete inside the cylinder and the inner wall [6]. The geometric structure of the rheometer, especially the distance between the rotor and the outer cylinder, the shape of the rotor, and other factors, have a significant impact on the measurement results.

The BTRHEOM rheometer is a typical representative of parallel plate rheometer. Between two horizontal plates, the circular concrete is subjected to shear around the central axis. The upper plate can rotate, and both the upper and lower plates have ribs, which can avoid relative sliding between the concrete and the instrument and affect the determination of rheological results. At the same time, vibration can also be applied to the concrete through the container that supports it at the bottom [7].

3. RHEOLOGICAL MODEL

The rheological properties of freshly mixed concrete can be characterized by rheological models, including the Bingham model, Herschel Bulkley model, and Modified Bingham model [8]. The Bingham model can effectively meet the requirements for measuring the rheological parameters of concrete in engineering. The rheological parameters can be calculated using a rheometer, and the method is relatively simple. Within a certain range, the shear stress increases linearly with the increase of shear rate. Its mathematical expression is:

$$\tau = \tau_0 + \eta \dot{\gamma} \quad (3-1)$$

In the formula, τ is the shear stress (Pa); τ_0 is the yield stress (Pa); η is the plastic viscosity (Pa • s); $\dot{\gamma}$ is the shear rate (s⁻¹).

The advantage of the Herschel Bulkley model is that it can better describe the nonlinearity of the relationship between shear stress and shear rate of materials and avoid the occurrence of negative yield stress based on the Bingham model. Its expression is:

$$\tau = \tau_0 + k \dot{\gamma}^n \quad (3-2)$$

In the formula, k is the consistency factor (Pa • sⁿ); n is the power-law exponent ($n < 1$ indicates

shear thinning, $n > 1$ indicates shear thickening, $n = 1$ indicates the standard Bingham linear model).

For the shortcomings of the Herschel Bulkley model, the Modified Bingham model can be used to characterize the rheological properties of cement-based materials [9]. Self compacting concrete often exhibits rheological properties of shear thickening, which can be characterized by the Modified Bingham model. Its expression is:

$$\tau = \tau_0 + \eta\dot{\gamma} + c\dot{\gamma}^2 \quad (3-3)$$

In the formula, c is the correction factor ($c > 0$ indicates shear thickening, $c < 0$ indicates shear thinning, and $c = 0$ indicates Bingham model).

4. FACTORS AFFECTING RHEOLOGICAL PROPERTIES

Rheometers can be used to measure rheological parameters such as yield stress and plastic viscosity of freshly mixed concrete, where yield stress is the parameter that starts or stops the flow of concrete during pouring, and plastic viscosity reflects the rheological properties of concrete during the process of overcoming yield stress flow [7]. Various factors such as water cement ratio, mineral admixtures, aggregate properties, steel fiber properties, and additives can all affect the rheological properties of steel fiber reinforced concrete.

4.1 Water cement ratio

The rheological properties of cement-based materials are largely related to the water cement ratio. Lee et al. [10] studied the effect of different water cement ratios (0.38, 0.41, and 0.44) on the rheological parameters of synthetic fiber-reinforced self compacting cement-based composites. The results showed that the yield stress and plastic viscosity both decreased with increasing water cement ratio. Sadrmomtazi et al. [11] conducted a study on the influence of different water cement ratios (0.18, 0.20, and 0.22) on the rheological properties of ultra-high performance concrete (UHPC), and concluded that the yield stress decreases with increasing water cement ratio. Madandoust et al. [12] found through studying self compacting concrete (SCC) containing metakaolin with different water cement ratios (0.32, 0.38, and 0.45) that a metakaolin rotary cone distillation tower with appropriate stability can be produced without the use of viscosity modifiers at different water cement ratios.

4.2 Mineral admixture

Guo et al. [13] conducted experimental research on the influence of different fly ash contents on the rheological and workability properties of lightweight aggregate concrete. The results showed that the addition of fly ash can reduce the yield stress and plastic viscosity of lightweight aggregate concrete, and effectively improve its workability. Güneyisi et al. [14] prepared glass fiber reinforced self compacting concrete by mixing nano silica (NS) and fly ash. When the NS content increased from 0% to 4% and the glass fiber volume fraction increased from 0% to 1.5%, it resulted in an increase in the slump expansion and V-funnel time of the concrete mixture. Wu et al. [15] studied the effect of varying the content of silica fume (0, 5%, 10%, 15%, 20%, 25%) on the rheological properties of UHPC. They found that the mechanical interlocking between steel fibers and surrounding particles increased the flow resistance, so high content silica fume could increase the yield stress and plastic viscosity of UHPC. However, when 10% and 15% silica fume were added, there was a tendency to reduce the plastic viscosity. Keke et al. [16] studied the effect of bentonite content on the rheological properties of UHPC and found that when the bentonite content increased from 0% to 15%, due to its strong water swelling and PCE adsorption properties, the flowability of UHPC mixtures decreased by 55.71%, while the static yield stress, dynamic

yield stress, plastic viscosity, and thixotropy increased by 17.05 times, 5.57 times, 1.16 times, and 0.04 times, respectively.

4.3 Aggregate characteristics

The characteristics of aggregates also have a significant impact on the rheological properties of concrete. Guo et al. [17] studied the influence of fine aggregate morphology on the rheological parameters of C30 concrete. The results showed that as the angularity and two-dimensional shape index of the composite fine aggregate increased, the yield stress and viscosity coefficient of the concrete mixture also increased. Zhang [18] studied the effects of different aggregate particle sizes (5-10 mm, 5-16 mm, 5-20 mm, and 5-25 mm) on the rheological and workability properties of SCC. The results showed that as the aggregate particle size increased, the yield stress and plastic viscosity of SCC showed a trend of first decreasing and then increasing, the slump expansion first increased and then slightly decreased, and T500 first decreased and then increased. Jiao et al. [19] investigated the effect of aggregate coating thickness on the rheological properties of concrete. The results showed that the yield stress and plastic viscosity of fresh concrete generally decreased with the increase of aggregate coating thickness, and the slump gradually increased, improving the fluidity of concrete. Jiao et al. [20] conducted experimental research on the influence of coarse aggregate gradation on the rheological parameters of concrete. The results showed that the yield stress decreased with the increase of large particle size aggregate content, while the plastic viscosity was mainly related to the content of small and intermediate particle size aggregates. With the increase of small particle size aggregate content, the plastic viscosity first decreased and then increased. Santos et al. [21] found through their research that the influence of aggregate gradation on plastic viscosity in SCC is much greater than its effect on yield stress.

4.4 Steel fiber characteristics

The type, aspect ratio, and dosage of steel fibers fundamentally affect the rheological properties of steel fiber reinforced concrete. Zeyad [22] studied the effect of steel fiber types on the rheological properties of steel fiber self compacting concrete (SFRCC). The results showed that end hooked steel fibers were more affected by the end shape and could lower the rheological properties of SFRCC than low-carbon steel fibers and bent steel fibers. Alrawashden et al. [23] studied the effects of aspect ratios (60, 80) and volume fractions (0.35%, 0.45%, and 0.55%) of end hooked steel fibers on the rheological properties of SFRSC. The results showed that the rheological properties of SFRSC decreased with increasing aspect ratios and volume fractions of steel fibers. Ding et al. [24] showed that the characteristics of freshly mixed SCC are more affected by the length of steel fibers than their volume fraction.

4.5 Admixture

Common additives include water reducing agents, viscosity modifiers, air entraining agents, etc. [25], all of which can affect the rheological properties of cement-based materials. Water reducing agents are mainly organic water-soluble polymers, commonly used to improve the workability of concrete and significantly reduce its rheological parameters [26, 27]. The main types of water reducing agents include sulfonated naphthaldehyde (SNF), polycarboxylate ether (PCE), lignin sulfate (LS), hydroxycarboxylic acid, carbohydrates, etc [28]. Among them, PCE and SNF high-efficiency water reducing agents have been widely used. Qian et al. [29] studied the different effects of PCE and SNF high-efficiency water reducers on the dynamic yield stress of cement slurry. They observed that both PCE and SNF high-efficiency water reducers reduced the dynamic yield stress of the slurry, but compared with SNF high-efficiency water reducer, PCE

high-efficiency water reducer was more effective in reducing the dynamic yield stress of the slurry. Yu et al. [30] found through studying the effect of high-efficiency water reducing agent (SP) on the rheological parameters of fresh UHPC that the yield stress and plastic viscosity showed a trend of first decreasing and then increasing with the increase of SP dosage. When the SP dosage was 3.5%, UHPC with a dense microstructure could be obtained. Wang et al. [31] studied the effect of changing the dosage of SP on the rheological parameters of a new type of UHPC mortar. The results showed that as the dosage of SP increased, the yield stress significantly decreased, but the effect on plastic viscosity was not significant.

Meng et al. [32] found that adding a high molecular weight ethylene oxide viscosity modifier can increase the yield stress and plastic viscosity of UHPC under a fixed water cement ratio. Geng et al. [33] used UWB II flocculant as a viscosity modifier (VMA) to prepare underwater non dispersible concrete (UNC). The study found that the expansion time increased exponentially with the decrease of slump expansion. When the slump, slump expansion, and T_{500} were 280 mm, 830 mm, and 0.9 s, respectively, the best workability of freshly mixed UNC could be obtained. Tang et al. [34] systematically studied the effects of polycarboxylate SP and VMA on the rheological properties of ECC mortar. The results showed that increasing the amount of SP without VMA resulted in a rapid decrease in yield stress and a steady decrease in plastic viscosity; After adding an appropriate amount of VMA, increasing the amount of SP still effectively reduces the yield stress value while maintaining a plastic viscosity higher than 1.1 Pa·s. Yuan et al. [35] used two types of VMA and two types of SP, namely hydroxypropyl methyl cellulose (HPMC), Weilun gum and polycarboxylate (PCA), and polynaphthalene sulfonate (PNS), to study the coupling effect of additives on the rheological properties of cement slurry. The results showed that the interaction between PNS and HPMC was stronger. Yun et al. [36] found through studying the effect of air entraining agents on the rheological properties of high-performance wet mix shotcrete (HPWMS) that the use of air entraining agents aims to reduce flow resistance and torque viscosity, which can effectively improve the pumping performance of HPWMS. The rate of decrease in torque viscosity decreases with the increase of air content. Kim et al. [37] investigated the relevant characteristics of lightweight aggregate porous concrete (LACC) with a large amount of air entrainment, and the results showed that LACC containing sufficient air entraining agent had higher workability.

5. CONCLUSION

For decades, the workability of concrete has been a widely concerned issue in the field of engineering and construction. The working performance of concrete, such as pumping, pouring, self compacting, and forming, is closely related to its rheological properties. On the other hand, the rheological properties of concrete also have an impact on its strength and durability after hardening. Adding steel fibers to concrete will to some extent change its workability and rheological properties. How to improve the workability of steel fiber reinforced concrete is still a topic that needs further research, and the current research on the rheological properties of steel fiber reinforced concrete also needs to be continuously enriched.

REFERENCES

- [1] Zhang XZ, Bi MD, Liu TJ, Sun HL, Zhang C, Mu R, et al. Research progress on influencing factors of fiber distribution characteristics in steel fiber reinforced concrete [J]. *Journal of Ceramics*, 2021, 49 (8): 1732-1742.
- [2] Zhang P, Gao Z, Wang J, Guo JJ, Wang TY. Influencing factors analysis and optimized prediction model for rheology and flowability of nano-SiO₂ and PVA fiber reinforced alkali-activated composites [J]. *Journal of Cleaner Production*, 2022, 366: 132988.
- [3] Gao C. Research on the Testing Method of Rheological Properties of Cementitious Materials [D]. Central South University, 2022.
- [4] Chen B, Wu CJ, Chen Z. Comparative analysis of rheological properties tests of cement-based materials [J]. *Concrete*, 2022, (9): 93-98.
- [5] Liu Y. Measurement, Modeling, and Application of Rheology in Freshly Mixed Concrete [D]. China Academy of Building Materials Science, 2021.
- [6] Alberti MG, Enfedaque A, GÁLVEZ JC. The effect of fibres in the rheology of self-compacting concrete [J]. *Construction and Building Materials*, 2019, 219: 144-53.
- [7] Huang FL, Li HJ, Xie YJ, Yi ZL, Tan YB. Research progress on the correlation between workability and rheological parameters of fresh concrete [J]. *Concrete*, 2015, (10): 119-123+127.
- [8] Feng H, Feng ZJ, Wang WS, Deng ZL, Zheng BC. Impact of polycarboxylate superplasticizers (PCEs) with novel molecular structures on fluidity, rheological behavior and adsorption properties of cement mortar[J]. *Construction and Building Materials*, 2021, 292: 123285.
- [9] Peng JW, Deng DH, Liu ZQ, Yuan Q, Ye T. Rheological models for fresh cement asphalt paste[J]. *Construct Build Mater*, 2014, 71: 254-262.
- [10] Lee SJ, Ryu S, Won JP. Relationship between the rheology and flowability of self-compacting structural synthetic fibre-reinforced cementitious composites [J]. *Composite Structures*, 2021, 267: 113862.
- [11] Sadrmomtazi A, Tajasosi S, Tahmouresi B. Effect of materials proportion on rheology and mechanical strength and microstructure of ultra-high performance concrete (UHPC) [J]. *Construction and Building Materials*, 2018, 187: 1103-1112.
- [12] Madandoust R, Mousavi SY. Fresh and hardened properties of self-compacting concrete containing metakaolin [J]. *Construction and Building Materials*, 2012, 35: 752-760.
- [13] Guo Z, Song SM. Study on the Effect of Fly Ash on the Performance and Slurry Rheology of LC15 Lightweight Concrete [J]. *Concrete and Cement Products*, 2019, (3): 27-31.
- [14] Güneyisi E, Atewi YR, Hasan MF. Fresh and rheological properties of glass fiber reinforced self-compacting concrete with nanosilica and fly ash blended [J]. *Construction and Building Materials*, 2019, 211: 349-362.
- [15] Wu ZM, Khayat KH, Shi CJ. Changes in rheology and mechanical properties of ultra-high performance concrete with silica fume content [J]. *Cement and Concrete Research*, 2019, 123: 105786.
- [16] Li KK, Leng Y, Xu LL, Zhang JJ, Liu KN, Fan DQ, et al. Rheological characteristics of Ultra-High performance concrete (UHPC) incorporating bentonite [J]. *Construction and Building Materials*, 2022, 349: 128793.
- [17] Guo C, Shui ZH, Fei XF, Guo W. Study on the influence of fine aggregate morphology on the

- rheological properties of C30 concrete [J]. *Concrete and Cement Products*, 2020, (7): 21-25+29.
- [18] Zhang ZC. Study on the influence of aggregate particle size on the rheological properties, workability, and static stability of self compacting concrete [J]. *Silicates Bulletin*, 2020, 39 (7): 2139-2144.
- [19] Jiao DW, An XP, Shi CJ, Liu Y, Li H, He FQ. The influence of aggregate coating thickness on the rheological properties of concrete [J] *Journal of Ceramics*, 2017, 45 (9): 1360-1366.
- [20] Jiao DW, Shi CJ, An XP, Liu Y, He FQ. Optimization design of coarse aggregate gradation based on rheological properties [J]. *Silicates Bulletin*, 2017, 36 (3): 1064-1070.
- [21] Santos ACP, Ortiz-lozano J A, Villegas N, Aguado A. Experimental study about the effects of granular skeleton distribution on the mechanical properties of self-compacting concrete (SCC) [J]. *Construction and Building Materials*, 2015, 78: 40-49.
- [22] Zeyad AM. Effect of fibers types on fresh properties and flexural toughness of self-compacting concrete [J]. *Journal of Materials Research and Technology*, 2020, 9(3): 4147-4158.
- [23] Alrawashdeh A, Eren O. Mechanical and physical characterisation of steel fibre reinforced self-compacting concrete: Different aspect ratios and volume fractions of fibres [J]. *Results in Engineering*, 2022, 13: 100335.
- [24] Ding XX, Li CY, Han B, Lu YZ, Zhao SB. Effects of different deformed steel-fibers on preparation and fundamental properties of self-compacting SFRC [J]. *Construction and Building Materials*, 2018, 168: 471-481.
- [25] Jiao DW, Shi CJ, Yuan Q, An XP, Liu Y, Li H. Effect of constituents on rheological properties of fresh concrete-A review [J]. *Cement and Concrete Composites*, 2017, 83: 146-159.
- [26] Khayat KH, Meng W, Vallurupalli K, Teng L. Rheological properties of ultra-high-performance concrete — An overview [J]. *Cement and Concrete Research*, 2019, 124: 105828.
- [27] Adjoudj M, Ezziane K, Kadri EH, Ngo TT, Kaci A. Evaluation of rheological parameters of mortar containing various amounts of mineral addition with polycarboxylate superplasticizer [J]. *Construction and Building Materials*, 2014, 70: 549-559.
- [28] Mandal R, Panda SK, Nayak S. Rheology of Concrete: Critical Review, recent Advancements, and future perspectives [J]. *Construction and Building Materials*, 2023, 392: 132007.
- [29] Qian Y, De SG. Different Effects of NSF and PCE Superplasticizer on Adsorption, Dynamic Yield Stress and Thixotropy of Cement Pastes [J/OL]. *Materials*, 2018, 11(5): 695.
- [30] Yu R, Zhou FJ, Yin TY, Wang ZY, Ding MX, Liu Z, Leng Y, et al. Uncovering the approach to develop ultra-high performance concrete (UHPC) with dense meso-structure based on rheological point of view: Experiments and modeling [J]. *Construction and Building Materials*, 2021, 271: 121500.
- [31] Wang R, Gao XJ, Zhang JY, Han GS. Spatial distribution of steel fibers and air bubbles in UHPC cylinder determined by X-ray CT method [J]. *Construction and Building Materials*, 2018, 160: 39-47.
- [32] Meng W, Khayat KH. Improving flexural performance of ultra-high-performance concrete by rheology control of suspending mortar [J]. *Composites Part B: Engineering*, 2017, 117:

26-34.

- [33] Geng HB, Wang HJ, Li XK, Wang L, Zhong H, Li CY. An Orthogonal Test Study on the Preparation of Self-Compacting Underwater Non-Dispersible Concrete [J]. *Materials*, 2023, 16(19):6599.
- [34] Tang ZX, Litina C, Al-tabbaa A. Optimisation of rheological parameters and mechanical properties of Engineered Cementitious Composites (ECC) using regression-based models [J]. *Construction and Building Materials*, 2021, 310: 125281.
- [35] Yuan Q, Liu WT, Wang C, Deng DH, Liu ZQ, Long GC. Coupled effect of viscosity enhancing admixtures and superplasticizers on rheological behavior of cement paste [J]. *Journal of Central South University*, 2017, 24(9): 2172-2179.
- [36] Yun KK, Choi SY, Yeon JH. Effects of admixtures on the rheological properties of high-performance wet-mix shotcrete mixtures [J]. *Construction and Building Materials*, 2015, 78: 194-202.
- [37] Kim HK, Jeon JH, Lee HK. Workability, and mechanical, acoustic and thermal properties of lightweight aggregate concrete with a high volume of entrained air [J]. *Construction and Building Materials*, 2012, 29: 193-200.

UNDER PEER REVIEW