

Nanoparticles for Biomedical Science and Research

Abstract

Nanoparticles refer to clusters of a few to several thousand atoms or molecules. The term "nano" refers to their size, typically ranging from 1 to 100 nanometers; a nanometer (symbol: nm) is equal to 10^{-9} meters = 0.000 000 001 meters = 1 billionth of a meter = 1 millionth of a millimeter. According to ISO/TS 27687:2008, nanoparticles are nano-objects with three outer dimensions. "Nano" is derived from the Greek "nanos" meaning "dwarf" or "dwarfish." Nanoparticles can be composed of various substances and pose an environmental burden. Nanoparticles made of plastic, smaller than microplastics, are called nanoplastics. There are numerous potential applications for nanoparticles. They could be used to enhance various household materials. In medicine, nanoparticles could facilitate targeted drug delivery in the body or provide a gentler form of cancer therapy. Additionally, in electronics, nanoparticles could contribute to enabling more powerful and smaller computers. The significant benefits of nanoparticles have led to a drastic increase in their production and application, but it also presents a wide range of potential hazards for us and our environment. It is still unclear which nanoparticles have an impact on organisms. Ecotoxicology addresses potential hazards posed by nanoparticles during their production, use, and disposal, as nanoparticles exhibit novel chemical and physical properties.

Nanoparticle-Science-Medicine-Research

Introduction

The terms nanoparticle or nanoparticle refer to aggregates of a few to several thousand atoms or molecules. The name Nano refers to their size, which typically ranges from 1 to 100 nanometers; One nanometer (symbol: nm) is equal to 10^{-9} m = 0.000 000 001 meters = 1 billionth of a meter = 1 millionth of a millimeter. Nanoparticles are defined as nano-objects with three outer dimensions according to ISO/TS 27687:2008. "Nano" is derived from the Greek "nanos" for "dwarf" or "dwarfish". Nanoparticles can be made of different substances and pose an environmental burden. Nanoparticles made of plastic that are smaller than microplastics are called nanoplastics. There are many potential applications for nanoparticles. For example, they could be used to improve various household materials. In medicine, nanoparticles could be used to achieve targeted drug delivery in the body or a gentler form of cancer therapy. In electronics, nanoparticles could contribute to enabling more powerful and smaller computers. The high potential for benefits has led to a drastic increase in the production and use of various types of nanoparticles, but it also opens up a wide range of potential dangers for us and our environment. It is still unclear which nanoparticles have an effect on organisms. Ecotoxicology deals with possible hazards posed by nanoparticles during their production, use, and disposal, as nanoparticles exhibit novel chemical and physical properties.

Properties of nanoscale particles

Ultimately, these properties of nanoparticles are based on the extremely high surface charge seeking compensation. However, this increased reactivity limits the lifespan as "singular nanoparticles" to very short times. If targeted isolation through ion or micelle loading does not occur, charge balance occurs very quickly through agglomeration or aggregation, which can only be resolved again with correspondingly high energy inputs according to the 2nd law of thermodynamics. The lifespan of singular nanoparticles can be a criterion in risk assessment and occasionally exclude the inclusion of nanostructured materials in risk assessments. Nanoparticles exhibit special chemical and physical properties that significantly differ from those of bulk solids or larger particles. These include higher chemical reactivity due to large specific surface area (large particle surface area relative to volume), reduced influence of mass forces and increasing influence of surface forces, increasing importance of surface charge and thermodynamic effects (Brownian molecular motion), resulting in stable suspensions or aggregation and special optical properties (Najahi-Missaoui W et al. 2020). These nanoparticle properties are based on the extremely high surface charge seeking compensation. However, this increased reactivity limits the lifespan of "singular nanoparticles" to very short periods (Hendricks AR et al. 2023). Without targeted isolation through ion or micelle loading, charge balance occurs quickly through agglomeration or aggregation (e.g., through ultrasonic treatment and vortexing), which can only be resolved with correspondingly high energy inputs, according to the second law

of thermodynamics (Ali M et al. 2023, XU M et al. 2024). The lifespan of singular nanoparticles can be a criterion in risk assessment and occasionally exclude the inclusion of nanostructured materials in risk assessments (Madadi M et al. 2023).

Occurrences and Forms of Nanoparticles

Nanoparticles can enter the environment through natural means (e.g., viruses, volcanic eruptions, or anthropogenic influences, such as vehicle and industrial emissions (Jaison JP et al. 2024). Industrial soot refers to very small carbon particles that can be generated during combustion processes. Synthetic nanoparticles are artificially produced particles with new properties and/or functionalities, such as electrical conductivity and chemical reactivity (He Q et al. 2020). Synthetic nanoparticles can be classified based on their chemical and physical properties (Medina C et al. 2007). Commonly used groups in research and applications include: metal and semiconductor oxides (silicon dioxide (SiO₂), titanium dioxide (TiO₂), aluminum oxide (Al₂O₃), iron oxides (Fe₂O₃ or Fe₃O₄), zinc oxide (ZnO), as well as zeolites and other silicon-based mesoporous materials like MCM-41 or SBA-15), semiconductors (cadmium telluride (CdTe), cadmium selenide (CdSe), silicon), metals (gold (Au), silver (Ag), iron (Fe)), metal sulfides and nanoplastics (Wen J et al. 2021). Carbon-containing nanoparticles can exist in various forms like Fullerenes, single- and multi-walled nanotubes, Graphene, Nanofibers, Polymers such as dendrimers and block copolymers, industrial soot, diamond-like and onion-like carbon (Zaman M et al. 2014). Industrial soot is composed of 96–99% carbon, with the remaining portions being hydrogen, oxygen, nitrogen, and sulfur, mostly chemically bound to the surface. The oxidized groups on the pore surface have the greatest influence on the physicochemical properties of industrial soot, such as water adsorption capacity and catalytic, chemical, and electrical reactivity (Cui G et al. 2022). Mainly, basic hydroxy, acidic carboxy, as well as carbonyl and lactone groups form on the surface. During the production of active soots, functional oxygen groups with a mass fraction of up to 15% can be introduced (Mohanto S et al. 2024).

"Ultrafine Particles"

Ultrafine particles are particles with a thermodynamic diameter of less than 0.1 μm, regardless of their specific characteristics, in air quality measurements (Jaques D et al. 2014). The thermodynamic diameter describes a spherical particle with identical diffusion behavior to the particle under consideration.

Semiconductor Nanoparticles

Semiconductor nanoparticles exhibit special fluorescence properties (Chugh G et al. 2022). Similar to macroscopic semiconductors, they have a band gap, meaning that optical excitation can generate excitons (electron-hole pairs) that emit photons upon recombination, i.e., emit light in the form of fluorescence (Arick DQ et al. 2015). The energy of the photons correlates with the particle size, with the band gap increasing as the particle size decreases.

Carbon Nanotubes

Carbon nanotubes consist of cylindrical graphite layers with diameters of 1–100 nm (Kim et al. 2024). They exhibit high thermal conductivity, high tensile strength, extreme elasticity, and durability (Talkar S et al. 2018, Amreddy N et al. 2017). Depending on the structure, the electrical properties within the tube can be conductive or semiconductive.

Metals

Metallic nanoparticles have altered chemical properties compared to larger configurations of metals due to their smaller size and resulting high surface-to-volume ratio. (Feliu N et al. 2014). For example, colloidal gold exhibits stronger catalytic activity and significantly lower melting points at very small sizes. Gold, copper, silver, and other metal nanoparticles show different optical properties compared to the same metals in larger arrangements, with a broad absorption band in the visible spectrum and intense color (characteristic color of gold colloids: red to purple) (Ali M et al. 2023, Jergens E et al. 2023, Medina C et al. 2007).

Nanowater

Researchers in the United States successfully created stable nanowater droplets with a diameter of 25 nanometers using electrospray. These nanowater droplets remained stable for up to four hours due to increased surface tension compared to normal water droplets. Additionally, highly reactive oxygen radicals like hydroxyl radicals and superoxides were encapsulated in the nanodroplets, which exhibited aggressive behavior by damaging the cell membranes of airborne bacteria, leading to the term "nanobomb" for the water particles. Nanowater was considered for use as a residue-free disinfectant.

Distinction from Aerosols

Aerosol is the collective term for finely dispersed solid and liquid particles (particulates) of different sizes suspended in gases (Wang S et al. 2024, Guan K et al. 2023). The same natural laws apply to nanoparticles suspended in gas, regardless of whether they are intentionally or unintentionally generated.

Production

Various methods have been established for producing nanoparticles, categorized as Bottom-Up and Top-Down approaches, depending on whether a material is nanostructured (Top-Down) or particles are synthesized from a fluid phase.

Top-Down Methods:

- Grinding processes
- Laser ablation
- Lithographic methods such as:
 - Photolithography
 - Electron-beam lithography
 - Nano-imprint lithography

Bottom-Up Methods:

- Chemical synthesis in solutions (e.g., sol-gel method)
- Plasma synthesis using gaseous reactants, alternatively through a heated reactor (e.g., chemical vapor deposition)
- Self-organized diffusion-limited growth on surfaces or with templates (e.g., hydrothermal synthesis of nanoporous cetineites)
- Targeted nucleation of molecules from a supersaturated liquid or gas phase (Ostwald ripening or precipitation)
- Electrospinning
- Microemulsion techniques
- Solvated metal atom dispersion (SMAD)

The choice of nanoparticle production method depends on the desired particle size distribution and the chemical nature of the nanoparticles (Starsich et al. 2019). Processes in solution or self-organization typically yield the best results, but they are challenging to scale up for industrial production.

Applications

Nanoelectronics

Carbon nanotubes and semiconductor nanowires have been used to create logic circuits, potentially leading to the realization of nanocomputers (Zhang X et al.2019). Zinc oxide nanoparticles have also been demonstrated in logic circuits. Due to their transparency to electromagnetic waves in the visible spectrum, these circuits are particularly interesting for transparent electronics. Zinc oxide can also be deposited in nanoparticle form using printing processes, enabling circuit integration through printing. However, the performance is limited by the relatively low charge carrier mobility, making the components mainly suitable for low-cost/low-performance applications.

Nanomaterials

Nanoparticles are already used in the production of many products (Prajitha N et al. 2019). Concrete, for example, contains nanoscale crystals that contribute to its strength. Various cosmetic products, such as sunscreens, deodorants, and toothpaste, contain nanoparticles like titanium dioxide (TiO₂) and aluminum oxide (Al₂O₃). Nanoparticles are also added to food products. Nanocomposites are being researched for more efficient lithium-ion battery electrodes at the Nano Energy Technology Center (NETZ). Further examples include nanoparticles in paints, coatings, and surface treatments for protection against mechanical damage. Nanoparticles are also used in modern tires to reduce rolling resistance and save fuel (Khan FA et al. 2018). Additionally, nanoporous filters are being developed for improved exhaust gas cleaning in vehicles.

Disposal

There is limited experience and knowledge regarding the disposal of nanoparticles (Chen X et al. 2022). Initial studies on nanoparticle combustion showed that they mostly remain in the ash and slag during synthesis. Further research is ongoing to understand the fate of nanoparticles in water and sewage sludge (Deng H et al. 2018).

Potential Risks

The reactivity and widespread use of nanoparticles pose a broad spectrum of potential risks for human health and the environment (Sampath S et al. 2024, Daglioglu Y et al. 2018, Öztürk B et al. 2021). Studies on ecotoxicology of nanoplastics suggest that they can enter the food chain, reaching humans and animals and causing health issues (Singh D et al. 2014, Heath JR et al. 2015). Nanoplastics have been shown to damage the cell membranes of living organisms (Daglioglu Y et al. 2018, Öztürk B et al. 2021).Therefore, it is essential to assess the potential harmful nanoparticles during their production processes, especially when the direct benefits are limited. The German Federal Environment Agency recommends avoiding products with nanoparticles until their effects on the environment and human health are better understood. Studies have shown that nanoparticles can affect brain development in fetuses and lead to lung inflammation in animal models. Numerous studies highlight the potential environmental and health risks of

nanotechnologies, such as nanoparticle uptake through the respiratory system, skin, and oral ingestion. The use of nanoparticle-containing products can expose individuals to potentially harmful substances, leading to health issues. It is crucial to establish standardized methods for nanoparticle characterization and measurement to assess their safety accurately.

Conclusion

Overall, the risks associated with nanoparticles in terms of human health and the environment are still being actively researched, and caution is advised in their production, use, and disposal.

References

1. Najahi-Missaoui W, Arnold RD, Cummings BS. Safe Nanoparticles: Are We There Yet? *Int J Mol Sci.* 2020 Dec 31;22(1):385. doi: 10.3390/ijms22010385. PMID: 33396561; PMCID: PMC7794803.
2. Lewinski N, Colvin V, Drezek R. Cytotoxicity of nanoparticles. *Small.* 2008 Jan;4(1):26-49. doi: 10.1002/sml.200700595. PMID: 18165959.
3. Richards BA, Goncalves AG, Sullivan MO, Chen W. Engineering protein nanoparticles for drug delivery. *Curr Opin Biotechnol.* 2024 Apr;86:103070. doi: 10.1016/j.copbio.2024.103070. Epub 2024 Feb 13. PMID: 38354452.
4. Eilers A, Witt S, Walter J. Aptamer-Modified Nanoparticles in Medical Applications. *Adv Biochem Eng Biotechnol.* 2020;174:161-193. doi: 10.1007/10_2020_124. PMID: 32157319.
5. Hendricks AR, Williams BF, Cohen RS, Tien T, McEwen GA, Borgognoni KM, Ackerson CJ. Cloneable inorganic nanoparticles. *Chem Commun (Camb).* 2023 Jul 11;59(56):8626-8643. doi: 10.1039/d3cc01319g. PMID: 37345851; PMCID: PMC10334364.
6. Ali M. What function of nanoparticles is the primary factor for their hyper-toxicity? *Adv Colloid Interface Sci.* 2023 Apr;314:102881. doi: 10.1016/j.cis.2023.102881. Epub 2023 Mar 12. PMID: 36934512.
7. Xu M, Wei S, Duan L, Ji Y, Han X, Sun Q, Weng L. The recent advancements in protein nanoparticles for immunotherapy. *Nanoscale.* 2024 Jun 27;16(25):11825-11848. doi: 10.1039/d4nr00537f. PMID: 38814163.
8. Madadi M, Khoee S. Magnetite-based Janus nanoparticles, their synthesis and biomedical applications. *Wiley Interdiscip Rev Nanomed Nanobiotechnol.* 2023 Nov-Dec;15(6):e1908. doi: 10.1002/wnan.1908. Epub 2023 Jun 4. PMID: 37271573.
9. Jaison JP, Balasubramanian B, Gangwar J, Pappuswamy M, Meyyazhagan A, Kamyab H, Paari KA, Liu WC, Taheri MM, Joseph KS. Bioactive nanoparticles derived from marine brown seaweeds and their biological applications: a review. *Bioprocess Biosyst Eng.* 2024 Oct;47(10):1605-1618. doi: 10.1007/s00449-024-03036-x. Epub 2024 Jun 10. PMID: 38856773.
10. He Q, Wu Q, Feng X, Liao Z, Peng W, Liu Y, Peng D, Liu Z, Mo M. Interfacing DNA with nanoparticles: Surface science and its applications in biosensing. *Int J Biol Macromol.* 2020 May 15;151:757-780. doi: 10.1016/j.ijbiomac.2020.02.217. Epub 2020 Feb 20. PMID: 32088233.
11. Medina C, Santos-Martinez MJ, Radomski A, Corrigan OI, Radomski MW. Nanoparticles: pharmacological and toxicological significance. *Br J Pharmacol.* 2007 Mar;150(5):552-8. doi: 10.1038/sj.bjp.0707130. Epub 2007 Jan 22. PMID: 17245366; PMCID: PMC2189773.
12. Wen J, Moloney EB, Canning A, Donohoe E, Ritter T, Wang J, Xiang D, Wu J, Li Y. Synthesized nanoparticles, biomimetic nanoparticles and extracellular vesicles for treatment of autoimmune disease: Comparison and prospect. *Pharmacol Res.* 2021 Oct;172:105833. doi: 10.1016/j.phrs.2021.105833. Epub 2021 Aug 18. PMID: 34418563.
13. Zaman M, Ahmad E, Qadeer A, Rabbani G, Khan RH. Nanoparticles in relation to peptide and protein aggregation. *Int J Nanomedicine.* 2014 Feb 12;9:899-912. doi: 10.2147/IJN.S54171. PMID: 24611007; PMCID: PMC3928455.
14. Cui G, Su W, Tan M. Formation and biological effects of protein corona for food-related nanoparticles. *Compr Rev Food Sci Food Saf.* 2022 Mar;21(2):2002-2031. doi: 10.1111/1541-4337.12838. Epub 2021 Oct 29. PMID: 34716644.
15. Mohanto S, Biswas A, Gholap AD, Wahab S, Bhunia A, Nag S, Ahmed MG. Potential Biomedical Applications of Terbium-Based Nanoparticles (TbNPs): A Review on Recent Advancement. *ACS Biomater Sci Eng.* 2024 May 13;10(5):2703-2724. doi: 10.1021/acsbiomaterials.3c01969. Epub 2024 Apr 22. PMID: 38644798.
16. Jaque D, Martínez Maestro L, del Rosal B, Haro-Gonzalez P, Benayas A, Plaza JL, Martín Rodríguez E, García Solé J. Nanoparticles for photothermal therapies. *Nanoscale.* 2014 Aug 21;6(16):9494-530. doi: 10.1039/c4nr00708e. PMID: 25030381.
17. Chugh G, Singh BR, Adholeya A, Barrow CJ. Role of proteins in the biosynthesis and functioning of metallic nanoparticles. *Crit Rev Biotechnol.* 2022 Nov;42(7):1045-1060. doi: 10.1080/07388551.2021.1985957. Epub 2021 Oct 31. PMID: 34719294.
18. Arick DQ, Choi YH, Kim HC, Won YY. Effects of nanoparticles on the mechanical functioning of the lung. *Adv Colloid Interface Sci.* 2015 Nov;225:218-28. doi: 10.1016/j.cis.2015.10.002. Epub 2015 Oct 14. PMID: 26494653.

19. Kim J, Eygeris Y, Ryals RC, Jozić A, Sahay G. Strategies for non-viral vectors targeting organs beyond the liver. *Nat Nanotechnol.* 2024 Apr;19(4):428-447. doi: 10.1038/s41565-023-01563-4. Epub 2023 Dec 27. PMID: 38151642.
 20. Talkar S, Dhoble S, Majumdar A, Patravale V. Transmucosal Nanoparticles: Toxicological Overview. *Adv Exp Med Biol.* 2018;1048:37-57. doi: 10.1007/978-3-319-72041-8_3. PMID: 29453531.
 21. Amreddy N, Babu A, Muralidharan R, Panneerselvam J, Srivastava A, Ahmed R, Mehta M, Munshi A, Ramesh R. Recent Advances in Nanoparticle-Based Cancer Drug and Gene Delivery. *Adv Cancer Res.* 2018;137:115-170. doi: 10.1016/bs.acr.2017.11.003. Epub 2017 Dec 7. PMID: 29405974; PMCID: PMC6550462.
 22. Feliu N, Parak WJ. Developing future nanomedicines. *Science.* 2024 Apr 26;384(6694):385-386. doi: 10.1126/science.abq3711. Epub 2024 Apr 25. PMID: 38662849.
 23. Ali M. What function of nanoparticles is the primary factor for their hyper-toxicity? *Adv Colloid Interface Sci.* 2023 Apr;314:102881. doi: 10.1016/j.cis.2023.102881. Epub 2023 Mar 12. PMID: 36934512.
 24. Jergens E, de Araujo Fernandes-Junior S, Cui Y, Robbins A, Castro CE, Poirier MG, Gurcan MN, Otero JJ, Winter JO. DNA-caged nanoparticles *via* electrostatic self-assembly. *Nanoscale.* 2023 Jun 1;15(21):9390-9402. doi: 10.1039/d3nr01424j. PMID: 37184508.
 25. Medina C, Santos-Martinez MJ, Radomski A, Corrigan OI, Radomski MW. Nanoparticles: pharmacological and toxicological significance. *Br J Pharmacol.* 2007 Mar;150(5):552-8. doi: 10.1038/sj.bjp.0707130. Epub 2007 Jan 22. PMID: 17245366; PMCID: PMC2189773.
 26. Wang S, He H, Mao Y, Zhang Y, Gu N. Advances in Atherosclerosis Theranostics Harnessing Iron Oxide-Based Nanoparticles. *Adv Sci (Weinh).* 2024 May;11(17):e2308298. doi: 10.1002/advs.202308298. Epub 2024 Feb 17. PMID: 38368274; PMCID: PMC11077671.
 27. Guan K, Liu K, Jiang Y, Bian J, Gao Y, Dong E, Li Z. Nanoparticles Internalization through HIP-55-Dependent Clathrin Endocytosis Pathway. *Nano Lett.* 2023 Dec 27;23(24):11477-11484. doi: 10.1021/acs.nanolett.3c03074. Epub 2023 Dec 12. PMID: 38084909.
 28. Starsich FHL, Herrmann IK, Pratsinis SE. Nanoparticles for Biomedicine: Coagulation During Synthesis and Applications. *Annu Rev Chem Biomol Eng.* 2019 Jun 7;10:155-174. doi: 10.1146/annurev-chembioeng-060718-030203. PMID: 31173522.
 29. Zhang X, Wang F, Sheng JL, Sun MX. Advances and Application of DNA-functionalized Nanoparticles. *Curr Med Chem.* 2019;26(40):7147-7165. doi: 10.2174/0929867325666180501103620. PMID: 29714139.
 30. Prajitha N, Athira SS, Mohanan PV. Bio-interactions and risks of engineered nanoparticles. *Environ Res.* 2019 May;172:98-108. doi: 10.1016/j.envres.2019.02.003. Epub 2019 Feb 8. PMID: 30782540.
 31. Khan FA, Almohazey D, Alomari M, Almoftly SA. Impact of nanoparticles on neuron biology: current research trends. *Int J Nanomedicine.* 2018 May 9;13:2767-2776. doi: 10.2147/IJN.S165675. PMID: 29780247; PMCID: PMC5951135.
 32. Chen X, Liu Y, Liu X, Lu C. Nanoparticle-based single molecule fluorescent probes. *Luminescence.* 2022 Nov;37(11):1808-1821. doi: 10.1002/bio.4364. Epub 2022 Aug 31. PMID: 35982510.
 33. Deng H, Zhang Y, Yu H. Nanoparticles considered as mixtures for toxicological research. *J Environ Sci Health C Environ Carcinog Ecotoxicol Rev.* 2018 Jan 2;36(1):1-20. doi: 10.1080/10590501.2018.1418792. Epub 2018 Jan 9. PMID: 29313413.
 34. Sampath S, Sunderam V, Manjusha M, Dlamini Z, Lawrance AV. Selenium Nanoparticles: A Comprehensive Examination of Synthesis Techniques and Their Diverse Applications in Medical Research and Toxicology Studies. *Molecules.* 2024 Feb 9;29(4):801. doi: 10.3390/molecules29040801. PMID: 38398553; PMCID: PMC10893520.
 35. Singh D, McMillan JM, Kabanov AV, Sokolsky-Papkov M, Gendelman HE. Bench-to-bedside translation of magnetic nanoparticles. *Nanomedicine (Lond).* 2014 Apr;9(4):501-16. doi: 10.2217/nnm.14.5. PMID: 24910878; PMCID: PMC4150086.
 36. Heath JR. Nanotechnologies for biomedical science and translational medicine. *Proc Natl Acad Sci U S A.* 2015 Nov 24;112(47):14436-43. doi: 10.1073/pnas.1515202112. PMID: 26598663; PMCID: PMC4664315.
-
37. **DAĞLIOĞLU, Y, ÖZKAN YILMAZ H:** Ekotoksisite Deneylerinde Nanopartikül Karakterizasyonunun Öneme Yöntemleri. *Marmara Fen Bilimleri Dergisi*, 30(1), 1-17.
 38. Daglioglu Y: Desmodemus multivariabilis' in bor partiküllerine maruz kalmada biyolojik birikiminin değerlendirilmesi. *Biological Diversity and Conservation*, 9(3), 204-209.
 39. Daglioglu, Y, Yavuz MC, Ertürk O, Ameen F, Khatami, M: Investigation of cell damage of periodontopathic bacteria exposed to silver, zirconium oxide, and silicon oxide nanoparticles as antibacterial agents. *Micro & Nano Letters*, 18(9-12), e12178.
 40. Ozturk B. Y., DAĞLIOĞLU Y.: Extracellular synthesis of silver nanoparticles using Cladophora sp. and its antimicrobial activity effects on lipid peroxidation and antioxidant activities of extracts. *Fresenius Environmental Bulletin*, 30(06B), 7422-7432.

41. Daglioglu Y, Öztürk B: Green Synthesis of Silver Nanoparticles Using *Mandragora autumnalis*; Its Characterization, Antioxidant and Antimicrobial Activities. *Erzincan University Journal of Science and Technology*, 14(3), 1039-1054.
42. Daglioglu Y, Türkis S: The comparative toxicity of nano and micro boron particles to freshwater microalga (*Desmodesmusmultivariabilis*): the importance of particles size. *Fresenius Environmental Bulletin*, 27(12), 9602-9610.
43. Öztürk B, NANOTEKNOLOJİ İLE KARSİNOGENEZ SÜRECİNDE miRNA'LARIN ROLÜ VE PROFİLENMESİ. *Türk BilimselDerlemelerDergisi*, 15(1), 86-114.

ACKNOWLEDGEMENTS: none

AUTHOR CONTRIBUTIONS

SB wrote the manuscript

FUNDING: none

COMPETING INTERESTS

The author declares no competing interests.

ETHICS APPROVAL: none

ADDITIONAL INFORMATION: none

DISCLAIMER (ARTIFICIAL INTELLIGENCE)

Author(s) hereby declare that NO generative AI technologies such as Large Language Models (ChatGPT, COPILOT, etc.) and text-to-image generators have been used during the writing or editing of this manuscript.