

Original Research Article

Green synthesis and characterization of Silver Nanoparticles synthesized using *Piper longum* and its antioxidant activity

Running title: Synthesize of *Piper longum* based silver nanoparticle and to analyse its antioxidant activity.

Abstract:

Introduction: *Piper longum*, a traditional plant used for regenerative medicine commonly known as the long pepper, is used to treat many pathological conditions. *Piper longum* is used as a source for obtaining the production of various nanoparticles and testing their efficacy. *Piper longum* has many beneficial activities, such as antifungal, anti-amoebic, anti-asthmatic, anti-cancer, anti-oxidant, anti-inflammatory, antidepressant, activities. The beneficial activities of *Piper longum* include antioxidant properties which have the ability to treat chronic conditions. The chemical nature of these constituents is the ability to produce antioxidant activity. Nanoparticles are minute particles that range from 1 to 100 nm on a nanometer scale. Different nanoparticles possess different properties; they vary in physical and chemical nature. Silver nanoparticles are widely and commonly used for the conduction of electricity, have a localized resonance effect on the surface plasmon, and have a wide range of antimicrobial activity against various microorganisms. The most important method used to synthesize silver nanoparticles involves the chemical method because of the nature of the silver nanoparticles which have the ease to simply dissolve in the prepared aqueous solution.

Material and methods: *Piper longum* plant extract was prepared and silver nanoparticles extract was synthesized. DPPH assay was then performed to assess the free radical scavenging activity of the *Piper longum* silver nanoparticle extract. The further analysis was that the formation of brownish-red color observed was evident, resulting in the synthesis of silver nanoparticles.

Results: Brown discoloration represents formation of silver nanoparticles and the antioxidant activity was noted to be from 60% to 70% from 10 to 50 μ L. But when compared to standard vitamin C values the *Piper longum* silver nanoparticles showed less antioxidant activity.

Conclusion: The *Piper longum* mediated silver nanoparticles showed remarkable and considerable antioxidant activity but when compared with the standard sample values the antioxidant activity was low.

Key words: Antioxidant, Innovative technique, eco-friendly, green synthesis, *Piper longum*

Introduction:

Piper longum, a traditional plant used for regenerative medicine commonly known as the long pepper, is used to treat many pathological conditions¹. Various substitutes that are derived from *Piper longum*, one of the most important derivatives, is piperine. It's used to treat diarrhea, chronic bronchitis, stomach pain, asthma, hepatitis, and other respiratory insufficiencies. Advanced technology implying the use of nanoparticles in biomedical research, is gaining its agenda, incorporating almost all natural materials as sources². Drug delivery is the most common use of nanoparticles in the current technological application.

Piper longum is used as a source for obtaining the production of various nanoparticles and testing their efficacy. *Piper longum* possesses various pharmacologically beneficial activities, such as insecticide and acaricidal, anti-fungal, anti amoebic, anti-asthmatic, anti-cancer, anti-oxidant, anti-inflammatory, antidepressants, antiulcer activities on routine consumption³⁻⁵. The fruit of the *Piper longum* has hepatoprotective activity⁶. It is considered as an ayurvedic medicine providing enough treating ability to boost up the immune system to fight against various pathological disorders.

Piperlongumine, sesamin, and sylvatin are important phytoconstituents of *Piper longum*⁷. The chemical nature of these constituents is the ability to produce antioxidant activity. Nanoparticles are minute particles that range from 1 to 100 nm on a nanometer scale. Different nanoparticles possess different properties; they vary in physical and chemical nature. Nanotechnology is now widely used for synthesizing drugs in the pharmaceutical industry. Formulation of nanoparticles, nanospheres, nanocapsules, nanoemulsion, and nanosuspensions are few applications of nanotechnology in the field of nanomedicine. The most common synthesized nanoparticles are plasmonic silver and gold because they possess unique physical and chemical properties when compared to other large surface areas and have strong electronic properties⁸.

Nanoparticles are physically and chemically altered to have high potency to act upon the biological cell structure of the body^{9,10}. Silver nanoparticles are widely and commonly used for the conduction of electricity¹¹. They also have a localized resonance effect on the surface plasmon and have a wide range of antimicrobial activity against various microorganisms¹². The synthesis of silver nanoparticles involves 3 complex methods, they include physical synthesis, chemical synthesis, and biological synthesis¹³. The most important method used to synthesize silver nanoparticles involves the chemical method because of the nature of the silver nanoparticles which have the ease to simply dissolve in the prepared aqueous solution¹⁴. Silver nanoparticles are commonly used in nanotechnology¹⁵. Antioxidant activity is generally stated as prevention of oxidation of various constituents of the body, thus substances that tend to possess antioxidant activity which will block the oxidation of protein, DNA, and lipids present in our body.

An antioxidant prevents the formation of free radicals and their storage in tissues thus helps to prevent tissue depletion^{16,17}. Various naturally occurring plant sources and their products have antioxidant properties, which depresses and overcomes the oxidative stress caused by free radicals¹⁸. The beneficial activities of *Piper longum* include antioxidant properties which have the ability to treat chronic conditions¹⁶. Our team has extensive knowledge and research experience that has translated into high quality publications¹⁹²⁰⁻³³³⁴⁻³⁸,³⁴⁻³⁸. Thus

the aim of this study is to green synthesize and characterize the silver nanoparticles using *Piper longum* plant extract and to observe its antioxidant capacity.

Materials and methods:

Preparation of plant extract:

Commercially available dry powder of *Piper longum* was used for this experiment. This experiment was an in vitro study which was conducted in Saveetha Dental College, Chennai, Tamilnadu. The experiment was carried out by dissolving 1g of *Piper longum* powder in 100ml of water. The mixture was then boiled in a heating mantle at 70 degrees celsius for up to 10 minutes. The boiled mixture was then filtered using a Whatman number 1 filter paper to obtain the plant extract. Then 40 ml of plant extract was measured using a measuring cylinder and the mixture was added to 60ml of 1 mM silver nitrate (0.0169g) dissolved in 60ml distilled water. The lab technician reconfirmed the synthesized *Piper longum* silver nanoparticles to avoid sampling error for further analysis. The further analysis was that the formation of brownish-red color observed was evident, resulting in the synthesis of silver nanoparticles.

Reagent and Chemicals :

1g of *Piper longum* powder

1 mM silver nitrate (0.0169g)

2-10 µg/ml concentration of *Piper longum* extract at various concentrations (10 µL, 20 µL, 30 µL, 40 µL, and 50 µL)

0.1 mM DPPH in methanol

50 mM of tris HCl buffer

Control: BHT: Butylated hydroxytoluene

Antioxidant activity:

Piper longum was the plant used to determine the antioxidant activity by taking only 5 samples in distinct test tubes and adding 10 µL, 20 µL, 30 µL, 40 µL, and 50 µL of the solution respectively using a micropipette. The micropipette usage was dealt with care to avoid methodology error. Random sampling method was performed to eliminate sampling bias and the validation of the procedure was done by principal investigator and by experts in nanotechnology. Other plants and activities were not tested in this present study.

To check the antioxidant activity, a DPPH assay was used to test the antioxidant activity of biogenic synthesized silver nitrate nanoparticles. Diverse concentrations (2-10 µg/ml) of

Piper longum leaf extract interceded silver nitrate nanoparticle was mixed with 1 ml of 0.1 mM DPPH in methanol and 450 µl of 50 mM of Tris HCl buffer (pH 7.4) and incubated for 30 minutes. Later, the reduction in the quantity of DPPH free radicals was assessed dependent on the absorbance at 517 nm. BHT was employed as control. The percentage of inhibition was determined from the following equation:

$$\% \text{ Inhibition} = \frac{\text{Absorbance of control} - \text{Absorbance of sample}}{\text{Absorbance of control}} \times 100$$

The percentage of Inhibition was then calculated and correlated with the standard vitamin C concentration values which were not performed. And the antioxidant activity was correlated using Spearman's correlation in SPSS software version 23.0, the correlation graph was then represented and the p value was less than 0.05 for the non parametric correlation analysis proving statistical significance.

Results:

The optical observation of the experiment was determined using a UV-visible spectrum providing the characterization of the prepared silver particles. The formation and synthesis of silver nanoparticles were determined by the brownish-yellow discoloration shown in **Figure 1**. The corresponding formation of silver nanoparticles is shown in peaks at 517nm in **Figure 4** of the UV spectrophotometer graph. The presence of the surface plasmon resonance was the reason for the color change of the solution. Silver nanoparticles are formed by the reaction between the plant extract and the silver ions. Only potential plants are able to synthesize nanoparticles thus the change in color of the solution acts as a primary identification tool. The DPPH assay performed to test the antioxidant activity of the synthesized *Piper longum* silver nanoparticles is shown on **Figure 2**.

Table 1 shows the percentage of inhibition of the synthesized *Piper longum* silver nanoparticles was noted to be 61.2%, 64.5%, 66.1%, 67.4% and 69.3% at 10 µL, 20 µL, 30 µL, 40 µL and 50 µL respectively and where as the values of the standard vitamin C solution are 76.5%, 78.8%, 84.9%, 89.2% and 92.3% at 10 µL, 20 µL, 30 µL, 40µL and 50µL respectively. The correlation analysis performed using SPSS version 23.0 and is shown in **Figure 3**. There is a positive correlation between the concentration of the sample prepared and percentage of inhibition. Thus the antioxidant activity is increasing with increased concentration of the synthesized silver nanoparticles.




Figure 1: The colour change indicates the synthesis of silver nanoparticles after 72 hrs and its corresponding correlation of the UV spectroscopy (figure 4).




Figure 2: Antioxidant activity of the silver nanoparticles using the plant extract and the colour change is noted.

Percentage of Inhibition (%)		
Concentration (μL)	Silver nitrate nanoparticles	Standard
10 μL	61.2%	76.5%
20 μL	64.5%	78.8%
30 μL	66.1%	84.9%
40 μL	67.4%	89.2%
50 μL	69.3%	92.3%

Table 1: The percentage of Inhibition for the different concentrations of the silver nanoparticles (ranging from 10 μL to 50 μL) in comparison with the standard.




Figure 3: Antioxidant activity of silver nanoparticles. The X-axis represents the concentration of the silver nanoparticles and standard solution and the Y-axis represents the percentage of inhibition. Graph representing the percentage of inhibition observed with the different concentrations ranging from 10 μL to 50 μL in comparison to the standard value, the correlation was found to be positive using spearman's correlation. And the non-parametric correlation was found with P value less than .05 proving statistically significance.




Figure 4: The UV/Visible spectrum of the silver nanoparticles synthesized using the *Piper longum* plant leaf extract.




Figure 5: The line graph represents the comparative observation of the antioxidant activity of *Piper longum* AgNPs (blue) and the standard solution antioxidant activity (green). The X-axis represents the concentration of the silver nanoparticles and standard solution and the Y-axis represents the percentage of inhibition. The correlation was found to be positive using Spearman's correlation. And the non-parametric correlation was found with P value less than .05 proving statistical significance.

Discussion:

The present study investigates the optical observation which is the initial and novel technique that reveals the characterization of the synthesized silver nanoparticles as it presents a result of the UV- visible absorption spectra. **Figure 1** shows the brownish-yellow discoloration indicative of the formation of the silver nanoparticles. The silver nanoparticle formation showed significant color change because of the occurrence of the surface plasmon resonance³⁹⁴⁰. As the color change serves as a primary tool, this is useful in the detection of the potential plants for the synthesis of silver nanoparticles.

The colour change in the prepared solution is correlated with its UV spectrophotometer graph in **Figure 4**, in which the peak of the synthesized *Piper longum* solution with silver nanoparticles production is 517 nm. Similar studies show that the prepared nanoparticles accompanied with the respective natural plant components used in assessing its antioxidant activity was comparative⁴¹⁴². The synthesis and production of the chosen nanoparticles are believed to have formed at the range of 400-520 nm in a UV visible spectrophotometer graph⁴³. So compatible values of the UV spectrophotometer graph reveals the silver nanoparticle produced in 48 hrs.

2,2-diphenyl-1-picrylhydrazyl is an organic chemical compound which stands as the full form of DPPH, it is an assay performed to determine the antioxidant that is the free radical scavenging activity of a substance⁴⁴. So the DPPH assay was performed to observe the antioxidant activity of the synthesized silver nanoparticles in this present study. **Figure 2** shows the antioxidant activity of the newly synthesized silver nanoparticles using the plant extract of *Piper longum*. **Figure 3** represents the bar graph which represents the comparison between the percentage of inhibition between the silver nanoparticles synthesized and the standard solution. **Figure 5** represents the line graph version of the already displayed bar graph of the results in **table1**.

In comparison to various works conducted by different authors, the study conducted by S.N Kharat⁴⁵ the DPPH assay scavenging ability was in a purely dose-dependent manner, the scavenging property at 50 μL was 15.23% which was the lowest concentration whereas when compared to the present study the antioxidant activity was 61.2% at the lowest concentration that is at 10 μL shown in **Figure 3** which represents a correlation analysis. The work conducted by Rajeshkumar³⁹ also concluded that the free radical scavenging activity was concentration dependent as well. Keshari⁴⁶ concluded in study that AgNPs have the scavenging property of more than 29% stating its high free radical scavenging activity. Comparing works of DPPH radical scavenging with the work done by Zdenka⁴⁷ states that the activity is more than 89% at the highest concentration being 50 μL .

Opposing work conducted by⁴⁸ without the involvement of nanoparticles showed that there is potential antioxidant activity exhibited by the synthesized *Piper longum* extract. The *Piper* species are accountable and known for their reduction of oxidative stress which makes them a good source of an antioxidant substance. They are successfully used to treat Alzheimer's disease and Parkinson's disease which are common disorders affecting the central nervous system⁴⁹.

Generally the silver nanoparticles are remarkable for its significant antioxidant activity⁵⁰, they also show numerous beneficial activities such as antimicrobial^{51,52} and anti-inflammatory⁵³, so silver nanoparticles are of the most commonly used metal nanoparticles in nanomedicine⁵⁴. So silver nanoparticles play a crucial role in nanomedicine involving nano technological advances and also for biomedicine using genetic engineering⁵⁵. The use of silver nanoparticles made the present study economical, less cost effective, and easily available⁵⁶. But not so on the bright side, recent researchers have found that silver nanoparticles consumption has caused some adverse effects on human metabolism. The toxic adverse effects include suppressing activity of the cell growth, division and multiplication⁵⁷, which was found to be in a pure concentration consumption and exposure manner.

The present study was based on the silver nanoparticles having the property of possessing equally accessible antioxidant activity when compared to the standard scavenging property of the vitamin C solution⁵⁸. Vitamin C was chosen for this present study from the other two free radical scavenging vitamins that are A and E because of the slightly higher values of the antioxidant activities shown by them on various biomedical facilities⁵⁹. Vitamin C free radical scavenging property is due to its capacity to donate an electron which provides the basic properties of a vitamin which is potent enough to show strong antioxidant activity. An antioxidant thus works by preventing the oxidation of the cells and tissues present in the human body and thereby neutralizing the free radicals produced⁶⁰. Substances which possess strong antioxidant activity have a great potential to treat and cure many high risk human

metabolic problems like atherosclerosis and cardiovascular disorders ⁶¹. In vitro studies have clearly ruled out the antioxidant activity of vitamin c in biological systems ⁶².

The present study deals with the comparison of the prepared *Piper longum* plant extract nanoparticles with standard Vitamin C values which shows significant values of free radical scavenging property. But the plant extract nanoparticle prepared had less antioxidant activity than the standard values. **Table 1** shows clear and accurate values of the antioxidant activity of the two solutions used to check its antioxidant activity.

Limitations of the present study were less sample size taken for the study, different plants could be taken as they all show different antioxidant capacity and other beneficial properties. Only antioxidant activity of the *Piper longum* plant was assessed, and the specification in using silver nanoparticles may also be limitations of the study. Value changes may be formed due to errors in experiment performance.

According to the present study conducted, the free radical scavenging property of the prepared *Piper longum* plant extract silver nanoparticles was from an average range of 60% to 70% of the antioxidant activity. The maximum antioxidant activity was shown at the highest concentration that is at 50 μ L it showed nearly 70% of inhibition. Thus the prepared *Piper longum* silver nanoparticles have good antioxidant activity and can be potentially used in nanomedicine to treat various biological conditions. The future scope of this study is the properties of synthesizing nanoparticles which are further implied in nanotechnology which may be useful for nanomedicine, biomedicine and other sourcing fields. Furthermore research works are needed to potentiate the various aspects of the use of nanoparticles in different fields.

Conclusion:

The *Piper longum* mediated silver nanoparticles show remarkable and considerable antioxidant activity when compared with the standard values of vitamin C. The potential free radical scavenging property of the plant leaves extract mediated silver nanoparticles, is applicable in nanomedicine through the help of advanced technologies to support the medical voided fields. The properties of the synthesized nanoparticles are further implied in nanotechnology which may be useful for other sourcing fields. Further research studies are required to assess the full potential of the plant mediated nanoparticles.

References:

1. Kumar S, Kamboj J, Suman, Sharma S. Overview for various aspects of the health benefits of Piper longum linn. fruit. *J Acupunct Meridian Stud.* 2011Jun;4(2):134–40.
2. Khushbu C, Roshni S, Anar P, Carol M, Mayuree P, Others. Phytochemical and therapeutic potential of Piper longum Linn a review. *International journal of research in Ayurveda and pharmacy.*2011;2(1):157–61.
3. Zaveri M, Khandhar A, Patel S, Patel A. Chemistry and pharmacology of Piper longum L. *Internationaljournalofpharmaceuticalsciencesreviewandresearch.*2010;5(1):67–76.
4. Brundha MP. A Comparative Study-The Role of Skin and Nerve Biopsy in Hansen's Disease. *Res J Pharm Biol Chem Sci.*2015;7(10):837.
5. Brundha MP, Pathmashri VP, Sundari S. Quantitative Changes of Red Blood cells in Cancer Patients under Palliative Radiotherapy-A Retrospective Study. *Research Journal of Pharmacy and Technology.*2019;12(2):687–92.
6. Jalalpure SS, Patil MB, Prakash NS, Hemalata K, Manvi FV. Hepatoprotective activity of the fruits of piper longum linn. *Indian J Pharm Sci.*2003;65(4):363.
7. Reddy NJ, Nagoor Vali D, Rani M, Rani SS. Evaluation of antioxidant, antibacterial and cytotoxic effects of green synthesized silver nanoparticles by Piper longum fruit. *Mater Sci Eng C Mater Biol Appl.* 2014 Jan1;34:115–22.
8. Alaqad K, Saleh TA. Gold and silver nanoparticles: Synthesis methods, characterization routes and applications towards drugs. *J Environ Anal Toxicol [Internet].* 2016;6(4). Available from:<http://dx.doi.org/10.4172/2161-0525.1000384>
9. Mendoza KC, McLane VD, Kim S, Griffin JD. In vitro application of gold nanoprobe in live neurons for phenotypical classification, connectivity assessment, and electrophysiological recording. *Brain Res.* 2010 Apr14;1325:19–27.
10. Timothy CN, Samyuktha PS, Brundha MP. Dental pulp Stem Cells in Regenerative Medicine--A Literature Review. *Research Journal of Pharmacy and Technology.* 2019;12(8):4052–6.
11. Chernousova S, Epple M. Silver as antibacterial agent: ion, nanoparticle, and metal. *Angew Chem Int Ed Engl.* 2013 Feb4;52(6):1636–53.
12. Shen J, Shi M, Li N, Yan B, Ma H, Hu Y, et al. Facile synthesis and application of Ag-chemically converted graphene nanocomposite. *NanoRes.*2010May1;3(5):339–49.
13. Rajeshkumar S, Malarkodi C. In Vitro Antibacterial Activity and Mechanism of Silver Nanoparticles against Foodborne Pathogens. *Bioinorg Chem Appl.* 2014 Sep 17;2014:581890.
14. Yu J, Zhou X. Synthesis of Dendritic Silver Nanoparticles and Their Applications as SERS Substrates. *Advances in Materials Science and Engineering [Internet].* 2013 Dec 17 [cited 2021 Feb 15];2013. Available from:<http://dx.doi.org/10.1155/2013/519294>

15. Karthiga P, Rajeshkumar S, Annadurai G. Mechanism of Larvicidal Activity of Antimicrobial Silver Nanoparticles Synthesized Using *Garcinia mangostana* Bark Extract. *J Cluster Sci.* 2018 Nov1;29(6):1233–41.
16. McCune LM. Traditional medicinal plants of indigenous peoples of Canada and their antioxidant activity in relation to treatment of diabetes. *Bioactive Food as Dietary Interventions for Diabetes: Bioactive Foods in Chronic Disease States.* 2012;221.
17. Harsha L, Brundha MP. Prevalence of Dental Developmental Anomalies among Men and Women and its Psychological Effect in a Given Population. *Journal of Pharmaceutical Sciences and Research; Cuddalore.* 2017 Jun20;9(6):869–73.
18. Rajeshkumar S. Anticancer activity of eco-friendly gold nanoparticles against lung and liver cancer cells. *J Genet Eng Biotechnol.* 2016 Jun;14(1):195–202.
19. Anita R, Paramasivam A, Priyadharsini JV, Chitra S. The m6A readers YTHDF1 and YTHDF3 aberrations associated with metastasis and predict poor prognosis in breast cancer patients. *Am J Cancer Res.* 2020 Aug1;10(8):2546–54.
20. Jayaseelan VP, Paramasivam A. Emerging role of NET inhibitors in cardiovascular diseases. *Hypertens Res.* 2020 Dec;43(12):1459–61.
21. Sivakumar S, Smiline Girija AS, Vijayashree Priyadharsini J. Evaluation of the inhibitory effect of caffeic acid and gallic acid on tetR and tetM efflux pumps mediating tetracycline resistance in *Streptococcus* sp., using computational approach. *Journal of King Saud University - Science.* 2020 Jan1;32(1):904–9.
22. Smiline Girija AS. Delineating the Immuno-Dominant Antigenic Vaccine Peptides Against gacS-Sensor Kinase in *Acinetobacter baumannii*: An in silico Investigational Approach. *Front Microbiol.* 2020 Sep8;11:2078.
23. Iswarya Jaisankar A, Smiline Girija AS, Gunasekaran S, Vijayashree Priyadharsini J. Molecular characterisation of csgA gene among ESBL strains of *A. baumannii* and targeting with essential oil compounds from *Azadirachta indica*. *Journal of King Saud University - Science.* 2020 Dec1;32(8):3380–7.
24. Girija ASS. Fox3+ CD25+ CD4+ T-regulatory cells may transform the nCoV's final destiny to CNS! *J Med Virol* [Internet]. 2020 Sep 3; Available from: <http://dx.doi.org/10.1002/jmv.26482>
25. Jayaseelan VP, Ramesh A, Arumugam P. Breast cancer and DDT: putative interactions, associated gene alterations, and molecular pathways. *Environ Sci Pollut Res Int.* 2021 Jun;28(21):27162–73.
26. Arumugam P, George R, Jayaseelan VP. Aberrations of m6A regulators are associated with tumorigenesis and metastasis in head and neck squamous cell carcinoma. *Arch Oral Biol.* 2021 Feb;122:105030.
27. Kumar SP, Girija ASS, Priyadharsini JV. Targeting NM23-H1-mediated inhibition of tumour metastasis in viral hepatitis with bioactive compounds from *Ganoderma lucidum*: A computational study. *pharmaceutical-sciences* [Internet]. 2020;82(2). Available from: <https://www.ijpsonline.com/articles/targeting-nm23h1-mediated-inhibition-of-tumour->

metastasis-in-viral-hepatitis-with-bioactive-compounds-from-ganoderma-lucidum-a-comp-3883.html

28. Girija SA, Priyadharsini JV, Paramasivam A. Prevalence of carbapenem-hydrolyzing OXA-type β -lactamases among *Acinetobacter baumannii* in patients with severe urinary tract infection. *Acta Microbiol Immunol Hung*. 2019 Dec9;67(1):49–55.
29. Priyadharsini JV, Paramasivam A. RNA editors: key regulators of viral response in cancer patients. *Epigenomics*. 2021Feb;13(3):165–7.
30. Mathivadani V, Smiline AS, Priyadharsini JV. Targeting Epstein-Barr virus nuclear antigen 1 (EBNA-1) with *Murrayakoengii* bio-compounds: An in-silico approach. *Acta Virol*. 2020;64(1):93–9.
31. Girija As S, Priyadharsini J V, A P. Prevalence of Acb and non-Acbcomplex in elderly populationwithurinarytractinfection(UTI).*ActaClinBelg*.2021Apr;76(2):106–12.
32. Anchana SR, Girija SAS, Gunasekaran S, Priyadharsini VJ. Detection of *csgA* gene in carbapenem-resistant *Acinetobacter baumannii* strains and targeting with *Ocimum sanctum* biocompounds. *Iran J Basic Med Sci*. 2021May;24(5):690–8.
33. Girija ASS, Shoba G, Priyadharsini JV. Accessing the T-Cell and B-Cell Immuno-Dominant Peptides from *A.baumannii* Biofilm Associated Protein (bap) as Vaccine Candidates: A Computational Approach. *Int J Pept Res Ther*. 2021 Mar1;27(1):37–45.
34. Arvind P TR, Jain RK. Skeletally anchored forsus fatigue resistant device for correction of Class II malocclusions-A systematic review and meta-analysis. *OrthodCraniofac Res*. 2021 Feb;24(1):52–61.
35. Venugopal A, Vaid N, Bowman SJ. Outstanding, yet redundant? After all, you may be another *Choluteca* Bridge! *Semin Orthod*. 2021 Mar1;27(1):53–6.
36. Ramadurai N, Gurunathan D, Samuel AV, Subramanian E, Rodrigues SJL. Effectiveness of 2% Articaine as an anesthetic agent in children: randomized controlled trial. *Clin Oral Investig*. 2019Sep;23(9):3543–50.
37. Varghese SS, Ramesh A, Veeraiyan DN. Blended Module-Based Teaching in Biostatistics and Research Methodology: A Retrospective Study with Postgraduate Dental Students. *J Dent Educ*. 2019Apr;83(4):445–50.
38. Mathew MG, Samuel SR, Soni AJ, Roopa KB. Evaluation of adhesion of *Streptococcus mutans*, plaque accumulation on zirconia and stainless steel crowns, and surrounding gingival inflammation in primary molars: randomized controlled trial [Internet]. Vol. 24, *Clinical Oral Investigations*. 2020. p. 3275–80. Available from: <http://dx.doi.org/10.1007/s00784-020-03204-9>
39. Rajeshkumar S. Antioxidant activity of characterized silver nanoparticles synthesized using flower extracts of *Chrysanthemum indicum*. *Res J Biotechnol*. 2017;12(8):38–43.
40. Rajeshkumar S, Bharath LV. Mechanism of plant-mediated synthesis of silver nanoparticles - A review on biomolecules involved, characterisation and antibacterial activity. *Chem Biol Interact*. 2017 Aug1;273:219–27.

41. Maillard M-N, Soum M-H, Boivin P, Berset C. Antioxidant Activity of Barley and Malt: Relationship with Phenolic Content. *LWT - Food Science and Technology*. 1996 May 1;29(3):238–44.
42. Miliauskas G, van Beek TA, Venskutonis PR, Linssen JPH, de Waard P, Sudhölter EJR. Antioxidant activity of *Potentilla fruticosa* [Internet]. Vol. 84, *Journal of the Science of Food and Agriculture*. 2004. p.1997–2009. Available from: <http://dx.doi.org/10.1002/jsfa.1914>
43. Miller NJ, Rice-Evans CA. Spectrophotometric determination of antioxidant activity. *Redox Rep*. 1996 Jun;2(3):161–71.
44. Dizhbite T, Telysheva G, Jurkane V, Viesturs U. Characterization of the radical scavenging activity of lignins—natural antioxidants. *Bioresour Technol*. 2004 Dec 1;95(3):309–17.
45. Kharat SN, Mendhulkar VD. Synthesis, characterization and studies on antioxidant activity of silver nanoparticles using *Elephantopus scaber* leaf extract. *Materials Science and Engineering: C*. 2016;719–24.
46. Keshari AK, Srivastava R, Singh P, Yadav VB, Nath G. Antioxidant and antibacterial activity of silver nanoparticles synthesized by *Cestrum nocturnum*. *J Ayurveda Integr Med*. 2020 Jan;11(1):37–44.
47. Bedlovičová Z, Strapáč I, Baláž M, Salayová A. A Brief Overview on Antioxidant Activity Determination of Silver Nanoparticles. *Molecules* [Internet]. 2020 Jul 13;25(14). Available from: <http://dx.doi.org/10.3390/molecules25143191>
48. Chaudhary SK, Mukherjee PK, Maiti N, De AK, Bhadra S, Saha BP. Evaluation of Angiotensin converting enzyme inhibition and anti-oxidant activity of *Piper longum* L. 2013; Available from: <http://nopr.niscair.res.in/handle/123456789/19446>
49. Karthikeyan J, Rani P. Enzymatic and non-enzymatic antioxidants in selected *Piper* species. *Indian J Exp Biol*. 2003 Feb;41(2):135–40.
50. Abou El-Nour KMM, Eftaiha A, Al-Warthan A, Ammar RAA. Synthesis and applications of silver nanoparticles. *Arabian Journal of Chemistry*. 2010 Jul 1;3(3):135–40.
51. Rajeshkumar S. Phytochemical constituents of fucoidan (*Padina tetrastromatica*) and its assisted AgNPs for enhanced antibacterial activity. *IET Nanobiotechnol*. 2017 Apr;11(3):292–9.
52. Kundara R. SYNTHESIS OF SILVER NANOPARTICLES BY EXTRACT OF NEEM (*AZADIRACHTA*), TULSI (*OCIMUM TENUIFLORUM*) AND MINT (*MENTHA*) LEAVES USING2020;
53. Mani AKM, Seethalakshmi S, Gopal V. Evaluation of in-vitro anti-inflammatory activity of silver nanoparticles synthesised using *piper nigrum* extract. *J Nanomed Nanotechnol*. 2015;6(2):1.
54. Ankamwar B, Damle C, Ahmad A, Sastry M. Biosynthesis of gold and silver nanoparticles using *Embllica Officinalis* fruit extract, their phase transfer and transmetallation in an organic solution. *J Nanosci Nanotechnol*. 2005 Oct;5(10):1665–71.

55. Midha K, Singh G, Nagpal M, Arora S. Potential Application of Silver Nanoparticles in Medicine. *Nanoscience & Nanotechnology-Asia*.2016;6(2):82–91.
56. Ahmad N, Sharma S, Alam MK, Singh VN, Shamsi SF, Mehta BR, et al. Rapid synthesis of silver nanoparticles using dried medicinal plant of basil. *Colloids Surf B Biointerfaces*. 2010 Nov1;81(1):81–6.
57. Parveen K, Banse V, Ledwani L. Green synthesis of nanoparticles: Their advantages and disadvantages. *AIP Conf Proc*. 2016 Apr13;1724(1):020048.
58. Bosetti M, Massè A, Tobin E, Cannas M. Silver coated materials for external fixation devices: invitro biocompatibility and genotoxicity. *Biomaterials*.2002Feb;23(3):887–92.
59. Padayatty SJ, Katz A, Wang Y, Eck P, Kwon O, Lee J-H, et al. Vitamin C as an antioxidant: evaluation of its role in disease prevention. *J Am Coll Nutr*.2003Feb;22(1):18–35.
60. Mittal AK, Kaler A, Banerjee UC. Free Radical Scavenging and Antioxidant Activity of Silver Nanoparticles Synthesized from Flower Extract of *Rhododendron dauricum*. *Nano Biomed Eng*.2012;4(3).
61. Fotherby MD, Williams JC, Forster LA, Craner P, Ferns GA. Effect of vitamin C on ambulatory blood pressure and plasma lipids in older persons. *J Hypertens*. 2000 Apr;18(4):411–5.
62. Asard H, May J, Smirnoff N. *Vitamin C: Its Functions and Biochemistry in Animals and Plants*. Taylor & Francis; 2004. 344p.