

## **REVIEW ON POLYMERIC NANOPARTICLES FOR IMPROVE BIOAVAILIBLTY OF LESS WATER SOLUBLE DRUG**

### **Abstract:**

In this review study about the polymeric nanoparticles and how polymer based nanoparticles increase bioavailability of less water soluble drugs. Polymeric nanoparticles have a matrix of biodegradable and biocompatible polymers of synthetic and natural origin. Polymer based nanoparticles are very useful for increase the solubility of the poor water-soluble drugs by decrease the particles size. Polymeric nanoparticles are very useful for targeting the drug to the specific site. Polymeric nanoparticles are also used to maintain and control the release of the drug. In present review study on the type of polymer used for the preparation of the polymer based nanoparticles. The choice of method depends on a number of factors, such as, particles size, area of application and characterization of polymeric nanoparticles.

### **Keywords**

Nanosphere or Nano capsules, natural and synthetic polymer, solvent evaporation method, zeta potential

### **Introduction**

Nanotechnology is the advanced technology used in the research area. In this technology impressive development in the medical field and used various technology for formulate the nanoparticles with according to requirement<sup>1</sup>. For preparing the polymeric nanoparticles the material are used to enhance the physiochemical features of the drug. Due to Nano size of nanoparticles, nanoparticles the surface area larger than macro-sized material. Nanotechnology used in the developments in the field of biosensor, biomedicine and bio Nano technology<sup>2</sup>.

### **Challenges come in oral drug delivery system**

Various factors that are affect oral drug delivery system. Oral drug delivery system are suitable for drugs with greater water solubility and permeability. But now a day most new compounds are currently lipophilic and therefore low water solubility.<sup>3</sup> A number of new therapeutically bodies are characterised by the BCS classification system. BCS class 2 (low water solubility and high permeability) and BCS class 4 (low water solubility and low permeability) drug have low water solubility and number of barrier are present in GIT which are reduce the pharmacological effect of the drug. Various enzymes present in the GIT and pH of the GIT also affect the bioavailability of the drug. Due to change in the pH and presence of the enzyme in the GIT influence the oral bioavailability of many drugs.<sup>4</sup>

Various Reasons for poor oral bioavailability of water insoluble drugs

- Poor aqueous solubility
- Degradation in GIT track

- First pass metabolism
- Insufficient time for absorption
- Inappropriate partition coefficient
- Insufficient time for absorption

To overcome these problems nanotechnology are developed. In present review study about polymeric nanoparticles used to enhance oral bioavailability of the less water soluble drug by using many type of polymer or study the different method used for preparation of the polymer based nanoparticles.<sup>5</sup>

### **Polymer based nanoparticles**

UNDER PEER REVIEW

The solid colloidal particles are come in size from 1 nm to 1000nm are called polymeric nanoparticles. In this type of technology the drug is dissolved, enclosed or attached into matrix of nanoparticles. The surface of these structures is very large. Polymer is very useful in pharmaceutical for preparing the macro and small size molecules.<sup>6</sup> Polymeric nanoparticles consist of natural polymer (e.g., gelatine, chitosan etc.) which are biodegradable and biocompliment, or synthetic polymers (e.g., poly lactides, poly acryl cyano acrylates etc.).

The choice of material for polymeric nanoparticles is determined by the factors below.

- Particle Size and surface features required
- Drug and other active ingredients solubility and stability
- Biodegradability standard
- Biocompatibility and toxicity
- Required profile of drug release<sup>6</sup>

### **Types of Polymeric nanoparticles are:**

Nanosphere

Nanocapsule

#### **Nano capsules**

Nano capsule are the reservoir systems. In this system drug is entrapped in unique polymer membrane.

#### **Nanosphere**


Nanosphere is matrix systems. In this system drug is dispersed in polymeric matrix.<sup>6</sup>

For preparation of polymer based nanoparticles two main strategies are used such as

- Top-down approach
- Bottom-up approach.

In top-down approach polymeric nanoparticles are developed by dispersion of the polymer.

In the bottom-up approach polymer based nanoparticles are developed by polymerization of monomers.



**Fig No.1 Explain Top-down approach and Bottom-up approach.**

Selection of the suitable method used for the preparation of the polymeric nanoparticles depend on the various factors, such as

- Particle size of drug
- Type of solvent
- Type of Polymer
- Application area

Monomer used in Molecular inclusion as their starting point for “bottom-up” process to formulate polymer based nanoparticles.

**Stabilizing agent used for the preparation**

- Poly (vinyl alcohol)
- Di-decyl di-methyl ammonium bromide

**Organic solvents used for the preparation**

- Dichloromethane
- Ethyl acetate
- Acetone

Organic solvent produces toxic effects. So, In the recent study use alternative are used they are less toxic.<sup>7</sup>

**Advantages**

- Polymer based Nanoparticles are more effective for targeting drug in specific site.
- Polymer based nanoparticles are useful for controlled and sustained release of the drug.
- It is helpful to increase the stability of any volatile agents.

UNDER PEER REVIEW

- It has more benefits in term of quality than conventional oral methods of administration.
- The choice of polymer and their ability to regulate release of medicine from polymer based nanoparticles have made it suitable for cancer treatment, vaccine delivery, contraception and supply of selective antibiotics.

## **Method used for preparation of polymer based nanoparticles according to type of polymer based nanoparticles**

Methods used for the preparation of the polymer based nanoparticles according to the type of drug and rout of drug administration. For the processing of the particles various type of method is used, mainly two strategies are such as

- Diffusion of performed polymer
- Polymerization of monomers

In all methods use performing polymers and organic solvent used for firstly dissolve the polymer. But organic solvent produces toxic effect and environment risk. So, the solvent residue removes for the final product. When the drug loads to the polymeric nanoparticles, methods depend on the polymerization of the monomer and permit the addition with larger effectiveness and in one single step. Method of preparation not employed carefully then the product is converted to the aqueous colloidal suspension.

### **Nano spheres**

- Solvent evaporation method
- Solvent diffusion
- Nano precipitation
- Reverse salting out

### **Nanocapsule**

- Nano precipitation


### **Solvent evaporation**

The oldest process used for polymeric nanoparticles preparation was solvent evaporation. Nanoparticles made from the performed polymer in this process. In this method firstly prepare oil with the water emulsion form (O/W).After that prepare nanosphere.<sup>8,9</sup>

### **Steps involved in solvent evaporation**

- Prepared organic phase by the use of the polar organic solvent polymer are dissolved in this solvent.
- After that add the drug by dissolution or dispersion.
- Acetone used as a solvent.<sup>10</sup>
- But they are toxic so they are replaced by ethyl acetate.<sup>11</sup>
- Ethyl acetate show better toxicological profile so they are used biomedical applications<sup>12</sup>
- Aqueous phase prepared with the surfactant such as polyvinyl acetate(PVA)<sup>11</sup>
- Add drop by drop organic phase in aqueous phase
- This emulsion has been split into nanodroplets by applying exterior energy during sonication.
- For remove the solvent by evaporating the solvent by magnetic stirring at 300 rpm under atmospheric condition for 2 hours.<sup>13</sup>
- After removing the solvent lyophilization done for dry the liquid sample


- Then evaluate the formulation.



**Fig.No.2 Graphical representation of solvent evaporation method**

## Solvent Diffusion


- In this method is modification method of the emulsification / reverse salt process.
- In this technique, first prepare an oil in water type emulsion of the polymer and drug with water soluble solvent and aqueous solution with a surfactant<sup>14,15</sup> In this type emulsion the internal phase consists the hydro-organic solvent and this solvent saturated with water and both phases are thermodynamically equilibrium of the two phases at room temperature.<sup>16</sup>
- When dilution done with the great amount of the water, after diffusion of solvent colloidal particles, diffuse the solvent from the dispersed droplets to external phase after diffusion of the solvent colloidal particles are formed.
- Nan sphere are formed by this method and Nano capsules can also be formulated by this method but if the small amount of oil.
- In final step boiling of the organic solvent are avoided by evaporation and filtration.<sup>17</sup> After filtration and evaporation nanoparticles are obtained dimensions range from 80 to 900 nm.
- In current study this technology is used for the development of the polymeric nanoparticles by use of high volume of aqueous phase. And risk of diffusion of the hydrophilic drug into aqueous phase are avoided by must be removed from the colloidal dispersion.<sup>18,19</sup>



**Fig No.3 Graphical representation of solvent diffusion method**

### Reverse Salting-Out


- In this technique water soluble solvent are separate from an aqueous solution by salting out effect so this method is useful for the development of the nanosphere<sup>20</sup>
- In this process O / W emulsion composition is different because the water-mixable polymers solvent are used.
- Add salting out agent and colloidal stabilizer in aqueous phase.<sup>21</sup>
- Salting out agents are
  - ◆ Magnesium chloride ( $MgCl_2$ )
  - ◆ Calcium chloride ( $CaCl_2$ )
  - ◆ Magnesium acetate ( $Mg(CH_3COO)_2$ )
  - ◆ Non-electrolytes, e.g., sucrose.<sup>22</sup>
- Acetone and water miscibility are decrease by aqueous phase saturation that permits an O/W emulsion are formed from the other miscible phase.<sup>23</sup>
- O/W type emulsion produced by intense agitation at room temperature.
- After that emulsion was diluted to permit for dispersion of organic solvent in other stage by a suitable voltage of deionized water or an aqueous solution.
- The precipitating polymer and therefore production of nanosphere.
- The remaining solvent and salting agent is separated by filtration.
- The condition is not required but simplify the execution process between organic solvent and water.<sup>20,24</sup>
- The dimensions of nanosphere obtained with this technique range from 170 to 1000 nm.
- Standard size can be modified between 200 and 500 nm by adjusting the inner phase polymer concentration /outer phase length<sup>25</sup>



**Fig.No.4 Graphical representation of reverse salting out method**

## Nano precipitation

- In this approach two miscible solvent are required, this approach is also known as solvent displacement method.
- Acetone or acetonitrile are a mixable organic solvent and polymer dissolve in this solvent<sup>26-30</sup>
- They are easily removed by the evaporation due to the insolubility with water. <sup>31</sup>
- The polymer dissolved in water-soluble polarity solvent and this solution has to applied with continue stirring by controlled rate in an aqueous solution.
- Nanoparticles are obtained after the diffusion of the polymer in aqueous phase<sup>31</sup>
- When solvent dispersed from the Nano droplets then Nano capsule and nanosphere are formed in the form of polymer precipitates.<sup>32</sup>
- In the phase, Surfactants may be used to make sure the stability of colloidal suspension, but existence of the surfactant is not needed to confirm the production of nanoparticles.
- Nanoparticles are getting by this technique they are usually described in definite size and small size distribution.
- This method is very good method as compare to other evaporation technique of the emulsifying solvent<sup>33</sup>
- In current study Nano precipitation is extremely helpful method for formation of polymeric nanoparticles in size range 170 nm in size<sup>34</sup>
- This method is used for the formation of nanosphere or Nano capsules<sup>34</sup>



**Fig No.5 Graphical representation of Nanoprecipitation method**

## Characterization of Polymer based Nanoparticles

Physical properties of polymer based nanoparticles are different such as

- Arrangement
- Strength
- Size
- Shape
- Surface properties
- Crystallinity
- Dispersion state.

They are the most commonly used method<sup>3536</sup>

## Morphology

Electron microscope used for study about the size of particle and shape of polymeric nanoparticles.

Scanning and transmission electron type microscope mostly used for determine particles size and shape.

- For study about size and shape of the polymeric nanoparticles are determine by use of Scanning or transmission electron microscope.
- Scanning Electron Microscope used for find out Particles surface morphology of formulation by descriptions a sample by scanning.
- In this technique greater energy beam of electrons used.
- Electron interacts by the atom and produce the signal this signal consists the information regarding the sample's surface topography, composition or other features for example electrical conductivity.

- SEM technology is very important for study structure of the sample because of very small electron beam providing three-dimensional features.
- Transmission electron microscope is also used for differentiate the nano capsule and nanosphere because they are able to measure the thickness of wall of the Nanocapsule.<sup>11</sup>

UNDER PEER REVIEW

- Atomic force microscopy is also used for describe surface morphology of polymeric Nanoparticles <sup>37</sup>
- AFM give the three-dimension information with high resolution.<sup>38</sup>
- This approach has been used to observe complex topography on surface of nanoparticles, though small cavities and pores are also found in the sample analysis.<sup>25</sup>

## Particle Size Distribution

- Different techniques are used for development of the polymeric nanoparticles in different particle size range.
- Particles diameters ranging between 60 to 70 nm. <sup>39</sup>
- Nanoparticles size can be considered using many approaches for example:
  - Dynamic light scattering (DLS)
  - Static light scattering (SLS),
  - TEM, SEM and AFM <sup>40</sup>
  - For example, electron microscopy produces an image of particle separated from surrounding areas, while DLS enables hydrodynamic radius of suspended particles to be determined volume measurements can differ based on the process used.
  - In addition , DLS is main accompaniment to TEM because it can calculate more volumes by detecting changes in the distribution of particles size by providing information about the aggregation in solution<sup>40,41</sup>

## Polymer molar mass distribution

Molar mass distribution of polymer is studied behind the preparation this method helpful for study effect of formulation component on polymerization method and chemical reaction between drug and polymer information about the degradation of polymer<sup>42</sup>

- Size -exclusion chromatography is common technique used for study the polymer mass distribution.<sup>43</sup>
- The strength of light extend by polymeric NPs are analyzed by static light scattering. <sup>41</sup>

## Surface Area and Chemistry

- Various methods measure various surface aspects. Direct measurement of surface area of nanoparticles uses adsorption to create single layer of gas coverage like N<sub>2</sub> under varied pressure
- The total surface area is the total area in relation to number of gas molecules essential to form a single layer as well as cross-sectional region of gas molecule absorbed.<sup>44</sup>

## Zeta Potential

Zeta potential is useful for study surface charge between particles. Zeta potential of polymeric nanoparticles is useful for study surface charge of nanoparticles. They are produced electrical potential in particles and is affected by arrangement of nanoparticles and the medium in which itself-dispersed <sup>45</sup>. If the zeta potential reaches (+/-) 30 mV then the suspension means that surface charge prevent accumulation of the particles.<sup>46</sup> The suspension is stable because surface charge prevents aggregation of particles. Zeta potential is useful in deciding loaded active material is encapsulated or adsorbed on surface inside Nanocapsule center. Zeta sizer provides full sensitivity, precision and zeta potential resolution ever. Also very low mobility can be evaluated and distributions of mobility measured.

- Stability of emulsion
- Stability of formulation

- Pigment functioning
- To determine the Impurity

Table 1: The zeta potential limits for colloids in water

UNDER PEER REVIEW

| Stability                     | Range                |
|-------------------------------|----------------------|
| Fast clotting or flocculation | 0 to $\pm 5$         |
| Volatility Incipient          | $\pm 10$ to $\pm 30$ |
| Mild stability                | $\pm 30$ to $\pm 40$ |
| Good stability                | $\pm 40$ to $\pm 60$ |
| Excellent stability           | Over $\pm 60$        |

Potentiality of the zeta represents the surface load of the particles due to changes in interface with dispersing medium breakdown of functional groups on surface of particles and ionic adsorption there in aquatic medium and solvent effect<sup>45</sup> the zeta potential is determined from electrophoretical movability of particles in their respective solvent<sup>46-48</sup>

## Suspensions pH

The pH can be tracked as a function of the time to obtained relevant information on nanoparticles stability. The pH shift, For example, can show a deterioration of polymers suggesting changes in protons on the surface of the particles. Decrease of Molar mass confirmed after 6 months of storage in Nanocapsule and Nanocapsule suspension with the resulting decrease in pH However, in the short period of time, the decrease in the pH of the suspensions may be due, depending on polymeric water power to carboxylic groups in polymer and release of protons in surrounding medium. Furthermore, the pH of the medium may have an effect on zeta potential and electrostatic stability of solution, and monitoring it is of great importance.<sup>17</sup>

## Stability of Polymeric NPs Suspensions

- The sedimentation process for sub micrometric particles, typically not separated until few month of preparation is sluggish and even reduced by Brownian movement.
- However, agglomeration of particles and sediments can take place over time<sup>49</sup>
- A number the stable colloidal suspensions may have effect, for example on the nanoparticles surface adsorption of active molecules and existence of absorbed surfactants.
- Various physiological parameters are important for stability of polymer based nanoparticles.<sup>50</sup>
- In these nanoparticles, concentrated solution of medicines and adsorption phenomena are preserve due to problems of low physiochemical stability and longer storage periods.<sup>51</sup>
- The principle limitations include the aggregation of particles, the chemical stability of the polymer. Furthermore, the need to add preservative in Oder to postpone or to prevent such physicochemical and micro biological problem typically involves the drying process<sup>52</sup>.
- In Freeze-drying removing of water by sublimation, generally used for drying nanosphere, while spray drying is an alternative to lyophilizing, in Oder to improve stability of solid lipid nanoparticles, it consists of transferring the solution into drying chamber through an orifice of atomized atom, with hot counter-current or mixed air co-flow, which favors the quick droplet drying.<sup>53</sup>
- The separated and collect dry solid particles are formed in form powder, granules and agglomerates<sup>54,55</sup>

## Study about the Drug Association

Study about the quantity of active ingredient related with nanoparticles is especially difficult due to its small size, which make it hard to distinguish active ingredient from the relevant fraction<sup>56</sup> Ultracentrifugation is well used system of separation, where free drug in suspension is calculated after centrifugation. Dissolution is helpful for determine total drug concentration is typically determined into an acceptable solvent of a fraction of the nanoparticles. The nanoparticles active substance concentration is then determined difference

between the total concentration and free active substance concentration<sup>57,58</sup> the ultra filtration centrifugation, where the membrane is used to isolate a section of aqueous phase from colloidal suspension, is also a tool that has been used. The free active ingredient concentration is estimated in the ultra filtrate, and also by subtract total and free levels of the active substance fraction associated with the nanostructure<sup>57</sup>.

UNDER PEER REVIEW

- Various factors can influence the amount of drug in nanostructure systems according to published studies such as:
  - ❖ The drugs Physiochemical properties
  - ❖ The medium pH value
  - ❖ Properties of the NP surface or type of polymer,
  - ❖ The Amount of drugs used in the formulation, <sup>59,60</sup>
- It is possible to get unlike drug association rates with the same initial drug concentration by changing particle surface properties, via adsorption.
- In determining capability to extend the drug action time, this parameter is very important.
- The adsorption isotherm on the surface of nanoparticles should also be calculated, since it offers details about the distribution of the material on the surfaces of the particles and how related power is the drug has different type of nanosphere interaction <sup>60</sup> the drug has different type of nanosphere interaction, which can be dissolving or dispersed in polymer matrix or adsorbed on polymer.
- Nanocapsule is developed to improve the loading of lipophilic active substances that should be found in an oily core polymer membrane dissolved.
- Since then it is also becoming a complex method to evaluate the mode of associated with nanoparticles is determined by the available method.
- Therefore only comparable studies of the capacity of zeta potential, release profile, division of the molar mass, studies of adsorption, and rate of drug association with nanostructures. <sup>61</sup>

### **Pharmaceutical In Vitro Release Kinetics**

Discharge of drugs from polymeric Nanopartilces is determined by following factors<sup>62,63</sup> Various experimental techniques for determining kinetics in vitro release of a drug entangled in nanoparticles:

- a) Artificial or biological membranes side by side diffusion cell
- b) Dialysis bag distribution method
- c) Reverse dialysis sac system
- d) Ultracentrifugation
- e) Ultra filtration
- f) Centrifugal Ultra filtration method <sup>64</sup>

**Release rate of entrapped medicine affected by different factors. Release of medicine depends on:**

- 1 Polymer based nanoparticles structure
- 2 Polymer Type and length of polymer
- 3 Degradation or erosion

The kinetics of nanosphere release from drug are typically exponential perhaps due to dispersion of drug from polymeric matrix to its surrounding atmosphere. <sup>62,65</sup> For Nano capsules the medicinal substance supposedly dissolved in oil nucleus will be released by diffusion Nano capsules and Nano emulsion related drug release profile suggested a polymeric surface of the Nanocapsule.

UNDER PEER REVIEW

The Ecotoxicology division was identified in 1969 as " toxicology branch in an integral sense research into the field of Ecotoxicology progress fastly because environment toxic waste from quick industrial development, which include toxicology, which produces natural and synthetic pollutants, in terms of ecosystem, animals ( including human) plant and microbe component.<sup>66</sup>Ecotoxicology testing evolved quickly because of environmental contamination caused by rapid industrial development<sup>67,68</sup> In 1989 Nanoecotoxicology means the toxicological effects of nanoparticles can produced on human beings and natural organisms when released into the environment <sup>67</sup>Humans and animals exposure to nanoparticles-based substance has been developed mainly for the purpose of marine toxicology people need to determine their possible environmental risk before these particles can be used for different products that can enter the atmosphere, considering the more awareness about natural and synthetic nanoparticles. The toxicity of non material to environmental organism currently has little knowledge that restricts the risk assessment of nonmaterial's in quantitative sense.<sup>48</sup>

### **Challenges in research in Nanoecotoxicology**

In 2008, a Behra and Krug publication in part on nature Nanotechnology identify three key issues that to need to solve these issues in few years <sup>67</sup>

- The selection of nanoparticles in experiments and biological tests for the identification of nanoparticles before, during and after the experiments it is important to determined the physical or chemical properties, aggregation and sedimentation ability.
- Manner in which species in various ecosystems accumulate synthetic nanoparticles must be investigated.
- Collection of species for use of experiments and measurement points.

### **In Vitro and Vivo Toxicological Studies**

This system has consisted of various advantages and they are providing stable formulation. In this type drug delivery system different active ingredient are encapsulated. But in this system nanotoxicity are produced and unexpected toxic effects are occurred. <sup>69</sup> Toxological and response profile of the nanoparticles are proved in suitable animal modal. In this modal represent the pathophysiology of human disorder.<sup>70</sup> The main characteristics of the polymeric nanoparticles is Biocompatibility, biodegradability and non-toxicity<sup>69,71,72</sup> Polymeric nanoparticles are useful for to improve the bioavailability and they are safe for human being. They are stable and contain the ability to encapsulate a number of substances. In current study biodegradable and non-biodegradable polymeric carriers are used for oral drug delivery system<sup>73</sup>.For example curcumin loaded polymeric nanoparticles used for oral drug delivery system are used they provide 5-6-fold more oral bioavailability than pure curcumin<sup>73</sup>.Polymeric nanogels have also been shown to show a minimal toxicity, serum stabilization and stimulus reactivity, as they are highly encapsulated, tunable size are obtained. So, the surface image of topical administration polystyrene NPs ex vivo studies have shown aggregation of NPs in the follicular openings, are commonly used in biomimetic material and biosensors, drug delivery, tissue engineering. <sup>71,72</sup>the transdermal drug delivery system can assess the first pass metabolism effect thus less drug use can be effectively used with less toxicity<sup>74</sup>.Researcher spoke about biomimetic methods such as cell-membrane camouflage and the creation of stubborn Nano supply systems<sup>75</sup>.Polymeric NPs are difficult to use as chemotherapeutic systems as there is low circulation stability and targeting inefficiency. Biocompatible and biodegradable pH reactive hybrid NPs has been achieved to solve these problems. These Nano structure based on the PLGA nucleus, have been protected by a cross linked bovine serum albumin shell. <sup>76</sup>

Presently, the effect of polymeric nanoparticles is important in medicine. So, it is very important clinical use of the drugs is controlled because the components are toxic in nature and polymers are used, they are

biodegradable so they excrete by common metabolic pathways <sup>77</sup>The toxic effect of the components is screened for study the toxicity <sup>78</sup>

**Nanotechnology used for enhance the bioavailability of poorly water soluble drug**

UNDER PEER REVIEW

The onset of action of water insoluble drugs are slow, less oral bioavailability, Drugs with low solubility, be short of dose proportionality, lack of stable plasma concentration, and unwanted side effects are studied. Due to poor water solubility result poor patient compliance The conventional dosage forms can therefore result in over or medication and poor patient compliance.<sup>79</sup> So, overcome these challenges by using novel drug delivery. In this review study about the polymeric nanoparticles and how prepare polymeric nanoparticles. PNs are useful for reduce the dose frequency; reduce the dose size, site specific targeting, enhanced permeability, and improvement in oral bioavailability. Polymeric nanoparticles are the type nanotechnology is a capable approach in the development of drug delivery systems especially for those potent drugs whose clinical development failed due to their poor solubility, low permeability, inadequate bioavailability, and other poor biopharmaceutical properties. The present review provides a information about the polymeric nanoparticles.<sup>5</sup>

## Conclusions

The objective of this review is obtained the information about the technology used for preparing the polymeric nanoparticles for enhance the bioavailability of the poorly water soluble drugs and gives the knowledge about the use of ingredients such as polymer, co-surfactant, surfactant, solvent used for the preparation. In this review various researcher are focus on the physiochemical properties of the polymeric nanoparticles so researches study the difficulty are come for study the Nano size of the particles. The physiochemical properties of the drug are characterized by many combined analytical method and obtained the various method used for characterization of the polymeric nanoparticles and obtained the list of the polymer are used for the preparing the polymeric nanoparticles.

## References

1. Abhilash M. Potential applications of nanoparticles. *International Journal of Pharma and Bio Sciences*. 2010;1(1).
2. Bagul R, Mahajan V, Dhake A. New Approaches in Nanoparticulate Drug Delivery System - a Review. *Current Pharmaceutical Research*. 2012;4(3):29-38.
3. Delmar K, Bianco-Peled H. Composite chitosan hydrogels for extended release of hydrophobic drugs. *Carbohydrate Polymers*. 2016;136:570-580. doi:10.1016/j.carbpol.2015.09.072
4. Gupta H, Bhandari D, Sharma A. Recent Trends in Oral Drug Delivery: A Review. *Recent Patents on Drug Delivery & Formulation*. 2009;3(2):162-173. doi:10.2174/187221109788452267
5. Sharma M, Sharma R, Jain DK. Nanotechnology Based Approaches for Enhancing Oral Bioavailability of Poorly Water Soluble Antihypertensive Drugs. *Scientifica*. 2016;2016. doi:10.1155/2016/8525679
6. Jawahar N, Meyyanathan S. Polymeric nanoparticles for drug delivery and targeting: A comprehensive review. *International Journal of Health & Allied Sciences*. 2012;1(4):217. doi:10.4103/2278-344x.107832
7. Material N, Singh N. Polymer Nanoparticles Learn more about Polymer Nanoparticles Drug delivery : advancements and chal- lenges Sustainable Delivery Systems Through Green Nanotechnology. Published online 2017.
8. Desgouilles S, Vauthier C, Bazile D, et al. The Design of Nanoparticles Obtained by Solvent Evaporation: A Comprehensive Study. *Langmuir*. 2003;19(22):9504-9510. doi:10.1021/la034999q
9. Vieira, Souto, Sánchez-López, et al. Sugar-Lowering Drugs for Type 2 Diabetes Mellitus and Metabolic Syndrome—Review of Classical and New Compounds: Part-I. *Pharmaceuticals*.

2019;12(4):152. doi:10.3390/ph12040152

10. Grumezescu AM. *Nanobiomaterials in Cancer Therapy: Applications of Nanobiomaterials.*; 2016. doi:10.1016/C2015-0-00383-5

UNDER PEER REVIEW

11. Bohrey S, Chourasiya V, Pandey A. Polymeric nanoparticles containing diazepam: Preparation, optimization, characterization, in-vitro drug release and release kinetic study. *Nano Convergence*. 2016;3(1):3. doi:10.1186/s40580-016-0061-2
12. Zandanel C, Legouffe R, Trochon-Joseph V, et al. Biodistribution of polycyanoacrylate nanoparticles encapsulating doxorubicin by Matrix-Assisted Laser Desorption Ionization (MALDI) Mass Spectrometry Imaging (MSI). *Journal of Drug Delivery Science and Technology*. 2018;47:55-61. doi:10.1016/j.jddst.2018.06.023
13. Sharma N, Madan P, Lin S. Effect of process and formulation variables on the preparation of parenteral paclitaxel-loaded biodegradable polymeric nanoparticles: A co-surfactant study. *Asian Journal of Pharmaceutical Sciences*. 2016;11(3):404-416. doi:10.1016/j.ajps.2015.09.004
14. Kumar S, Dilbaghi N, Saharan R, Bhanjana G. Nanotechnology as Emerging Tool for Enhancing Solubility of Poorly Water-Soluble Drugs. *BioNanoScience*. 2012;2(4):227-250. doi:10.1007/s12668-012-0060-7
15. Souto EB, Souto SB, Campos JR, et al. Nanoparticle Delivery Systems in the Treatment of Diabetes Complications. *Molecules*. 2019;24(23):4209. doi:10.3390/molecules24234209
16. Souto EB, Severino P, Santana MHA. Preparação de Nanopartículas Poliméricas a partir da Polimerização de Monômeros - Parte I. *Polimeros*. 2012;22(1):96-100. doi:10.1590/S0104-14282012005000006
17. Guterres SS, Alves MP, Pohlmann AR. *Polymeric Nanoparticles, Nanospheres and Nanocapsules, for Cutaneous Applications*. Vol 2.; 2007. doi:10.33393/DTI.2007.1300
18. Quintanar-Guerrero D, Allémann E, Doelker E, Fessi H. Preparation and characterization of nanocapsules from preformed polymers by a new process based on emulsification-diffusion technique. *Pharmaceutical Research*. 1998;15(7):1056-1062. doi:10.1023/A:1011934328471
19. Vasile C. Polymeric Nanomaterials: Recent Developments, Properties and Medical Applications. In: *Polymeric Nanomaterials in Nanotherapeutics*. Elsevier; 2018:1-66. doi:10.1016/B978-0-12-813932-5.00001-7
20. Wang Y, Li P, Truong-Dinh Tran T, Zhang J, Kong L. Manufacturing Techniques and Surface Engineering of Polymer Based Nanoparticles for Targeted Drug Delivery to Cancer. *Nanomaterials*. 2016;6(2):26. doi:10.3390/nano6020026
21. Lim K, Hamid ZAA. Polymer nanoparticle carriers in drug delivery systems: Research trend. In: *Applications of Nanocomposite Materials in Drug Delivery*. Elsevier; 2018:217-237. doi:10.1016/B978-0-12-813741-3.00010-8
22. Pinto Reis C, Neufeld RJ, Ribeiro AJ, Veiga F. Nanoencapsulation I. Methods for preparation of drug-loaded polymeric nanoparticles. *Nanomedicine: Nanotechnology, Biology, and Medicine*. 2006;2(1):8-21. doi:10.1016/j.nano.2005.12.003
23. Vauthier C, Bouchemal K. Methods for the Preparation and Manufacture of Polymeric Nanoparticles. *Pharmaceutical Research*. 2009;26(5):1025-1058. doi:10.1007/s11095-008-9800-3
24. Mahalingam M, Krishnamoorthy K. Selection of a suitable method for the preparation of polymeric nanoparticles: Multi-criteria decision making approach. *Advanced Pharmaceutical Bulletin*. 2015;5(1):57-67. doi:10.5681/apb.2015.008
25. Crucho CIC, Barros MT. Polymeric nanoparticles: A study on the preparation variables and characterization methods. *Materials Science and Engineering C*. 2017;80:771-784. doi:10.1016/j.msec.2017.06.004

26. Araújo J, Vega E, Lopes C, Egea MA, Garcia ML, Souto EB. Effect of polymer viscosity on physicochemical properties and ocular tolerance of FB-loaded PLGA nanospheres. *Colloids and Surfaces B: Biointerfaces*. 2009;72(1):48-56. doi:10.1016/j.colsurfb.2009.03.028

UNDER PEER REVIEW

27. Cañadas C, Alvarado H, Calpena AC, et al. In vitro, ex vivo and in vivo characterization of PLGA nanoparticles loading pranoprofen for ocular administration. *International Journal of Pharmaceutics*. 2016;511(2):719-727. doi:10.1016/j.ijpharm.2016.07.055
28. Sánchez-López E, Egea MA, Cano A, et al. PEGylated PLGA nanospheres optimized by design of experiments for ocular administration of dexibuprofen-in vitro, ex vivo and in vivo characterization. *Colloids and Surfaces B: Biointerfaces*. 2016;145:241-250. doi:10.1016/j.colsurfb.2016.04.054
29. Sánchez-López E, Egea MA, Davis BM, et al. Memantine-Loaded PEGylated Biodegradable Nanoparticles for the Treatment of Glaucoma. *Small*. 2018;14(2):1701808. doi:10.1002/sml.201701808
30. Sánchez-López E, Ettcheto M, Egea MA, et al. Memantine loaded PLGA PEGylated nanoparticles for Alzheimer's disease: In vitro and in vivo characterization. *Journal of Nanobiotechnology*. 2018;16(1):32. doi:10.1186/s12951-018-0356-z
31. Salatin S, Barar J, Barzegar-Jalali M, Adibkia K, Kiafar F, Jelvehgari M. Development of a nanoprecipitation method for the entrapment of a very water soluble drug into Eudragit RL nanoparticles. *Research in Pharmaceutical Sciences*. 2017;12(1):1. doi:10.4103/1735-5362.199041
32. Martínez Rivas CJ, Tarhini M, Badri W, et al. Nanoprecipitation process: From encapsulation to drug delivery. *International Journal of Pharmaceutics*. 2017;532(1):66-81. doi:10.1016/j.ijpharm.2017.08.064
33. Bilati U, Allémann E, Doelker E. Nanoprecipitation versus emulsion-based techniques or the encapsulation of proteins into biodegradable nanoparticles and process-related stability issues. *AAPS PharmSciTech*. 2005;6(4):E594-E604. doi:10.1208/pt060474
34. Chidambaram M, Krishnasamy K. Modifications to the conventional nanoprecipitation technique: An approach to fabricate narrow sized polymeric Nanoparticles. *Advanced Pharmaceutical Bulletin*. 2014;4(2):205-208. doi:10.5681/apb.2014.030
35. Silva AM, Alvarado HL, Abrego G, et al. In Vitro Cytotoxicity of Oleanolic/Ursolic Acids-Loaded in PLGA Nanoparticles in Different Cell Lines. *Pharmaceutics*. 2019;11(8):362. doi:10.3390/pharmaceutics11080362
36. Carbone C, Martins-Gomes C, Pepe V, et al. Repurposing itraconazole to the benefit of skin cancer treatment: A combined azole-DDAB nanoencapsulation strategy. *Colloids and Surfaces B: Biointerfaces*. 2018;167:337-344. doi:10.1016/j.colsurfb.2018.04.031
37. Andreani T, Kiill CP, De Souza ALR, et al. Effect of cryoprotectants on the reconstitution of silica nanoparticles produced by sol-gel technology. *Journal of Thermal Analysis and Calorimetry*. 2015;120(1):1001-1007. doi:10.1007/s10973-014-4275-4
38. Mathurin J, Pancani E, Deniset-Besseau A, et al. How to unravel the chemical structure and component localization of individual drug-loaded polymeric nanoparticles by using tapping AFM-IR. *Analyst*. 2018;143(24):5940-5949. doi:10.1039/c8an01239c
39. Hickey JW, Santos JL, Williford JM, Mao HQ. Control of polymeric nanoparticle size to improve therapeutic delivery. *Journal of Controlled Release*. 2015;219:536-547. doi:10.1016/j.jconrel.2015.10.006
40. Brar SK, Verma M. Measurement of nanoparticles by light-scattering techniques. *TrAC - Trends in Analytical Chemistry*. 2011;30(1):4-17. doi:10.1016/j.trac.2010.08.008
41. Carvalho PM, Felício MR, Santos NC, Gonçalves S, Domingues MM. Application of light scattering techniques to nanoparticle characterization and development. *Frontiers in Chemistry*. 2018;6:237.

doi:10.3389/fchem.2018.00237

42. Doncom KEB, Blackman LD, Wright DB, Gibson MI, O'Reilly RK. Dispersity effects in polymer self-assemblies: A matter of hierarchical control. *Chemical Society Reviews*. 2017;46(14):4119-4134. doi:10.1039/c6cs00818f

UNDER PEER REVIEW

43. Stals PJM, Gillissen MAJ, Paffen TFE, et al. Folding polymers with pendant hydrogen bonding motifs in water: The effect of polymer length and concentration on the shape and size of single-chain polymeric nanoparticles. *Macromolecules*. 2014;47(9):2947-2954. doi:10.1021/ma500273g
44. Comba P. *Structure and Function*. Vol 1.; 2010. doi:10.1007/978-90-481-2888-4
45. Honary S, Zahir F. Effect of zeta potential on the properties of nano-drug delivery systems - A review (Part 1). *Tropical Journal of Pharmaceutical Research*. 2013;12(2):255-264. doi:10.4314/tjpr.v12i2.19
46. Zielińska A, Ferreira NR, Feliczak-Guzik A, Nowak I, Souto EB. Loading, release profile and accelerated stability assessment of monoterpenes-loaded solid lipid nanoparticles (SLN). *Pharmaceutical Development and Technology*. 2020;25(7):832-844. doi:10.1080/10837450.2020.1744008
47. Ostolska I, Wisniewska M. Application of the zeta potential measurements to explanation of colloidal Cr<sub>2</sub>O<sub>3</sub> stability mechanism in the presence of the ionic polyamino acids. *Colloid and Polymer Science*. 2014;292(10):2453-2464. doi:10.1007/s00396-014-3276-y
48. Doktorovová S, Santos DL, Costa I, Andreani T, Souto EB, Silva AM. Cationic solid lipid nanoparticles interfere with the activity of antioxidant enzymes in hepatocellular carcinoma cells. *International Journal of Pharmaceutics*. 2014;471(1-2):18-27. doi:10.1016/j.ijpharm.2014.05.011
49. González AE. Colloidal Aggregation Coupled with Sedimentation: A Comprehensive Overview. In: *Advances in Colloid Science*. InTech; 2016. doi:10.5772/65699
50. Kamiya H, Gotoh K, Shimada M, et al. CHARACTERISTICS AND BEHAVIOR OF NANOPARTICLES AND ITS DISPERSION SYSTEMS. In: *Nanoparticle Technology Handbook*. Elsevier; 2008:113-176. doi:10.1016/b978-044453122-3.50006-4
51. Lazzari S, Moscatelli D, Codari F, Salmona M, Morbidelli M, Diomede L. Colloidal stability of polymeric nanoparticles in biological fluids. *Journal of Nanoparticle Research*. 2012;14(6):1-10. doi:10.1007/s11051-012-0920-7
52. Heinz H, Pramanik C, Heinz O, et al. Nanoparticle decoration with surfactants: Molecular interactions, assembly, and applications. *Surface Science Reports*. 2017;72(1):1-58. doi:10.1016/j.surfrep.2017.02.001
53. Abdelwahed W, Degobert G, Stainmesse S, Fessi H. Freeze-drying of nanoparticles: Formulation, process and storage considerations. *Advanced Drug Delivery Reviews*. 2006;58(15):1688-1713. doi:10.1016/j.addr.2006.09.017
54. Ziaee A, Albadarin AB, Padrela L, Femmer T, O'Reilly E, Walker G. Spray drying of pharmaceuticals and biopharmaceuticals: Critical parameters and experimental process optimization approaches. *European Journal of Pharmaceutical Sciences*. 2019;127:300-318. doi:10.1016/j.ejps.2018.10.026
55. Wanning S, Süverkrüp R, Lamprecht A. Pharmaceutical spray freeze drying. *International Journal of Pharmaceutics*. 2015;488(1-2):136-153. doi:10.1016/j.ijpharm.2015.04.053
56. de Jong. Drug delivery and nanoparticles: Applications and hazards. *International Journal of Nanomedicine*. 2008;3(2):133. doi:10.2147/IJN.S596
57. Wallace SJ, Li J, Nation RL, Boyd BJ. Drug release from nanomedicines: Selection of appropriate encapsulation and release methodology. *Drug Delivery and Translational Research*. 2012;2(4):284-292. doi:10.1007/s13346-012-0064-4
58. Bohnert T, Gan LS. Plasma protein binding: From discovery to development. *Journal of*

*Pharmaceutical Sciences*. 2013;102(9):2953-2994. doi:10.1002/jps.23614

59. Patra JK, Das G, Fraceto LF, et al. Nano based drug delivery systems: Recent developments and future prospects 10 Technology 1007 Nanotechnology 03 Chemical Sciences 0306 Physical

UNDER PEER REVIEW

Chemistry (incl. Structural) 03 Chemical Sciences 0303 Macromolecular and Materials Chemistry 11 Medical and Health Sciences 1115 Pharmacology and Pharmaceutical Sciences 09 Engineering 0903 Biomedical Engineering Prof Ueli Aebi, Prof Peter Gehr. *Journal of Nanobiotechnology*. 2018;16(1):71. doi:10.1186/s12951-018-0392-8

60. Khan I, Saeed K, Khan I. Nanoparticles: Properties, applications and toxicities. *Arabian Journal of Chemistry*. 2019;12(7):908-931. doi:10.1016/j.arabjc.2017.05.011
61. Singh R, Lillard JW. Nanoparticle-based targeted drug delivery. *Experimental and Molecular Pathology*. 2009;86(3):215-223. doi:10.1016/j.yexmp.2008.12.004
62. Kamaly N, Yameen B, Wu J, Farokhzad OC. Degradable controlled-release polymers and polymeric nanoparticles: Mechanisms of controlling drug release. *Chemical Reviews*. 2016;116(4):2602-2663. doi:10.1021/acs.chemrev.5b00346
63. Bohrey S, Chourasiya V, Pandey A. Polymeric nanoparticles containing diazepam: Preparation, optimization, characterization, in-vitro drug release and release kinetic study. *Nano Convergence*. 2016;3(1):3. doi:10.1186/s40580-016-0061-2
64. Shen J, Burgess DJ. In vitro dissolution testing strategies for nanoparticulate drug delivery systems: Recent developments and challenges. *Drug Delivery and Translational Research*. 2013;3(5):409-415. doi:10.1007/s13346-013-0129-z
65. Lee JH, Yeo Y. Controlled drug release from pharmaceutical nanocarriers. *Chemical Engineering Science*. 2015;125:75-84. doi:10.1016/j.ces.2014.08.046
66. Truhaut R. Ecotoxicology: Objectives, principles and perspectives. *Ecotoxicology and Environmental Safety*. 1977;1(2):151-173. doi:10.1016/0147-6513(77)90033-1
67. Kahru A, Dubourguier HC. From ecotoxicology to nanoecotoxicology. *Toxicology*. 2010;269(2-3):105-119. doi:10.1016/j.tox.2009.08.016
68. Ali H, Khan E, Ilahi I. Environmental chemistry and ecotoxicology of hazardous heavy metals: Environmental persistence, toxicity, and bioaccumulation. *Journal of Chemistry*. 2019;2019. doi:10.1155/2019/6730305
69. Chenthamara D, Subramaniam S, Ramakrishnan SG, et al. Therapeutic efficacy of nanoparticles and routes of administration. *Biomaterials Research*. 2019;23(1):1-29. doi:10.1186/s40824-019-0166-x
70. Jain AK, Thareja S. *In vitro* and *in vivo* characterization of pharmaceutical nanocarriers used for drug delivery. *Artificial Cells, Nanomedicine, and Biotechnology*. 2019;47(1):524-539. doi:10.1080/21691401.2018.1561457
71. Pinelli F, Perale G, Rossi F. Coating and Functionalization Strategies for Nanogels and Nanoparticles for Selective Drug Delivery. *Gels*. 2020;6(1):6. doi:10.3390/gels6010006
72. Lombardo D, Kiselev MA, Caccamo MT. Smart Nanoparticles for Drug Delivery Application: Development of Versatile Nanocarrier Platforms in Biotechnology and Nanomedicine. *Journal of Nanomaterials*. 2019;2019. doi:10.1155/2019/3702518
73. Maurya A, Singh AK, Mishra G, et al. Strategic use of nanotechnology in drug targeting and its consequences on human health: A focused review. *Interventional Medicine and Applied Science*. 2019;11(1):38-54. doi:10.1556/1646.11.2019.04
74. Shi C, Zhang Z, Wang F, Luan Y. Active-targeting docetaxel-loaded mixed micelles for enhancing antitumor efficacy. *Journal of Molecular Liquids*. 2018;264:172-178. doi:10.1016/j.molliq.2018.05.039

75. Fam SY, Chee CF, Yong CY, Ho KL, Mariatulqabtiah AR, Tan WS. Stealth Coating of Nanoparticles in Drug-Delivery Systems. *Nanomaterials*. 2020;10(4):787. doi:10.3390/nano10040787
76. Palanikumar L, Al-Hosani S, Kalmouni M, et al. pH-responsive high stability polymeric nanoparticles

UNDER PEER REVIEW

for targeted delivery of anticancer therapeutics. *Communications Biology*. 2020;3(1):1-17.  
doi:10.1038/s42003-020-0817-4

77. Lima T, Bernfur K, Vilanova M, Cedervall T. Understanding the Lipid and Protein Corona Formation on Different Sized Polymeric Nanoparticles. *Scientific Reports*. 2020;10(1):1129.  
doi:10.1038/s41598-020-57943-6
78. Calzoni E, Cesaretti A, Polchi A, Di Michele A, Tancini B, Emiliani C. Biocompatible Polymer Nanoparticles for Drug Delivery Applications in Cancer and Neurodegenerative Disorder Therapies. *Journal of Functional Biomaterials*. 2019;10(1):4. doi:10.3390/jfb10010004
79. Association of Pharmaceutical Teachers of India. 2015;(October).

UNDER PEER REVIEW