

CYTOTOXIC ACTIVITY OF ZINC OXIDE NANOPARTICLE SYNTHESIS USING LEAVES EXTRACT OF *ABIES WEBBIANA*

ABSTRACT:

Aim: The present study aimed to analyse the cytotoxicity of zinc oxide nanoparticles (ZnO NPs) that are biosynthesized using extract of *Abies webbiana*

Methodology: Zinc oxide nanoparticles were synthesized by green approach using *A. webbiana* and were characterized by UV- vis spectroscopy. The powdered *A. Webbiana* mediated ZnO NPs were subjected to cytotoxic tests for different concentrations by brine shrimp lethality assay.

Results: ZnO NPs synthesized from *A. webbiana* showed reduced toxicity at lower concentrations. After 48 hours, it was found that at a minimal concentration of 5 μ l, 90% of the nauplii and in concentration of 10 μ l and 20 μ l, 80% of the nauplii were alive. At a concentration of 40 μ l and 80 μ l, 70% of the nauplii were alive. Whereas the control showed 100% of the nauplii to be alive.

Conclusion: Various nanoformulations of *A. webbiana* mediated ZnO NPs can be developed at optimal concentrations for therapeutics that are safe and economical.

Keywords: Abies Webbiana; brine shrimp lethality assay; cytotoxicity; green synthesis; innovative technology, zinc oxide nanoparticles

1. INTRODUCTION

Nanoparticles are broadly applied in medicine, engineering, agriculture and in almost all other fields (1). The properties of nanoparticles demonstrate enormous applications compared to those of mass materials because of their incredibly small size (2). Metal nanoparticles are extensively used in a wide range of applications including chemical and biological sensing, catalysis, energy, drug and gene delivery and electronics (1,3–8). Nanoparticles have been intensively studied over the last decade due to their characteristics such as the physical, chemical, electronic and electrical properties (9).

Zinc oxide nanoparticles (ZnO NPs), which are known to be nontoxic, chemically stable, biocompatible, and could be used as drug carriers, cell imaging agents, anticancer agents, antimicrobials, biosensors, antidiabetics, and cosmetics, because of their novel physicochemical properties. Crude extracts of *Abies Webbiana* leaf had antibacterial, mast cell stabilizing, anxiolytic, anti-tumor, anti-inflammatory, antitussive and central nervous system (CNS) depressant actions (10–14). With reference to our previous studies (2,15–22) and other available literature, no report has yet highlighted the synthesis of ZnO NPs using *A. Webbiana*. Cytotoxicity is the nature of being harmful to cells. Brine shrimp lethality assay using the larvae of the crustacean, *Artemia salina* is a more common method which is employed

to analyse the cytotoxicity of bioactive compounds (23,24). Our team has extensive knowledge and research experience that has translated into high quality publications.(25–37),(38–42) (43) (44). The present study aimed to analyse the cytotoxicity of the *A. webbiana* mediated zinc oxide nanoparticles.

2. MATERIALS AND METHODS

2.1 Preparation of *A. Webbiana* Extract

Dried *A. webbiana* powder was procured from Annai Aravindh Vedic Centre, Chennai. To prepare the *A. webbiana* extract, 50 mL of distilled water was added to 0.5 g of *A. webbiana* powder in a conical flask. The heating mantle was utilized to heat the reaction mixture with the temperature of 50°C for 6-8 minutes. After heating, the solution was filtered using Whatman filter paper to get a clear filtrate.

2.2 Synthesis of ZnO NPs

For synthesizing ZnO NPs, 0.5 g of anhydrous Zinc sulfate was taken and to this 70 mL of distilled water was added. Then the solution was added to the previously prepared 30 mL of plant extract. The solution was brown in color and subjected to an orbital shaker for uniform dispersion of the reaction mixture and the color changes were visually observed at various periods of time. After complete synthesis of ZnO NPs, the solution was then dried by heating. The obtained ZnO NPs were utilized for further examination. The optical properties of the ZnO NPs were determined utilizing UV-vis spectroscopy.

2.3 Cytotoxic effect of ZnO NPs

Brine shrimp lethality assay was performed for determining the cytotoxic effect of ZnO NPs. Brine shrimp eggs were procured from Aquatic Remedies, Chennai. The hatching of eggs was encouraged by adding it to the artificially made seawater by dissolving 36 g of sea salt in 1000 mL of distilled water. This artificial seawater was added to the chamber that had a partition for dark and light areas. Shrimp eggs were added to the dark area of the chamber. Once the eggs hatched, it took 2-3 days for it to mature into larvae. These larvae moved to the light area of the partition. The hatched nauplii was used for the cytotoxicity evaluation, A 6-well ELISA plate was taken and 5 mL of artificial seawater was added to each of the 6 wells and 10 nauplii were added to each well. Then, 5 different concentrations of dried ginger mediated copper nanoparticles (5 μ l, 10 μ l, 20 μ l, 30 μ l, 50 μ l) were introduced to each of the 5 wells and a control containing only the seawater was taken in one well. The wells were left uncovered under the lamp. The number of surviving nauplii was recorded periodically after 24 h and 48 h of incubation.




Fig. 1. This picture shows the procedure used to obtain *A. webbia* mediated ZNO NPs




Fig. 2. Brine shrimp lethality assay comprising ELISA plate wells with different concentrations of *A. webbia* mediated ZnO NPs and a control observed for the presence of live nauplii after 24 h and 48 h incubation




Fig. 3. UV- vis spectroscopic analysis of ZnO NPs synthesized from *A. webbia* recorded as function of time

3. RESULTS AND DISCUSSION

Nanobiotechnology is the merge between biotechnology and nanotechnology for developing biosynthetic and ecofriendly technology for the synthesis of nanomaterials (45). Among the metal nanoparticles ZnO.NPs are interesting due to its impressive properties from which the wide band gap, large binding energy and high piezoelectric property (46). ZnO.NPs which can exhibit a wide variety of nanostructures are believed to be biosafe, non toxic and biocompatible, been used in various technologies and industries such as optoelectronics, piezoelectric and magnetic sensors, biological labelling, ceramic and rubber processing, environmental protection, biology and medicinal (8,47,48). Chemically, the surface of ZnO is rich in -OH groups, which permit ZnO to slowly dissolve in both acidic (e.g., the tumor cells and tumor microenvironment) and strong basic conditions. Based on this property, ZnO.NPs have gained immense interest in biomedical applications(49).

3.1 Visual Observation

In the visual identification, there was color change at various intervals of the incubation time. The first color change was observed when the Zinc sulphate was reduced to ZnO NPs giving a brown color. After 2 hours of the incubation period there was change from brown to light yellow (Figure 1). Similar visual observations of colour change were found in the study done by Bisht et al and Sonia et al (50,51).

3.2 The UV- Spectrophotometer Analysis

Spectrophotometer analysis depends on the arising color of the reaction mixture due to transition of ions from ground state to excited state. The reduction process of the solution was optically measured at different wavelengths and was recorded. The UV- vis spectroscopy analysis of the present study showed that the surface plasmon resonance band peak was positioned at the wavelength of 290 nm (Figure 3).

3.3 Cytotoxicity Analysis

Brine shrimp lethality assay is an important test in the study of toxicity, that gives us the information about the cytotoxic effect exhibited by a bioactive compound to cells. The viability of the nauplii was analysed for different concentrations of ZnO NPs that are synthesized from *A. webbiana* (Figure 2). After 24 hours, 100% of the nauplii were alive in concentration of 5 μ l, 10 μ l, 20 μ l, 40 μ l and 80 μ l. The control also showed 100% of the nauplii to be alive. After 48 hours, it was found that at a minimal concentration of 5 μ l, 90% of the nauplii and in concentration of 10 μ l and 20 μ l, 80% of the nauplii were alive. At a concentration of 40 μ l and 80 μ l, 70% of the nauplii were alive. Whereas the control showed 100% of the nauplii to be alive (Table 1) (Figure 4). Thus, the increase in concentration increased the cytotoxicity. These findings were found to be in agreement with the findings of research on cytotoxicity by Rishey et al, Renugadevi et al and Begum.A et al (52–54). More specific cytotoxicity studies need to be undertaken in order to study the exact mechanism of action. Cytotoxicity was seen to be higher in 40 μ l and 80 μ l concentrations in the present study.

Table 1. Brine shrimp lethality assay for different concentrations of *A. webbiana* mediated ZNO NPs observed after 24 h and 48 h incubation

	5 μ L	10 μ L	20 μ L	40 μ L	80 μ L	control
Day 1	10	10	10	10	10	10
Day 2	9	8	8	7	7	10




Fig. 4. This graph depicts the cytotoxic effect of *A. webbiana* mediated ZNO NPs

4.CONCLUSION:

Within the limitations of the study we can conclude that *A. webbiana* enabled the synthesis of a stable Zn-NPs. The results indicate that the zinc nanoparticles synthesized from *A. webbiana* showed reduced toxicity. Thus, various nano-formulations at lower concentrations of these nanoparticles can be developed that are safe, eco friendly and economical. Future research in *A. webbiana* mediated ZNO NPs evaluating its biological properties like antimicrobial, antiinflammatory and antioxidant activities can bring about the development of nano-formulations like mouthwash, toothpaste and oral gels as therapeutics in various oral diseases.

CONSENT

It is not applicable

ETHICAL APPROVAL

It is not applicable

REFERENCES:

1. Agarwal H, Venkat Kumar S, Rajeshkumar S. A review on green synthesis of zinc oxide nanoparticles – An eco-friendly approach. Resour-efic technol. 2017 Dec 1;3(4):406–13.
2. Santhoshkumar J, Rajeshkumar S, Venkat Kumar S. Phyto-assisted synthesis, characterization and

applications of gold nanoparticles - A review. *Biochem Biophys Rep.* 2017 Sep 1;11:46–57.

3. Abd-Elhalim BT, R. F. G, Kh. A. A-T, A. A. H. Biosynthesis of Copper nanoparticles using bacterial supernatant optimized with certain agro-industrial byproducts. *Nov Res Microbiol J.* 2019 Dec 28;3(6):558–78.
4. El-Nahrawy AM, Abou Hammad AB, Khattab TA, Haroun A, Kamel S. Development of electrically conductive nanocomposites from cellulose nanowhiskers, polypyrrole and silver nanoparticles assisted with Nickel(III) oxide nanoparticles. *React Funct Polym.* 2020 Apr 1;149:104533.
5. Kamel S, Haroun AA, El-Nahrawy AM, Diab MA. Electroconductive Composites Containing Nanocellulose, Nanopolypyrrole, and Silver Nano particles. *Journal of Renewable Materials.* 2019;7(2):193–203.
6. Mody VV, Siwale R, Singh A, Mody HR. Introduction to metallic nanoparticles. *J Pharm Bioallied Sci.* 2010 Oct;2(4):282–9.
7. Rizk MZ, Abo-El-Matty DM, Aly HF, Abd-Alla HI, Saleh SM, Younis EA, et al. Therapeutic activity of sour orange albedo extract and abundant flavanones loaded silica nanoparticles against acrylamide-induced hepatotoxicity. *Toxicol Rep.* 2018 Sep 9;5:929–42.
8. Wang EC, Wang AZ. Nanoparticles and their applications in cell and molecular biology. *Integr Biol (Camb)* 6 (1): 9--26. 2014.
9. Mamidi N, Leija HM, Diabb JM, Lopez Romo I, Hernandez D, Castrejón JV, et al. Cytotoxicity evaluation of unfunctionalized multiwall carbon nanotubes-ultrahigh molecular weight polyethylene nanocomposites. *J Biomed Mater Res A.* 2017 Nov;105(11):3042–9.
10. Ghosh AK, Srikanth K, Jha T. Inhibitory effects of *Abies webbiana* on tumor cells in mice. *Indian J Nat Prod.* 2001;7:17–9.
11. Singh RK, Bhattacharya SK, Acharya SB. Pharmacological activity of *Abies pindrow*. *J Ethnopharmacol.* 2000 Nov;73(1-2):47–51.
12. Kumar V, Singh RK, Jaiswal AK, Bhattacharya SK, Acharya SB. Anxiolytic activity of Indian *Abies pindrow* Royle leaves in rodents: an experimental study. *Indian J Exp Biol.* 2000 Apr;38(4):343–6.
13. Nayak SS, Ghosh AK, Debnath B, Vishnoi SP, Jha T. Synergistic effect of methanol extract of *Abies webbiana* leaves on sleeping time induced by standard sedatives in mice and anti-inflammatory activity of extracts in rats. *J Ethnopharmacol.* 2004 Aug;93(2-3):397–402.
14. Vishnoi SP, Ghosh AK, Debnath B, Samanta S, Gayen S, Jha T. Antibacterial activity of *Abies webbiana*. *Fitoterapia.* 2007 Feb;78(2):153–5.
15. Wani IA, Ahmad T, Khosla A. Recent Advances in Anticancer and Antimicrobial Activity of Silver Nanoparticles Synthesized Using Phytochemicals and Organic Polymers. *Nanotechnology [Internet].* 2021 Aug 2; Available from: <http://dx.doi.org/10.1088/1361-6528/ac19d5>
16. Rajeshkumar S, Tharani M, Jeevitha M, Santhoshkumar J. Anticariogenic activity of fresh aloe Vera gel mediated copper oxide nanoparticles. *Indian j public health res dev.* 2019;10(11):3664.
17. Menon S, Ks SD, R S, S R, S VK. Selenium nanoparticles: A potent chemotherapeutic agent and an elucidation of its mechanism. *Colloids Surf B Biointerfaces.* 2018 Oct 1;170:280–92.
18. Happy Agarwal, Soumya Menon, Venkat Kumar S, Rajeshkumar S. Mechanistic study on antibacterial action of zinc oxide nanoparticles synthesized using green route. *Chem Biol Interact.* 2018 Apr 25;286:60–70.

19. Rajeshkumar S, Naik P. Synthesis and biomedical applications of Cerium oxide nanoparticles – A Review. *Biotechnol Rep (Amst)*. 2018 Mar 1;17:1–5.
20. Menon S, S. R, S. VK. A review on biogenic synthesis of gold nanoparticles, characterization, and its applications. *Resource-Efficient Technologies*. 2017 Dec 1;3(4):516–27.
21. Rajeshkumar S, Bharath LV. Mechanism of plant-mediated synthesis of silver nanoparticles - A review on biomolecules involved, characterisation and antibacterial activity. *Chem Biol Interact*. 2017 Aug 1;273:219–27.
22. Kandhan TS, Roy A, Lakshmi T, Rajeshkumar S. Green synthesis of Rosemary oleoresin mediated silver nanoparticles and its effect on Oral pathogens. *Research Journal of Pharmacy and Technology*. 2019;12(11):5379–82.
23. Meyer BN, Ferrigni NR, Putnam JE, Jacobsen LB, Nichols DE, McLaughlin JL. Brine shrimp: a convenient general bioassay for active plant constituents. *Planta Med*. 1982 May;45(5):31–4.
24. Sarah QS, Anny FC, Mir M, Others. Brine shrimp lethality assay. *Bangladesh J Pharmacol*. 2017;12(2):186–9.
25. Ramesh A, Varghese S, Jayakumar ND, Malaiappan S. Comparative estimation of sulfiredoxin levels between chronic periodontitis and healthy patients - A case-control study. *J Periodontol*. 2018 Oct;89(10):1241–8.
26. Paramasivam A, Priyadharsini JV, Raghunandhakumar S, Elumalai P. A novel COVID-19 and its effects on cardiovascular disease. *Hypertens Res*. 2020 Jul;43(7):729–30.
27. S G, T G, K V, Faleh A A, Sukumaran A, P N S. Development of 3D scaffolds using nanochitosan/silk-fibroin/hyaluronic acid biomaterials for tissue engineering applications. *Int J Biol Macromol*. 2018 Dec;120(Pt A):876–85.
28. Del Fabbro M, Karanxha L, Panda S, Bucchi C, Nadathur Doraiswamy J, Sankari M, et al. Autologous platelet concentrates for treating periodontal infrabony defects. *Cochrane Database Syst Rev*. 2018 Nov 26;11:CD011423.
29. Paramasivam A, Vijayashree Priyadharsini J. MitomiRs: new emerging microRNAs in mitochondrial dysfunction and cardiovascular disease. *Hypertens Res*. 2020 Aug;43(8):851–3.
30. Jayaseelan VP, Arumugam P. Dissecting the theranostic potential of exosomes in autoimmune disorders. *Cell Mol Immunol*. 2019 Dec;16(12):935–6.
31. Vellappally S, Al Kheraif AA, Divakar DD, Basavarajappa S, Anil S, Fouad H. Tooth implant prosthesis using ultra low power and low cost crystalline carbon bio-tooth sensor with hybridized data acquisition algorithm. *Comput Commun*. 2019 Dec 15;148:176–84.
32. Vellappally S, Al Kheraif AA, Anil S, Assery MK, Kumar KA, Divakar DD. Analyzing Relationship between Patient and Doctor in Public Dental Health using Particle Memetic Multivariable Logistic Regression Analysis Approach (MLRA2). *J Med Syst*. 2018 Aug 29;42(10):183.
33. Varghese SS, Ramesh A, Veeraiyan DN. Blended Module-Based Teaching in Biostatistics and Research Methodology: A Retrospective Study with Postgraduate Dental Students. *J Dent Educ*. 2019 Apr;83(4):445–50.
34. Venkatesan J, Singh SK, Anil S, Kim S-K, Shim MS. Preparation, Characterization and Biological Applications of Biosynthesized Silver Nanoparticles with Chitosan-Fucoidan Coating. *Molecules* [Internet]. 2018 Jun 12;23(6). Available from: <http://dx.doi.org/10.3390/molecules23061429>

35. Alsubait SA, Al Aylan R, Mitwalli H, Aburaisi N, Mahmood A, Muthurangan M, et al. Cytotoxicity of Different Concentrations of Three Root Canal Sealers on Human Mesenchymal Stem Cells. *Biomolecules* [Internet]. 2018 Aug 1;8(3). Available from: <http://dx.doi.org/10.3390/biom8030068>
36. Venkatesan J, Rekha PD, Anil S, Bhatnagar I, Sudha PN, Dechsakulwatana C, et al. Hydroxyapatite from Cuttlefish Bone: Isolation, Characterizations, and Applications. *Biotechnol Bioprocess Eng*. 2018 Aug 1;23(4):383–93.
37. Vellappally S, Al Kheraif AA, Anil S, Wahba AA. IoT medical tooth mounted sensor for monitoring teeth and food level using bacterial optimization along with adaptive deep learning neural network. *Measurement*. 2019 Mar 1;135:672–7.
38. PradeepKumar AR, Shemesh H, Nivedhitha MS, Hashir MMJ, Arockiam S, Uma Maheswari TN, et al. Diagnosis of Vertical Root Fractures by Cone-beam Computed Tomography in Root-filled Teeth with Confirmation by Direct Visualization: A Systematic Review and Meta-Analysis. *J Endod*. 2021 Aug;47(8):1198–214.
39. R H, Ramani P, Tilakaratne WM, Sukumaran G, Ramasubramanian A, Krishnan RP. Critical appraisal of different triggering pathways for the pathobiology of pemphigus vulgaris-A review. *Oral Dis* [Internet]. 2021 Jun 21; Available from: <http://dx.doi.org/10.1111/odi.13937>
40. Ezhilarasan D, Lakshmi T, Subha M, Deepak Nallasamy V, Raghunandhakumar S. The ambiguous role of sirtuins in head and neck squamous cell carcinoma. *Oral Dis* [Internet]. 2021 Feb 11; Available from: <http://dx.doi.org/10.1111/odi.13798>
41. Sarode SC, Gondivkar S, Sarode GS, Gadbail A, Yuwanati M. Hybrid oral potentially malignant disorder: A neglected fact in oral submucous fibrosis. *Oral Oncol*. 2021 Jun 16;105390.
42. Kavarthapu A, Gurumoorthy K. Linking chronic periodontitis and oral cancer: A review. *Oral Oncol*. 2021 Jun 14;105375.
43. Vellappally S, Abdullah Al-Kheraif A, Anil S, Basavarajappa S, Hassanein AS. Maintaining patient oral health by using a xeno-genetic spiking neural network. *J Ambient Intell Humaniz Comput* [Internet]. 2018 Dec 14; Available from: <https://doi.org/10.1007/s12652-018-1166-8>
44. Aldhuwayhi S, Mallineni SK, Sakhamuri S, Thakare AA, Mallineni S, Sajja R, et al. Covid-19 Knowledge and Perceptions Among Dental Specialists: A Cross-Sectional Online Questionnaire Survey. *Risk Manag Healthc Policy*. 2021 Jul 7;14:2851–61.
45. Sobha K, Surendranath K, Meena V. Emerging trends in nanobiotechnology. *BioTechnology* [Internet]. 2010; Available from: <https://academicjournals.org/journal/BMBR/article-abstract/5FF052811265>
46. Vaseem M, Umar A, Hahn Y-B. Metal oxide nanostructures and their applications. *American Scientific Publishers*. 2010;5:1–36.
47. Theodore L. *Nanotechnology: Basic Calculations for Engineers and Scientists*. John Wiley & Sons; 2006. 368 p.
48. Dagdeviren C, Hwang S-W, Su Y, Kim S, Cheng H, Gur O, et al. Transient, biocompatible electronics and energy harvesters based on ZnO. *Small*. 2013 Oct 25;9(20):3398–404.
49. Liu D, Wu W, Qiu Y, Yang S, Xiao S, Wang Q-Q, et al. Surface functionalization of ZnO nanotetrapods with photoactive and electroactive organic monolayers. *Langmuir*. 2008 May 6;24(9):5052–9.
50. Bisht G, Rayamajhi S. ZnO Nanoparticles: A Promising Anticancer Agent. *Nanobiomedicine (Rij)*.

2016 Jan;3:9.

51. Sonia S, Ruckmani K, Sivakumar M, Others. Antimicrobial and antioxidant potentials of biosynthesized colloidal zinc oxide nanoparticles for a fortified cold cream formulation: a potent nanocosmeceutical application. *Materials Science and Engineering: C*. 2017;79:581–9.
52. Rieshy v, Jeevitha m, Rajeshkumar s. Cytotoxicity of copper nanoparticles synthesized using dried ginger. *Plant cell biotechnology and molecular biology*. 2020 Nov 17;1–6.
53. Renugadevi K, Kumar N, Nachiyar CV. Phytosynthesis of Silver Nanoparticle using Ginger extract as a Reducing agent by Microwave Irradiation method and invitro Evaluation of its Antibacterial activity and Cytotoxicity. *Research Journal of Pharmacy and Technology*. 2017;10(12):4142–6.
54. Begum A, Jeevitha M, Preetha S, Rajeshkumar S. Cytotoxicity of Iron Nanoparticles Synthesized Using Dried Ginger. *Journal of Pharmaceutical Research International*. 2020 Nov 2;112–8.

UNDER PEER REVIEW