

# BLUE TEA MEDIATED SYNTHESIS AND CHARACTERISATION OF COPPER NANOPARTICLES: AN IN VITRO STUDY

Running Title: Synthesis and characterisation of copper nanoparticles using blue tea

## ABSTRACT:

**Background:** Nanoparticles (NPs) are being viewed as fundamental building blocks of this technology. Butterfly-pea flower tea commonly known as Blue Tea is a caffeine free or herbal tea made from infusion of the flower petals of the *Clitoria ternatea* plant. Plant extracts may act both as reducing agents and stabilising agents in the synthesis of nanoparticles.

Comment [L1]: nanotechnology

Comment [L2]: should be italic

Comment [L3]: delete it

**Aim:** The aim of the study is to assess the characterisation of the copper nanoparticles obtained from blue tea.

Comment [L4]: was

**Materials and Methods:** The blue tea mediated copper nanoparticles were synthesised using the green synthesis method. Morphological characters like the shape and size of the obtained green synthesized copper nanoparticles were observed by transmission electron microscope.

Comment [L5]: observed by UV spectrometry and transmission electron microscope.

Comment [L6]: were

**Results:** The results confirmed that the synthesised blue tea extract mediated nanoparticles are eco-friendly, good and non toxic. TEM images showed that the copper nanoparticles were well dispersed, crystalline in nature. Copper nanoparticles are spherical in nature. The particles were of the size 5-10 microns in size. The TEM image shows that nanoparticles are not combined but are separated by equal interspace between the particles, which was confirmed by microscopy visualising under the higher resolution.

Comment [L7]: were spherical in shape

Comment [L8]: The particles were 5-10  $\mu$ l in size.

Comment [L9]: showed

Comment [L10]: were

Comment [L11]: were

**Conclusion:** In this study, a simple, biological and low-cost approach was done for the preparation of copper nanoparticles using blue tea. Thus the synthesized copper nanoparticles can be subjected to various other biological activities such as antibacterial, antifungal and cytotoxic evaluation to know the efficiency of these nanoparticles.

**Keywords:** Butterfly pea; *Clitoria ternatea*; Green synthesis; Innovative; Nanoparticles.

Comment [L12]: should be italic

## INTRODUCTION:

The nanoparticles (NPs) are being viewed as fundamental building blocks of this technology(1). Metal nanoparticles are extensively used in various electrochemical, electro analytical and bio-electrochemical applications owing to their extraordinary electron catalytic activity(2). Copper nanoparticles (CuNPs) are of great interest due to their extraordinary properties which includes high surface-to-volume ratio, high yield strength, ductility, hardness, flexibility, and rigidity.

Comment [L13]: nanotechnology

CuNPs show high catalytic, antibacterial, antioxidant, and antifungal activities along with cytotoxicity and anticancer properties in many different applications(3). In this study, a simple, biological and low-cost approach was done for the preparation of copper nanoparticles using blue tea(4). Thus the synthesis copper nanoparticles can be subjected to the various other biological activities such as Antibacterial, Antifungal, Cytotoxic evaluation to know the efficiency of these nanoparticles. Hence they can be used in daily purposes as a substitute for conventional products and help in the betterment of life(5).

Comment [L14]: showed

Comment [L15]: synthesized

Comment [L16]: antibacterial, antifungal, cytotoxic

Plant extracts are very useful as they may act both as reducing agents and stabilizing agents in the synthesis of nanoparticles(6). Butterfly-pea flower tea commonly known as Blue Tea is a caffeine free or herbal tea, beverage made from infusion of the flower petals of the *Clitoria ternatea* plant. The biosynthetic pathway of nanoparticles preparation potentially eliminates the toxicity and makes the nanoparticles more biocompatible(7). Among the various biosynthetic approaches, the plant extracts has advantages such as easily available, safe to handle, possess a broad viability of metabolites, eliminating the cumbersome process such as maintaining the cell culture and extraction and separation can be easily scaled up for the large-scale synthesis of nanoparticles using biosynthesis(8). The main phytochemicals responsible for synthesis of nanoparticles are terpenoids, flavones, ketones, aldehydes amines etc(9). The green synthesis of copper nanoparticles is an eco-friendly method and uses natural solvent that requires no toxic solvents and no dangerous material for the environment(10) (11–13)(14–17) (18,19).

Comment [L17]: should be italic

Our team has extensive knowledge and research experience that has translated into high quality publications.(20)(21)(22)(23)(24)(25)(26)(27)(28)(29)(30–39) The aim of the study was to synthesise and characterise blue tea mediated copper nanoparticles using transmission electron microscope (TEM).

Comment [L18]: UV spectrometry and TEM.

## MATERIALS AND METHODS:

### Preparation of blue tea extract:

A sample of blue Tea powder is taken and measured accurately to 1g to which 100mL of distilled water is added and boiled for 15-20 minutes at 60-70 degrees and the obtained extract is cooled for sometime, then the solution is filtered by using whatman no.10 filter paper. The filtered extract was collected and stored in the refrigerator for further use.

Comment [L19]: tea (lower case)

Comment [L20]: was

Comment [L21]: was

Comment [L22]: was

Comment [L23]: was



Figure 1: Mixture of blue Tea extract in distilled water

Comment [L24]: tea




Figure 2: Concentrated extract of Blue Tea extract

### Synthesis of Copper Nanoparticles:

Synthesis of Copper Nanoparticles is done biologically using blue tea. 20mM of copper sulphate is added to the obtained extract. The colour change was observed visually and photographed. The solution is kept in a magnetic stirrer for nanoparticle synthesis. The reaction mixture of copper sulphate and blue tea was centrifuged at 8,000xg for 10 minutes. The resulting pellet was washed three times with distilled water and filtered and the supernatant so formed was collected.

Comment [L25]: copper nanoparticles was

Comment [L26]: was

Comment [L27]: was




Figure 3: Mixture of Copper sulphate and Blue tea



Figure 4: The final reaction with blue tea mediated  $\text{CuSO}_4$  Nanoparticles

Comment [L28]: blue tea mediated  $\text{CuSO}_4$

#### UV spectrometric analysis of synthesized nanoparticle:

Spectrometric analysis was evaluated by UV-visible spectroscopy. The biologically reduced solution mixture was scanned by Shimadzu, Lambda UV mini-1240 instrument operated at a resolution of 1 nm. The UV-visible analysis was performed in the absorption wavelength of 200 to 700 nm periodically for one hour to observe rapid reduction of copper nanoparticles and the results were recorded for the graphical analysis.

Comment [L29]: copper nanoparticles

#### Characterisation of prepared Copper Nanoparticles:

The synthesized Cu NPs were characterised using TEM (Transmission Electron Microscope). The morphological analysis of the particle was done with TEM. A sample of Cu NPs was loaded on a carbon-coated copper grid, followed by solvent evaporation at room temperature for an hour. The TEM micrograph images were recorded on Zeiss- EM10C instrument on carbon coated copper grids with an accelerating voltage of 80 KV. The clear microscopic views were observed and documented in different ranges of magnifications.

Comment [L30]: particles

\_\*

## RESULTS:

The synthesised copper nanoparticles were predicted through visual observation of solution colour change from light purple to dark purplish blue colour. The colour change signifies the presence of copper nanoparticles which was confirmed by the UV-Visible spectrophotometer.

Copper nanoparticles were successfully synthesized using blue tea extract after being subjected to continuous heat and stirring. The purple reaction mixture slowly changed to a thick purplish blue suspension after several minutes of reaction. The development of intense purplish blue in colour owing to the surface plasmon resonance confirmed the synthesis of the copper nanoparticles. Colour changes of the reaction mixture 240 minutes after the bioreduction process, which were recorded by UV-visible spectrophotometer. UV-Visible readings were recorded in the wavelength range of 200 - 600nm. The absorption formed in the reaction media has an absorbance peak at 570nm. The surface plasmon resonance absorbance was very sensitive to size and shape of the particles. It was observed that the SPR bands are located at the range 570 nm which is the characteristic absorption peak for copper nanoparticles in this study. (Figure 5)

Comment [L31]: were

The centrifuged substrate was then subjected for the TEM analysis for the characterisation so as to determine the size, shape and distribution of nanoparticles. TEM images show that particles are well dispersed, crystalline in nature is shown in the figure below, Copper nanoparticles were spherical in nature. The particle size was ranging from 5 to 10 microns in size. The TEM image showed that nanoparticles are not combined but are separated by equal interspace between the particles, which was confirmed by microscopy visualizing under the higher resolution. This image explains that the copper nanoparticles are bounded with the phytochemicals of the plant extract. (Figure 6)

Comment [L32]: showed

Comment [L33]: were

Comment [L34]: as

Comment [L35]: were

Comment [L36]: were




Figure 5: UV-Visible Spectrophotometer's image depicting the synthesis of copper nanoparticles using blue tea extract. The X axis represents the wavelength (nm) and the Y axis represents absorbance (Abs). The UV visible spectra of the copper nanoparticles showed a peak of 570 nm.




Figure 6: TEM image which confirms the synthesis of CuNPs, which were crystalline, cubical in shape with an average size 5-10 microns.

Comment [L37]: confirmed

Comment [L38]: spherical

## DISCUSSION:

The current study was undertaken to synthesize and characterise blue tea mediated copper nanoparticles. Thereby analysing its biologic properties to be used as adjunct in medical and dental fields.

Cheirmadurai K et al in 2014 synthesised copper nanoparticles using henna leaf extract and their morphological characteristics were evaluated using transmission electron microscope. The TEM analysis revealed the crystalline cubic shape of copper nanoparticles of size 25-30 nm synthesised from henna leaf. The UV-visible spectrum showed maximum absorption at 265 nm which confirms the presence of active compound lawsone (40). The change of colour from blue to reddish brown indicates the formation of copper nanoparticles.

Comment [L39]: confirmed

Comment [L40]: indicated

Comment [L41]: should be italic

Similarly, Sampath M et al in 2016 synthesised copper nanoparticles using *Eclipta prostrata* leaf extract and their morphological characteristics were evaluated using TEM (41). TEM analysis revealed the crystalline face centric cubic shape of copper nanoparticles of size 23-50 nm. The UV-

visible spectrum showed maximum absorption at 385 nm which confirms the presence of copper nanoparticles

Comment [L42]: confirmed

Niharika N et al in 2018 generated copper nanoparticles from *Azadirachta indica* leaves and their morphological characteristics were analyzed using UV-visible Spectrophotometer. The biosynthesised copper nanoparticles were crystalline, cubical in shape with the average size of 48 nm. The highly stable copper nanoparticles obtain the maximum absorption peak at 430 nm (42).

Comment [L43]: should be italic

Amir K et al in 2016 synthesised copper nanoparticles from coriander oleoresin extract and their morphological characteristics were analyzed using TEM (43). The copper nanoparticles synthesised were crystalline cubical in shape of an average size of 20 nm. The UV-visible spectra showed a surface plasmon resonance at 560 nm.

The current study was conducted similar to the previous studies (16) (18,19) and their characterisation done using transmission electron microscope revealed similar results to the articles mentioned above. However further analysis must be done to study their antibacterial, anti-inflammatory, antioxidant activities.

#### CONCLUSION:

In this study, a simple, biological and low-cost approach was used for the preparation of copper Nanoparticles using blue Tea (44) (45) (46) (47) (48) (49) (50) (51) (52) (53) (54) (55) (56) (57). The green synthesized copper nanoparticles can be subjected to the various other biological activities such as antibacterial, antifungal, cytotoxic evaluation to know the efficiency of these nanoparticles do that they can be used as a substitute for conventional chemical products thereby reducing the cytotoxicity.

#### REFERENCES:

1. Dhas NA, Arul Dhas N, Paul Raj C, Gedanken A. Synthesis, Characterization, and Properties of Metallic Copper Nanoparticles [Internet]. Vol. 10, Chemistry of Materials. 1998. p. 1446–52. Available from: <http://dx.doi.org/10.1021/cm9708269>
2. Dhas NA, Raj CP, Gedanken A. ChemInform Abstract: Synthesis, Characterization, and Properties of Metallic Copper Nanoparticles [Internet]. Vol. 29, ChemInform. 2010. p. no – no. Available from: <http://dx.doi.org/10.1002/chin.199832019>
3. Nagar N, Devra V. Green synthesis and characterization of copper nanoparticles using *Azadirachta indica* leaves [Internet]. Vol. 213, Materials Chemistry and Physics. 2018. p. 44–51. Available from: <http://dx.doi.org/10.1016/j.matchemphys.2018.04.007>
4. Salavati-Niasari M, Davar F, Mir N. Synthesis and characterization of metallic copper nanoparticles via thermal decomposition [Internet]. Vol. 27, Polyhedron. 2008. p. 3514–8. Available from: <http://dx.doi.org/10.1016/j.poly.2008.08.020>
5. Rezazadeh L, Sharafi S, Schaffie M, Ranjbar M. Synthesis and characterization of magnetic

nanoparticles from raffinate of industrial copper solvent extraction plants [Internet]. Vol. 229, Materials Chemistry and Physics. 2019. p. 372–9. Available from: <http://dx.doi.org/10.1016/j.matchemphys.2019.03.023>

6. Keihan AH, Veisi H, Veasi H. Green synthesis and characterization of spherical copper nanoparticles as organometallic antibacterial agent [Internet]. Vol. 31, Applied Organometallic Chemistry. 2017. p. e3642. Available from: <http://dx.doi.org/10.1002/aoc.3642>
7. - Biosynthesis and Characterization of Different Nanoparticles and Its Larvicidal Activity against Human Disease Vectors [Internet]. Marine Biomaterials. 2013. p. 296–311. Available from: <http://dx.doi.org/10.1201/b14723-18>
8. Mohanpuria P, Rana NK, Yadav SK. Biosynthesis of nanoparticles: technological concepts and future applications [Internet]. Vol. 10, Journal of Nanoparticle Research. 2008. p. 507–17. Available from: <http://dx.doi.org/10.1007/s11051-007-9275-x>
9. Rajakumar G, Rahuman AA. Phytosynthesis of Metal and Metal-Oxide Nanoparticles – Technological Concepts and Their Biomedical Applications [Internet]. Nanoparticles in the Fight Against Parasites. 2016. p. 51–80. Available from: [http://dx.doi.org/10.1007/978-3-319-25292-6\\_5](http://dx.doi.org/10.1007/978-3-319-25292-6_5)
10. Mishra S, Dixit S, Soni S. Methods of Nanoparticle Biosynthesis for Medical and Commercial Applications [Internet]. Bio-Nanoparticles. 2015. p. 141–54. Available from: <http://dx.doi.org/10.1002/9781118677629.ch7>
11. Khanna PK, Gaikwad S, Adhyapak PV, Singh N, Marimuthu R. Synthesis and characterization of copper nanoparticles [Internet]. Vol. 61, Materials Letters. 2007. p. 4711–4. Available from: <http://dx.doi.org/10.1016/j.matlet.2007.03.014>
12. J A, Aparna J, Rajeshkumar S. Cytotoxic and Antioxidant Activity of Zinc Oxide Nanoparticles Synthesised Using Maranta Arundinacea Root Extract [Internet]. Vol. 11, International Journal of Research in Pharmaceutical Sciences. 2020. p. 4372–7. Available from: <http://dx.doi.org/10.26452/ijrps.v11i3.2655>
13. ANTI-INFLAMMATORY ACTIVITY OF TITANIUM DIOXIDE NANOPARTICLES SYNTHESISED USING GRAPE SEED EXTRACT: AN in vitro STUDY [Internet]. [cited 2021 Aug 16]. Available from: <https://paperpile.com/app/p/2fe87431-ef18-02f1-a4d4-c018f73e5b66>
14. EFFICACY OF Aloe vera GEL AS AN ADJUNCT TO SCALING AND ROOT PLANING IN THE MANAGEMENT OF CHRONIC PERIODONTITIS [Internet]. [cited 2021 Aug 16]. Available from: <https://paperpile.com/app/p/74fa086a-c658-0095-afbd-baccfb582a75>
15. Kishen A, Rajeshkumar S, Preejitha VB. Cynodon dactylon Mediated Synthesis of Selenium Nanoparticles and Its Antimicrobial Activity Against Oral Pathogens [Internet]. Vol. 11, International Journal of Research in Pharmaceutical Sciences. 2020. p. 4152–6. Available from: <http://dx.doi.org/10.26452/ijrps.v11i3.2621>

16. Rajeshkumar S, Nandhini NT, Manjunath K, Sivaperumal P, Krishna Prasad G, Alotaibi SS, et al. Environment friendly synthesis copper oxide nanoparticles and its antioxidant, antibacterial activities using Seaweed (*Sargassum longifolium*) extract [Internet]. Vol. 1242, Journal of Molecular Structure. 2021. p. 130724. Available from: <http://dx.doi.org/10.1016/j.molstruc.2021.130724>
17. ANTIFUNGAL ACTIVITY OF GRAPE SEED EXTRACT MEDIATED ZINC OXIDE NANOPARTICLES - AN In vitro STUDY [Internet]. [cited 2021 Aug 16]. Available from: <https://paperpile.com/app/p/d2434c40-e3a0-0fed-9ebe-2a13d846baf9>
18. SYNTHESIS AND CHARACTERIZATION OF GRAPE SEED MEDIATED TITANIUM DIOXIDE NANOPARTICLES: AN in vitro STUDY [Internet]. [cited 2021 Aug 16]. Available from: <https://paperpile.com/app/p/3479aa0f-9f72-0224-9cf3-85f5b6492e82>
19. GREEN SYNTHESIS OF SELENIUM NANOPARTICLES (SeNPs) USING AQUEOUS EXTRACT OF CLOVE AND CINNAMON [Internet]. [cited 2021 Aug 16]. Available from: <https://paperpile.com/app/p/8deb9cd6-c0cc-04e5-9d5b-a1a14726faac>
20. Ramesh A, Varghese S, Jayakumar ND, Malaiappan S. Comparative estimation of sulfiredoxin levels between chronic periodontitis and healthy patients - A case-control study. J Periodontol [Internet]. 2018 Oct;89(10):1241–8. Available from: <http://dx.doi.org/10.1002/JPER.17-0445>
21. Paramasivam A, Priyadharsini JV, Raghunandhakumar S, Elumalai P. A novel COVID-19 and its effects on cardiovascular disease. Hypertens Res [Internet]. 2020 Jul;43(7):729–30. Available from: <http://dx.doi.org/10.1038/s41440-020-0461-x>
22. S G, T G, K V, Faleh A A, Sukumaran A, P N S. Development of 3D scaffolds using nanochitosan/silk-fibroin/hyaluronic acid biomaterials for tissue engineering applications. Int J Biol Macromol [Internet]. 2018 Dec;120(Pt A):876–85. Available from: <http://dx.doi.org/10.1016/j.ijbiomac.2018.08.149>
23. Del Fabbro M, Karanxha L, Panda S, Bucchi C, Nadathur Doraiswamy J, Sankari M, et al. Autologous platelet concentrates for treating periodontal infrabony defects. Cochrane Database Syst Rev [Internet]. 2018 Nov 26;11:CD011423. Available from: <http://dx.doi.org/10.1002/14651858.CD011423.pub2>
24. Paramasivam A, Vijayashree Priyadharsini J. MitomiRs: new emerging microRNAs in mitochondrial dysfunction and cardiovascular disease. Hypertens Res [Internet]. 2020 Aug;43(8):851–3. Available from: <http://dx.doi.org/10.1038/s41440-020-0423-3>
25. Jayaseelan VP, Arumugam P. Dissecting the theranostic potential of exosomes in autoimmune disorders. Cell Mol Immunol [Internet]. 2019 Dec;16(12):935–6. Available from: <http://dx.doi.org/10.1038/s41423-019-0310-5>
26. Vellappally S, Al Kheraif AA, Divakar DD, Basavarajappa S, Anil S, Fouad H. Tooth implant prosthesis using ultra low power and low cost crystalline carbon bio-tooth sensor with hybridized data acquisition algorithm [Internet]. Vol. 148, Computer Communications. 2019. p. 176–84. Available from: <http://dx.doi.org/10.1016/j.comcom.2019.09.020>

27. Vellappally S, Al Kheraif AA, Anil S, Assery MK, Kumar KA, Divakar DD. Analyzing Relationship between Patient and Doctor in Public Dental Health using Particle Memetic Multivariable Logistic Regression Analysis Approach (MLRA2). *J Med Syst [Internet]*. 2018 Aug 29;42(10):183. Available from: <http://dx.doi.org/10.1007/s10916-018-1037-z>
28. Varghese SS, Ramesh A, Veeraiyan DN. Blended Module-Based Teaching in Biostatistics and Research Methodology: A Retrospective Study with Postgraduate Dental Students. *J Dent Educ [Internet]*. 2019 Apr;83(4):445–50. Available from: <http://dx.doi.org/10.21815/JDE.019.054>
29. Venkatesan J, Singh SK, Anil S, Kim S-K, Shim MS. Preparation, Characterization and Biological Applications of Biosynthesized Silver Nanoparticles with Chitosan-Fucoidan Coating. *Molecules [Internet]*. 2018 Jun 12;23(6). Available from: <http://dx.doi.org/10.3390/molecules23061429>
30. Alsubait SA, Al Ajlan R, Mitwalli H, Aburaisi N, Mahmood A, Muthurangan M, et al. Cytotoxicity of Different Concentrations of Three Root Canal Sealers on Human Mesenchymal Stem Cells. *Biomolecules [Internet]*. 2018 Aug 1;8(3). Available from: <http://dx.doi.org/10.3390/biom8030068>
31. Lee SY, Nielsen J, Stephanopoulos G. *Metabolic Engineering: Concepts and Applications [Internet]*. John Wiley & Sons; 2021. 976 p. Available from: <https://play.google.com/store/books/details?id=FoMxEAAAQBAJ>
32. Vellappally S, Al Kheraif AA, Anil S, Wahba AA. IoT medical tooth mounted sensor for monitoring teeth and food level using bacterial optimization along with adaptive deep learning neural network [Internet]. Vol. 135, *Measurement*. 2019. p. 672–7. Available from: <http://dx.doi.org/10.1016/j.measurement.2018.11.078>
33. PradeepKumar AR, Shemesh H, Nivedhitha MS, Hashir MMJ, Arockiam S, Uma Maheswari TN, et al. Diagnosis of Vertical Root Fractures by Cone-beam Computed Tomography in Root-filled Teeth with Confirmation by Direct Visualization: A Systematic Review and Meta-Analysis. *J Endod [Internet]*. 2021 Aug;47(8):1198–214. Available from: <http://dx.doi.org/10.1016/j.joen.2021.04.022>
34. R H, Hannah R, Ramani P, Tilakaratne WM, Sukumaran G, Ramasubramanian A, et al. Author response for “Critical appraisal of different triggering pathways for the pathobiology of *pemphigus vulgaris*—A review” [Internet]. 2021. Available from: <http://dx.doi.org/10.1111/odi.13937/v2/response1>
35. Ezhilarasan D, Lakshmi T, Subha M, Deepak Nallasamy V, Raghunandhakumar S. The ambiguous role of sirtuins in head and neck squamous cell carcinoma. *Oral Dis [Internet]*. 2021 Feb 11; Available from: <http://dx.doi.org/10.1111/odi.13798>
36. Sarode SC, Gondivkar S, Sarode GS, Gadbail A, Yuwanati M. Hybrid oral potentially malignant disorder: A neglected fact in oral submucous fibrosis. *Oral Oncol [Internet]*. 2021 Jun 16;105390. Available from: <http://dx.doi.org/10.1016/j.oraloncology.2021.105390>

37. Kavarthapu A, Gurumoorthy K. Linking chronic periodontitis and oral cancer: A review. *Oral Oncol* [Internet]. 2021 Jun 14;105375. Available from: <http://dx.doi.org/10.1016/j.oraloncology.2021.105375>
38. Vellappally S, Al-Kheraif AA, Anil S, Basavarajappa S, Hassanein AS. Maintaining patient oral health by using a xeno-genetic spiking neural network [Internet]. *Journal of Ambient Intelligence and Humanized Computing*. 2018. Available from: <http://dx.doi.org/10.1007/s12652-018-1166-8>
39. Aldhuwayhi S, Mallineni SK, Sakhamuri S, Thakare AA, Mallineni S, Sajja R, et al. Covid-19 Knowledge and Perceptions Among Dental Specialists: A Cross-Sectional Online Questionnaire Survey. *Risk Manag Healthc Policy* [Internet]. 2021 Jul 7;14:2851–61. Available from: <http://dx.doi.org/10.2147/RMHP.S306880>
40. Dipankar C, Murugan S. The green synthesis, characterization and evaluation of the biological activities of silver nanoparticles synthesized from *Iresine herbstii* leaf aqueous extracts [Internet]. Vol. 98, *Colloids and Surfaces B: Biointerfaces*. 2012. p. 112–9. Available from: <http://dx.doi.org/10.1016/j.colsurfb.2012.04.006>
41. Sathishkumar G, Gobinath C, Wilson A, Sivaramakrishnan S. *Dendrophthoe falcata* (L.f) Ettingsh (Neem mistletoe): A potent bioresource to fabricate silver nanoparticles for anticancer effect against human breast cancer cells (MCF-7) [Internet]. Vol. 128, *Spectrochimica Acta Part A: Molecular and Biomolecular Spectroscopy*. 2014. p. 285–90. Available from: <http://dx.doi.org/10.1016/j.saa.2014.02.096>
42. Dang TMD, Le TTT, Fribourg-Blanc E, Dang MC. The influence of solvents and surfactants on the preparation of copper nanoparticles by a chemical reduction method [Internet]. Vol. 2, *Advances in Natural Sciences: Nanoscience and Nanotechnology*. 2011. p. 025004. Available from: <http://dx.doi.org/10.1088/2043-6262/2/2/025004>
43. Singh OV. *Bio-Nanoparticles: Biosynthesis and Sustainable Biotechnological Implications* [Internet]. John Wiley & Sons; 2015. 384 p. Available from: [https://books.google.com/books/about/Bio\\_Nanoparticles.html?hl=&id=1AMSCAAAQBAJ](https://books.google.com/books/about/Bio_Nanoparticles.html?hl=&id=1AMSCAAAQBAJ)
44. Danda AK. Comparison of a single noncompression miniplate versus 2 noncompression miniplates in the treatment of mandibular angle fractures: a prospective, randomized clinical trial. *J Oral Maxillofac Surg* [Internet]. 2010 Jul;68(7):1565–7. Available from: <http://dx.doi.org/10.1016/j.joms.2010.01.011>
45. Robert R, Justin Raj C, Krishnan S, Jerome Das S. Growth, theoretical and optical studies on potassium dihydrogen phosphate (KDP) single crystals by modified Sankaranarayanan–Ramasamy (mSR) method [Internet]. Vol. 405, *Physica B: Condensed Matter*. 2010. p. 20–4. Available from: <http://dx.doi.org/10.1016/j.physb.2009.08.015>
46. Krishnan V, Lakshmi T. Bioglass: A novel biocompatible innovation. *J Adv Pharm Technol Res* [Internet]. 2013 Apr;4(2):78–83. Available from: <http://dx.doi.org/10.4103/2231-4040.111523>

47. Soh CL, Narayanan V. Quality of life assessment in patients with dentofacial deformity undergoing orthognathic surgery—A systematic review [Internet]. Vol. 42, *International Journal of Oral and Maxillofacial Surgery*. 2013. p. 974–80. Available from: <http://dx.doi.org/10.1016/j.ijom.2013.03.023>
48. Lekha L, Kanmani Raja K, Rajagopal G, Easwaramoorthy D. Schiff base complexes of rare earth metal ions: Synthesis, characterization and catalytic activity for the oxidation of aniline and substituted anilines [Internet]. Vol. 753, *Journal of Organometallic Chemistry*. 2014. p. 72–80. Available from: <http://dx.doi.org/10.1016/j.jorganchem.2013.12.014>
49. Dhinesh B, Isaac Joshua Ramesh Lalvani J, Parthasarathy M, Annamalai K. An assessment on performance, emission and combustion characteristics of single cylinder diesel engine powered by *Cymbopogon flexuosus* biofuel [Internet]. Vol. 117, *Energy Conversion and Management*. 2016. p. 466–74. Available from: <http://dx.doi.org/10.1016/j.enconman.2016.03.049>
50. Pradeep Kumar AR, Shemesh H, Jothilatha S, Vijayabharathi R, Jayalakshmi S, Kishen A. Diagnosis of Vertical Root Fractures in Restored Endodontically Treated Teeth: A Time-dependent Retrospective Cohort Study. *J Endod* [Internet]. 2016 Aug;42(8):1175–80. Available from: <http://dx.doi.org/10.1016/j.joen.2016.04.012>
51. Vijayakumar GNS, Nixon Samuel Vijayakumar G, Devashankar S, Rathnakumari M, Sureshkumar P. Synthesis of electrospun ZnO/CuO nanocomposite fibers and their dielectric and non-linear optic studies [Internet]. Vol. 507, *Journal of Alloys and Compounds*. 2010. p. 225–9. Available from: <http://dx.doi.org/10.1016/j.jallcom.2010.07.161>
52. Kavitha M, Subramanian R, Narayanan R, Udhayabanu V. Solution combustion synthesis and characterization of strontium substituted hydroxyapatite nanocrystals [Internet]. Vol. 253, *Powder Technology*. 2014. p. 129–37. Available from: <http://dx.doi.org/10.1016/j.powtec.2013.10.045>
53. Sahu D, Kannan GM, Vijayaraghavan R. Size-Dependent Effect of Zinc Oxide on Toxicity and Inflammatory Potential of Human Monocytes [Internet]. Vol. 77, *Journal of Toxicology and Environmental Health, Part A*. 2014. p. 177–91. Available from: <http://dx.doi.org/10.1080/15287394.2013.853224>
54. Neelakantan P, Cheng CQ, Mohanraj R, Sriraman P, Subbarao C, Sharma S. Antibiofilm activity of three irrigation protocols activated by ultrasonic, diode laser or Er:YAG laser in vitro [Internet]. Vol. 48, *International Endodontic Journal*. 2015. p. 602–10. Available from: <http://dx.doi.org/10.1111/iej.12354>
55. Lekha L, Kanmani Raja K, Rajagopal G, Easwaramoorthy D. Synthesis, spectroscopic characterization and antibacterial studies of lanthanide(III) Schiff base complexes containing N, O donor atoms [Internet]. Vols. 1056-1057, *Journal of Molecular Structure*. 2014. p. 307–13. Available from: <http://dx.doi.org/10.1016/j.molstruc.2013.10.014>
56. Gopalakannan S, Senthilvelan T, Ranganathan S. Modeling and Optimization of EDM Process Parameters on Machining of Al 7075-B4C MMC Using RSM [Internet]. Vol. 38, *Procedia*

Engineering. 2012. p. 685–90. Available from: <http://dx.doi.org/10.1016/j.proeng.2012.06.086>

57. Parthasarathy M, Isaac JoshuaRamesh Lalvani J, Dhinesh B, Annamalai K. Effect of hydrogen on ethanol-biodiesel blend on performance and emission characteristics of a direct injection diesel engine. *Ecotoxicol Environ Saf* [Internet]. 2016 Dec;134(Pt 2):433–9. Available from: <http://dx.doi.org/10.1016/j.ecoenv.2015.11.005>

UNDER PEER REVIEW