

GREEN SYNTHESIS AND CHARACTERISATION OF MUCUNA PRURIENS MEDIATED TITANIUM DIOXIDE NANOPARTICLES USING TRANSMISSION ELECTRON MICROSCOPE

Running title: Green synthesis and characterisation of Mucuna pruriens mediated titanium dioxide nanoparticle

ABSTRACT:

Introduction:

Nanoscience and nanotechnology are the investigation and utilization of minuscule things and can be used over the different science fields, for instance, biology, chemistry, physical science, material science, and designing. In spite of the fact that advanced innovation requests the improvement of nanotechnologies in multidisciplinary science, including the creation of nanoparticles (NPs), it goes back from the Before-Christ time. Nanoparticles can be combined utilizing numerous techniques like physical, substance or organic, otherwise called green synthesis. Titanium dioxide (TiO₂) semiconductor nanoparticles are one sort of significant and promising photocatalysts in photocatalysis as a result of their extraordinary optical and electronic properties. Mucuna pruriens, broadly known as velvet bean or cowhage is a leguminous plant that has been utilized for quite a long time in Ayurvedic medication.

Aim:

The main aim of the present study is to evaluate the green synthesis and characterisation of Mucuna pruriens mediated titanium dioxide nanoparticles using transmission electron microscope.

Materials and methods:

The titanium dioxide was synthesised using the seed extract of Mucuna pruriens. Analytical tools like UV-Visible spectrophotometer and Transmission Electron microscope were used to understand the surface chemistry of the TiO₂ nanoparticles.

Result:

UV-vis spectroscopic analysis of TiO₂ nanoparticles synthesized using Mucuna pruriens showed the peak at 280 nm and confirms the TiO₂ nanoparticles formation. Under transmission electron microscopes, the nanoparticles were spherical and some were in undefined shapes. The average size of the nanoparticles was 25-76 nm.

Conclusion:

The present study concludes that the TiO₂ nanoparticles synthesised showed spherical shape.

KEYWORDS: Titanium dioxide nanoparticles, *Mucuna pruriens*, green synthesis, characterisation, Transmission electron microscope, UV- Spectrophotometer

INTRODUCTION:

Nanoscience and nanotechnology are the investigation and utilization of minuscule things and can be used over the different science fields, for instance, biology, chemistry, physical science, material science, and designing. In spite of the fact that advanced innovation requests the improvement of nanotechnologies in multidisciplinary science, including the creation of nanoparticles (NPs), it goes back from the Before-Christ time. Nanoparticles can be combined utilizing numerous techniques like physical, substance or organic, otherwise called green synthesis. Green synthesis incorporates utilization of microorganisms like organisms, yeast (eukaryotes) or microbes, actinomycetes (prokaryotes); utilization of plant concentrates or proteins or utilization of formats like DNA, films, infections and diatoms (Karthik, Arivarasu and Rajeshkumar, 2020). A few of the current cycles of nanoparticle age utilize harmful synthetics either as lessening specialists for metals or as settling specialists to stop agglomeration of the nanoparticles (Shree *et al.*, 2020). Disregarding the way that synthetic and actual techniques may successfully make unadulterated, all around portrayed nanoparticles, these are expensive and perhaps perilous to the climate (Devaraj *et al.*, 2020). As an option in contrast to noxious and expensive actual methodologies for amalgamation of, utilizing microorganisms, plants and green growth will help a ton (Nasim, Kamath and Rajeshkumar, 2020). Additionally, the noxious nature of the side-effect would be less when contrasted with other manufactured strategies (Balraj, 2020). The utility of plant-based phytochemicals by and large (Shankar *et al.*, 2020) blend and designing of Nano-phytomedicine is the relationship between plant science and nanotechnology that gives a naturally green way to deal with nanotechnology alluded to as green nanotechnology (Niveditha *et al.*, 2020). Phytochemicals show synergistic impact in the decrease of gold salt into its nano phytomedicine (S and Satheesha, 2020).

Titanium dioxide (TiO_2) semiconductor nanoparticles are one sort of significant and promising photocatalysts in photocatalysis as a result of their extraordinary optical and electronic properties (Duarte, António Armando Lima and Amorim, 2017). Ultrafine TiO_2 is utilized in sunscreens because of its capacity to obstruct UV radiation while staying straightforward on the skin (Shanmugam Rajeshkumar *et al.*, 2021). It is in rutile precious stone construction and covered with silica or/and alumina to forestall photocatalytic marvels (Barakat and Kumar, 2016). The wellbeing dangers of ultrafine TiO_2 from dermal

openness on flawless skin are viewed as amazingly low, and it is viewed as more secure than different substances utilized for UV insurance(Stock *et al.*, 2021).

Mucuna pruriens, broadly known as velvet bean or cowhage is a leguminous plant that has been utilized for quite a long time in Ayurvedic medication (Dhanasekaran, Tharakan and Manyam, 2008). It is a vivacious yearly climbing vegetable initially from southern China and eastern India, where it was all at once generally developed as a green vegetable yield (Hairiah, Stulen and Kuiper, 1990). It is perhaps the most mainstream green yields presently known in the jungles; velvet beans have incredible potential as both food and feed as proposed by encounters around the world (Jayasundara, no date). The velvet bean has been customarily utilized as a food source by certain ethnic gatherings in various nations (Shunmugam *et al.*, 2021). It is developed in Asia, America, Africa, and the Pacific Islands, where its units are utilized as a vegetable for human utilization, and its young leaves are utilized as creature grain(Ikechukwu, Okafor and Egba, 2020)(Devi, Subathra Devi and Gnanavel, 2014) (Gupta, Ariga and Deogade, 2018) (Saravanan *et al.*, 2018) (Needhidasan, Samuel and Chidambaram, 2014).

The plant's seeds contain approximately 3.1–6.1 percent L-DOPA, as well as serotonin, nicotine, and bufotenine. One examination utilizing 36 examples of seeds found no tryptamines present (S. Rajeshkumar *et al.*, 2021). *M. pruriens* var. *pruriens* has the most noteworthy substance of L-dopa (Saranya *et al.*, 2020). A normal of 52.11% debasement of L-dopa into harming quinones and responsive oxygen species was found in seeds of *M. pruriens* assortments (Maldonado, 2014; Vikneshan *et al.*, 2020). Our team has extensive knowledge and research experience that has translate into high quality publications(Rajeshkumar *et al.*, 2018; Nandhini, Rajeshkumar and Mythili, 2019; M. Gomathi *et al.*, 2020; Rajasekaran *et al.*, 2020; Vairavel, Devaraj and Shanmugam, 2020),(Santhoshkumar *et al.*, 2019),(Raj R, D and S, 2020),(Saravanan *et al.*, 2018),(Gheena and Ezhilarasan, 2019),(Ezhilarasan, Sokal and Najimi, 2018),(Ezhilarasan, 2018),(Dua *et al.*, 2019; A. C. Gomathi *et al.*, 2020; Vairavel, Devaraj and Shanmugam, 2020),(Ramesh *et al.*, 2018; Duraisamy *et al.*, 2019; Ezhilarasan, Apoorva and Ashok Vardhan, 2019; Arumugam, George and Jayaseelan, 2021; Joseph and Prasanth, 2021) ,(Gnanavel, Roopan and Rajeshkumar, 2019),(Markov *et al.*, 2021) . The main aim of the present study is to evaluate the green synthesis and characterisation of *Mucuna pruriens* mediated titanium dioxide nanoparticles using transmission electron microscope.

MATERIALS AND METHODS:

Titanium isopropoxide 97% (Aldrich) diluted in isopropyl alcohol 99.5% (Merck) was used as a starting solution, where TiO₂ nanoparticles were precipitated on the addition of alkaline distilled water (pH 8). The molar ratio of alkoxide:alcohol:water was fixed at 5:3:1. The as-prepared precipitate was washed using distilled water, centrifuged and heated at temperatures ranging from 200 to 1100 °C.

UV-vis spectrophotometer:

The bioreduction of pure TiO₂ is monitored using UV-vis spectroscopy at regular intervals. During the reduction, 0.1 ml of samples was taken and diluted several times with millipore water. After dilution, it was centrifuged at 800 rpm for 5 min. The supernatant was scanned using a UV-300 spectrophotometer (UNICAM, York Street, Cambridge, Cambridgeshire) for a UV-vis 1601 Shimadzu spectrophotometer (Kyoto, Japan), operated at a resolution of 420 nm.

Transmission electron microscopy:

Transmission electron microscopy (TEM) analysis of the sample was done using a Philips CM 200 instrument (Philips, Amsterdam, The Netherlands) operated at an accelerating voltage of 200 kV with a resolution of 0.23 nm. A drop of the solution was placed on a carbon-coated copper grid and later exposed to infrared light (45 min) for solvent evaporation.

RESULT AND DISCUSSION:




FIGURE 1: Shows UV-vis spectroscopic analysis of TiO₂ nanoparticles synthesized using *Mucuna pruriens*.




FIGURE 2: Shows TEM IMAGE TiO₂ nanoparticles synthesized using *Mucuna pruriens* and its morphology at 200 nm.

During the nanoparticles formation the solution was analysed for its surface plasmon resonance using UV-vis spectrophotometer. The nanoparticles were analysed for its morphology using transmission electron microscopes.

UV-vis spectrophotometer:

The reduction of aqueous titanium ions by *M. Pruriens* seed extract mediated synthesis of TiO₂ NPs was identified in this study. UV-vis spectral analysis was used to confirm the formation of TiO₂ NPs in aqueous solution. The reduction of titanium ions and generation of TiO₂ NPs were completed after an overnight incubation at room temperature,

according to the results. The reduction of titanium ions was indicated by the formation of a light green colour. For the seed extract solution exposed to TiO₂ NPs, the absorption spectra of the TiO₂ NPs formed in the solution had absorbance peaks at around 280 nm (Rajakumar *et al.*, 2012). In previous studies, Srinivasan *et al.* observed the peak at 240nm using UV–vis spectral analysis (Srinivasan *et al.*, 2019; Barma *et al.*, 2020) and Mohammad *et al.* observed the maximum peak at 360 nm (Nasrollahzadeh and Mohammad Sajadi, 2015).

Transmission electron microscopy:

Green synthesised TiO NPs revealed a homogeneously dispersed nanocrystalline structure with a diameter of 25- 76 nm in morphology and arrangement. Figure 2 depicts a TEM bright field picture of TiO₂ NPs. According to TEM research, *Mucuna pruriens* mediated TiO₂ NPs had spherical and irregular shapes, with an average diameter of 25-76 nm. Recently, Santhoshkumar *et al.* obtained irregular shaped titanium dioxide NPs under transmission electron microscope (Santhoshkumar *et al.*, 2014). In previous studies, Tarafdar *et al.* observed different shapes and sizes of TiO₂ nanoparticles (Tarafdar *et al.*, 2014) (Pushpaanjali, Geetha and Lakshmi, 2020) (Aathira, Geetha and Lakshmi, 2020) (Baskar and Lakshmi, 2020) (Manya Suresh, 2020) (*First Report on Marine Actinobacterial Diversity around Madras Atomic Power Station (MAPS), India*, no date) (*Physicochemical Profile of Acacia Catechu Bark Extract – An in Vitro Stud - International Journal of Pharmaceutical and Phytopharmacological Research*, no date) (Lakshmi, 2021) (*Awareness of Drug Abuse among Teenagers - International Journal of Pharmaceutical and Phytopharmacological Research*, no date) (Mangal, Anitha and Lakshmi, 2018) (*COX2 Inhibitory Activity of Abutilon Indicum - Pharmaceutical Research and Allied Sciences*, no date) (Jibu, Geetha and Lakshmi, 2020) (Sindhu *et al.*, 2020) (Nivethitha *et al.*, 2020) (Mariona, Roy and Lakshmi, 2020)

CONCLUSION:

The synthesis of TiO₂ nanoparticles using a *M. pruriens* seed extract was successfully achieved. Analytical tools like UV-Visible spectrophotometer and Transmission Electron microscope helped to understand the surface chemistry of the TiO₂ nanoparticles (Rajendran *et al.*, 2019) (Ashok, Ajith and Sivanesan, 2017) (Malli *et al.*, 2019) (Mohan and Jagannathan, 2014) (Menon *et al.*, 2018) (Samuel, Acharya and Rao, 2020) (Praveen *et al.*, 2001) (Neelakantan *et al.*, 2011) ('Oligonucleotide therapy: An emerging focus area for drug delivery in chronic inflammatory respiratory diseases', 2019) (Kumar *et al.*, 2006). The TiO₂ nanoparticles synthesis showed spherical shape. This could open the door to a lot of applications.

REFERENCE:

Aathira, C. M., Geetha, R. V. and Lakshmi, T. (2020) 'Knowledge and Awareness about the Mode of Transmission of Vector Borne Diseases among General Public', *Journal of Pharmaceutical Research International*, pp. 87–96.

Arumugam, P., George, R. and Jayaseelan, V. P. (2021) 'Aberrations of m6A regulators are associated with tumorigenesis and metastasis in head and neck squamous cell carcinoma', *Archives of oral biology*, 122, p. 105030.

Ashok, B. S., Ajith, T. A. and Sivanesan, S. (2017) 'Hypoxia-inducible factors as neuroprotective agent in Alzheimer's disease', *Clinical and experimental pharmacology & physiology*, 44(3). doi: 10.1111/1440-1681.12717.

Awareness of Drug Abuse among Teenagers - International Journal of Pharmaceutical and Phytopharmacological Research (no date). Available at: <https://eijppr.com/article/awareness-of-drug-abuse-among-teenagers> (Accessed: 31 August 2021).

Balraj, S. (2020) 'Neuroprotective Role of Diosmin on Rotenone Induced Neurotoxicity in SH-SY5Y Neuroblastoma Cells', *Bioscience Biotechnology Research Communications*, pp. 1782–1787. doi: 10.21786/bbrc/13.4/20.

Barakat, M. A. and Kumar, R. (2016) 'Photocatalytic Activity Enhancement of Titanium Dioxide Nanoparticles', *SpringerBriefs in Molecular Science*, pp. 1–29. doi: 10.1007/978-3-319-24271-2_1.

Barma, M. D. *et al.* (2020) 'Antibacterial Activity of Mouthwash Incorporated with Silica Nanoparticles against *S. aureus*, *S. mutans*, *E. faecalis*: An in-vitro Study', *Journal of Pharmaceutical Research International*, pp. 25–33. doi: 10.9734/jpri/2020/v32i1630646.

Baskar, K. and Lakshmi, T. (2020) 'Knowledge, Attitude and Practices Regarding HPV Vaccination among Undergraduate and Postgraduate Dental Students in Chennai', *Journal of Pharmaceutical Research International*, pp. 95–100.

COX2 Inhibitory Activity of Abutilon Indicum - Pharmaceutical Research and Allied Sciences (no date). Available at: <https://ijpras.com/article/cox2-inhibitory-activity-of-abutilon-indicum> (Accessed: 31 August 2021).

Devaraj, E. *et al.* (2020) ' β -Sitosterol attenuates carbon tetrachloride-induced oxidative stress and chronic liver injury in rats', *Naunyn-Schmiedeberg's Archives of Pharmacology*, pp. 1067–1075. doi: 10.1007/s00210-020-01810-8.

Devi, V. S., Subathra Devi, V. and Gnanavel, B. K. (2014) 'Properties of Concrete Manufactured Using Steel Slag', *Procedia Engineering*, pp. 95–104. doi: 10.1016/j.proeng.2014.12.229.

Dhanasekaran, M., Tharakan, B. and Manyam, B. V. (2008) 'Antiparkinson drug - *Mucuna pruriens* shows antioxidant and metal chelating activity', *Phytotherapy Research*, pp. 6–11. doi: 10.1002/ptr.2109.

Dua, K. *et al.* (2019) 'The potential of siRNA based drug delivery in respiratory disorders: Recent advances and progress', *Drug development research*, 80(6), pp. 714–730.

Duarte, A. A. L. S., António Armando Lima and Amorim, M. T. P. (2017) 'Photocatalytic Treatment Techniques using Titanium Dioxide Nanoparticles for Antibiotic Removal from Water', *Application of Titanium Dioxide*. doi: 10.5772/intechopen.69140.

Duraisamy, R. *et al.* (2019) 'Compatibility of Nonoriginal Abutments With Implants: Evaluation of Microgap at the Implant-Abutment Interface, With Original and Nonoriginal Abutments', *Implant dentistry*, 28(3), pp. 289–295.

Ezhilarasan, D. (2018) 'Oxidative stress is bane in chronic liver diseases: Clinical and experimental perspective', *Arab journal of gastroenterology: the official publication of the Pan-Arab Association of Gastroenterology*, 19(2), pp. 56–64.

Ezhilarasan, D., Apoorva, V. S. and Ashok Vardhan, N. (2019) 'Syzygium cumini extract induced reactive oxygen species-mediated apoptosis in human oral squamous carcinoma cells', *Journal of oral pathology & medicine: official publication of the International Association of Oral Pathologists and the American Academy of Oral Pathology*, 48(2), pp. 115–121.

Ezhilarasan, D., Sokal, E. and Najimi, M. (2018) 'Hepatic fibrosis: It is time to go with hepatic stellate cell-specific therapeutic targets', *Hepatobiliary & pancreatic diseases international: HBPD INT*, 17(3), pp. 192–197.

First Report on Marine Actinobacterial Diversity around Madras Atomic Power Station (MAPS), India (no date). Available at: <http://alinteridergisi.com/article/first-report-on-marine-actinobacterial-diversity-around-madras-atomic-power-station-maps-india/> (Accessed: 31 August 2021).

Gheena, S. and Ezhilarasan, D. (2019) 'Syringic acid triggers reactive oxygen species-mediated cytotoxicity in HepG2 cells', *Human & experimental toxicology*, 38(6), pp. 694–702.

Gnanavel, V., Roopan, S. M. and Rajeshkumar, S. (2019) 'Aquaculture: An overview of chemical ecology of seaweeds (food species) in natural products', *Aquaculture*, 507, pp. 1–6.

Gomathi, A. C. *et al.* (2020) 'Anticancer activity of silver nanoparticles synthesized using aqueous fruit shell extract of Tamarindus indica on MCF-7 human breast cancer cell line', *Journal of drug delivery science and technology*, 55, p. 101376.

Gomathi, M. *et al.* (2020) 'Green synthesis of silver nanoparticles using Gymnema sylvestre leaf extract and evaluation of its antibacterial activity', *South African Journal of Chemical Engineering*, pp. 1–4. doi: 10.1016/j.sajce.2019.11.005.

Gupta, P., Ariga, P. and Deogade, S. C. (2018) 'Effect of Monopoly-coating Agent on the Surface Roughness of a Tissue Conditioner Subjected to Cleansing and Disinfection: A Contact Profilometric Study', *Contemporary clinical dentistry*, 9(Suppl 1), pp. S122–S126.

Hairiah, K., Stulen, I. and Kuiper, P. J. C. (1990) 'Aluminium tolerance of the velvet beans *Mucuna pruriens* var. *utilis* and *Mucuna deeringiana*', *Plant Nutrition — Physiology and Applications*, pp. 365–374. doi: 10.1007/978-94-009-0585-6_61.

Ikechukwu, E. L., Okafor, P. N. and Egba, S. I. (2020) 'In vitro assessment of the anti-sickling properties of *Buchholzia coriacea* and *Mucuna pruriens* seed extracts', *In vitro cellular & developmental biology. Animal*, 56(9), pp. 773–782.

Jayasundara, M. D. P. (no date) 'ESTIMATION L-DOPA CONTENT OF *Mucuna pruriens* SEEDS BEFORE AND AFTER PURIFICATION'. doi: 10.31357/fapsmst.2010.00456.

Jibu, R. M., Geetha, R. V. and Lakshmi, T. (2020) 'Isolation, Detection and Molecular Characterization of *Staphylococcus aureus* from Postoperative Infections', *Journal of Pharmaceutical Research International*, pp. 63–67.

Joseph, B. and Prasanth, C. S. (2021) 'Is photodynamic therapy a viable antiviral weapon against COVID-19 in dentistry?', *Oral surgery, oral medicine, oral pathology and oral radiology*, pp. 118–119.

Karthik, V., Arivarasu, L. and Rajeshkumar, S. (2020) 'Hyaluronic Acid Mediated Zinc Nanoparticles against Oral Pathogens and Its Cytotoxic Potential', *Journal of Pharmaceutical Research International*, pp. 113–117. doi: 10.9734/jpri/2020/v32i1930716.

Kumar, M. S. *et al.* (2006) 'Expression of matrix metalloproteinases (MMP-8 and -9) in chronic periodontitis patients with and without diabetes mellitus', *Journal of periodontology*, 77(11), pp. 1803–1808.

Lakshmi, T. (2021) 'Antifungal Activity of *Ficus racemosa* Ethanolic Extract against Dermatophytes-An in vitro Study', *Journal of Research in Medical and Dental Science*, 9(2), pp. 191–193.

Maldonado, R. G. (2014) *Mucuna versus Parkinson: treatment with natural levodopa*. Rafael González Maldonado.

Malli, S. N. *et al.* (2019) 'Concentrated Growth Factors as an Ingenious Biomaterial in Regeneration of Bony Defects after Periapical Surgery: A Report of Two Cases', *Case reports in dentistry*, 2019. doi: 10.1155/2019/7046203.

Mangal, C. S. K., Anitha, R. and Lakshmi, T. (2018) 'Inhibition of Nitric oxide Production and Nitric oxide Synthase Gene Expression in LPS Activated RAW 264 .7 Macrophages by Thyme oleoresin from *Thymus vulgaris*', *Journal of young pharmacists: JYP*, 10(4), p. 481.

Manya Suresh, L. T. (2020) 'Wound Healing Properties of Aloe Barbadensis Miller-In Vitro Assay', *Journal of Complementary Medicine Research*, 11(5), pp. 30–34.

Mariona, P., Roy, A. and Lakshmi, T. (2020) 'Survey on lifestyle and food habits of patients with PCOS and obesity', *Journal of Complementary Medicine Research*, 11(5), pp. 93–98.

Markov, A. *et al.* (2021) 'Mesenchymal stem/stromal cells as a valuable source for the treatment of immune-mediated disorders', *Stem cell research & therapy*, 12(1), p. 192.

Menon, S. *et al.* (2018) 'Selenium nanoparticles: A potent chemotherapeutic agent and an elucidation of its mechanism', *Colloids and surfaces. B, Biointerfaces*, 170. doi: 10.1016/j.colsurfb.2018.06.006.

Mohan, M. and Jagannathan, N. (2014) 'Oral field cancerization: an update on current concepts', *Oncology reviews*, 8(1). doi: 10.4081/oncol.2014.244.

Nandhini, N. T., Rajeshkumar, S. and Mythili, S. (2019) 'The possible mechanism of eco-friendly synthesized nanoparticles on hazardous dyes degradation', *Biocatalysis and agricultural biotechnology*, 19, p. 101138.

Nasim, I., Kamath, K. and Rajeshkumar, S. (2020) 'Evaluation of the re-mineralization capacity of a gold nanoparticle-based dental varnish: An in vitro study', *Journal of Conservative Dentistry*, p. 390. doi: 10.4103/jcd.jcd_315_20.

Nasrollahzadeh, M. and Mohammad Sajadi, S. (2015) 'Synthesis and characterization of titanium dioxide nanoparticles using *Euphorbia heteradena* Jaub root extract and evaluation of their stability', *Ceramics International*, pp. 14435–14439. doi: 10.1016/j.ceramint.2015.07.079.

Needhidasan, S., Samuel, M. and Chidambaram, R. (2014) 'Electronic waste - an emerging threat to the environment of urban India', *Journal of environmental health science & engineering*, 12(1), p. 36.

Neelakantan, P. *et al.* (2011) 'The impact of root dentine conditioning on sealing ability and push-out bond strength of an epoxy resin root canal sealer', *International endodontic journal*, 44(6). doi: 10.1111/j.1365-2591.2010.01848.x.

Niveditha, A. S. *et al.* (2020) 'Will Alternative Medicine Help Us to Fight Against

COVID-19', *International Journal of Current Research and Review*, pp. 112–116. doi: 10.31782/ijcrr.2020.sp47.

Nivethitha, R. *et al.* (2020) 'In Vitro Anticancer Effect of Sesamum Indicum Extract -', *Journal of Complementary Medicine Research*, 11(5), pp. 99–105.

'Oligonucleotide therapy: An emerging focus area for drug delivery in chronic inflammatory respiratory diseases' (2019) *Chemico-biological interactions*, 308, pp. 206–215.

Physicochemical Profile of Acacia Catechu Bark Extract – An in Vitro Stud - International Journal of Pharmaceutical and Phytopharmacological Research (no date). Available at: <https://ejppr.com/article/physicochemical-profile-of-acacia-catechu-bark-extract-an-in-vitro-stud> (Accessed: 31 August 2021).

Praveen, K. *et al.* (2001) 'Hypotensive anaesthesia and blood loss in orthognathic surgery: a clinical study', *The British journal of oral & maxillofacial surgery*, 39(2). doi: 10.1054/bjom.2000.0593.

Pushpaanjali, G., Geetha, R. V. and Lakshmi, T. (2020) 'Knowledge and Awareness about Antibiotic Usage and Emerging Drug Resistance Bacteria among Dental Students', *Journal of Pharmaceutical Research International*, pp. 34–42.

Rajakumar, G. *et al.* (2012) 'Eclipta prostrata leaf aqueous extract mediated synthesis of titanium dioxide nanoparticles', *Materials Letters*, pp. 115–117. doi: 10.1016/j.matlet.2011.10.038.

Rajasekaran, S. *et al.* (2020) 'Collective influence of 1-decanol addition, injection pressure and EGR on diesel engine characteristics fueled with diesel/LDPE oil blends', *Fuel*, 277, p. 118166.

Rajendran, R. *et al.* (2019) 'Comparative Evaluation of Remineralizing Potential of a Paste Containing Bioactive Glass and a Topical Cream Containing Casein Phosphopeptide-Amorphous Calcium Phosphate: An in Vitro Study', *Pesquisa brasileira em odontopediatria e clinica integrada*, 19(0), p. 4668.

Rajeshkumar, S. *et al.* (2018) 'Biosynthesis of zinc oxide nanoparticles using *Mangifera indica* leaves and evaluation of their antioxidant and cytotoxic properties in lung cancer (A549) cells', *Enzyme and microbial technology*, 117, pp. 91–95.

Rajeshkumar, S. *et al.* (2021) 'Cytotoxicity behaviour of response surface model optimized gold nanoparticles by utilizing fucoidan extracted from *padina tetrastromatica*', *Journal of Molecular Structure*, p. 129440. doi: 10.1016/j.molstruc.2020.129440.

Rajeshkumar, S. *et al.* (2021) 'Employing sulphated polysaccharide (fucoidan) as medium for gold nanoparticles preparation and its anticancer study against HepG2 cell lines', *Materials Today Communications*, p. 101975. doi: 10.1016/j.mtcomm.2020.101975.

Raj R, K., D, E. and S, R. (2020) ' β -Sitosterol-assisted silver nanoparticles activates Nrf2 and triggers mitochondrial apoptosis via oxidative stress in human hepatocellular cancer cell line', *Journal of biomedical materials research. Part A*, 108(9), pp. 1899–1908.

Ramesh, A. *et al.* (2018) 'Comparative estimation of sulfiredoxin levels between chronic periodontitis and healthy patients - A case-control study', *Journal of periodontology*, 89(10), pp. 1241–1248.

Samuel, S. R., Acharya, S. and Rao, J. C. (2020) 'School Interventions-based Prevention of Early-Childhood Caries among 3-5-year-old children from very low socioeconomic status: Two-year randomized trial', *Journal of public health dentistry*, 80(1). doi: 10.1111/jphd.12348.

Santhoshkumar, J. *et al.* (2019) 'Toxicology evaluation and antidermatophytic activity of silver nanoparticles synthesized using leaf extract of *Passiflora caerulea*', *South African Journal of Chemical Engineering*, 29, pp. 17–23.

Santhoshkumar, T. *et al.* (2014) 'Green synthesis of titanium dioxide nanoparticles using *Psidium guajava* extract and its antibacterial and antioxidant properties', *Asian Pacific Journal of Tropical Medicine*, pp. 968–976. doi: 10.1016/s1995-7645(14)60171-1.

Saranya, G. *et al.* (2020) 'L-DOPA synthesis in *Mucuna pruriens* (L.) DC. is regulated by polyphenol oxidase and not CYP 450/tyrosine hydroxylase: An analysis of metabolic pathway using biochemical and molecular markers', *Phytochemistry*, 178, p. 112467.


Saravanan, M. *et al.* (2018) 'Synthesis of silver nanoparticles from *Phenerochaete chrysosporium* (MTCC-787) and their antibacterial activity against human pathogenic bacteria', *Microbial pathogenesis*, 117, pp. 68–72.

Shankar, S. B. *et al.* (2020) 'Biosynthesis of Hydroxy Citric Acid Mediated Zinc Nanoparticles and Its Antioxidant and Cytotoxic Activity', *Journal of Pharmaceutical Research International*, pp. 108–112. doi: 10.9734/jpri/2020/v32i2630845.

Shree, M. K. *et al.* (2020) 'Cytotoxicity and Antimicrobial Activity of Chromium Picolinate Mediated Zinc Oxide Nanoparticle', *Journal of Pharmaceutical Research International*, pp. 28–32. doi: 10.9734/jpri/2020/v32i2030726.

Shunmugam, R. *et al.* (2021) 'Biosynthesis of gold nanoparticles using marine microbe (*Vibrio alginolyticus*) and its anticancer and antioxidant analysis', *Journal of King Saud*

University - Science, p. 101260. doi: 10.1016/j.jksus.2020.101260.

Sindhu, P. K. *et al.* (2020) 'Anorectic drugs: an experimental and clinical perspective  Review', *Journal of Complementary Medicine Research*, 11(5), pp. 106–112.

Srinivasan, M. *et al.* (2019) 'Green synthesis and characterization of titanium dioxide nanoparticles (TiO₂ NPs) using *Sesbania grandiflora* and evaluation of toxicity in zebrafish embryos', *Process Biochemistry*, pp. 197–202. doi: 10.1016/j.procbio.2019.02.010.

S, S. K. and Satheesha, K. S. (2020) 'In-Vitro Antibacterial Activity of Black Tea (*Camellia sinensis*) Mediated Zinc Oxide Nanoparticles Against Oral Pathogens', *Bioscience Biotechnology Research Communications*, pp. 2077–2080. doi: 10.21786/bbrc/13.4/66.

Stock, V. *et al.* (2021) 'Photoactive Titanium Dioxide Films with Embedded Gold Nanoparticles for Quantitative Determination of Mercury Traces in Humic Matter-Containing Freshwaters', *Nanomaterials (Basel, Switzerland)*, 11(2). doi: 10.3390/nano11020512.

Tarafdar, J. C. *et al.* (2014) 'Development of Zinc Nanofertilizer to Enhance Crop Production in Pearl Millet (*Pennisetum americanum*)', *Agricultural Research*, pp. 257–262. doi: 10.1007/s40003-014-0113-y.

Vairavel, M., Devaraj, E. and Shanmugam, R. (2020) 'An eco-friendly synthesis of *Enterococcus* sp.–mediated gold nanoparticle induces cytotoxicity in human colorectal cancer cells', *Environmental Science and Pollution Research*, 27(8), pp. 8166–8175.

Vikneshan, M. *et al.* (2020) 'Algal biomass as a source for novel oral nano-antimicrobial agent', *Saudi Journal of Biological Sciences*, pp. 3753–3758. doi: 10.1016/j.sjbs.2020.08.022.